

Paramagnetic Resonance of Ni⁺⁺, V⁺⁺, and Cr⁺⁺⁺ in ZnF₂

MARTIN PETER AND J. B. MOCK
Bell Telephone Laboratories, Murray Hill, New Jersey

(Received October 21, 1959)

The millimeter wave paramagnetic resonance spectra of Ni⁺⁺, V⁺⁺, and Cr⁺⁺⁺ have been measured in ZnF₂. Evidence was found that the extra charge of Cr⁺⁺⁺ is compensated by an F⁻ ion, sitting on one of two available nonequivalent neighboring sites. The antiferromagnetic resonance line in NiF₂ which has been postulated by Moriya, is now expected to occur at 320 kMc/sec.

THE paramagnetic spectra of the ions Ni⁺⁺, V⁺⁺, and Cr⁺⁺⁺ have been measured in the diamagnetic ZnF₂ lattice. They are described by the spin Hamiltonian

$$\mathcal{H}_s = D[S_z^2 - \frac{1}{3}S(S+1)] + E(S_x^2 - S_y^2) + g\beta\mathbf{H} \cdot \mathbf{S} + A\mathbf{I} \cdot \mathbf{S}.$$

The parameters for these ions are summarized in Table I. In Ni⁺⁺, V⁺⁺, and Cr⁺⁺⁺, spectrum *A*, the *z* axis is the [001] axis of ZnF₂ and the *x* axis follows [110]. In these spectra we do not know the sign of *E*. In Cr⁺⁺⁺, spectrum *B*, the *z* axis is in a (110) plane, 9° off the [110] axis, and the *y* axis follows the [110] axis.

The Cr⁺⁺⁺ spectra have previously been measured by Tinkham,¹ but we find 20% smaller zero field splittings than he predicted. We agree, however, with Tinkham's measurement of the directions of the main axes of the spin Hamiltonian, and also with his conclusion that they are due to the presence of an anion which compensates the excess charge on Cr⁺⁺⁺, and which can occupy either one of two nonequivalent positions. The fact that Cr⁺⁺⁺ can be introduced in considerable amounts, together with recent measurements in CaF₂² suggests F⁻ as the compensating ion.

The *D* term in Ni⁺⁺ has been predicted by Stout³ from susceptibility measurements. Moriya⁴ has shown, that the Ni⁺⁺ spins are aligned along the [110] axes of

NiF₂, if *D* > 0. He predicts an antiferromagnetic resonance to occur at $\nu = 4E\langle S \rangle$. Here, $\langle S \rangle \approx 1.0$ is the expectation value of the spin. This resonance is now predicted at 320 kMc/sec. If VF₂ can be grown with the NiF₂ structure, then it should show a similar resonance at 28 kMc/sec. From crystal field theory we expect that the *D* and *E* terms should be proportional for V⁺⁺ ($3d^3 \ ^4F$) and Ni⁺⁺ ($3d^8 \ ^3F$), the proportionality factor being the square ratio of the spin-orbit couplings. This is seen to hold approximately. The same theory

TABLE I. Summary of the ion parameters (in kMc/sec).

	<i>D</i>	<i>E</i>	<i>g</i>	<i>A</i>
Ni ⁺⁺	125.5	80.1	2.33	
V ⁺⁺	12.74	4.58	1.97	0.090
Cr ⁺⁺⁺ spectrum <i>A</i>	21.65	2.30	1.95	
Cr ⁺⁺⁺ spectrum <i>B</i>	21.35	2.75	1.97	

predicts a small anisotropy for *g* and *A*, and this effect as well as the structure of the Ni resonance due to the surrounding fluorine ions are now under study.

ACKNOWLEDGMENTS

We wish to thank Professor J. W. Stout for the Ni-doped crystal, L. G. van Uitert for the V-doped crystal and H. J. Guggenheim for the Cr-doped specimen, and to B. Cetlin for doing the machine computations. We are indebted to R. Kompfner and C. F. Hempstead for lending to us a prototype backward-wave oscillator working up to 120 kMc/sec.

¹ M. Tinkham, Proc. Roy. Soc. (London) **A236**, 535 (1956).

² B. Bleaney, P. M. Llewellyn, and D. A. Jones, Proc. Phys. Soc. (London) **B69**, 858 (1956).

³ J. W. Stout (private communication).

⁴ T. Moriya (to be published).