Letters to the Editor

DROMPT publication of brief reports of important discoveries in physics may be secured by addressing them to this department. Closing dates for this department are, for the first issue of the month, the eighteenth of the preceding month, for the second issue, the third of the month. Because of the late closing dates for the section no proof can be shown to authors. The Board of Editors does not hold itself responsible for the opinions expressed by the correspondents.

Communications should not in general exceed 600 words in length.

Dislocations and Magnetization

WILLIAM FULLER BROWN, IR. Palmer Physical Laboratory, Princeton University, Princeton, New Jersey February 27, 1941

HE writer recently suggested that line concentrations of force might be responsible for the term a/H in the empirical formula for the magnetization curve of nickel at high fields, $J = J_s - a/H - b/H^2 + CH$, and tentatively identified these line concentrations with the "dislocations" of plasticity theory. The following approximate calculation, based directly on dislocation theory, shows that both the occurrence of the a/H term and the increase of a and bwith plastic strain may be attributed to internal stresses produced by the dislocations.

Let Oy be the direction of the field and of the specimen axis, Oz the direction of the dislocation lines (radially outward from the axis in the region under consideration), and Ox the direction of slip; this is roughly the situation in a twisted wire. If $\alpha = \cos(J, x)$ is small, the magnetostrictive energy density2 for a specimen with saturation magnetostriction $-\lambda_{\infty}$ is $3\lambda_{\infty}X_y\alpha$. The shearing stress X_y at a distance r from a dislocation³ is $\lambda_0 G' \phi(\theta) / \pi r$, where λ_0 is the distance between atoms along Ox, $G' \cong$ the rigidity, and $\phi(\theta)$ is an angular factor. For a single dislocation, therefore, α varies in the xy-plane in accordance with the equation1

$$\nabla^2 \alpha - \eta \alpha = k\phi(\theta)/r, \tag{1}$$

where $k = 3\lambda_{\infty}G'\lambda_0/\pi C$, $\eta = HJ_s/C$; $C \cong 10^{-5}$ erg/cm measures the strength of the interatomic coupling forces. Transformation to the dimensionless variable $v = \eta^{\frac{1}{2}}r$ shows

$$\alpha = k\eta^{-\frac{1}{2}}f(v,\theta),\tag{2}$$

where the function f is dimensionless.

For n dislocations per cm², distributed at random, $1-J/J_s$ is found by integrating $\frac{1}{2}\alpha^2$ over the xy-plane and multiplying by n. Since $dxdy = \eta^{-1}vdvd\theta$, the result is $c_1 n \pi k^2 / \eta^2$, where $c_1 = \int f^2 v dv d\theta / 2\pi$ is a numerical constant; or $J_s - J = b/H^2$, with

$$b = (9c_1/\pi)n(\lambda_{\infty}G'\lambda_0)^2/J_s.$$
 (3)

This may be rewritten

$$J/J_s = 1 - c_1'(\lambda_\infty \sigma_i/HJ_s)^2,$$

with

$$\sigma_i = c_2 G' \lambda_0 \sqrt{n}, \tag{5}$$

where c_1' and c_2 are numerical constants. Equation (4) is identical with that given by the Becker-Kersten rotation theory² for "internal stress" σ_i ; Eq. (5) suggests that σ_i may be identified with the stress produced by the dislocations in Taylor's theory of hardening.3 In Becker's theory $c_1 \cong \frac{3}{5}$, and in Taylor's $c_2 \cong \frac{1}{5}$. If the tentative value $9c_1/\pi = c_1'c_2^2 = 3/125$ is inserted in Eq. (3), n may be calculated from Kaufmann's data on the increase of b with plastic twist. The result is $n/\gamma \cong 10^{12}$ dislocations per cm² per unit of plastic shear (γ) , in agreement with the value calculated from purely mechanical data by Taylor's theory.1

Dislocations are of two signs, and opposite kinds attract each other toward a common value of x. They therefore tend to form pairs separated by a short distance l parallel to Oy. The value of α for such a doublet may be found by applying the operator $-l\partial/\partial y$ to the right member of Eq. (2); it is of the form $\alpha = klg(v, \theta)$. For n' doublets per cm², $J_s - J = a/H$, with $a = (9c_3/\pi)n'l^2(\lambda_{\infty}G'\lambda_0)^2/C$. If $n' \cong n$ and $10^{-2} \le 9c_3/\pi \le 1$, Kaufmann's values of a give 10^{-5} cm $\geq l \geq 10^{-6}$ cm; thus l is less than the mean distance between dislocations but considerably greater than the interatomic distance—a plausible result.

It has been assumed here that the integrals c_1 and c_3 converge. Actually c_1 diverges logarithmically at $v = \infty$; in the rigorous theory b is not exactly constant, but contains a logarithmic term in H.

¹ W. F. Brown, Jr., Phys. Rev. **58**, 736 (1940). ² R. Becker and W. Döring, *Ferromagnetismus* (Springer, Berlin, 1939), p. 146; pp. 167–8, 175. ³ G. I. Taylor, Proc. Roy. Soc. **A145**, 362 (1934); J. M. Burgers, Proc. K. Ned. Akad. Wet. **42**, 293 (1939), especially pp. 305–6. ⁴ A. R. Kaufmann, Phys. Rev. **57**, 1089A (1940) and private communication.

Rotational Analysis, Perturbation and Predissociation in the CD and CH Bands

L. GERÖ AND R. F. SCHMID Physical Institute, Royal Hungarian University for Technical and Economic Sciences, Budapest, Hungary January 17, 1941

N strongly condensed high frequency electric discharges through vapors of deutero-paraffin and ordinary benzol under various pressures, the entire CD and CH spectrum was photographed with a grating spectrograph of high dispersion and good resolution.

Rotational analysis of the CD bands in the region of 3150A has been made and the branches of the bands (0,0), (1,1) and (2,2) were followed up to K'=39(v'=0), K' = 34(v' = 1) and K' = 27(v' = 2), where predissociation of the $C^2\Sigma^-$ state occurs. The corresponding predissociation in the CH bands has been suspected1 and we found confirmation by observing the effect at K'=26(v'=0) and K' = 21(v' = 1) on the $C^2\Sigma^-$ state of CH.

A comparison of the predissociation effects on the 4300A CD and CH bands completes the findings of a previous paper, based on pictures of CH bands alone, as follows: The $A^2\Delta \rightarrow X^2\Pi$ bands show two predissociation phenom-