

### A Slow Component in the Decay of the Scintillation Phosphors

JASPER A. JACKSON AND F. B. HARRISON

Los Alamos Scientific Laboratory, University of California,  
Los Alamos, New Mexico

(Received November 10, 1952)

WE have measured the fraction of the light emitted by some of the common phosphors, which has a decay constant longer than about 0.5  $\mu\text{sec}$ .<sup>1</sup> The following apparatus was used: The phosphor was held in a beaker lined with aluminum foil, excited by a beam of x-rays, and viewed by an end-window photomultiplier. The x-ray tube may be gated off by applying a negative pulse to its grid. The photomultiplier is normally turned off by making its first dynode 8 v negative with respect to the cathode; it may be gated on by applying a positive square wave to dynode 1. The sequence of events is the following: First the photomultiplier is gated on, then the x-ray tube is gated off, and then the photomultiplier is gated off. The x-ray beam turns back on after 40  $\mu\text{sec}$ . Two photographs were taken of each phosphor, one showing the whole trace, the other with 10 times the gain to show the details in the region just after the x-ray beam is turned off.

The results are given in Table I. The residual signal in the case of the liquid phosphor may have been due to a number of effects, such as after-pulses in the photomultiplier and imperfect cutoff of

TABLE I. Fraction of the light emitted in the slow component, and its decay time.

	Decay time ( $\mu\text{sec}$ )	Percentage of light
Terphenyl in toluene 5 g/l	...	<0.1
Terphenyl crystal	47 $\pm$ 6	2.5 $\pm$ 0.2
Trans-stilbene	80 $\pm$ 10	4.3 $\pm$ 0.2
Anthracene	47 $\pm$ 6	5.6 $\pm$ 0.4
Sodium iodide	220 $\pm$ 40	5.0 $\pm$ 0.2

the x-ray beam, as well as a slow component in the light emission. This measurement gives an upper limit of 0.1 percent for all these effects, and we have therefore neglected them in the analysis of the data for the crystals.

The absence of a slow component in the terphenyl solution, as contrasted with crystalline terphenyl, is probably due to a deformation of potential energy surfaces during collisions in the liquid, which allow a conversion of the excitation energy of the metastable state into thermal energy.<sup>2</sup> The shorter mean life of fluorescence in the liquid is presumed to be due to the same type of process.

<sup>1</sup> Bittman, Furst, and Kallmann, *Phys. Rev.* **87**, 83 (1952).

<sup>2</sup> M. Kasha, *Chem. Revs.* **41**, 401 (1947).

### Spectral Location of the Absorption Due to Color Centers in Alkaline Earth Halide Crystals

HENRY F. IVEY

Skiatron Electronics and Television Corporation, New York, New York

(Received October 28, 1952)

RECENTLY Smakula<sup>1</sup> has measured the spectral location of the absorption bands induced by x-rays in crystals of  $\text{CaF}_2$  (3350A, 4000A, and 5800A) and  $\text{BaF}_2$  (3800A, 4800A, and 6700A). His results for  $\text{CaF}_2$  are in good agreement with those obtained earlier by Herman and Silverman<sup>2</sup> and later by Barile.<sup>3</sup> Smakula has obtained evidence for a fourth band in both  $\text{CaF}_2$  and  $\text{BaF}_2$  near 2200A. This additional band was determined by Barile as lying at 2280A in  $\text{CaF}_2$ , but the exact location in the case of  $\text{BaF}_2$  is still not known. Measurements have apparently not been reported for other alkaline earth halides.

Smakula<sup>1</sup> has pointed out that his data do not fit the relationship,  $\nu d^2 = \text{constant}$  or  $\lambda = ad^2$  ( $\nu$  = frequency of maximum absorption,  $\lambda$  = the corresponding wavelength,  $d$  = lattice constant, and

$a = \text{constant}$ ), obtained by Mollwo<sup>4</sup> experimentally for the case of the  $F$ -band in the alkali halides. The same expression has also been obtained theoretically by Fröhlich<sup>5</sup> on the basis of a model for the  $F$ -center which is not now generally accepted. The writer<sup>6</sup> has shown, however, that the location of the  $F$ ,  $R_1$ ,  $R_2$ ,  $M$ , and  $V$  bands in the alkali halides having the NaCl structure can be satisfactorily related to the lattice constant<sup>7</sup> by equations of the general form  $\lambda = ad^n$ , where  $a$  and  $n$  are constants for a given band, but  $n$  is not necessarily equal to two ( $n = 1.84$  for the  $F$ ,  $R_1$ , and  $R_2$  band, 1.56 for the  $M$  band, and 1.10 for the  $U$  band). Inui and Uemura<sup>8</sup> have also recently considered the dependence of the  $F$ -absorption peak in the alkali halides upon the lattice constant from a theoretical viewpoint.

The two constants in the expression  $\lambda = ad^n$  can, of course, be determined from Smakula's data for the three bands in  $\text{CaF}_2$  and  $\text{BaF}_2$ . The results of these calculations are

$$\text{I: } \lambda = 614d,$$

$$\text{II: } \lambda = 346d^{1.444},$$

$$\text{III: } \lambda = 833d^{1.144},$$

where  $\lambda$  and  $d$  are both in Angstrom units. (For convenience the three bands, starting with that corresponding to shortest wave-

TABLE I. Location of absorption bands in alkaline earth halides. (Values in parentheses are predicted.)

Comp-ound	Lattice constant (angstroms)	Absorption peak (angstroms)		
		I	II	III
$\text{CaF}_2$	5.451	3350	4000	5800
$\text{SrF}_2$	5.86	(3610)	(4450)	(6310)
$\text{BaF}_2$	6.184	3800	4800	6700
$\text{SrCl}_2$	7.00	(4300)	(5740)	(7730)
$\text{BaCl}_2$	7.34	(4520)	(6170)	(8170)

lengths, and going in the direction of increasing wavelength, have been indicated as I, II, and III.) It would be very desirable if data were available on a third alkaline earth halide to serve as a check on the reliability of the determination of the constants in the above relations, but this is unfortunately not the case.

Because of the experience with the alkali halides, however, it is believed that the above equations are probably satisfactory for the purpose of predicting the spectral location of the absorption bands in alkaline earth halides of the same fluorite crystal structure as  $\text{CaF}_2$  and  $\text{BaF}_2$  (cubic, space group  $O_h^5$ ) which are as yet unmeasured. Of the remaining alkaline earth halides, only  $\text{SrF}_2$  and  $\text{SrCl}_2$  normally possess this crystal structure. Vainshtein<sup>9</sup> has recently reported, however, the existence of the fluorite structure in very thin films of  $\text{BaCl}_2$ . The results of such calculations are shown in the Table I.

<sup>1</sup> A. Smakula, *Phys. Rev.* **77**, 408 (1950).

<sup>2</sup> R. Herman and S. Silverman, *J. Opt. Soc. Am.* **37**, 871 (1947).

<sup>3</sup> S. Barile, *J. Chem. Phys.* **20**, 297 (1952).

<sup>4</sup> E. Mollwo, *Nachr. Ges. Wiss. Göttingen*, No. 14, 97 (1931).

<sup>5</sup> H. Fröhlich, *Z. Physik* **80**, 819 (1933).

<sup>6</sup> H. F. Ivey, *Phys. Rev.* **72**, 341 (1947).

<sup>7</sup> In the equations given in reference 6 for the alkali halides,  $d$  actually indicates the interionic distance and not the lattice constant. For the NaCl structure these quantities differ, of course, only by a factor of two.

<sup>8</sup> T. Inui and Y. Uemura, *Prog. Theoret. Phys.* **5**, 252 (1950).

<sup>9</sup> B. K. Vainshtein, *Doklady Akad. Nauk, S.S.S.R.* **60**, 1169 (1948).

### Purification and Prevention of Segregation in Single Crystals of Germanium

W. G. PFANN AND K. M. OLSEN

Bell Telephone Laboratories, Murray Hill, New Jersey

(Received November 11, 1952)

GERMANIUM ingots of such high purity that they have intrinsic electrical resistivity at room temperature and germanium single crystals having an extrinsic resistivity which is essentially constant in over 80 percent of their volume have been prepared by new techniques. These new experimental results