

Letters to the Editor

PUBLICATION of brief reports of important discoveries in physics may be secured by addressing them to this department. The closing date for this department is five weeks prior to the date of issue. No proof will be sent to the authors. The Board of Editors does not hold itself responsible for the opinions expressed by the correspondents. Communications should not exceed 600 words in length and should be submitted in duplicate.

The Metamict State

WILLIAM PRIMAK

Chemistry Division, Argonne National Laboratory, Lemont, Illinois
(Received May 10, 1954)

IN a preliminary report on the behavior of a number of insulators exposed to energetic neutrons within a nuclear reactor,¹ it was reported that large changes in physical properties had been observed in diamond, silicon carbide, quartz, and vitreous silica. These property changes and their behavior seemed similar to the property changes associated with the metamictization of minerals,² which is attributed to the passage of alpha particles emitted from their own radioactive content. The substances previously examined and a number of others have now been exposed simultaneously in a nuclear reactor at a temperature believed to be above room temperature but below 100°C. An x-ray examination of these substances has now been completed and suggests a rather different conclusion as to the substances susceptible to metamictization than those suggested by Goldschmidt,³ Pellas,⁴ and others. It therefore seems desirable to report the results.

As a result of the irradiation, the following substances showed no detectable change in powder pattern: beryl, germanium dioxide (α -quartz structure), germanium, silicon, corundum, and rutile; the following substances showed only the small percent increases in lattice constant given in parentheses: magnesium oxide (0.1), spinel (0.12), calcium fluoride (0.08); the following substances showed the large percent changes given in parentheses but did not show any marked diffuseness in their diffraction patterns: diamond (0.9), silicon carbide (a , 0.68; c , 0.68). In the same irradiation were present samples of quartz, tridymite, and cristobalite. Their diffraction patterns became so diffuse that it was no longer possible to measure the positions of any lines. Chrysoberyl and phenacite irradiated under similar conditions but for about half the time showed a noticeable increase in lattice constant as shown by displacement of lines in the back reflection region (θ ca 80 deg) of $\frac{1}{2}$ to 1 deg but there was no noticeable line broadening. On the other hand, the diffraction pattern of a sample of tridymite irradiated simultaneously was diffuse even in the forward reflection region, and no lines could be distinguished past θ ca 10 degs.

From these results it is clear that the effects associated

with metamictization cannot be associated with a particular crystal structure or bond type. Rather, it seems necessary that the substance possess a quasi-stable vitreous (disordered) state under the conditions of irradiation. The susceptibleness to metamictization is not determined by the state present *ab initio*, but by the difficulty of recrystallization of the disordered regions formed by the traverse of energetic atomic particles, and by the difficulty with which the displaced atoms can again form bonds. The former would give rise to large changes in the x-ray diffraction pattern, the latter to large amounts of stored energy.

The x-ray diffraction patterns were taken and measured by Stanley Siegel of this Laboratory.

Notes added in proof: (1) All of the samples which were irradiated simultaneously, were irradiated in the same container for the same time. The significant neutron flux as a function of energy E is not known, but probably does not differ greatly (by more than a factor of two) from the distribution (constant/ E). From a combination of theoretical considerations and experiments performed in various reactor facilities, it seems likely that most of the damage was produced by neutrons between 0.01 and 1–2 Mev. Then, if a dosage unit is defined as the damage produced in a standard substance by $(10^{18} \int_{0.01}^1 d \ln E)$ neutrons/cm², the radiation-damage dosage of these samples was found to be about 120 units and of the chrysoberyl and phenacite about 50 units, to within the precision usually attained in such experiments (20 percent).

(2) The elastic-constant changes reported by Binnie and Liebschutz⁵ for silicon irradiated for a shorter dosage than the sample reported here is taken as evidence of the recrystallization hypothesis proposed here.

¹ Primak, Fuchs, and Day, *Phys. Rev.* **92**, 1064 (1953).

² A. Pabst, *Am. Mineralogist* **37**, 137 (1952).

³ V. M. Goldschmidt, *Skrifter Norske, Videnskaps-Akad. Oslo, I. Mat.-Naturv. Kl. I*, No. 5, 51–58 (1924).

⁴ P. Pellas, *Compt. rend.* **233**, 369 (1951).

⁵ W. P. Binnie and A. M. Liebschutz, *Phys. Rev.* **94**, 1410 (1954).

Shape of the F Band

R. V. HESKETH AND E. E. SCHNEIDER*

King's College, University of Durham,
Newcastle upon Tyne, England

(Received June 7, 1954)

PREVIOUS measurements by Mollwo¹ have shown that the F absorption band in additively colored alkali halide crystals has a Lorentzian shape, and it has been generally assumed that this shape is a fundamental property of the F center and independent of the method of coloration. However, several measurements on potassium chloride crystals colored by 200-kv x-rays have shown that the F band thus formed is more nearly Gaussian in shape.

Crystals were colored at both 290°K and 113°K. In the former case a maximum concentration of 10^{17} centers per cc was obtained, while at the lower temperature only 10^{16} centers per cc were formed, though it is probable that this was not a maximum concentration. The concentrations were sensibly uniform through crystals of several millimeters thickness.