

## Half-Metal–Spin-Gapless-Semiconductor Junctions as a Route to the Ideal Diode

Ersoy Şaşıoğlu<sup>1,\*</sup>, Thorsten Aull<sup>1,†</sup>, Dorothea Kutschabsky<sup>1</sup>, Stefan Blügel<sup>2</sup>, and Ingrid Mertig<sup>1,3</sup>

<sup>1</sup>*Institute of Physics, Martin Luther University Halle-Wittenberg, D-06120 Halle (Saale), Germany*

<sup>2</sup>*Peter Grünberg Institut and Institute for Advanced Simulation, Forschungszentrum Jülich and JARA, D-52425 Jülich, Germany*

<sup>3</sup>*Max Planck Institute of Microstructure Physics, Weinberg 2, D-06120 Halle (Saale), Germany*



(Received 20 February 2020; accepted 9 June 2020; published 27 July 2020)

The ideal diode is a theoretical concept that completely conducts the electric current under forward bias without any loss and that behaves like a perfect insulator under reverse bias. However, real diodes have a junction barrier that electrons have to overcome and thus they have a threshold voltage  $V_T$ , which must be supplied to the diode to turn it on. This threshold voltage gives rise to power dissipation in the form of heat and hence is an undesirable feature. In this work, based on half-metallic magnets (HMMs) and spin-gapless semiconductors (SGSs) we propose a diode concept that does not have a junction barrier and the operation principle of which relies on the spin-dependent transport properties of the HMM and SGS materials. We show that the HMM and SGS materials form an Ohmic contact under any finite forward bias, while for a reverse bias the current is blocked due to spin-dependent filtering of the electrons. Thus, the HMM-SGS junctions act as a diode with zero threshold voltage  $V_T$  and linear current-voltage ( $I$ - $V$ ) characteristics as well as an infinite on:off ratio at zero temperature. However, at finite temperatures, non-spin-flip thermally excited high-energy electrons as well as low-energy spin-flip excitations can give rise to a leakage current and thus reduce the on:off ratio under a reverse bias. Furthermore, a zero threshold voltage allows one to detect extremely weak signals and due to the Ohmic HMM-SGS contact, the proposed diode has a much higher current drive capability and low resistance, which is advantageous compared to conventional semiconductor diodes. We employ the nonequilibrium Green's function method combined with density-functional theory to demonstrate the linear  $I$ - $V$  characteristics of the proposed diode based on two-dimensional half-metallic Fe/MoS<sub>2</sub> and spin-gapless semiconducting VS<sub>2</sub> planar heterojunctions.

DOI: [10.1103/PhysRevApplied.14.014082](https://doi.org/10.1103/PhysRevApplied.14.014082)

### I. INTRODUCTION

A diode is a two-terminal device that conducts electric current in only one direction but restricts current from flowing in the opposite direction, i.e., it acts as a one-way switch for current. Diodes are also known as rectifiers because they change alternating current into direct current. Diodes are of several types, with different properties depending on the materials that they consist of [1–3]. For instance,  $p$ - $n$ -junction diodes are formed by joining a  $p$ -type semiconductor to an  $n$ -type semiconductor and they are the elementary building blocks of three-terminal transistors. The Esaki diode (or tunnel diode) [4] is a heavily doped  $p$ - $n$ -junction diode, in which the electron transport in the contact region is via quantum-mechanical tunneling under forward bias and it shows the negative-differential-resistance (NDR) effect (see Fig. 1), which allows it to function as an oscillator and amplifier.

In connection with the Esaki diode, when the doping concentration on the  $p$  side or the  $n$  side is nearly or not quite degenerate, the current in the reverse direction is much larger than in the forward direction and hence such a device is called a backward diode [1,5,6]. In contrast to semiconductor-semiconductor diodes, a Schottky-barrier diode [1] is formed by joining a metal to an  $n$ -type semiconductor. Compared to typical  $p$ - $n$  junctions, Schottky diodes have very fast switching times and a higher current drive capability.

Diodes are used for various applications, ranging from power conversion to overvoltage protection and from signal detection and mixing to switches. Due to the junction barrier, diodes have a threshold (or turn-on) voltage  $V_T$ , which must be supplied to the diode for it to conduct any considerable forward current. In Fig. 1, we show schematically the current-voltage ( $I$ - $V$ ) characteristics of the different types of diodes and compare them with the concepts of the ideal diode and the Ohmic junction. For  $p$ - $n$ -junction (silicon) diodes, the threshold voltage  $V_T$  is around 0.7 V, while for Schottky diodes  $V_T$  is between 0.2

\*ersoy.sasioglu@physik.uni-halle.de

†thorsten.aull@physik.uni-halle.de




FIG. 1. (a) A schematic representation of the current-voltage ( $I$ - $V$ ) characteristics of the conventional three types of diodes [Schottky,  $p$ - $n$ , and metal-insulator-metal ( $M$ - $I$ - $M$ ) diodes]. (b) The  $I$ - $V$  curves of an ideal diode, an Ohmic junction, an Esaki (tunnel diode), and a backward diode.

$V$  and 0.3 V. Backward diodes have zero threshold voltage but their on:off current ratios as well as their voltage-operation windows are rather small. The threshold voltage  $V_T$  gives rise to power dissipation ( $P = V_T \times I$ ) in the diode in the form of heat and hence is an undesirable feature. The larger the value of  $V_T$ , the higher is the power dissipation.

Although the ideal diode is a theoretical concept, it has been suggested that superconductor-semiconductor junctions possess  $I$ - $V$  characteristics that are similar to the ideal one under a forward bias [7]. Initial experiments by McColl *et al.* on a superconductor-semiconductor junction diode based on lead and  $p$ -type GaAs have shown ideal-diode behavior for forward applied voltages less than the superconducting-energy-gap parameter  $\Delta$ . In this voltage window (a few millielectronvolts), the diode exhibits a high degree of nonlinearity in its  $I$ - $V$  characteristics [7]. Superconductor-semiconductor junctions have subsequently been studied as the most sensitive detectors and mixers of microwaves [8–12]. However, in contrast to the Schottky-diode behavior, superconductor-semiconductor junctions possess symmetric  $I$ - $V$  curves with  $I(-V) = -I(V)$ , close to zero bias, giving rise to a relatively small on:off current ratio [12]. Furthermore, the operation temperature of such diodes is limited by the phase-transition temperature of superconductors, which is far below room temperature. Another type of diode that has a zero threshold voltage  $V_T$  is the so-called geometric diode, the operation principle of which relies on the geometric asymmetry of a conducting thin film [13–16]. Geometric diodes are ultrafast ballistic transport devices, where the critical dimension of the device is comparable to the mean-free path length of the electrons. It has, however, been shown that the geometric asymmetry of the diode alone cannot induce a current rectification and thus in addition to geometry, nonlinearity (high-order many-body interactions) is required to realize the geometric diode [17]. This also explains why the experimentally measured current rectification in graphene-related geometric diodes is very




FIG. 2. A schematic representation of the density of states for (a) a half-metallic magnet, (b) a type-I spin-gapless semiconductor, and (c) a type-II spin-gapless semiconductor.

low [13,14], as the nonlinearity, i.e., the electron-phonon interactions, is rather weak in these systems.

For device applications, a special class of materials, the so-called spin-gapless semiconductors (SGSs), are receiving substantial attention. The concept of SGSs was proposed by Wang in 2008 [18,19]. By employing first-principles calculations, the author predicted SGS behavior in the Co-doped dilute magnetic semiconductor  $\text{PbPdO}_2$ . Subsequently, different classes of materials ranging from two dimensional (2D) to three dimensional (3D) have been predicted to possess SGS behavior and some of them have been confirmed experimentally. The SGSs lie on the border between magnetic semiconductors and half-metallic magnets (HMMs) [20]. A schematic density of states (DOS) of HMMs and SGSs is shown in Fig. 2. In SGSs, the mobility of charge carriers is essentially higher than in normal semiconductors, making them promising materials for nanoelectronic applications. Moreover, the spin-dependent transport properties of SGSs and HMMs lead to the emergence of device concepts in spintronics. Recently, a reconfigurable magnetic tunnel diode and transistor concept based on SGSs and HMMs has been proposed [21,22]. The magnetic tunnel diode allows electric current to pass either in one or the other direction, depending on the relative orientation of the magnetization of the HMM and SGS electrodes. Moreover, the proposed devices present the tunnel magnetoresistance effect, allowing the combination of nonvolatility and reconfigurability on the diode (transistor) level, which is not achievable in semiconductor nanoelectronics.

In this paper, we propose a diode concept, based on a HMM and a SGS electrode, that we call the Ohmic spin diode (OSD) and demonstrate proof of the principle by *ab initio* quantum transport calculations. Analogous to the metal-semiconductor junction diode (the Schottky-barrier diode), HMM-SGS junctions act as a diode, the operation principle of which relies on the spin-dependent transport properties of the HMM and SGS materials. We show that HMM and SGS materials form an Ohmic contact under any finite forward bias, giving rise to linear current-voltage ( $I$ - $V$ ) characteristics, while for a reverse

bias the current is blocked due to the filtering of the electrons. In contrast to the Schottky diode, the proposed diode does not require the doping of the SGS and also does not have a junction barrier and thus it has a zero threshold voltage  $V_T$  and an infinite on:off current ratio at zero temperature. However, at finite temperatures, non-spin-flip thermally excited high-energy electrons as well as low-energy spin-flip excitations can give rise to leakage current and thus reduce the on:off ratio under a reverse bias. Moreover, due to the Ohmic HMM-SGS contact, the proposed diode has a much higher current drive capability and low resistance, which is advantageous compared to conventional semiconductor diodes. To demonstrate the linear  $I$ - $V$  characteristics of the concept, we construct a planar HMM-SGS junction based on 2D half-metallic Fe/MoS<sub>2</sub> and spin-gapless semiconducting VS<sub>2</sub> and employ the nonequilibrium Green's function method combined with density-functional theory (DFT). We find that at zero bias the VS<sub>2</sub> and Fe/MoS<sub>2</sub> electrodes couple ferromagnetically; however, this coupling changes sign from ferro to antiferromagnetic for a critical forward bias voltage of  $V = 180$  mV. The VS<sub>2</sub>-Fe/MoS<sub>2</sub> junction diode possesses linear  $I$ - $V$  characteristics for forward bias voltages up to  $V = 180$  mV and a very small threshold voltage of  $V_T = 30$  meV, which can be attributed to the minority-electron conduction-band minimum of the spin-gapless semiconducting VS<sub>2</sub> material. Moreover, we obtain a very high current density ( $J = 2350 \mu\text{A}/\mu\text{m}$  for  $V = 180$  mV), which makes the VS<sub>2</sub>-Fe/MoS<sub>2</sub> OSD highly promising for low-temperature nanoelectronic applications.

## II. HMM-SGS JUNCTIONS

The structure of the proposed OSD and its  $I$ - $V$  characteristics are shown schematically in Fig. 3. Analogous to the metal-semiconductor Schottky-barrier diode, the OSD is composed of a HMM electrode and a type-II SGS electrode. Depending on the magnetization direction of the electrodes, the diode conducts current either under forward bias [Fig. 3(a), parallel orientation (ferromagnetic interelectrode coupling)] or under reverse bias [Fig. 3(a), antiparallel orientation (antiferromagnetic interelectrode coupling)], similar to the case of the backward diode mentioned in Sec. I. In the presentation of the schematic  $I$ - $V$  characteristics of the OSD in Fig. 3, we assume that HMM material possesses a gap in the spin-up channel around the Fermi level, while type-II SGS material has a gap in the spin-up (spin-down) channel above (below) the Fermi level, as shown schematically in Fig. 2. In type-II SGSs, the conduction- and valence-band edges of the different spin channels touch at the Fermi energy, while in type-I SGSs the spin-up (majority-spin) band looks like the one in HMMs but the difference is in the spin-down (minority-spin) band. The valence- and conduction-band edges are touching at the Fermi energy, so that a zero-width gap




FIG. 3. (a) A schematic representation of the HMM-SGS junction for parallel orientation of the magnetization directions of the electrodes and the corresponding current-voltage ( $I$ - $V$ ) curves. (b) The same as (a) for the antiparallel orientation of the magnetization directions of the electrodes. The white arrows indicate the direction of the magnetization of the electrodes.

exists. One of the important advantages of type-I SGSs is that no energy is required for the excitation of the electrons from the valence to the conduction band and excited electrons or holes can be 100% spin-polarized as in HMMs. In construction of the OSD, the use of a type-I SGS instead of the HMM is also possible.

The linear  $I$ - $V$  characteristics of the OSD presented in Fig. 3(a) can be qualitatively explained on the basis of the schematic energy-band diagram shown in Fig. 4. If we assume that both HMM and SGS electrodes have the same work function and equal Fermi levels, then no charge transfer takes place between the electrodes. However, in real materials, due to different work functions there might be a charge transfer from one material to another at the interface, which might give rise to band bending for the SGS. Besides this, due to interactions, junction materials might not retain their half-metallic and spin-gapless semiconducting properties near the interface and hence the band diagram will not be as sharp as in Fig. 4. For the device configuration shown in Fig. 3(a), the relevant channel for the transport is the minority-spin (spin-down) channel, whereas the majority-spin (spin-up) channel is insulating due to the spin gap of the HMM material on the right-hand side of the junction. In the spin-down channel, the HMM behaves like a normal metal, with states below and above the Fermi energy, while the SGS electrode on the left-hand side behaves like a semiconductor (or insulator) but with a Fermi level touching the conduction-band minimum. Due to this electronic band structure of the SGS, in contrast to the Schottky diode, no energy barrier is formed at the interface between a HMM and a SGS material. Such a junction acts as an Ohmic contact under forward bias, as shown in Fig. 4(b). In this case, the spin-down electrons from the occupied valence band of the HMM electrode can flow into the unoccupied conduction band of the SGS electrode without experiencing a potential barrier, while for a reverse bias the current is blocked due to the spin gap of the HMM material [see Fig. 4(c)]. Note that under a forward bias, the current flowing through the OSD is 100% spin polarized. Note also that




FIG. 4. A schematic representation of the band diagram and thermal (non-spin-flip) electron-hole excitations for spin-up and spin-down electrons for the SGS-HMM contact for parallel (P) orientation of the magnetization directions of the electrodes: (a) for zero bias, (b) for forward bias, and (c) for reverse bias. The Fermi level is denoted by red dashed line. (d)–(f) The same as (a)–(c) for the antiparallel (AP) orientations of the magnetization directions of the electrodes [see Figs. 3(a) and 3(b)].

the same discussion applies in the case of antiparallel orientations of the magnetization directions of the electrodes [see Figs. 4(d), 4(e), and 4(f)].

As the HMM-SGS contact is Ohmic under a forward bias, the current  $I$  through the diode varies linearly with the applied voltage  $V$  and the ratio  $V/I$  gives the combination of the interface ( $R_I$ ) and series resistance ( $R_S$ ) of the HMM and SGS materials ( $V/I = R_I + R_S$ ). The resistance of SGS materials is usually much lower than that of conventional  $n$ - or  $p$ -type semiconductors [23] and thus the combination of low resistance with the Ohmic nature of the interface allows a much higher current drive capability of the proposed OSD. It is worth noting that diodes with low resistance are critical for the performance of high-speed electronic devices. Besides the higher current drive capability of the OSD, the threshold voltage  $V_T$  can be tuned by a proper choice of the SGS material. The value of  $V_T$  is set by the energy difference between the minority-spin conduction-band minimum and the Fermi level. In an ideal SGS, this difference is zero and thus  $V_T = 0$ . Note, however, that in type-II SGSs, the spin-gapless semiconducting properties are not protected by any symmetry and thus ideal SGS behavior can only arise if a free parameter—e.g., pressure, strain, or doping—is tuned to a specific value. A zero  $V_T$  allows one to detect extremely weak signals, even when no external bias circuit is used. Similar to the Schottky diode, the OSD is also a majority-carrier diode but it does not require doping and it will possess all the advantages of the Schottky diode, such as high operation frequencies, low resistance and capacitance, etc. Note also that, in principle, a Schottky diode can be turned into an Ohmic contact by heavily doping the semiconductor electrode; however, in this case it loses its diode functionality.

Up to now, the discussion of the  $I$ - $V$  characteristics of the OSD is based on the schematic band diagram at zero temperature and thus an infinite on:off current ratio can be achieved. However, at finite temperatures, thermally excited electrons and holes can significantly reduce the on:off ratio. At this point, it is important to note that in conventional metal-semiconductor Schottky diodes, electrons flow from the semiconductor to the metal electrode under a forward bias, whereas in the OSD shown in Fig. 3(a), the process is just the opposite, i.e., from the half-metal to the spin-gapless semiconductor. In the former case, the on-state current stems from the combination of thermionic emission over the Schottky barrier and tunneling through the barrier [24–26]. A very detailed analysis of these processes and their relative contributions to the total forward (on-state) current in Schottky diodes can be found in Ref. [24]. Similarly, under a reverse bias, both processes contribute to the leakage current in Schottky diodes, with a significant weight coming from the tunneling (or thermionic field emission), since in this case the height of the Schottky barrier is fixed and only a very small fraction of the thermally excited high-energy electrons, which are at the tail of the Fermi-Dirac distribution function, can pass over the barrier. By increasing the height of the Schottky barrier, the contribution of thermionic emission can be significantly reduced, as the Fermi-Dirac distribution function decays exponentially at high energies [see Fig. 3(a)]; however, the contribution of the tunneling through the barrier cannot be prevented and at the same time the threshold voltage  $V_T$  increases. In the OSD, the leakage current due to tunneling does not exist; however, thermally excited high-energy electrons contribute to the reverse current, similar to the case of the Schottky diode. In Figs. 5(b) and 5(c), we show schematically the population of unoccupied




FIG. 5. (a) The Fermi-Dirac distribution for  $T = 0$  K (black) and  $T > 0$  K (red) and a thermal population of states around the Fermi level for (b) a HMM and (c) type-II SGS. The occupied and unoccupied states above and below the Fermi level, respectively, are marked with a shaded red color.

states around the Fermi energy for a HMM and a type-II SGS. In a HMM, thermal population of the states obeys the Fermi-Dirac distribution, i.e., more states in the metallic spin-channel and very few states for the insulating spin-channel, as they are far from the Fermi level. However, the situation turns out to be slightly different in type-II SGSs, due to their band structure, i.e., only a small fraction of the electrons can be thermally excited due to the gap in both spin channels, somewhat similar to the case of intrinsic semiconductors. Consequently, the reverse-bias current (or the leakage current) is mainly determined by the size of the band gaps in SGS and HMM electrodes and by a proper choice of the large band-gap materials, the on:off current ratio can be significantly increased in OSDs. In addition to thermal excitation, spin-flip processes can reduce the on:off current ratio and this will be discussed later.

In contrast to the Schottky diode, the spin degree of freedom provides a rich configuration space for the  $I$ - $V$  curves of the OSD, which are determined by two parameters: (i) the magnetic coupling between electrodes, which allows the dynamical configuration of the diode in the case of antiferromagnetic interelectrode coupling via an external magnetic field; and (ii) the spin character of the gap in HMMs and SGSs. Depending on the magnetic coupling between electrodes, the OSD is in the on state either under forward bias (ferromagnetic interelectrode coupling or parallel orientation) or under reverse bias (antiferromagnetic interelectrode coupling or antiparallel orientation), as shown in Fig. 3. The second parameter, which plays a decisive role in determining the  $I$ - $V$  characteristics of the OSD, is the spin-channel dependence of the gap in HMM and SGS electrodes. For instance, as mentioned above in the presentation of the schematic  $I$ - $V$  characteristics of the OSD in Fig. 3, we assume that the HMM material has a gap in the spin-up channel and that the SGS material has gaps in the spin-down (below  $E_F$ ) and spin-up channels (above  $E_F$ ). Although all known type-II SGSs possess an electronic band structure similar to that in Fig. 2(c), there

TABLE I. The  $I$ - $V$  characteristics of the OSD for parallel (P) and antiparallel (AP) orientations of the magnetization directions of the electrodes and all possible combinations of the spin character of the gaps in HMMs and SGSs. SGS( $\downarrow\uparrow$ ) indicates the spin channel, where the gap exists below and above the Fermi level.

Spin gap	Orientation	Forward bias	Reverse bias
SGS ( $\downarrow\uparrow$ )/HMM ( $\uparrow\uparrow$ )	P	On	Off
SGS ( $\downarrow\uparrow$ )/HMM ( $\uparrow\downarrow$ )	AP	Off	On
SGS ( $\downarrow\uparrow$ )/HMM ( $\downarrow\downarrow$ )	P	Off	On
SGS ( $\uparrow\downarrow$ )/HMM ( $\downarrow\downarrow$ )	AP	On	Off
SGS ( $\uparrow\downarrow$ )/HMM ( $\uparrow\uparrow$ )	P	Off	On
SGS ( $\uparrow\downarrow$ )/HMM ( $\uparrow\downarrow$ )	AP	On	Off
SGS ( $\uparrow\downarrow$ )/HMM ( $\downarrow\downarrow$ )	P	On	Off
SGS ( $\uparrow\downarrow$ )/HMM ( $\downarrow\uparrow$ )	AP	Off	On

are many HMMs, such as Heusler alloys, with a gap in the spin-down channel and OSD diodes constructed from such materials might have a different current direction than the present case. For completeness, in Table I we present the  $I$ - $V$  characteristics of the OSD by taking into account both magnetic configurations of the electrodes and all possible combinations of the spin character of the gaps in HMMs and SGSs.

As the OSD is comprised of magnetic materials, its operation temperature is limited by the Curie temperature  $T_C$  of the constituent materials and thus for realization of the OSD, HMMs and SGSs with high  $T_C$  values are required. Two-dimensional transition-metal dichalcogenides [27–30] and 3D quaternary Heusler compounds [31–36] offer a unique platform to design, within the same family of compounds, HMMs and SGSs with high  $T_C$  values and similar lattice parameters and compositions, which allow coherent growth of these materials on top of each other. Besides high  $T_C$  values, large spin gaps in HMMs and SGSs are crucial in order to achieve a high on:off current ratio in the OSD. In recent years, 2D transition-metal dichalcogenides have received significant experimental and theoretical interest, as they present unique electronic, optical, mechanical, and magnetic properties, thus holding great promise for a wide range of device applications. Devices ranging from vertical tunnel diodes to vertical and lateral tunnel field-effect transistors (TFETs) have been experimentally demonstrated [37–44]. In particular, 2D lateral heterojunctions have opened up a direction in materials science and device applications [45]. TFETs based on 2D material heterojunctions (WTe<sub>2</sub>-MoS<sub>2</sub>, MoTe<sub>2</sub>-MoS<sub>2</sub>) have been reported to exhibit a subthreshold slope below 5 mV per decade and high  $I_{\text{on}}/I_{\text{off}}$  ratios (approximately  $10^8$ ) at a low drain bias of 0.3 V, making them ideal candidates for ultralow-power computing [46].

Among the 2D transition-metal dichalcogenides, V-based compounds (VS<sub>2</sub>, VSe<sub>2</sub>, VTe<sub>2</sub>) have attracted

particular interest due to their intrinsic ferromagnetism. These compounds can crystallize into two different structures: the  $1H$  phase and the  $1T$  phase. The former phase is energetically more stable and possesses a SGS ground state [47,48]. Although, theoretically, both  $1H$  and  $1T$  phases of  $V$ -based 2D compounds have been predicted to show ferromagnetism [49], experimentally the ferromagnetism has, however, only been observed in the  $1T$  phase of  $VS_2$  [50] and  $VSe_2$  [51]. Note that the  $1T$  phase of  $VSe_2$  does not present SGS behavior; it is a normal ferromagnetic metal. However, in the one-monolayer limit, several 2D transition-metal dichalcogenides can adopt either a  $1T$  or a  $1H$  structure depending on the growth conditions [52]. It is very likely that  $VS_2$  can also be grown in a  $1H$  structure.

### III. COMPUTATIONAL METHOD

Ground-state electronic structure calculations are carried out using DFT, implemented in the QuantumATK P-2019.03 package [53]. We use the generalized-gradient-approximation (GGA)–Perdew–Burke–Ernzerhof (PBE) exchange–correlation functional [54] together with PseudoDojo pseudopotentials [55] and LCAO basis sets. A dense  $24 \times 24 \times 1$   $\mathbf{k}$ -point grid and a density mesh cutoff of 120 hartree are used. To prevent interactions between the periodically repeated images, 20 Å of vacuum are added and Dirichlet and Neumann boundary conditions are employed. The electron temperature is set to 10 K. The total energy and forces converge to at least  $10^{-4}$  eV and 0.01 eV/Å, respectively. In order to estimate the magnetic anisotropy energy, we employ the magnetic force theorem, including spin-orbit coupling [56].

The transport calculations are performed using DFT combined with the nonequilibrium Green’s function method (NEGF). We use a  $24 \times 1 \times 172$   $\mathbf{k}$ -point grid in self-consistent DFT-NEGF calculations. The  $I$ - $V$  characteristics are calculated within a Landauer approach [57], where  $I(V) = (2e/h) \sum_{\sigma} \int T^{\sigma}(E, V) [f_L(E, V) - f_R(E, V)] dE$ . Here,  $V$  denotes the bias voltage,  $T^{\sigma}(E, V)$  is the spin-dependent transmission coefficient for an electron with spin  $\sigma$ , and  $f_L(E, V)$  and  $f_R(E, V)$  are the Fermi-Dirac distributions of the left and right electrodes, respectively. The transmission coefficient  $T^{\sigma}(E, V)$  is calculated using a  $300 \times 1$   $\mathbf{k}$ -point grid.

### IV. RESULTS AND DISCUSSION

The OSD concept introduced in Sec. II can be realized either by using 3D Heusler compounds or 2D transition-metal dichalcogenides. In the following, due to their structural simplicity, we focus on the 2D materials and demonstrate the proof of principle by *ab initio* quantum transport calculations. As the electrode materials of the OSD, we choose  $VS_2$  and  $Fe/MoS_2$ . The former is an intrinsic ferromagnet with spin-gapless semiconducting

behavior in the monolayer  $1H$  phase, while the half-metallic ferromagnetism in the latter  $Fe/MoS_2$  material is achieved by functionalization of the  $1H$  semiconducting  $MoS_2$ . Based on first-principles calculations, Jiang *et al.* [58] have shown that deposition of the Fe atoms on  $MoS_2$  gives rise to the 2D half-metallic ferromagnetism with a relatively high  $T_C$  value of 465 K and a large spin gap, which makes the  $Fe/MoS_2$  a promising material for spintronic and nanoelectronic applications.

Since the electronic and magnetic as well as the structural properties of both electrode materials have been extensively discussed in the literature, in the following we will briefly overview their basic properties, which will be necessary in order to understand the transport characteristics of the OSD. In Table II, we present the optimized lattice constants and the total magnetic moments as well as the magnetic anisotropy energies for the  $1H$  phase of  $VS_2$  and  $Fe/MoS_2$ . Our ground-state calculations for both materials are in good agreement with previously published data. In particular, similar lattice parameters and compositions, as well as the same  $1H$  phase, of the two materials are crucial for realization of the planar  $VS_2$ - $Fe/MoS_2$  heterojunctions.  $VS_2$  has a relatively simple band structure, shown in Fig. 6(b), where the exchange splitting of the  $V$ - $3d$  (predominantly  $d_{z^2}$ ) bands around the Fermi energy is responsible for its spin-gapless semiconducting nature and thus it has a magnetic moment of  $1 \mu_B$ , carried by the V atom. Furthermore,  $VS_2$  is not a perfect SGS; it has a very small indirect band gap of 50 meV, i.e., the valence-band maximum and the conduction-band minimum are at around 20 meV and 30 meV, respectively. The former plays a decisive role in determining the threshold voltage  $V_T$  of the OSD in the case of ferromagnetic coupling of the  $VS_2$  and  $Fe/MoS_2$  electrodes, while the latter plays the same role in the case of antiferromagnetic coupling. Note that in the present OSD based on a planar  $VS_2$ - $Fe/MoS_2$  heterostructure, the coupling between the electrodes is ferromagnetic, as is discussed later. On the other hand, the Fe-deposited  $MoS_2$  turns into a half-metallic magnet with a gap of about 1 eV in the spin-up channel and with a total magnetic moment of  $2 \mu_B$ , which is localized on the Fe atom. Note that PBE is well known to underestimate the band gap of semiconductors compared to the more accurate  $GW$  approach. However, the situation is different for 2D SGSs, since the application of the  $GW$  method for the similar material  $VSe_2$  reduces the band gap from 250 meV (PBE) to 170 meV [29]. We expect a similar behavior for the  $VS_2$  compound when the  $GW$  method is employed. Also, spin-orbit coupling has a negligible effect on the spin polarization of both materials and thus it is not taken into account in our device calculations.

In Fig. 6(a), we show the atomic structure of the OSD, which is formed by joining one monolayer of  $VS_2$  (left electrode) and one monolayer of  $Fe/MoS_2$  (right electrode) laterally in a single plane. Due to the almost




FIG. 6. (a) The atomic structure of the  $\text{VS}_2$ - $\text{Fe}/\text{MoS}_2$  Ohmic spin diode. The arrows show the magnetic moments of V and Fe atoms in the SGS and HMM electrodes within the scattering region. The size of the arrows is proportional to the magnitude of the magnetic moments. The system is periodic in the  $x$  direction in the plane orthogonal to the magnetization direction, which is also the transport direction. The vertical dashed lines denote the interface. (b) The calculated spin-resolved bulk electronic band structure along the high-symmetry lines in the Brillouin zone for  $\text{VS}_2$  (left-hand panel) and  $\text{Fe}/\text{MoS}_2$  (right-hand panel). For both compounds, the dashed lines denote the Fermi energy, which is set to zero.

identical lattice parameters of both materials, as well as their similar compositions, they form a perfect interface. We assume periodicity of the device in the  $x$  direction. The  $z$  direction is chosen as the transport direction. The total length of the scattering region is about  $115.5 \text{ \AA}$ , which consists of  $77 \text{ \AA}$   $\text{VS}_2$  and  $38.5 \text{ \AA}$   $\text{Fe}/\text{MoS}_2$ . The length of the former electrode is chosen to be larger because of the longer screening length in SGSs.

When the half-metallic  $\text{Fe}/\text{MoS}_2$  makes contact with  $\text{VS}_2$ , free electrons will flow from the half-metallic  $\text{Fe}/\text{MoS}_2$  side to the spin-gapless semiconducting  $\text{VS}_2$  side, because the work function of the  $\text{Fe}/\text{MoS}_2$  is smaller than that of  $\text{VS}_2$  (see Table II). Note that the work function of the SGS  $\text{VS}_2$  is defined in the same way as in metals, i.e., the energy difference between the vacuum level and the

TABLE II. The calculated lattice parameter  $a$ , the total magnetic moment  $m_T$ , the magnetic anisotropy energy  $K$  (per formula unit), and the work function  $\phi$  for  $\text{VS}_2$  and  $\text{Fe}/\text{MoS}_2$ . The values of the Curie temperature  $T_C$  are taken from the literature.

Compound	$a$ ( $\text{\AA}$ )	$m_T$ ( $\mu_B$ )	$K$ (meV)	$\phi$ (eV)	$T_C$ (K)
$\text{VS}_2$	3.174	1.00	0.20	5.71	138 [49]
$\text{Fe}/\text{MoS}_2$	3.175	2.00	0.42	4.72	465 [58]

Fermi energy  $E_F$ . When the charge redistribution reaches equilibrium, near the interface region the  $\text{Fe}/\text{MoS}_2$  will be positively charged, whereas the  $\text{VS}_2$  will be negatively charged. Thus, an electric dipole will be induced at the interface region. Such a charge redistribution influences the electronic and magnetic properties of the materials near the interface, as seen in the zero-bias projected device density of states (DDOS) shown in Fig. 7. Near the interface, charge transfer takes place within the spin-down channel and thus the magnetic moment of the Fe atoms increases toward the interface, i.e.,  $2.15 \mu_B \rightarrow 2.17 \mu_B \rightarrow 2.56 \mu_B$ , as shown by the arrows in Fig. 6(a), where the size of the arrows is proportional to the magnitude of the magnetic moments. The transferred charge occupies the spin-down channel on the  $\text{VS}_2$  side by creating interface states, which can be clearly seen on the projected DDOS shown in Fig. 7 and as a consequence the magnetic moment of the V atoms at the interface and subinterface lines is reduced from its bulk value of  $1.13 \mu_B$  to  $0.53 \mu_B$  and  $0.95 \mu_B$ , respectively. As can be seen, the influenced region is rather small, being within four atomic lines and restricted to the spin-down channel. The change in the spin-up channel is more or less negligible.

Long-range magnetic order is prohibited in 2D magnets at finite temperatures due to the Mermin-Wagner




FIG. 7. (a) The zero-bias projected device density of states (DDOS) for the majority (left-hand panel) and minority (right-hand panel) electrons for the Ohmic spin diode around the interface (see Fig. 6 for the atomic structure of the OSD). The horizontal white dashed lines indicate the Fermi level. The vertical red dashed lines denote the interface.

theorem [59]. However, this restriction can be removed by magnetic anisotropy and it enables the occurrence of 2D magnetic order at finite temperatures. For both materials, we calculate the magnetic anisotropy energies  $K$ , which are presented in Table II. Both materials have an in-plane magnetization with  $K$  values of 0.2 meV ( $\text{VS}_2$ ) and 0.42 meV ( $\text{Fe}/\text{MoS}_2$ ). However, the magnetic anisotropy within the plane for  $\text{VS}_2$  is negligibly small (a few nano-electronvolts), while for  $\text{Fe}/\text{MoS}_2$  it is around  $5 \mu\text{eV}$ , which is large enough for a finite-temperature magnetic order. The negligible value of  $K$  for  $\text{VS}_2$  implies the lack of finite-temperature magnetic order by virtue of the Mermin-Wagner theorem. However, room-temperature ferromagnetism has been experimentally detected in similar materials such as  $\text{VSe}_2$  [51], which has also negligible in-plane magnetic anisotropy, and the origin of the long-range ferromagnetic order is attributed to the finite-size effects [60,61]. However, in the  $\text{VS}_2$ - $\text{Fe}/\text{MoS}_2$  junction, the  $\text{Fe}/\text{MoS}_2$  acts as a pinning electrode, which introduces a preferred in-plane magnetic orientation in the  $\text{VS}_2$  electrode via the ferromagnetic interelectrode coupling. Our calculations show that ferromagnetic interelectrode coupling is preferable compared to antiferromagnetic interelectrode coupling and that the energy difference between the two configurations is about 22 meV.

Besides the magnetic anisotropy energy  $K$  and the interelectrode coupling, another important parameter for the realization of the OSD is the Curie temperature  $T_C$  of the constituent materials. The  $T_C$  values for both materials have been estimated from first principles in Refs. [49] and [58] (see Table II). The  $T_C$  value of  $\text{Fe}/\text{MoS}_2$  is higher than room temperature, while for  $\text{VS}_2$  ( $T_C = 139$  K) it is below room temperature. Nevertheless, such a value is high enough for an experimental demonstration of the device.

Next, we discuss the electronic and transport properties of the OSD under a finite bias voltage. As mentioned above, although at zero bias the coupling between the

SGS and HMM electrodes is ferromagnetic, we find that this coupling changes sign from ferromagnetic to antiferromagnetic under a forward bias of about 180 mV. Note that electric field or voltage control of magnetism on the nanoscale is highly appealing for the development of nanoelectronic devices with low power consumption [62–64]. A voltage-induced interlayer exchange coupling in magnetic tunnel junctions has been discussed theoretically via high-voltage tunneling [65–67] and has been experimentally demonstrated via mobile oxygen vacancies [68]. A sign change in magnetic coupling with the bias voltage allows the realization of devices with unique functionalities, which will be considered in a separate paper. In Figs. 8(a) and 8(b), we show the spin-resolved projected DDOS for bias voltages of 0.3 V (forward bias) and  $-0.3$  V (reverse bias), respectively. Note that for the purpose of the demonstration of the OSD concept, we constrain the magnetic coupling between electrodes to the ferromagnetic state (parallel orientation) in the  $\text{VS}_2$ - $\text{Fe}/\text{MoS}_2$  junction for bias voltages higher than 180 mV. As can be seen, for a forward bias, the spin-gapless and the half-metallic behavior is more or less preserved at the interface for both spin channels. Just a few new states arise at the interface in the spin-up channel, this being due to antiferromagnetic coupling of the single V atom at the interface. The interface V atom possesses a magnetic moment of  $-0.55 \mu_B$  and variation of the magnetic moments in Fe and other V atoms near the interface is also negligible.

On the other hand, for a reverse bias, the coupling between electrodes remains ferromagnetic and thus the electronic and magnetic structure near the interface is similar to the zero-bias case with the exception of the band bending in the  $\text{VS}_2$  electrode, which takes place near the interface region, within 40 Å. Note that the band bending is not linear due to charge transfer as well as the complex metallic screening of the  $\text{Fe}/\text{MoS}_2$  electrode. Indeed, we observe a flat region of about 15 Å on the






FIG. 8. (a) The projected device density of states (DDOS) for the majority (left-hand panel) and minority (right-hand panel) electrons for the  $\text{VS}_2\text{-Fe/MoS}_2$  Ohmic spin diode (see Fig. 6 for the atomic structure of the Ohmic spin diode) under a positive voltage of  $V = 0.3$  V. The middle panel shows the calculated transmission spectrum for the majority and minority electrons for the same applied voltage of  $V = 0.3$  V. The upper and lower white (black) dashed lines indicate the Fermi level of the SGS and HMM electrodes. (b) The same as (a) for a negative voltage of  $V = -0.3$  V.

projected DDOS [see Fig. 8(b)] of the junction on the  $\text{VS}_2$  side and then the potential drops more or less linearly with distance.

The  $I$ - $V$  characteristics of the  $\text{VS}_2\text{-Fe/MoS}_2$  OSD can be qualitatively explained on the basis of the projected DDOS shown in Fig. 8. For a forward bias, the OSD is in the on state, i.e., minority-spin electrons from the occupied states of the  $\text{Fe/MoS}_2$  electrode can flow into the unoccupied states of the  $\text{VS}_2$  electrode due to the Ohmic contact and thus the transmission coefficient takes finite values within the bias window, as shown in the middle panel of Fig. 8(a). Meanwhile, for majority-spin electrons the transmission coefficient is zero because both  $\text{Fe/MoS}_2$  and  $\text{VS}_2$  have no states within the voltage window. Thus the on-state current of the OSD is 100% spin polarized. On the other hand, for a reverse bias voltage, no current flows through the OSD, since the energy gap in the majority spin channel of the  $\text{Fe/MoS}_2$  electrode prevents the flow of the spin-up electrons from the  $\text{VS}_2$  electrode into the  $\text{Fe/MoS}_2$  [see Fig. 8(b) left-hand panel], giving rise to a zero transmission coefficient. Similarly, the transmission coefficient for the spin-down channel is also zero due to the energy gap in the  $\text{VS}_2$  electrode below the Fermi level.

Figure 9 shows the calculated  $I$ - $V$  characteristics of the  $\text{VS}_2\text{-Fe/MoS}_2$  OSD at zero temperature. In the on state, the current increases linearly with the applied bias and reaches  $2350 \mu\text{A}/\mu\text{m}$  for a bias voltage of 180 mV, which is the maximum bias voltage at which ferromagnetic coupling between electrodes is retained. The  $\text{VS}_2\text{-Fe/MoS}_2$  diode possesses a very small threshold voltage of about 30 mV, stemming from the indirect band gap of the SGS  $\text{VS}_2$  electrode, which has a conduction-band minimum of 30 meV [see Fig. 6(b)] as discussed before. For bias voltages larger than 180 mV, the  $I$ - $V$  curve of the OSD takes a plateau shape, i.e., the current first monotonically increases up to 250 mV and then it starts to decrease. Such behavior can be attributed to the antiferromagnetic coupling of a single V atom at the interface, which now has a gap in the spin-down channel above the Fermi energy, in contrast to the rest of the atoms in the junction. This energy gap acts as a small potential barrier, giving rise to more reflection of the electrons, and thus it reduces the transmission. Furthermore, in the bias-voltage range from 180 mV to 300 mV, the magnetic moment of the V atom at the interface increases from  $-0.2 \mu_B$  to  $-0.55 \mu_B$ , which also explains the plateaulike shape of the  $I$ - $V$  curve at higher voltages.




FIG. 9. The calculated current-voltage ( $I$ - $V$ ) characteristics of the  $\text{VS}_2$ -Fe/MoS<sub>2</sub> Ohmic spin diode. The red line shows the Ohmic behavior in the voltage range between 40 mV and 180 mV. The inset shows an enlargement of the range between -10 mV to 60 mV, to specify the threshold voltage  $V_T$ .

A feature of the proposed  $\text{VS}_2$ -Fe/MoS<sub>2</sub> OSD is that it has a much higher current-drive capability, i.e., in the on state, for a bias voltage of  $V = 180$  meV the calculated current density turns out to be around  $I = 2350 \mu\text{A}/\mu\text{m}$ . This value is much higher than the on-state current density of devices based on 2D semiconducting materials [69] and lies far above the International Roadmap for Devices and Systems (IRDS) [69,70] requirement ( $1350 \mu\text{A}/\mu\text{m}$ ). A negligible turn-on voltage of  $V_T = 30$  mV allows us to detect extremely weak signals and thus the OSD might find potential applications in antenna-coupled diode solar cells [71–73]. Besides this, the  $\text{VS}_2$ -Fe/MoS<sub>2</sub> OSD possesses an infinite on:off current ratio at zero temperature. However, as discussed in Sec. II, thermally excited high-energy electrons would reduce the on:off current ratio to finite values. In the Landauer formalism of electronic current, the temperature effects can be taken into account via the Fermi-Dirac distribution function of the left [ $f_L(E, V, T)$ ] and right [ $f_R(E, V, T)$ ] electrodes (see Ref. [24]) and thus the on:off current ratio can be calculated for a given temperature  $T$ . However, this standard treatment should be modified for SGS materials due to their electronic band structure, which is discussed in Sec. II. Specifically, each spin channel of the SGS material with a proper population of the states above and below the Fermi energy should be taken into account. Since this modification has not been implemented in the current version of the QuantumATK package, we present the  $I$ - $V$  characteristics only for zero temperature in Fig. 9.

As mentioned in Sec. II, the spin degree of freedom brings a certain functionality to the OSD, which can be dynamically configured by an external magnetic field; thus the OSD can be used as a switch. However, this is possible only for OSDs having electrodes that couple antiferromagnetically (the AP orientation). So in this case,

in reversing the magnetization direction of one electrode from the antiparallel to the parallel orientation, the OSD switches from the on state to the off state like a transistor. This switching can be easily understood with the help of the schematic band diagram shown in Fig. 4 and will not be discussed here. The situation is even more interesting in the case of  $\text{VS}_2$ -Fe/MoS<sub>2</sub> OSD, i.e., in addition to the voltage-induced switching from the on state to the off state at around  $V = 180$  mV, the OSD can again be switched back to the on state by a weak external magnetic field, making the  $\text{VS}_2$ -Fe/MoS<sub>2</sub> OSD highly appealing for nanoelectronic applications.

Finally, we would like to comment on the effect of low-energy spin excitations on the  $I$ - $V$  characteristics of the  $\text{VS}_2$ -Fe/MoS<sub>2</sub> OSD. Apart from the high-energy thermal (non-spin-flip) excitations that we discuss in Sec. II, the temperature affects the electronic and magnetic structure of the  $\text{VS}_2$  and Fe/MoS<sub>2</sub> via spin-dependent excitations, i.e., Stoner excitation and collective spin waves or magnons. In type-II SGSs such as  $\text{VS}_2$ , electrons can be excited from the majority-spin channel to the minority-spin channel via spin flip with almost vanishing energy [see Fig. 2(c)]. These excitations are known as single-particle Stoner excitations. They can populate the unoccupied minority-spin channel of  $\text{VS}_2$  just above the Fermi energy. However, in  $\text{VS}_2$ , Stoner excitations require a large momentum transfer, since the valance-band maximum and the conduction-band minimum are at different  $\mathbf{k}$  points in the Brillouin zone. The former is at the  $\Gamma$  point, while the latter is close to the  $M$  point [for the band structure of  $\text{VS}_2$ , see Fig. 6(b)] and thus single-particle spin-flip excitation requires a large momentum transfer and takes place at high temperatures close to the Curie temperature  $T_C$ . Nevertheless, they can populate the unoccupied minority channel above the Fermi energy and give rise to a leakage current under a reverse bias [see Fig. 4(c)]. Moreover, the on:off current ratio will be further reduced. On the other hand, in half-metallic Fe/MoS<sub>2</sub>, Stoner excitations are not allowed due to the existence of the spin gap; however, at finite temperatures, electron-magnon interaction can give rise to the appearance of nonquasiparticle states within the half-metallic gap just above the Fermi energy [74]. Thus, such states can reduce the spin polarization of the half-metallic Fe/MoS<sub>2</sub> and affect its transport properties. Lastly, in addition to non-spin-flip as well as spin-flip excitations, defects at the interface, which destroy the SGS or HMM behavior, can also reduce the on:off current ratio of the OSD.

## V. CONCLUSIONS

In conclusion, we propose a diode concept that we call the OSD, based on SGS and HMM materials. Analogous to the metal-semiconductor junction diode (the Schottky-barrier diode), HMM-SGS junctions act as a diode the operation principle of which relies on the

spin-dependent transport properties of the constituent HMM and SGS materials. We show that the HMM and SGS materials form an Ohmic contact under any finite forward bias voltage, giving rise to linear  $I$ - $V$  characteristics, while for a reverse bias the current is blocked due to spin-dependent filtering of the electrons. In contrast to the Schottky diode, the proposed OSD does not require doping of the SGS electrode and it also does not have a junction barrier; thus it has a zero threshold voltage  $V_T$  and an infinite on:off current ratio at zero temperature. However, at finite temperatures, non-spin-flip thermally excited high-energy electrons as well as low-energy spin-flip excitations can give rise to a leakage current and thus reduce the on:off ratio under a reverse bias. As the leakage current is mainly determined by the size of the band gaps in SGS and HMM electrodes and by a proper choice of large band-gap materials, the on:off current ratio can be significantly increased in OSDs. Moreover, the spin degree of freedom provides a rich configuration space for the  $I$ - $V$  characteristics of the OSD, which are determined by two parameters: (i) the spin character of the gap in HMM and SGS; and (ii) the magnetic coupling between electrodes, which allows the dynamical configuration of the diode in the case of antiferromagnetic coupling (antiparallel orientation) via an external magnetic field. We show that depending on the magnetic coupling between electrodes, the OSD is in the on state either under forward bias (parallel orientation) or under reverse bias (antiparallel orientation).

By employing the NEGF method combined with DFT, we demonstrate the rectification characteristics of the proposed OSD based on 2D half-metallic Fe/MoS<sub>2</sub> and spin-gapless semiconducting VS<sub>2</sub> planar heterojunctions. We find that the VS<sub>2</sub>-Fe/MoS<sub>2</sub> junction diode possesses linear  $I$ - $V$  characteristics for forward bias voltages up to 180 mV and that a bias voltage-induced ferromagnetic to antiferromagnetic interelectrode coupling then takes place. Such a sign change in magnetic coupling with bias voltage allows the realization of devices with unique functionalities, which will be considered in a separate paper. Moreover, the VS<sub>2</sub>-Fe/MoS<sub>2</sub> OSD has a much higher current-drive capability ( $I = 2350 \mu\text{A}/\mu\text{m}$ ) and a very small threshold voltage of  $V_T = 30$  mV, which allows us to detect extremely weak signals; thus it might find potential applications in antenna-coupled diode solar cells. We expect that our results will pave the way for experimentalists to fabricate the OSD based on 2D materials.

#### ACKNOWLEDGMENTS

E.Ş. and I.M. acknowledge support from *Sonderforschungsbereich* TRR 227 of the Deutsche Forschungsgemeinschaft (DFG) and funding provided by the European Union (EFRE), Grant No. ZS/2016/06/79307.

E.Ş. and T.A. contributed equally to this work.

- [1] Simon M. Sze and Kwok K. Ng, *Physics of Semiconductor Devices* (John Wiley & Sons, Hoboken, 2007), 3rd ed.
- [2] Umesh K. Mishra and Jasprit Singh, *Semiconductor Device Physics and Design* (Springer Science & Business Media, Dordrecht, 2008).
- [3] J.-P. Colinge and Cynthia A. Colinge, *Physics of Semiconductor Devices* (Springer Science & Business Media, New York, 2006).
- [4] Leo Esaki, New phenomenon in narrow germanium  $p$ - $n$  junctions, *Phys. Rev.* **109**, 603 (1958).
- [5] Xiaochi Liu, Deshun Qu, Hua-Min Li, Inyong Moon, Faisal Ahmed, Changsik Kim, Myeongjin Lee, Yongsuk Choi, Jeong Ho Cho, James C. Hone *et al.*, Modulation of quantum tunneling via a vertical two-dimensional black phosphorus and molybdenum disulfide  $p$ - $n$  junction, *ACS Nano* **11**, 9143 (2017).
- [6] Krishna Murali, Medha Dandu, Sarthak Das, and Kausik Majumdar, Gate-tunable WSe<sub>2</sub>/SnSe<sub>2</sub> backward diode with ultrahigh-reverse rectification ratio, *ACS Appl. Mater. Interfaces* **10**, 5657 (2018).
- [7] M. McColl, M. F. Millea, and A. H. Silver, The superconductor-semiconductor Schottky barrier diode detector, *Appl. Phys. Lett.* **23**, 263 (1973).
- [8] M. McColl, R. J. Pedersen, M. F. Bottjer, M. F. Millea, A. H. Silver, and F. L. Vernon, Jr., The super-Schottky diode microwave mixer, *Appl. Phys. Lett.* **28**, 159 (1976).
- [9] A. W. Kleinsasser, T. N. Jackson, D. McInturff, F. Rammo, G. D. Pettit, and J. M. Woodall, Crossover from tunneling to metallic behavior in superconductor-semiconductor contacts, *Appl. Phys. Lett.* **57**, 1811 (1990).
- [10] A. W. Kleinsasser and A. Kastalsky, Excess voltage and resistance in superconductor-semiconductor junctions, *Phys. Rev. B* **47**, 8361 (1993).
- [11] Shun-Tsung Lo, Kuang Yao Chen, Sheng-Di Lin, J.-Y. Wu, T. L. Lin, M. R. Yeh, T.-M. Chen, and C.-T. Liang, Controllable disorder in a hybrid nanoelectronic system: Realization of a superconducting diode, *Sci. Rep.* **3**, 2274 (2013).
- [12] Dimtry Panna, Krishna Balasubramanian, Shlomi Bouscher, Yujia Wang, Pu Yu, Xi Chen, and Alex Hayat, Nanoscale high- $T_c$  YBCO/GaN super-Schottky diode, *Sci. Rep.* **8**, 5597 (2018).
- [13] Zixu Zhu, Saumil Joshi, Sachit Grover, and Garret Moddel, Graphene geometric diodes for terahertz rectennas, *J. Phys. D: Appl. Phys.* **46**, 185101 (2013).
- [14] Zixu Zhu, Saumil Joshi, and Garret Moddel, High performance room temperature rectenna IR detectors using graphene geometric diodes, *IEEE J. Sel. Top. Quantum Electron.* **20**, 70 (2014).
- [15] Gregory Auton, Dmytro B. But, Jiawei Zhang, Ernie Hill, Dominique Coquillat, Christophe Consejojo, Philippe Nouvel, Wojciech Knap, Luca Varani, Frederic Teppe, Jeremie Torres, and Aimin Song, Terahertz detection and imaging using graphene ballistic rectifiers, *Nano Lett.* **17**, 7015 (2017).
- [16] Taehee Kang, R. H. Joon-Yeon Kim, Geunchang Choi, Jaiu Lee, Hyunwoo Park, Hyeongtag Jeon, Cheol-Hwan Park, and Dai-Sik Kim, Terahertz rectification in ring-shaped quantum barriers, *Nat. Commun.* **9**, 4914 (2018).

- [17] Nianbei Li and Jie Ren, Non-reciprocal geometric wave diode by engineering asymmetric shapes of nonlinear materials, *Sci. Rep.* **4**, 6228 (2014).
- [18] X. L. Wang, Proposal for a New Class of Materials: Spin Gapless Semiconductors, *Phys. Rev. Lett.* **100**, 156404 (2008).
- [19] Xiaolin Wang, Germanas Peleckis, Chao Zhang, Hideo Kimura, and Shixue Dou, Colossal electroresistance and giant magnetoresistance in doped PbPdO<sub>2</sub> thin films, *Adv. Mater.* **21**, 2196 (2009).
- [20] R. A. De Groot, F. M. Mueller, P. G. Van Engen, and K. H. J. Buschow, New Class of Materials: Half-Metallic Ferromagnets, *Phys. Rev. Lett.* **50**, 2024 (1983).
- [21] E. Şaşıoğlu and S. Blügel, Magnetic tunnel diode and magnetic tunnel transistor, U.S. Patent No. US20180309047A1 (2016).
- [22] Ersoy Şaşıoğlu, Stefan Blügel, and Ingrid Mertig, Proposal for reconfigurable magnetic tunnel diode and transistor, *Appl. Electron. Mater.* **1**, 1552 (2019).
- [23] Siham Ouardi, Gerhard H. Fecher, Claudia Felser, and Jürgen Kübler, Realization of Spin Gapless Semiconductors: The Heusler Compound Mn<sub>2</sub>CoAl, *Phys. Rev. Lett.* **110**, 100401 (2013).
- [24] Daniele Stradi, Umberto Martinez, Anders Blom, Mads Brandbyge, and Kurt Stokbro, General atomistic approach for modeling metal-semiconductor interfaces using density functional theory and nonequilibrium Green's function, *Phys. Rev. B* **93**, 155302 (2016).
- [25] H. Zhang, E. J. Miller, and E. T. Yu, Analysis of leakage current mechanisms in Schottky contacts to GaN and Al<sub>0.25</sub>Ga<sub>0.75</sub>N/GaN grown by molecular-beam epitaxy, *J. Appl. Phys.* **99**, 023703 (2006).
- [26] A. Latreche, Combined thermionic emission and tunneling mechanisms for the analysis of the leakage current for Ga<sub>2</sub>O<sub>3</sub> Schottky barrier diodes, *SN Appl. Sci.* **1**, 188 (2019).
- [27] Mingsheng Xu, Tao Liang, Minmin Shi, and Hongzheng Chen, Graphene-like two-dimensional materials, *Chem. Rev.* **113**, 3766 (2013).
- [28] Nicolas Mounet, Marco Gibertini, Philippe Schwaller, Davide Campi, Andrius Merkys, Antimo Marrazzo, Thibault Sohier, Ivano Eligio Castelli, Andrea Cepellotti, Giovanni Pizzi, and Nicola Marzari, Two-dimensional materials from high-throughput computational exfoliation of experimentally known compounds, *Nat. Nanotechnol.* **13**, 246 (2018).
- [29] Sten Hastrup, Mikkel Strange, Mohnish Pandey, Thorsten Deilmann, Per S. Schmidt, Nicki F. Hinsche, Morten N. Gjerding, Daniele Torelli, Peter M. Larsen, Anders C. Riis-Jensen, Jakob Gath, Karsten W. Jacobsen, Jens J. Mortensen, Thomas Olsen, and Kristian S. Thygesen, The computational 2D materials database: High-throughput modeling and discovery of atomically thin crystals, *2D Mater.* **5**, 042002 (2018).
- [30] M. Gibertini, M. Koperski, A. F. Morpurgo, and K. S. Novoselov, Magnetic 2D materials and heterostructures, *Nat. Nanotechnol.* **14**, 408 (2019).
- [31] K. Özdoğan, E. Şaşıoğlu, and I. Galanakis, Slater-Pauling behavior in LiMgPdSn-type multifunctional quaternary Heusler materials: Half-metallicity, spin-gapless and magnetic semiconductors, *J. Appl. Phys.* **113**, 193903 (2013).
- [32] Sergey V. Faleev, Yari Ferrante, Jaewoo Jeong, Mahesh G. Samant, Barbara Jones, and Stuart S. P. Parkin, Heusler compounds with perpendicular magnetic anisotropy and large tunneling magnetoresistance, *Phys. Rev. Mater.* **1**, 024402 (2017).
- [33] Tanja Graf, Claudia Felser, and Stuart S. P. Parkin, Simple rules for the understanding of Heusler compounds, *Prog. Solid State Chem.* **39**, 1 (2011).
- [34] Qiang Gao, Ingo Opahle, and Hongbin Zhang, High-throughput screening for spin-gapless semiconductors in quaternary Heusler compounds, *Phys. Rev. Mater.* **3**, 024410 (2019).
- [35] Thorsten Aull, Ersoy Şaşıoğlu, Igor V. Maznichenko, Sergey Ostanin, Arthur Ernst, Ingrid Mertig, and Iosif Galanakis, *Ab initio* design of quaternary Heusler compounds for reconfigurable magnetic tunnel diode and transistor, *Phys. Rev. Mater.* **3**, 124415 (2019).
- [36] Worasak Rotjanapittayakul, Jariyaneee Prasongkit, Ivan Rungger, Stefano Sanvito, Wanchai Pijitrojana, and Thomas Archer, Search for alternative magnetic tunnel junctions based on all-Heusler stacks, *Phys. Rev. B* **98**, 054425 (2018).
- [37] Branimir Radisavljevic, Aleksandra Radenovic, Jacopo Brivio, Valentina Giacometti, and Andras Kis, Single-layer MoS<sub>2</sub> transistors, *Nat. Nanotechnol.* **6**, 147 (2011).
- [38] Likai Li, Yijun Yu, Guo Jun Ye, Qingqin Ge, Xuedong Ou, Hua Wu, Donglai Feng, Xian Hui Chen, and Yuanbo Zhang, Black phosphorus field-effect transistors, *Nat. Nanotechnol.* **9**, 372 (2014).
- [39] Deep Jariwala, Vinod K. Sangwan, Lincoln J. Lauhon, Tobin J. Marks, and Mark C. Hersam, Emerging device applications for semiconducting two-dimensional transition metal dichalcogenides, *ACS Nano* **8**, 1102 (2014).
- [40] Gianluca Fiori, Francesco Bonaccorso, Giuseppe Iannaccone, Tomás Palacios, Daniel Neumaier, Alan Seabaugh, Sanjay K. Banerjee, and Luigi Colombo, Electronics based on two-dimensional materials, *Nat. Nanotechnol.* **9**, 768 (2014).
- [41] Tania Roy, Mahmut Tosun, Xi Cao, Hui Fang, Der-Hsien Lien, Peida Zhao, Yu-Ze Chen, Yu-Lun Chueh, Jing Guo, and Ali Javey, Dual-gated MoS<sub>2</sub>/WSe<sub>2</sub> van der Waals tunnel diodes and transistors, *ACS Nano* **9**, 2071 (2015).
- [42] Yuan Liu, Nathan O. Weiss, Xidong Duan, Hung-Chieh Cheng, Yu Huang, and Xiangfeng Duan, Van der Waals heterostructures and devices, *Nat. Rev. Mater.* **1**, 16042 (2016).
- [43] Rusen Yan, Sara Fathipour, Yimo Han, Bo Song, Shudong Xiao, Mingda Li, Nan Ma, Vladimir Protasenko, David A. Muller, Debdeep Jena, and Huili G. Xing, Esaki diodes in van der Waals heterojunctions with broken-gap energy band alignment, *Nano Lett.* **15**, 5791 (2015).
- [44] Filippo Giannazzo, Giuseppe Greco, Fabrizio Roccaforte, and Sushant S. Sonde, Vertical transistors based on 2D materials: Status and prospects, *Crystals* **8**, 70 (2018).
- [45] Ming-Yang Li, Chang-Hsiao Chen, Yumeng Shi, and Lain-Jong Li, Heterostructures based on two-dimensional layered materials and their potential applications, *Mater. Today* **19**, 322 (2016).

- [46] Jean Choukroun, Marco Pala, Shiang Fang, Efthimios Kaxiras, and Philippe Dollfus, High performance tunnel field effect transistors based on in-plane transition metal dichalcogenide heterojunctions, *Nanotechnology* **30**, 025201 (2018).
- [47] Houlong L. Zhuang and Richard G. Hennig, Stability and magnetism of strongly correlated single-layer VS<sub>2</sub>, *Phys. Rev. B* **93**, 054429 (2016).
- [48] Nannan Luo, Chen Si, and Wenhui Duan, Structural and electronic phase transitions in ferromagnetic monolayer VS<sub>2</sub> induced by charge doping, *Phys. Rev. B* **95**, 205432 (2017).
- [49] Huei-Ru Fuh, Ching-Ray Chang, Yin-Kuo Wang, Richard F. L. Evans, Roy W Chantrell, and Horng-Tay Jeng, New-type single-layer magnetic semiconductor in transition-metal dichalcogenides VX<sub>2</sub> (X = S, Se and Te), *Sci. Rep.* **6**, 32625 (2016).
- [50] Daqiang Gao, Qixin Xue, Xingze Mao, Weixiao Wang, Qiang Xu, and Desheng Xue, Ferromagnetism in ultrathin VS<sub>2</sub> nanosheets, *J. Mater. Chem. C* **1**, 5909 (2013).
- [51] Manuel Bonilla, Sadhu Kolekar, Yujing Ma, Horacio Coy Diaz, Vijaysankar Kalappattil, Raja Das, Tatiana Eggers, Humberto R. Gutierrez, Manh-Huong Phan, and Matthias Batzill, Strong room-temperature ferromagnetism in VSe<sub>2</sub> monolayers on van der Waals substrates, *Nat. Nanotechnol.* **13**, 289 (2018).
- [52] Gang Hee Han, Dinh Loc Duong, Dong Hoon Keum, Seok Joon Yun, and Young Hee Lee, Van der Waals metallic transition metal dichalcogenides, *Chem. Rev.* **118**, 6297 (2018).
- [53] Søren Smidstrup, Daniele Stradi, Jess Wellendorff, Petr A. Khomyakov, Ulrik G. Vej-Hansen, Maeng-Eun Lee, Tushar Ghosh, Elvar Jónsson, Hannes Jónsson, and Kurt Stokbro, First-principles Green's-function method for surface calculations: A pseudopotential localized basis set approach, *Phys. Rev. B* **96**, 195309 (2017).
- [54] John P. Perdew, Kieron Burke, and Matthias Ernzerhof, Generalized Gradient Approximation Made Simple, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [55] M. J. Van Setten, Matteo Giantomassi, Eric Bousquet, Matthieu J. Verstraete, Don R. Hamann, Xavier Gonze, and G.-M. Rignanese, The PseudoDojo: Training and grading a 85 element optimized norm-conserving pseudopotential table, *Comput. Phys. Commun.* **226**, 39 (2018).
- [56] Søren Smidstrup *et al.*, QuantumATK: An integrated platform of electronic and atomic-scale modelling tools, *J. Phys. Condens. Matter* **32**, 015901 (2019).
- [57] M. Büttiker, Y. Imry, R. Landauer, and S. Pinhas, Generalized many-channel conductance formula with application to small rings, *Phys. Rev. B* **31**, 6207 (1985).
- [58] Chenghuan Jiang, Yitian Wang, Yehui Zhang, Haowei Wang, Qian Chen, and Jianguo Wan, Robust half-metallic magnetism in two-dimensional Fe/MoS<sub>2</sub>, *J. Phys. Chem. C* **122**, 21617 (2018).
- [59] N. David Mermin and Herbert Wagner, Absence of Ferromagnetism or Antiferromagnetism in One- or Two-Dimensional Isotropic Heisenberg Models, *Phys. Rev. Lett.* **17**, 1133 (1966).
- [60] S. T. Bramwell and P. C. W. Holdsworth, Magnetization: A characteristic of the Kosterlitz-Thouless-Berezinskii transition, *Phys. Rev. B* **49**, 8811 (1994).
- [61] Daniele Torelli, Kristian Sommer Thygesen, and Thomas Olsen, High throughput computational screening for 2D ferromagnetic materials: The critical role of anisotropy and local correlations, *2D Mater.* **6**, 045018 (2019).
- [62] Fumihiro Matsukura, Yoshinori Tokura, and Hideo Ohno, Control of magnetism by electric fields, *Nat. Nanotechnol.* **10**, 209 (2015).
- [63] R. O. Cherifi, V. Ivanovskaya, L. C. Phillips, A. Zobelli, I. C. Infante, E. Jacquet, V. Garcia, S. Fusil, P. R. Briddon, N. Guiblin, A. Mougín, A. A. Ünal, F. Kronast, S. Valencia, B. Dkhil, A. Barthélémy, and M. Bibes, Electric-field control of magnetic order above room temperature, *Nat. Mater.* **13**, 345 (2014).
- [64] V. L. Korenev, I. V. Kalitukha, I. A. Akimov, V. F. Sapega, E. A. Zhukov, E. Kirstein, O. S. Ken, D. Kudlacik, G. Karczewski, M. Wiater, N. D. Ilyinskaya, N. M. Lebedeva, T. A. Komissarova, Yu. G. Kusrayev, D. R. Yakovlev, and M. Bayer, Low voltage control of exchange coupling in a ferromagnet-semiconductor quantum well hybrid structure, *Nat. Commun.* **10**, 2899 (2019).
- [65] Chun-Yeol You and S. D. Bader, Prediction of switching/rotation of the magnetization direction with applied voltage in a controllable interlayer exchange coupled system, *J. Magn. Magn. Mater.* **195**, 488 (1999).
- [66] Y.-H. Tang, Nicholas Kioussis, Alan Kalitsov, W. H. Butler, and Roberto Car, Controlling the Nonequilibrium Interlayer Exchange Coupling in Asymmetric Magnetic Tunnel Junctions, *Phys. Rev. Lett.* **103**, 057206 (2009).
- [67] Shehrin Sayed, Cheng-Hsiang Hsu, Niklas Roschewsky, See-Hun Yang, and Sayeef Salahuddin, Electric-field control of the interlayer exchange coupling for magnetization switching, arXiv:1911.00183 (2019).
- [68] T. Newhouse-Illige, Yaohua Liu, M. Xu, D. Reifsnnyder Hickey, A. Kundu, H. Almasi, Chong Bi, Xiao Wang, J. W. Freeland, D. J. Keavney, C. J. Sun, Y. H. Xu, M. Rosales, X. M. Cheng, Shufeng Zhang, K. A. Mkhoyan, and W. G. Wang, Voltage-controlled interlayer coupling in perpendicularly magnetized magnetic tunnel junctions, *Nat. Commun.* **8**, 15232 (2017).
- [69] Zhi-Qiang Fan, Xiang-Wei Jiang, Jun-Wei Luo, Li-Ying Jiao, Ru Huang, Shu-Shen Li, and Lin-Wang Wang, In-plane Schottky-barrier field-effect transistors based on 1T/2H heterojunctions of transition-metal dichalcogenides, *Phys. Rev. B* **96**, 165402 (2017).
- [70] International Roadmap for Devices and Systems (IRDS) (2017), available at <https://irds.ieee.org>.
- [71] Mazen Shanawani, Diego Masotti, and Alessandra Costanzo, THz rectennas and their design rules, *Electronics* **6**, 99 (2017).
- [72] Saamil Joshi and Garret Moddel, Simple figure of merit for diodes in optical rectennas, *IEEE J. Photovolt.* **6**, 668 (2016).
- [73] Sachit Grover, Saamil Joshi, and Garret Moddel, Quantum theory of operation for rectenna solar cells, *J. Phys. D: Appl. Phys.* **46**, 135106 (2013).
- [74] M. I. Katsnelson, V. Yu. Irkhin, Liviu Chioncel, A. I. Lichtenstein, and Robert A. de Groot, Half-metallic ferromagnets: From band structure to many-body effects, *Rev. Mod. Phys.* **80**, 315 (2008).