



Effect of vacancy defects on geometrically frustrated magnets

Sergey Syzranov 

Physics Department, University of California, Santa Cruz, California 95064, USA

 (Received 11 June 2022; revised 25 September 2022; accepted 17 October 2022; published 25 October 2022)

Quenched disorder may prevent the formation of the widely sought quantum spin-liquid states (QSLs) or mask their signatures by inducing a spin-glass state, which is why considerable experimental efforts are directed at purifying materials that may host QSLs. However, in geometrically frustrated (GF) magnets, the largest class of materials in which QSLs are sought, the glass-transition temperature T_g grows with decreasing the density of vacancy defects, accompanied by a simultaneous growth of the magnetic susceptibility. In this Letter, we develop a phenomenological theory of glass transitions and magnetic susceptibility in three-dimensional geometrically frustrated magnetic materials. We consider a model of a GF magnet in which the glass transition occurs in the absence of vacancies, e.g., due to other types of quenched disorder. We show that disorder that creates weak local perturbations, e.g., weak random strain, leads to the growth of the transition temperature T_g . By contrast, vacancies reduce T_g for small vacancy concentrations. Another consequence of the presence of vacancies is the creation of quasispins, effective magnetic moments localized near the vacancies, that contribute to the magnetic susceptibility of the system together with the bulk spins. We show that increasing the vacancy density leads to an increase of the total magnetic susceptibility.

DOI: [10.1103/PhysRevB.106.L140202](https://doi.org/10.1103/PhysRevB.106.L140202)

Quenched disorder (impurities, irregularities, vacancies, etc.) is one of the main obstacles to observing widely sought quantum spin-liquid (QSL) states [1]. Quenched disorder may not only hide the QSL signatures, such as the temperature dependence of the heat capacity, but, in three-dimensional (3D) systems [2–7], also induce the spin-glass state that may be incompatible with a QSL. At present, the effect of quenched disorder on QSLs and magnetic materials expected to support QSL states is far from being understood.

A common expectation, confirmed by the existing theories of spin glasses [8–13], is that purifying a material makes random spin freezing less favorable and thus lowers the glass-transition temperature, which, in turn, should make QSL signatures more vivid. Available experimental data, however, for spin-glass transitions in geometrically frustrated (GF) magnets [14], the largest class of materials in which QSLs are sought, reveals several surprising trends [13], summarized in Fig. 1, that contradict common intuition.

The most common type of quenched disorder in GF materials is vacancies, i.e., randomly located nonmagnetic atoms that replace magnetic atoms of the GF medium. With *decreasing* the concentration of vacancies in GF materials, which contribute to quenched disorder but of which they may not be the only source, the glass-transition temperature *increases*, reaching a finite value T^* , the “hidden energy scale,” in the limit of a vacancy-free material [13]. While vacancies in many GF materials are the only known source of disorder, such a spin freezing may present a challenge for the observation of QSLs.

The origin of the hidden energy scale still remains to be explored. In most frustrated materials, it has the same or-

der of magnitude, $T^* \sim 10$ K, significantly exceeded by the exchange couplings between the spins. In some materials, exemplified by $\text{Y}_2\text{Mo}_2\text{O}_7$ [15], the hidden energy scale may be presumed to come from sources of disorder other than vacancies, such as random strain fields due to the dynamic Jahn-Teller effect. In other materials, however, there are no other significant known sources of disorder distinct from vacancies. The origin and the value of the hidden energy scale, thus, require a careful further investigation.

Another remarkable universal trend that GF systems exhibit and that persists regardless of the source of disorder is the growth of the magnetic susceptibility $\chi(T_g)$ with decreasing the critical temperature T_g , $\frac{d\chi(T_g)}{dT_g} < 0$ [see Fig. 1(a)], when changing the concentration of vacancies. This trend holds for *all* GF magnets, for whom experimental data on spin glasses are available [13,16–24], and is in contrast with the opposite trend, $\frac{d\chi(T_g)}{dT_g} > 0$, in conventional spin glasses [Fig. 1(b)].

The growth of the susceptibility with vacancy concentration is consistent with the empirical picture of “orphan” spins or quasispins [25–28]: The shielding of a vacancy by the spins creates a degree of freedom that acts as a magnetic moment (a “quasispin”). As a result, adding vacancies to a GF material leads to the growth of the susceptibility $\chi(T)$ [Fig. 1(a)], similarly to the growth of susceptibility observed in a nonmagnetic medium (conventional spin glass) when adding magnetic impurities [Fig. 1(b)]. Empirically, the contribution of the quasispin degrees of freedom may be separated from that of the *bulk spins*, i.e., spins sufficiently far from the vacancies, which behave as an independent subsystem (e.g., have a different Weiss constant [25,26]).




FIG. 1. Schematic of the behavior [13] of the susceptibility $\chi(T)$ and glass-transition temperature T_g in (a) geometrically frustrated magnets and (b) conventional spin glasses for various densities of defects.

Quasispins alone cannot account for the observed [13] decrease of the glass-transition temperature with increasing the concentration of vacancies; in a system of randomly located magnetic moments, the glass-transition temperature grows with the density of the moments [8–13]. If one assumes that the bulk spins in the GF medium undergo freezing at the transition, instead of the vacancy-induced quasispins, then diluting such bulk spins by vacancies may be qualitatively consistent with lowering the glass-transition temperature. However, diluting the bulk spins by vacancies also decreases their contribution to the magnetic susceptibility. It is natural to assume, therefore, that describing the behavior of both the susceptibility $\chi(T)$ and the glass-transition temperature T_g should involve both the quasispin degrees of freedom and the degrees of freedom of the bulk spins.

In this Letter, we develop a phenomenological theory of the effect of vacancy defects on the properties of frustrated magnetic materials. We provide a scenario that explains simultaneously the observed, previously unexplained trends: the growth of the glass-transition temperature with decreasing vacancy concentration, the growth of the magnetic susceptibility with vacancy concentration, and the $d\chi(T_g)/dT_g < 0$ trend observed in GF magnets. It also predicts the growth of the glass-transition temperature with increasing the strength of disorder that creates weak local perturbations in the system, such as weak random strain.

Qualitative picture. We assume that the material undergoes a spin-glass phase transition in the absence of vacancies. Such a transition may be driven by quenched disorder other than randomly located vacancies, such as random strain fields in $Y_2Mo_2O_7$ [15], or conceivably occur even in the absence of disorder [29], similarly to the conventional liquid-glass transition [30]. The exact mechanism of the glass transition in a vacancy-free system is not important for our consideration. We assume that averaging of observables over the positions of vacancies and realizations of other forms of disorder can be carried out independently.

The temperature T_g of the glass transition is assumed to be significantly exceeded by the absolute value of the Weiss constant $|\theta_W|$, which is on the order of the energies of isolated spin-flip excitations in the GF medium [for instance, for isotropic exchange interactions with the coupling J , the mean-field approximation gives $\theta_W = -\frac{1}{3}ZJs(s+1)$, where Z is the coordination number and s is the value of the spin]. As

a result, isolated spin-flip excitations are strongly suppressed near the glass transition.

We show that at temperatures $T_g \lesssim T \ll |\theta_W|$, vacancies create, by breaking some of the bonds in the GF medium, degenerate states of the system with different magnetizations, which is equivalent to the existence of magnetic degrees of freedom (quasispins) associated with the vacancies. In a broad temperature interval, the magnetic susceptibility may be expected to obey the formula

$$\chi(T) = \frac{A(n - n_{\text{imp}})}{T + |\theta_W|} + \frac{Bn_{\text{imp}}}{T}, \quad (1)$$

which interpolates between the Curie-Weiss contribution of the bulk spins at $T \gtrsim |\theta_W|$ and the contribution of the vacancies at $T \ll |\theta_W|$; n_{imp} is the concentration of the vacancies.

At the same time, the dilution of the bulk-spin medium by vacancies reduces correlations between the bulk spins and lowers the glass-transition temperature, as we show below. The glass transition is thus driven by the degrees of freedom of the bulk spins and not by the quasispins associated with the vacancies.

Glass-transition temperature and vacancies. The transition can be detected via the glass order parameter $Q_r^{\alpha\beta} = \langle \hat{s}_r^\alpha \cdot \hat{s}_r^\beta \rangle$, the correlator of spins in different replica subspaces [8,10] α and β , where $\langle \dots \rangle$ is averaging over the states of the spin and nonvacancy disorder, if present, for particular locations of the vacancies. The order parameter $Q_r^{\alpha\beta}$ is finite at temperatures below the glass-transition temperature, $T < T_g$, and vanishes above the transition, at $T > T_g$.

The decrease of the transition temperature T_g when adding vacancies can be understood intuitively as a result of the decrease of the average coupling between the bulk spins of the GF medium that undergo the glass freezing. To describe this effect quantitatively, we assume that in the absence of vacancies the glass transition can be described by a mean-field replicated free energy

$$F(Q) = \frac{1}{2} Q_r^{\alpha\beta} (K^{-1})_{rr'} Q_r^{\alpha\beta} + O(Q^3), \quad (2)$$

in which the lowest eigenvalue of the matrix $(K^{-1})_{rr'}$ vanishes when approaching the transition,

$$K_{\mathbf{k}=0}^{-1} = a(T_g - T), \quad (3)$$

where $K_{\mathbf{k}}$ is the Fourier transform of the correlator $K_{rr'}$; summation over repeated indices is implied and $a > 0$. The free energy (2) describes the action of a vacancy-free system, averaged over the realizations of the other types of disorder, if present. Therefore, the matrix $K_{rr'}$ is translationally invariant.

For simplicity, we consider a system in which $Q_r^{\alpha\beta}$ does not have time dynamics, corresponding, e.g., to models with effectively classical spins. However, the argument developed here applies as well in the presence of quantum dynamics of spins, i.e., for a system described by the action (2) with the fields Q that depend on the Matsubara time τ in addition to the coordinates.

We note that for a particular pair of replicas $\alpha \neq \beta$, the corresponding quadratic form in Eq. (2) is negative above the transition, at $T > T_g$. However, the number $n(n-1)/2$ of such pairs is also negative in the replica limit $n \rightarrow 0$ [for example, for a replica-symmetric order parameter $Q_r^{\alpha\beta} = q$,

the free energy is given by $\tilde{F} = \lim_{n \rightarrow 0} \frac{F(q)}{n} \propto a(T - T_g)$, resulting in a positive action for $T > T_g$.

Because the free energy (2) is quadratic in small $Q_r^{\alpha\beta}$, the fluctuations of the order parameter $Q_r^{\alpha\beta}$ may be considered Gaussian above the transition ($T > T_g$). This allows one to describe the effects of vacancy defects and other small perturbations on the glass transition diagrammatically, with the matrix $K_{rr'}$ playing the role of the Green's function.

To consider the effect of a single vacancy or other defect added to the system, we add the term $\lambda(Q_\rho^{\alpha\beta})^2$ to the action (2) at site ρ . For $\lambda \rightarrow -\infty$, such a term leads to the vanishing of the field $Q_\rho^{\alpha\beta}$ and mimics a vacancy at site ρ . For small $\lambda > 0$, a combination of such terms can mimic, for example, the effect of weak fluctuations of the exchange coupling averaged over that coupling [12,13]. The presence of one defect modifies the correlator $K_{rr'} = \langle Q_r^{\alpha\beta} Q_{r'}^{\alpha\beta} \rangle / T$ of the fields $Q_r^{\alpha\beta}$ (see Supplemental Material [31]):

$$K_{rr'} \rightarrow K_{rr'} - K_{r\rho} \frac{\lambda}{1 + \lambda K_{\rho\rho}} K_{\rho r'}. \quad (4)$$

We note that the quantity $K_{\rho\rho} = \int \frac{d\mathbf{k}}{(2\pi)^d} K_{\mathbf{k}}$ is negative above the transition ($T > T_g$), nonsingular in $T - T_g$ for quadratically dispersive modes [$K_{\mathbf{k}}^{-1} \propto a(T_g - T) - b\mathbf{k}^2$] in 3D, and independent of the choice of the site ρ . For $\lambda \rightarrow -\infty$, corresponding to a vacancy defect, the correlator (4) in the presence of the vacancy vanishes for $\mathbf{r} = \rho$ or $\mathbf{r}' = \rho$ because $Q_\rho^{\alpha\beta} = 0$ at the location of the vacancy.

In the limit of dilute defects, the disorder-averaged correlator \tilde{K} of the fields $Q_\rho^{\alpha\beta}$ is given by

$$\tilde{K}_{\mathbf{k}}^{-1} = K_{\mathbf{k}}^{-1} + \frac{\lambda n_{\text{imp}}}{1 + \lambda K_{\rho\rho}}, \quad (5)$$

where n_{imp} is the defect density and we have used that the contributions of dilute defects to the ‘‘self-energy’’ $\Sigma_{\mathbf{k}} = K_{\mathbf{k}}^{-1} - \tilde{K}_{\mathbf{k}}^{-1}$ are additive. The effect of the impurities is, therefore, equivalent to the shift of temperature

$$T_g \rightarrow T_g + \frac{n_{\text{imp}} \lambda}{a(1 + \lambda K_{\rho\rho})}. \quad (6)$$

For $\lambda \rightarrow -\infty$, corresponding to vacancy defects, the glass-transition temperature is lowered by $n_{\text{imp}} / (a|K_{\rho\rho}|)$, in accordance with experimentally observed trends [13]. By contrast, quenched disorder that creates weak local perturbations ($0 < \lambda < |K_{\rho\rho}|^{-1}$) increases T_g .

Magnetic susceptibility of vacancies. In what immediately follows, we demonstrate microscopically the emergence of the quasispin degrees of freedom in a frustrated medium. We assume first that sources of quenched disorder distinct from vacancies are absent. If a disorder-free glass transition is possible, we also assume that the temperature of the system exceeds the transition temperature T_g . We consider a GF material whose ground states have zero magnetization. At a finite temperature, the fluctuations of the magnetization in the absence of vacancies lead to a finite magnetic Curie-Weiss susceptibility given by the first term in Eq. (1).

The presence of vacancies removes some of the bonds in the GF lattice and allows, in general, for degenerate ground states with nonzero magnetizations. Degenerate states with




FIG. 2. Spin configurations near a vacancy on a pyrochlore lattice. States (a) and (b) are obtained by removing a spin (shown in red) pointing, respectively, down and up from a ground state of a vacancy-free system. State (c) is obtained by removing a site from an excited state obtained from a ground state of a vacancy-free system by flipping all spins in a semi-infinite chain that starts at the removed site. The three states have the same energy.

different magnetizations give large Curie-type contributions $\chi(T) \propto n_{\text{imp}}/T$ to the magnetic susceptibility equivalent to that of free spins at low temperatures $T_g < T \ll |\theta_W|$.

To illustrate the emergence of such quasispin degrees of freedom, we consider Ising spins $s_{\mathbf{r}} = \pm 1$ on a pyrochlore lattice, a frustrated lattice consisting of tetrahedra touching at the corners. In the absence of vacancies, the Hamiltonian of this model is given by (see, e.g., Refs. [32–34])

$$H = J \sum_{(\mathbf{r}\mathbf{r}')} s_{\mathbf{r}} s_{\mathbf{r}'} = \frac{J}{2} \sum_i S_i^2 + \text{const}, \quad (7)$$

where the summation in the first sum is carried out over all nearest-neighbor pairs of spins $\mathbf{r}\mathbf{r}'$; $J > 0$ is the antiferromagnetic coupling constant; the last expression represents the sum over all the tetrahedra i that constitute the pyrochlore lattice and $S_i = \sum_{\mathbf{r} \in \mathcal{T}_i} s_{\mathbf{r}}$ is the sum of the spins of the i th tetrahedron.

In the absence of vacancies, the ground states correspond to the vanishing spins of all tetrahedra, $S_i = 0$, with two spins pointing up and two spins pointing down in each tetrahedron [32–34] (‘‘two-in, two-out’’ rule). Such states have a degeneracy that scales exponentially with the system size and can be parametrized by a Coulomb field (‘‘Coulomb phase’’ [32–34]).

A vacancy at location ρ can be modeled by adding the Hamiltonian $H_\rho = -J \sum_{(\rho\mathbf{r})} s_\rho s_{\mathbf{r}}$ to the Hamiltonian (7), which results in the effective cancellation of the exchange couplings next to the vacant site. The Hamiltonian of the system with such a vacancy at location ρ is given, up to an additive constant, by

$$\tilde{H} = \frac{J}{2} (S_1 - s_\rho)^2 + \frac{J}{2} (S_2 - s_\rho)^2 + \frac{J}{2} \sum_{i \neq 1,2} S_i^2, \quad (8)$$

where S_1 and S_2 are the total spins (including s_ρ) of the two tetrahedra that share site ρ .

Because $|S_{1,2} - s_\rho| \geq 1$, the minimum energy of the system with a vacancy is given by J . There are three types of such ground states, shown in Fig. 2: (a) $S_1 - s_\rho = S_2 - s_\rho = 1$, with two spins in the vacancy-sharing tetrahedra pointing up and one spin pointing down, (b) $S_1 - s_\rho = S_2 - s_\rho = -1$, with two spins in the vacancy-sharing tetrahedra pointing down and one spin pointing up, and (c) $S_1 - s_\rho = \pm 1$, $S_2 - s_\rho = \mp 1$ (with $S_i = 0$ for $i \neq 1, 2$).

States (a) and (b) are obtained by removing a spin pointing, respectively, down and up from a ground state of a vacancy-free system. Because the latter has zero total magnetization (spin), states (a) and (b) have total spins of $+1$ and -1 , respectively, and a degeneracy of $z/2$, where z is the degeneracy of ground states in a vacancy-free system. The magnetization comes from tetrahedra 1 and 2 and is thus concentrated near the vacancy.

State (c) has zero magnetization and is obtained by removing a spin from an excited state of the vacancy-free system in which one tetrahedron has a magnetization of 2 and the other tetrahedra have zero magnetization. In the representation of the Coulomb phase, such an excited state corresponds to a monopole excitation at the center of the respective tetrahedron. Each such excited state is obtained from a ground state of the vacancy-free system by flipping the direction of the Coulomb field along a semi-infinite chain (“Dirac string”) [32–34]. The degeneracy of states (c) is, therefore, on the order of or smaller than the degeneracy of states (a) and (b).

The existence of same-energy states with different finite magnetizations localized near the vacancy leads to a finite variance $\langle S^2 \rangle \sim 1$ of the total spin and, according to the fluctuation-dissipation theorem, a finite magnetic susceptibility $\chi_1(T) = \frac{g^2 \mu_B^2 \langle S^2 \rangle}{T}$ associated with one vacancy. For sufficiently dilute vacancies, their contributions are additive, and the magnetic susceptibility exhibits the $\chi(T) \propto n_{\text{imp}}/T$ behavior.

An alternative approach to deriving quasispin variables has been applied in Ref. [27]. In this approach, a GF system is described by Gaussian magnetic fluctuations with phenomenologically introduced parameters. By integrating out those fluctuations on the $\text{SrCr}_{9x}\text{Ga}_{12-9x}\text{O}_{19}$ lattice with a vacancy, it has been found in Ref. [27] that a vacancy is equivalent to a classical fractional spin in terms of its response to an external field. A fractional (quasi)spin associated with a vacancy in a triangular lattice has also been demonstrated numerically in Ref. [28] in the large- S approximation.

We expect that similar quasispin degrees of freedom associated with vacancies emerge generically for all GF lattices that have zero average magnetization in ground states. The removal of a site in such lattices may be expected to lead to nonzero magnetizations of the ground states of the lattice with a vacancy. In the presence of symmetry with respect to flipping or rotating all spins, the effect of a vacancy is then equivalent to the presence of a free magnetic moment in the system. We leave, however, a microscopic investigation of such quasispins and their values for other specific frustrated lattices for future studies.

Introducing vacancies to the system increases the quasispin contribution to the magnetic susceptibility. At the same time, it reduces the density of the bulk spins, thus suppressing their contribution. As can be seen from Eq. (1), however, the total magnetic susceptibility grows with increasing the density of vacancies, $d\chi(T)/dn_{\text{imp}} > 0$, in the dilute limit at low temperatures $T \ll |\theta_w|$ (assuming the constants A and B are of the same order of magnitude).

Interplay of quasispins with other sources of quenched disorder. For the model we consider in this Letter, the glass transition is driven by sources of disorder other than vacancies. Nonvacancy quenched disorder may, in principle, be varied in experiment by substituting nonmagnetic atoms in a GF compound by non-magnetic impurity atoms. Nonvacancy quenched disorder lifts the degeneracy between the ground states we have discussed. If such a lifting is sufficiently weak, its effect on the quasispins is equivalent to that of a random magnetic field.

The behavior of the quasispin contribution to the susceptibility will be unaltered at temperatures $|\theta_w| \gg T \gg \Delta E$ significantly exceeding the characteristic energy gap ΔE between the states of a quasispin. The contribution of the vacancies to the susceptibility, however, significantly changes at low temperatures $T \ll \Delta E$ (possibly below the glass transition). Due to random orientation of the effective magnetic field acting on the quasispins, the susceptibility of the vacancies is on the order of the transverse susceptibility of a two-level system with the splitting ΔE , which gives the estimate for the contribution of the vacancies to the magnetic susceptibility $\chi_{\text{vac}} \sim \frac{g^2 \mu_B^2}{\Delta E} n_{\text{imp}}$ (per magnetic atom in the material).

The quasispins also contribute to the heat capacity of the system. Their contribution is similar to that of an ensemble of two-level systems and can be estimated as [35] $C_{\text{vac}} \sim \frac{T}{\Delta E} n_{\text{imp}}$ (assuming the nonvanishing density of the effective field acting on the quasispins at small values of the field). Experimental observation of such a contribution to the heat capacity requires systematically accounting for the large contribution of bulk spins [36–39], as well as the heat capacity of the phonons.

Conclusion. We have developed a phenomenological theory of the glass transition and magnetic susceptibility in a geometrically frustrated (GF) magnet in the presence of vacancies, the most common type of defects in GF magnetic materials. In our model, the glass transition exists in the absence of vacancies, driven, e.g., by other sources of quenched disorder. Vacancies lead to the formation of quasispin degrees of freedom near the location of the vacancies, as well as to reducing the density of the spins. The interplay of these effects results in the increase of the total magnetic susceptibility of the system.

Increasing a small concentration of vacancies leads to a decrease in the glass-transition temperature, in contrast with quenched disorder that creates weak local perturbations (e.g., weak random strain). The described dependencies of the susceptibility and the transition temperature on the vacancy concentration is consistent with the experimentally observed trends in all GF magnetic materials [13]. The model proposed here and other predictions can be tested in experiment by varying nonvacancy quenched disorder, e.g., by substituting nonmagnetic atoms in GF magnets by nonmagnetic impurity atoms.

Acknowledgments. We are indebted to A. Alexandradinata and especially A. P. Ramirez for useful discussions and comments on the manuscript. This work has been supported by the NSF Grant No. DMR-2218130.

- [1] L. Savary and L. Balents, Quantum spin liquids: A review, *Rep. Prog. Phys.* **80**, 016502 (2017).
- [2] W. L. McMillan, Domain-wall renormalization-group study of the three-dimensional random Ising model, *Phys. Rev. B* **30**, 476 (1984).
- [3] A. K. Hartmann and A. P. Young, Lower critical dimension of Ising spin glasses, *Phys. Rev. B* **64**, 180404(R) (2001).
- [4] A. C. Carter, A. J. Bray, and M. A. Moore, Aspect-Ratio Scaling and the Stiffness Exponent θ for Ising Spin Glasses, *Phys. Rev. Lett.* **88**, 077201 (2002).
- [5] C. Amoruso, E. Marinari, O. C. Martin, and A. Pagnani, Scalings of Domain Wall Energies in Two Dimensional Ising Spin Glasses, *Phys. Rev. Lett.* **91**, 087201 (2003).
- [6] L. A. Fernandez, E. Marinari, V. Martin-Mayor, G. Parisi, and J. J. Ruiz-Lorenzo, Universal critical behavior of the two-dimensional Ising spin glass, *Phys. Rev. B* **94**, 024402 (2016).
- [7] H. Rieger, L. Santen, U. Blasum, M. Diehl, M. Jünger, and G. Rinaldi, The critical exponents of the two-dimensional Ising spin glass revisited: Exact ground-state calculations and Monte Carlo simulations, *J. Phys. A: Math. Gen.* **29**, 3939 (1996).
- [8] M. Mézard, G. Parisi, and M. A. Virasoro, *Spin Glass Theory and Beyond: An Introduction to the Replica Method and Its Applications*, Vol. 9 (World Scientific, Singapore, 1987).
- [9] V. S. Dotsenko, Physics of the spin-glass state, *Phys.-Usp.* **36**, 455 (1993).
- [10] K. Binder and A. P. Young, Spin glasses: Experimental facts, theoretical concepts, and open questions, *Rev. Mod. Phys.* **58**, 801 (1986).
- [11] T. E. Saunders and J. T. Chalker, Spin Freezing in Geometrically Frustrated Antiferromagnets with Weak Disorder, *Phys. Rev. Lett.* **98**, 157201 (2007).
- [12] A. Andreanov, J. T. Chalker, T. E. Saunders, and D. Sherrington, Spin-glass transition in geometrically frustrated antiferromagnets with weak disorder, *Phys. Rev. B* **81**, 014406 (2010).
- [13] S. V. Syzranov and A. P. Ramirez, Eminent phase in frustrated magnets: A challenge to quantum spin liquids, *Nat. Commun.* **13**, 2993 (2022).
- [14] A. P. Ramirez, Strongly geometrically frustrated magnets, *Annu. Rev. Mater. Sci.* **24**, 453 (1994).
- [15] P. M. M. Thygesen, J. A. M. Paddison, R. Zhang, K. A. Beyer, K. W. Chapman, H. Y. Playford, M. G. Tucker, D. A. Keen, M. A. Hayward, and A. L. Goodwin, Orbital Dimer Model for the Spin-Glass State in $\text{Y}_2\text{Mo}_2\text{O}_7$, *Phys. Rev. Lett.* **118**, 067201 (2017).
- [16] W. Ratcliff, S.-H. Lee, C. Broholm, S.-W. Cheong, and Q. Huang, Freezing of spin correlated nanoclusters in a geometrically frustrated magnet, *Phys. Rev. B* **65**, 220406(R) (2002).
- [17] J. E. Greedan, M. Sato, X. Yan, and F. S. Razavi, Spin-glass-like behavior in $\text{Y}_2\text{Mo}_2\text{O}_7$, a concentrated, crystalline system with negligible apparent disorder, *Solid State Commun.* **59**, 895 (1986).
- [18] Y. Ying, W. Zhang, J. Yu, L. Qiao, J. Zheng, W. Li, J. Li, W. Cai, and S. Che, Structure and magnetic properties of the Ti-doped pyrochlore molybdate $\text{Y}_2\text{Mo}_{2(1-x)}\text{Ti}_x\text{O}_7$, *J. Supercond. Novel Magn.* **32**, 3563 (2019).
- [19] B. Martínez, F. Sandiumenge, A. Rouco, A. Labarta, J. Rodríguez-Carvajal, M. Tovar, M. T. Causa, S. Galí, and X. Obradors, Magnetic dilution in the strongly frustrated kagome antiferromagnet $\text{SrGa}_{12-x}\text{Cr}_x\text{O}_{19}$, *Phys. Rev. B* **46**, 10786 (1992).
- [20] Y. Nambu, S. Nakatsuji, and Y. Maeno, Coherent behavior and nonmagnetic impurity effects of spin disordered state in NiGa_2S_4 , *J. Phys. Soc. Jpn.* **75**, 043711 (2006).
- [21] S. B. Oseroff, Magnetic susceptibility and EPR measurements in concentrated spin-glasses: $\text{Cd}_{1-x}\text{Mn}_x\text{Te}$ and $\text{Cd}_{1-x}\text{Mn}_x\text{Se}$, *Phys. Rev. B* **25**, 6584 (1982).
- [22] Y. Okamoto, M. Nohara, H. Aruga-Katori, and H. Takagi, Spin-Liquid State in the $S = 1/2$ Hyperkagome Antiferromagnet $\text{Na}_4\text{Ir}_3\text{O}_8$, *Phys. Rev. Lett.* **99**, 137207 (2007).
- [23] A. Balodhi, A. Thamizhavel, and Y. Singh, Evolution of magnetic, transport, and thermal properties in $\text{Na}_{4-x}\text{Ir}_3\text{O}_8$, *Phys. Rev. B* **91**, 224409 (2015).
- [24] P. G. LaBarre, D. Phelan, Y. Xin, F. Ye, T. Besara, T. Siegrist, S. V. Syzranov, S. Rosenkranz, and A. P. Ramirez, Fluctuation-induced interactions and the spin-glass transition in Fe_2TiO_5 , *Phys. Rev. B* **103**, L220404 (2021).
- [25] P. Schiffer and I. Daruka, Two-population model for anomalous low-temperature magnetism in geometrically frustrated magnets, *Phys. Rev. B* **56**, 13712 (1997).
- [26] A. D. LaForge, S. H. Pulido, R. J. Cava, B. C. Chan, and A. P. Ramirez, Quasispin Glass in a Geometrically Frustrated Magnet, *Phys. Rev. Lett.* **110**, 017203 (2013).
- [27] A. Sen, K. Damle, and R. Moessner, Fractional Spin Textures in the Frustrated Magnet $\text{SrCr}_{9p}\text{Ga}_{12-9p}\text{O}_{19}$, *Phys. Rev. Lett.* **106**, 127203 (2011).
- [28] A. Wollny, L. Fritz, and M. Vojta, Fractional Impurity Moments in Two-Dimensional Noncollinear Magnets, *Phys. Rev. Lett.* **107**, 137204 (2011).
- [29] J. Villain, Spin glass with non-random interactions, *J. Phys. C* **10**, 1717 (1977).
- [30] G. Parisi, P. Urbani, and F. Zamponi, *Theory of Simple Glasses: Exact Solutions in Infinite Dimensions* (Cambridge University Press, Cambridge, UK, 2020).
- [31] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevB.106.L140202> for the derivation of a correlator of a Gaussian quantity in the presence of delta potentials.
- [32] S. V. Isakov, K. Gregor, R. Moessner, and S. L. Sondhi, Dipolar Spin Correlations in Classical Pyrochlore Magnets, *Phys. Rev. Lett.* **93**, 167204 (2004).
- [33] C. L. Henley, Power-law spin correlations in pyrochlore antiferromagnets, *Phys. Rev. B* **71**, 014424 (2005).
- [34] C. L. Henley, The “Coulomb phase” in frustrated systems, *Annu. Rev. Condens. Matter Phys.* **1**, 179 (2010).
- [35] P. W. Anderson, B. I. Halperin, and C. M. Varma, Anomalous low-temperature thermal properties of glasses and spin glasses, *Philos. Mag.* **25**, 1 (1972).
- [36] A. P. Ramirez, G. P. Espinosa, and A. S. Cooper, Strong Frustration and Dilution-Enhanced Order in a Quasi-2D Spin Glass, *Phys. Rev. Lett.* **64**, 2070 (1990).
- [37] S. Nakatsuji, Y. Nambu, H. Tonomura, O. Sakai, S. Jonas, C. Broholm, H. Tsunetsugu, Y. Qiu, and Y. Maeno, Spin disorder on a triangular lattice, *Science* **309**, 1697 (2005).
- [38] D. Podolsky and Y. B. Kim, Halperin-Saslow modes as the origin of the low-temperature anomaly in NiGa_2S_4 , *Phys. Rev. B* **79**, 140402(R) (2009).
- [39] S. J. Garratt and J. T. Chalker, Goldstone modes in the emergent gauge fields of a frustrated magnet, *Phys. Rev. B* **101**, 024413 (2020).