# Dynamics of bistable Néel domain walls under spin-orbit torque

Eloi Haltz<sup>0</sup>,<sup>1,2</sup> Kévin J. A. Franke,<sup>1</sup> and Christopher H. Marrows<sup>1,\*</sup>

<sup>1</sup>School of Physics and Astronomy, University of Leeds, Leeds LS2 9JT, United Kingdom <sup>2</sup>LSPM-CNRS, UPR3407, Sorbonne Paris Nord University, Villetaneuse, France

(Received 13 September 2023; accepted 16 January 2024; published 6 February 2024; corrected 7 January 2025)

Néel magnetic domain walls that are stabilized by achiral energy terms instead of the usual Dzyaloshinskii-Moriya interaction will be bistable, with the two possible chiral forms being degenerate. Here we focus on the theoretical study of the spin-orbit torque driven dynamics of such bistable Néel domain walls. We find that, for a given domain wall, two propagation directions along a nanowire are possible, depending on its initial state. These dynamics also exhibit complex dependence on the spin-orbit torque magnitude, leading to important transient regimes. Finally, a few ways are proposed for controlled or random reversal of the domain wall propagation direction. A robust analytical model which handles all the observed behaviors of such domain walls is developed and validated by comparing with numerical simulations. The dynamics obtained by this approach opens the way for using domain walls in information storage and processing devices in ways that are not possible with fixed chirality walls.

DOI: 10.1103/PhysRevB.109.064406

### I. INTRODUCTION

The electrical manipulation of magnetic domain walls (DWs) and their potential technological applications have motivated intense research in magnetism and spintronics in the last few decades [1]. The possibility of encoding digital information in the magnetization and manipulating it by shifting the DWs along a nanowire opens new ways to construct data storage [1,2], logic devices [3,4], and, more recently, disruptive processing operations [5–10]. However, these new uses of DWs require more and more complex dynamics. So far, different mechanisms have been proposed for driving the DW motion in out-of-plane magnetized wires [11]: applied magnetic fields [12] or electrical currents *via* spin-transfer torques (STTs) [13] or, more efficiently, spin-orbit torques (SOTs) for Néel DWs [14].

Driving the motion of a Néel DW under SOT in a ferromagnetic (FM) and heavy metal (HM) bilayer relies on the combination of two phenomena. First, the spin Hall effect (SHE) converts the electrical current going through the HM layer into a transverse pure-spin current injected in the FM layer. The resulting antidampinglike SOT drives Néel DWs in a direction which depends on their chirality [15–17]. The second is an effect that stabilizes these DWs in the Néel structure [18–20]. Usually, that is achieved by the DMI emerging from the asymmetry between the interfaces of the FM layer which promotes the Néel type of the DWs with a given chirality, fixed by the FM-HM stack [16,17,21]. In that classic scenario, the sign of the DMI sets the chirality of the Néel DW and thus fixes the propagation direction for a given SOT drive.

Other phenomena can also be used to stabilize Néel DWs, such as an additional in-plane anisotropy [22] or depth gradients of thickness [23], strains [24-27], or magnetization. Unlike the DMI, these effects stabilize Néel DWs but without any preferential chirality. One can then speak of bistable Néel DWs where the chiralities are energetically degenerate. As before, the DW dynamics depends on the internal structure of the DW so, in this scenario, it can be reversed without changing the driving force if the chirality can be switched. This paradigm opens up many possibilities, one being to process information directly encoded into the chirality of the DW itself. Binary operations based on this degree of freedom have already been demonstrated numerically and experimentally for vortex DWs in in-plane magnetised Permalloy wires, driven by applied field [28]. In that case, the wall chirality does not affect its field-driven dynamics. Here, phenomena are described for out-of-plane magnetized systems under SOT, possibly field free, where the direction of motion reverses for a given drive when the chirality is flipped. The following results also demonstrate the additional use of these dynamics for random or quasirandom operations.

Here, the shape anisotropy resulting from the demagnetization effect in narrow magnetic wires is considered, allowing bistable Néel DWs [29,30]. That effect is suitable for a multitude of well-known magnetic systems in thin films just by patterning structures, making it very convenient and versatile. To manipulate such a bistable Néel DW with SOT, the FM wire can be sandwiched between two HM layers but of different thicknesses:  $HM_{thick}/FM/HM_{thin}$ , as shown Fig. 1(a). This cancels out any net Dzyaloshinskii-Moriya interaction (DMI) because of the symmetric FM interfaces and provides a nonzero net SHE as the electrical current density in each HM layer is different but with the same charge and spin conversion. Bistable Néel DWs have even already been imaged

<sup>\*</sup>c.h.marrows@leeds.ac.uk

Published by the American Physical Society under the terms of the Creative Commons Attribution 4.0 International license. Further distribution of this work must maintain attribution to the author(s) and the published article's title, journal citation, and DOI.



FIG. 1. Néel wall motion under SOT. (a) Sketch of a bistable Néel DW in an asymmetric HM/FM/HM trilayer. (b) Sketch of the propagation direction and internal dynamics of a bistable Néel DW depending on the orientation of the surrounding domains (written as Q = 1 for an up or down DW and Q = -1 for a down or up DW) and on the initial state of the DW ( $\varphi^0 = 0$  or  $\pi$ , shown as a gray arrow). The tilting of the internal magnetization of the DW is shown as a black curved arrow. These four cases summarize the results obtained with micromagnetic simulations. (c) Evolution of the DW velocity v (top panel) and associated internal angle  $\varphi$  (bottom panel) with the current density J for a DW with Q = 1,  $\varphi^0 = 0$ . Black points correspond to the values extracted from the numerical simulations after 20 ns of current injection. The yellow full lines show the theoretical evolution of these quantities in the steady-state regime  $v^{\infty}$  and  $\varphi^{\infty}$  given by Eqs. (4) and (5), respectively. The red and the blue vertical dashed lines correspond to the critical currents  $J_{\rm c} = 6 \,{\rm GA/m^2}$  and  $\frac{J_{\rm c}}{\sqrt{2}} = 4.25 \,{\rm GA/m^2}$ .

in such stack [30]. These required properties can also be obtained by introducing a thin metallic spacer layer between the HM and the FM (such as Cu: HM/Cu<sub>thin</sub>/FM) which prevents HM-FM direct interfaces but allows for spin injection though the thin metallic layer [31,32]. More generally, the use of an HM with a significant SHE but without DMI is possible (such as Au,  $\beta$ -Ta, or  $\beta$ -W).

#### **II. METHODS**

In the following, the dynamics of these bistable Néel DWs under SOT is explored. A collective coordinate model is developed to describe the DW behaviors with two variables: q, the DW position along the wire (and so its velocity  $v = \dot{q}$ ), and  $\varphi$ , the angle between the magnetization at the center of the DW and the current direction (with  $\varphi = 0$  or  $\pi$  referring to a Néel DW and  $\varphi = \pi/2$  or  $-\pi/2$  corresponding to a Bloch DW), as shown Fig. 1(a). For every following situation, the initial state of the DW is defined with two parameters:  $Q = \pm 1$  which corresponds to the orientation of the surrounding magnetic domains (Q = 1 for an up or down DW and Q = -1for a down or up DW), and  $\varphi^0$  the initial orientation of the magnetization at the center of the DW.

The obtained results are in very good agreement with numerical micromagnetic simulations that we have performed, validating some assumptions of the analytical model such as the DW shape or the demagnetization effects [29,33-35]. The micromagnetic simulations have been performed using the MUMAX3 open-source software allowing a finitedifference approach to the magnetization dynamics [36]. The magnetic wire is discretized into  $2 \text{ nm} \times 2 \text{ nm} \times 1 \text{ nm}$  cells. A saturation magnetization of  $M_s = 1 \times 10^6$  A/m, an exchange stiffness of  $A = 3 \times 10^{-11}$  J/m, an out-of-plane uniaxial anisotropy of  $K_0 = 1 \times 10^6 \text{ J/m}^3$ , a gyromagnetic ratio of  $\gamma_0 = 0.2 \times 10^6$  Hz/(A/m), and a Gilbert damping parameter of  $\alpha = 0.1$  have been considered [22,37]. The chosen 32-nm width and 1-nm thickness for the wire leads to an effective uniaxial shape anisotropy along the magnetic wire of magnitude  $K_{\rm IP} = 14 \text{ kJ/m}^3$ , which stabilizes bistable Néel DWs. The spin current  $J_s$  is injected into the magnetic wire with a spin direction transverse to the wire  $[\sigma = \hat{y}]$ , as shown in Fig. 1(a)]. The resulting SOT is taken into count as an antidampinglike torque acting on the local magnetization  $\tau \propto J\mathbf{m} \times (\mathbf{m} \times \boldsymbol{\sigma})$ . For simplicity, we assume a charge and spin conversion ratio of unity so that the charge and spin currents have equal magnitudes.

In both cases we have neglected any volume spin-transfer torque since this has been shown to be negligible in comparison to the SOT in such multilayer systems [38].

#### **III. RESULTS**

#### A. Domain wall dynamics under spin-orbit torque

First, the DW is set in a certain initial state  $(Q, \varphi^0)$  and a small spin current of  $J = 3 \text{ GA/m}^2$  is injected. The diagrams in Fig. 1(b) show in which direction the DW moves and how  $\varphi$  evolves under SOT depending on that  $(Q, \varphi^0)$  configuration. For a given Q [rows of the table in Fig. 1(b)], the DW moves in opposite directions depending on  $\varphi_0$ . Thus, just by reversing the initial orientation of the DW  $\varphi^0$ , its motion is reversed. Also, for a given chirality [diagonals of the table Fig. 1(b)] the up or down and down or up DWs move in the same direction. That is the so-called coherent shift of DWs and it has previously been ensured by the DMI. Here, since the chirality is not fixed, the up or down and down or up DW with the same  $\varphi^0$  move in opposite directions [columns of the table Fig. 1(b)]. This leads to the possible expansion or collapse of magnetic domains under SOT. Usually, that is not possible with current drive in the usual cases: under SOT with DMI, the DW motion only depends on the chirality, while for the STT, its direction of motion only depends on Q [11]. The DW motion also induces a tilt of its internal magnetization  $\varphi$  which deviates from a pure Néel state [as shown Fig. 1(b)]. That tilting increases with the SOT magnitude, leading to larger effects at higher current densities.

Figure 1(c) shows the simulated DW dynamics at larger current density J for a configuration Q = 1 and  $\varphi^0 = 0$ . For each value of J, the DW velocity v and angle  $\varphi$  (black dots of the top and bottom panels) are extracted from the micromagnetic simulations after 20 ns of current injection. For low current, v increases linearly with J and  $\varphi$  slightly deviates from its pure Néel state. When  $\varphi$  reach the value of  $\frac{\pi}{4}$  (blue dashed line), the DW velocity exhibits a maximum. For larger currents, the DW is pushed into its Bloch configuration. Since the SOT just acts on Néel DWs, the DW slows down. Above a critical current  $J_c$  [red dashed line Fig. 1(c)] the DW is locked into its pure Bloch configuration with  $\varphi = \pm \frac{\pi}{2}$  and then v = 0.

### B. Collective coordinate model

To understand the complex dynamics of such DW, it is convenient to use an analytical collective coordinate model that describes the DW dynamics with only a few parameters: q and  $\varphi$ , as defined beforehand and shown in Fig. 1(a). The analytical integration of the Landau-Lifshitz-Gilbert (LLG) equation considering the rigid Bloch DW ansatz [39] leads to coupled equations of motion [11,17,34,40]:

$$\dot{q} = \frac{\Delta}{\alpha \tau_0} \left( \alpha^2 Q j \cos \varphi + \frac{\sin 2\varphi}{2} \right), \tag{1}$$

$$\dot{\varphi} = \frac{1}{\tau_0} \left( Qj \cos \varphi - \frac{\sin 2\varphi}{2} \right), \tag{2}$$

where  $\Delta$  is the DW width (defined as positive).  $\tau_0 = \frac{1+\alpha^2}{\alpha_{Y0}H_{\text{KIP}}}$ is a timescale associated with the DW dynamics, mainly depending on  $H_{\text{KIP}} = \frac{2K_{\text{IP}}}{\mu_0 M_s}$ , the field associated to the shape anisotropy strength  $K_{\text{IP}}$ . The dimensionless current ratio  $j = \frac{J}{J_c} = \frac{\pi}{\alpha H_{\text{KIP}}}$  results from the competition between the shape anisotropy, which tends to stabilize the Néel state of the DW and the SOT which tends to tilt the DW internal magnetization, accounted as an effective field  $H_{\text{SOT}}$ . Equations (1) and (2) clearly show that  $\varphi$  governs the DW dynamics and that v depends on  $\varphi$  roughly as  $v \sim \sin 2\varphi$ . Equation (2) gives an implicit analytical expression of the time evolution of  $\varphi$  such as

$$e^{-t/\tau_0} = \frac{\frac{2(Qj-1)}{\sqrt{1-\sin\phi^0}}}{\frac{2(Qj+1)}{\sqrt{\frac{1+\sin\phi}{1+\sin\phi^0}}} (j^{2}-1)\sqrt{\frac{Qj-\sin\phi}{Qj-\sin\phi^0}}},$$
(3)

depending on  $\varphi^0$ , the internal angle at the considered initial time t = 0.

For asymptotic steady-state motion, the DW velocity and the internal angles are constant (i.e.,  $\dot{q}$  and  $\varphi$  take constant values that we denote  $v^{\infty}$  and  $\varphi^{\infty}$ ). Two steady-state dynamical regimes are obtained in this case, separated by the critical current density  $J_c$ :

$$v^{\infty} = \begin{cases} (S_1) \frac{\Delta}{\tau_0} \frac{1+\alpha^2}{\alpha} j\sqrt{1-j^2} & \text{if } J \leqslant J_c \ (j \leqslant 1), \\ 0 & \text{if } J \geqslant J_c \ (j \geqslant 1), \end{cases}$$
(4)

$$\varphi^{\infty} = \begin{cases} (\varphi^0) + (S_1) \arcsin j & \text{if } J \leqslant J_c, \\ (S_2)\frac{\pi}{2} & \text{if } J \geqslant J_c. \end{cases}$$
(5)

 $(S_1)$  and  $(S_2)$  are equal to  $\pm 1$  and give the DW propagation and tilt angle directions depending on the initial state of the DW and on the current direction:  $(S_1) = Q \operatorname{sgn}(\cos \varphi^0)$  and  $(S_2) = Q \operatorname{sgn}(J)$ .  $(\tilde{\varphi^0})$  determines whether the DW is mainly left or right handed:  $(\tilde{\varphi^0}) = 0$  if  $\varphi^0 \in ] - \frac{\pi}{2}, \frac{\pi}{2}[$  and  $= \pi$  if  $\varphi^0 \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$ . These expressions of  $(S_1), (S_2)$ , and  $(\tilde{\varphi^0})$  reproduce well the results sketched in the table shown in Fig. 1(b). These considerations also show that for  $J < J_c$ ,  $v^{\infty}$  and  $\varphi^{\infty}$ depend of the initial condition  $\varphi_0$  but not for  $J \ge J_c$ .

The variation of  $v^{\infty}$  and  $\varphi^{\infty}$  with *J*, plotted as yellow lines in Fig. 1(c), also reproduces the simulated results with a very good quantitative agreement in the main part of the current range, far from  $J_c$ . Equations (4) and (5) also show that a maximum velocity  $\Delta \gamma_0 H_{\text{KIP}}$  is reached for  $J = \frac{J_c}{\sqrt{2}}$  for which  $\varphi^{\infty} = \pm \frac{\pi}{4} [\pi]$ . Interestingly, that maximum only depends on the in-plane shape anisotropy but not directly on the SOT.

### C. Transient regime

The nonuniformity of the DW velocity with  $\varphi$  has a strong effect in the transient regime. These are most easily visible around the critical current, where the simulated DW velocity does not seem to vanish immediately at  $J \ge J_c$  as it is expected in the steady-state motion. Figure 2(a) shows the time evolution of the DW velocity during a 50-ns current pulse of different magnitudes for an initial DW configuration Q = 1 and  $\varphi^0 = 0$ . First, the loading time, just after the current onset is discussed. The relaxation dynamics is described in the following.

For  $J < \frac{J_c}{\sqrt{2}}$  (case 1), the velocity, as well as the internal angle (not shown here) tend continuously to the steady-state values, as expected for classical DW motion. For  $J > \frac{J_c}{\sqrt{2}}$ (case 2), the transient regime is divided into two parts: first the DW accelerates up to a maximum of velocity with a characteristic time of a few ns and then slows down, tending towards the steady-state values with a much longer characteristic time. These two parts are due to the continuous evolution of  $\varphi$  from  $\varphi^0 = 0$  to the steady-state value  $\varphi^{\infty}$  which implies to cross  $\pm \frac{\pi}{4} [\pi]$  where the velocity is at a maximum. The characteristic time of that velocity decay is much larger, up to tens of ns. For  $J > J_c$ , these two parts of the transient regime still exist. Even if the asymptotic velocity is zero, the DW moves for a significant amount of time before being locked into its Bloch configuration. That explains why the velocities extracted from the simulations [after 20 ns of current injection; in bold Fig. 2(a)] shown Fig. 1(c) are slightly above zero at and above  $J_c$ .

The variation of this characteristic time can be obtained by linearizing Eq. (2) for  $t \approx 0$  around  $\varphi^0$  or  $t \to \infty$  around  $\varphi^{\infty}$ . We can obtain that  $\dot{\varphi} \approx \dot{\varphi}(\varphi^{0(\infty)}) - \frac{\varphi - \varphi^{0(\infty)}}{\tau}$  with  $\dot{\varphi}(\varphi^{\infty}) \to 0$  and so

$$\tau = \frac{\tau_0}{Qj\,\sin\varphi^{0(\infty)} + \cos 2\varphi^{0(\infty)}},\tag{6}$$

the characteristic time of the  $\varphi$  variations at the beginning or at the end of the transient regime (i.e., for  $\varphi \approx \varphi^0$  or  $\varphi^{\infty}$ ). Thus, Eq. (6) captures the two different parts of the transient regime. For the first one,  $\varphi^0 = 0$  or  $\pi$  gives  $\tau =$  $\tau_0$  for any currents and  $v_{(t\approx 0)} \propto (\varphi_{(t\approx 0)} - \varphi^0) \propto (1 - e^{-t/\tau_0})$ .

![](_page_3_Figure_1.jpeg)

FIG. 2. Transient regimes of the DW dynamics. (a) The different plots show the time evolution of the DW velocity during 50-ns current pulses of different magnitudes: case 1,  $J = 3 \text{ GA/m}^2 < \frac{J_c}{\sqrt{2}}$ ; case 2,  $J = 5.5 \text{ GA/m}^2 \in [\frac{J_c}{\sqrt{2}}, J_c]$ ; case 3,  $J = 7 \text{ GA/m}^2 > J_c$ ; and case 4,  $J = 10 \text{ GA/m}^2 \gg J_c$ . For each plot, black dots show the values from the numerical simulations. During the current injection (for t < 50 ns), the colored lines are the exponential evolution with characteristic times  $\tau$ . After the current injection (for t > 50 ns), the purple lines show the analytical model considering Eqs. (1) and (7). (b) Evolution of the characteristic time  $\tau$  of the transient regime with J. Black dots correspond to the values of  $\tau$  obtained with the exponential fits of the data in (a) and the colored lines show the analytical expression of  $\tau$  for  $t \approx 0$  in yellow, and  $t \rightarrow \infty$  in blue for  $J \in [\frac{J_c}{\sqrt{2}}, J_c]$  and in red for  $J > J_c$ . Blue and red dashed vertical lines correspond to  $\frac{J_c}{\sqrt{2}}$  and  $J_c$ . (c) Shows the DW motion delay depending on the DW angle when the current is turned off  $\varphi^0$ . The yellow horizontal line shows the characteristic time  $\tau_0$  and the purple curve is the expected variation of the motion delay with  $\varphi^0$ .

For the second part, when it exists (i.e., for  $J > \frac{J_c}{\sqrt{2}}$ ), the characteristic time depends on J explicitly and implicitly through  $\varphi_{(J)}^{\infty}$  in Eq. (6). For  $J \in ]\frac{J_c}{\sqrt{2}}$ ,  $J_c[$ ,  $\tau_{(J)} = \frac{\tau_0}{1-j^2}$  and for J > Jc,  $\tau_{(J)} = \frac{\tau_0}{j-1}$ . For each case,  $(\varphi_{(t\approx\infty)} - \varphi^{\infty}) \propto (1 - e^{-t/\tau})$  and  $(v_{(t\approx\infty)} - v^{\infty}) \propto e^{-t/\tau}$ . The colored lines in Fig. 2(a) show the exponential decays of v, with the extracted characteristic times shown as black dots in Fig. 2(b). These are reproduced well by the analytical  $\tau$  versus J curves (yellow:  $J < \frac{J_c}{\sqrt{2}}$ , blue:  $J \in ]\frac{J_c}{\sqrt{2}}$ ,  $J_c[$ , and red:  $J > J_c$ ). This dependence of  $\tau$  on the strength of the drive J leads to nontrivial non-Newtonian dynamics.  $\tau$  even diverges at  $J_c$ , which means that the internal angle tends to  $\pm \frac{\pi}{2}$  but never reaches this value at this critical current. Conversely, for  $J > J_c$ ,  $\tau$  is finite, meaning that the DW reaches its pure Bloch configuration ( $\varphi = \pm \frac{\pi}{2}$ ).

When the current is turned off, the DW relaxes in its Néel configuration [as shown Fig. 2(a)] with  $\varphi_{(J=0)}^{\infty} = 0$  or  $\pi$  depending on the internal DW angle at this time  $\varphi^0$ . For J = 0,

Eq. (2) gives

$$\varphi(t) = (\widetilde{\varphi^0}) + \operatorname{arccot}(\operatorname{cot}(\varphi^0)e^{t/\tau_0}), \tag{7}$$

with  $(\varphi^0) = 0$  or  $\pi$  defined as before. The relaxation occurs with a characteristic time  $\tau_0$ , independent of  $\varphi^0$ . If the DW crosses  $\varphi = \pm \frac{\pi}{4} [\pi]$  during its relaxation, it exhibits a velocity peak after a delay of  $-\tau_0 \log |\cot(\varphi^0)|$  as visible Fig. 2(a). Figure 2(c) shows the evolution of the motion delay whenever it exists *versus* the DW angle at the end of the pulse  $[\varphi^0$  in Eq. (7)].

The velocity overshoot of the DW for  $J > \frac{J_c}{\sqrt{2}}$  might be very convenient for getting out eventual pinning centers as it is the case for other driving forces [41,42]; however, here, this property is intrinsic to the DW dynamics. Such spiky and delayed DW dynamics also echoes properties explored for brain-inspired computing [43–45].

#### D. Brownian motion under large current pulses

It is interesting to note that  $\varphi^{\infty}$  implicitly depends on  $\varphi^0$ according to Eq. (5). Thus, the angles  $\varphi^0 = \pm \frac{\pi}{2}$  are bifurcation points where the asymptotic angles  $\varphi^{\infty}$  towards which  $\varphi$  will tend are completely different for  $\varphi^0 = \pm \frac{\pi}{2} \pm 0^+$ . In particular, infinitesimal changes lead to opposite propagation directions of the DW. However, for large current  $(J \gg J_c)$ , required to reach the reversal points  $\varphi = \pm \frac{\pi}{2}$ , the SOT tends to keep the DW in that Bloch configuration [according to Eq. (5) and shown Fig. 1]. To achieve the reversal of the DW propagation taking advantage of these bifurcation points, we propose to use large current pulses, with magnitudes larger than  $J_c$ . The SOT pulse sets the DW in its Bloch state ( $\varphi =$  $\pm \frac{\pi}{2}$ ) and after the pulse, the DW relaxes into one of its Néel state  $\varphi_{(J=0)}^{\infty} = 0$  or  $\pi$  randomly, inducing DW motions. This internal dynamics is shown Fig. 3(a) for a 20-ns pulse of 15 GA/m<sup>2</sup> on a DW with an initial state Q = 1 and  $\varphi = 0$ . The insets and the colored highlights indicate if  $\varphi \in \left] - \frac{\pi}{2}, \frac{\pi}{2} \right[$ in green or  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  in purple. After the bifurcation point (shown as a red star) the DW relaxes in one of its Néel states driving the DW in opposite directions.

As the infinitesimal change of  $\varphi$  just plays a role at the end of the pulse, it is possible to mimic the random reversals of the DW propagation during a large number of pulse by considering a small random deviation of the DW internal angle at the end of each pulse. In practice, this is naturally achieved by the thermal fluctuations or the inhomogeneities of the system. Figure 3(b) shows the DW displacements and internal angle under a series of 20-GA/m<sup>2</sup> pulses with 20-ns widths and 20-ns delays. At the end of each pulse  $\varphi$  is deviated by a quantity following a normal distribution with a standard deviation of 0.1°. The red stars indicate if the DW reversal occurs.

Figure 3(c) shows the probability of the DW displacement in the positive direction (black curve) and the probability of the propagation reversal (red curve) *versus* the current density for 20-ns pulses. Above a critical current larger than  $J_c$ , the DW displacement in one or the other direction is completely equiprobable even if the reversal probability is gradually increasing. During this transition, the DW reversal is quite rare and the DW moves in the same direction for a large number of

![](_page_4_Figure_1.jpeg)

FIG. 3. Brownian motion of the DW under large current pulses: (a) Shows the reversal process of the DW at the end of a current pulse with a magnitude larger than  $J_c$ . The evolution of the DW position is calculated by numerical integration of Eqs. (1) and (2) (black line) for a pulse of 20-ns width and 20-GA/m<sup>2</sup> magnitude. The colored highlights indicate if  $\varphi \in \left] - \frac{\pi}{2}, \frac{\pi}{2}\right[$  in green or  $\varphi \in \left] \frac{\pi}{2}, \frac{3\pi}{2}\right]$  in purple. The insets sketch the DW state before and after the end of the pulse corresponding to a bifurcation point (indicated as a red star). (b) Shows the DW under a series of 20-GA/m<sup>2</sup> 20-ns pulses with 20-ns delays (as indicated in the inset). To capture the infinitesimal changes of  $\varphi$ , at the end of each pulse  $\varphi$  is deviated by an infinitesimal quantity obeying a normal distribution with a standard deviation of  $0.1^{\circ}$ . The red stars indicate when the DW reversal occurs. (c) Shows the probability of the DW motion in the positive direction (black curve) and of the DW reversal (red curve) calculated during 1000 pulses for different current densities. (d) Shows the square-root evolution of the mean-squared displacement  $\langle q^2 \rangle$  with the number of pulses averaged over 200 series of 100 pulses. The yellow line is the linear fit  $\langle q^2 \rangle \propto t$ .

pulses. After this transition, the reversal is completely random and the DW motion obeys the Brownian law. Figure 3(d) shows the expected square-root evolution of the mean-squared DW displacement with the number of pulses [46]  $\langle q^2 \rangle = 2Dt$ with a diffusivity  $D = 1.4 \times 10^{-2} \,\mu\text{m}^2/20$  ns pulse. The current pulse magnitude above which the DW displacement is Brownian decreases with the pulse duration and with the standard deviation of the  $\varphi$  deviation as these two quantities promote the DW reversal. This Brownian dynamics does not depend on the current sequence and can be also obtained for a square- or a sine-wave current with large amplitude (not shown here). In the following, the reversal of a moving DW under continuous currents is considered.

## E. Propagation reversal under perpendicular field

As for a DW motion driven by continuous current  $\dot{\varphi}_{(\varphi=\pm\frac{\pi}{2})} = 0$  [according to Eq. (2)], the controlled reversal of its propagation requires additional torques acting on  $\varphi$ . This could be achieved by using an in-plane field or fieldlike torques. However, this will not allow repeatedly reversing the propagation without changing the polarity of these torques. This implies knowing the DW state at any moment to reverse its propagation. On the other hand, the use of an out-of-plane

![](_page_4_Figure_7.jpeg)

FIG. 4. Propagation reversal under  $H_z$ : (a), (b) Show the propagation reversal of a DW driven by continuous SOT (with  $J = 3 \text{ GA}/\text{m}^2$ ) under out-of-plane field pulses in the  $(q, \varphi)$  space for Q = 1 and, respectively,  $\varphi^0 \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$  (a) and  $\varphi^0 \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  (b). For both (a) and (b), pulse width of duration  $t_{H_z} = 3$  ns and magnitude  $\mu_0 H_z = 2$ , 4, and 7 mT and are applied for, respectively, the cases 1, 2, and 3. Black dots and lines correspond to the numerical simulations. The spacing between dots corresponds to a 1-ns time interval. The colored lines correspond to the numerical integration of the q- $\varphi$ model given by Eqs. (8) and (9). The color shows if  $\varphi \in \left] - \frac{\pi}{2}, \frac{\pi}{2} \right[$ in green, or if  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  in purple, as indicated in the insets. The black arrows indicate the DW propagation directions. (c), (d) Show the reversal phase diagram in the  $(H_z, t_{H_z})$  space for a DW driven by  $J = 3 \text{ GA/m}^2$ . Colored dots indicate the final state of the DW after 10-ns relaxation following the field pulse obtained by the micromagnetic simulations:  $\varphi \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$  in green and  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  in purple. The black circles correspond to the configurations shown in (a) and (c). The background color shows the same results but obtained by the numerical integration of the q- $\varphi$  model [Eqs. (8) and (9)]. Black lines show the analytical hyperbolas, which separate the reversal regions obtained with the linearized model.

field  $H_z$  induces a torque on the magnetization independent of  $\varphi$  (only depending on Q). In the presence of  $H_z$  Eqs. (1) and (2) become

$$\dot{q} = \frac{\Delta}{\alpha \tau_0} \left( Q \alpha^2 [j \cos \varphi + h_z] + \frac{\sin 2\varphi}{2} \right), \tag{8}$$

$$\dot{\varphi} = \frac{1}{\tau_0} \left( Q[j \cos \varphi + h_z] - \frac{\sin 2\varphi}{2} \right), \tag{9}$$

with the dimensionless out-of-plane field  $h_z = \frac{H_z}{\alpha H_{\text{KIP}}}$  corresponding to the ratio between  $H_z$  which tends to rotate  $\varphi$  in the  $QH_z$  direction (whatever the value of  $\varphi$ ) and  $H_{\text{KIP}}$  which tends to keep the DW in its Néel state. In particular, when the field is applied,  $\dot{\varphi}_{(\varphi=\pm\frac{\pi}{2},H_z\neq0)}\neq 0$  which allows for overcoming the reversal limits  $\varphi=\pm\frac{\pi}{2}$ . Note that even if v changes while  $H_z$  is applied, the proper reversal is governed by the DW state when the field is turned off.

Figures 4(a) and 4(b) show some examples of propagation reversal driven by field pulses for pulse width of  $t_{H_2} = 3$  ns and different magnitudes  $(H_z > 0)$  plotted in the  $(q, \varphi)$  space for Q = 1. For every  $(H_z, t_{H_z})$  pulse, the DW stabilizes itself in its steady state under a continuous current of  $3 \text{ GA/m}^2$  (during 5 ns), a pulse of field is applied during  $t_{H_2}$ , and the DW relaxes in its new state during 5 ns. To avoid the initial transient regimes, we consider  $\varphi^0$  as  $\varphi^0 = \varphi^\infty \approx 0.2\pi \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$  or  $\varphi^0 = \varphi^\infty \approx 0.8\pi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  for Fig. 4(a) or 4(b), respectively. The black arrows indicate the propagation direction of the DW. In both Figs. 4(a) and 4(b), the black dots correspond to the evolution of the DW state obtained from the micromagnetic simulations with the space between them corresponding to 1-ns time intervals. The colored lines correspond to the numerical integration of the q- $\varphi$  model accounting a field pulse [given by Eqs. (1) and (2) in absence of the field and Eqs. (8) and (9) during the field pulse]. The color of these lines depends on  $\varphi$ : green for  $\varphi \in \left] - \frac{\pi}{2}, \frac{\pi}{2}\right[$  and purple for  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$ . The plots shown in Figs. 4(a) and 4(b) clearly demonstrate that the applied field can be used to overcome the reversal limit which flips the propagation direction of the DW after the field for, possibly, the two states of the DW.

This field-induced reversal strongly depends on the magnitude and width of the field pulse. To handle that dependence, the above simulation has been repeated for different  $(H_7, t_{H_2})$ . Figures 4(c) and 4(d) show the final state of the DW after the field pulse for each  $(H_7, t_{H_2})$  [obtained with the micromagnetic simulations (dots) and by numerically integrating the q- $\varphi$  model (background color)]. The configurations detailed in Figs. 4(a) and 4(b) are circled in black in Figs. 4(c)and 4(d). To obtain the reversal conditions, Eq. (9) can be linearized by considering the effect of the out-of-plane field on  $\varphi$  is much larger than the combined effects of the SOT and the in-plane anisotropy giving  $\varphi \approx \varphi^0 + \frac{Qh_z}{\tau_0}t$ . The conditions for a DW reversal can thus be defined as  $(\frac{4n+1}{2}\pi - \varphi^\infty) < Qh_z \frac{t_{H_z}}{\tau_0} < (\frac{4n+3}{2}\pi - \varphi^\infty)$  for  $\varphi^0 \in ] -\frac{\pi}{2}, \frac{\pi}{2}[$  [the cases shown in Figs. 4(a) and 4(c)], and  $(\frac{4n-1}{2}\pi + \varphi^{\infty}) < Qh_z \frac{t_{H_z}}{\tau_0} < Qh_z \frac{$  $(\frac{4n-3}{2}\pi + \varphi^{\infty})$  for  $\varphi^0 \in ]\frac{\pi}{2}, \frac{3\pi}{2}$  [ [the cases shown in Figs. 4(b) and 4(d)]. *n* corresponds to the number of flips in multiple flipping processes.

The analytic hyperbolic lines delimiting these regions in the  $(H_z, t_{H_z})$  space are plotted in black in Figs. 4(c) and 4(d). They match well to the simulated cases except for low fields and low pulse widths where the  $\dot{\varphi} \sim H_z$  assumption is not well justified. For larger  $H_z$  and  $t_{H_z}$ , the regions where the DW propagation is reversed are more and more condensed, which is equivalent to a quasirandom flipping process (similar to the coin reversal in a heads-or-tails process [47]).

Additionally, these reversal regions are not exactly the same for  $\varphi^0 \in ] - \frac{\pi}{2}, \frac{\pi}{2}[$  and  $\varphi^0 \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$ . Thus, it is possible to reverse only the DW pertaining to one of these cases, setting all the DW with the same  $\varphi$ , as shown in the second panel in Figs. 4(a) and 4(b). At the opposite, a pulse with conditions that correspond to a reversal for the two cases flips all the DWs, independently of their initial angle, as shown in the third panel in Figs. 4(a) and 4(b). The shift between the reversal regions for  $\varphi^0 \in ] - \frac{\pi}{2}, \frac{\pi}{2}[$  and  $\varphi^0 \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  increases with the current density as  $\varphi^{\infty}$  is much closer to the reversal point for

one type of DW than for the other [as visible in the table Fig. 1(b)].

### F. Step in anisotropy

Even if an out-of-plane field allows the propagation reversal, its effects are strongly dependent on the pulse width and magnitude, and significantly disturb the DW propagation with multiple reversals. To achieve similar effects in a much more controlled way, it is possible to consider a spatial variation of the out-of-plane anisotropy  $K_{(x)}$  (with *x* the position along the wire). That can be directly associated with an effective local out-of-plane field  $H_{z(q)}^K = -\frac{\Delta}{\mu_0 M_s} \partial_q \tilde{K}_{(q)}$  where  $\tilde{K}_{(q)} = \frac{\int K_{(x)}(1-m_{z(x,q)}^2)dx}{\int (1-m_{z(x,q)}^2)dx}$  is the effective variation of the out-of-plane anisotropy with *q*, the position of the DW along the magnetic wire. Here,  $m_z$  is the *z* component of the local unit magnetization vector  $\hat{m}$ . This field vanishes where the anisotropy is uniform and it has a maximum where *K* changes most rapidly with position *x*.

Figure 5(a) shows the effect of a step of anisotropy of magnitude  $\delta K$  at the position  $x_{\text{step}}$  on a moving DW with Q = 1and  $\varphi^0 = \varphi^{\infty}$  for different J and different step magnitudes. The evolution of the DW dynamics is represented in the  $(q, \varphi)$ space and the arrows indicate the DW propagation directions. The black dots correspond to the simulated evolution of the DW dynamics with a time interval between them of 1 ns. The gray curve in the background shows the anisotropy variation along the wire. As visible in the different cases, the DW can be either stopped (case 1), transmitted (case 2 or 4), or reflected (case 3), depending on J and  $\delta K$ .

As for a regular out-of-plane field,  $H_{\delta K}$  acts on  $\varphi$  as described by Eq. (9), but here the strength of the field experienced by the DW depends on its position along the wire q. For high positive  $\delta K$ , if  $H_{z(q)}^K \propto -\delta K$  pushes  $\varphi$  down to zero, the DW propagation is reversed (since  $v \sim \sin 2\varphi$ ) and the field experienced by the DW decreases. That pushes the DW back to its steady state with  $\varphi^{\infty} > 0$ , reversing again its propagation direction. The converging repetition of that process leads to the pinning of the DW before the anisotropy step as shown in the first panel of Fig. 5(a) (case 1).

If  $\varphi$  does not cross zero while the DW cross the region where the anisotropy changes, the DW propagation is not reversed and the DW is transmitted as shown in the second panel of Fig. 5(a) (case 2). That occurs for lower  $\delta K$ , where  $\varphi$ is less affected by the anisotropy step, and for larger J where  $\varphi^{\infty}$  is farther from 0 and the DW is faster, experiencing the effective field for a shorter period of time. For negative  $\delta K$ , and low J, the DW crosses the anisotropy step without crossing the reversal limit  $\varphi = \frac{\pi}{2}$ , and so it is transmitted, as shown in the third panel (case 2) in Fig. 5(a).

For larger J,  $\varphi^{\infty}$  is larger and even a small  $\delta K$  allows the DW to cross this reversal limit. The DW moves then farther from the anisotropy step and experiences  $H_z^K$  less and less. The DW is therefore reflected by the anisotropy step as shown in the fourth panel of Fig. 5(a), case 3.

For large and negative  $\delta K$ , the proximity of the anisotropy step can lead to multiple reversals of  $\varphi$ . If the current is too small, the DW is either reflected (for an odd number of reversals) or transmitted [for an even number of reversals; as shown

![](_page_6_Figure_1.jpeg)

FIG. 5. Propagation reversal at an anisotropy step: (a) Shows the propagation reversal of a DW at the anisotropy step at the position  $x_{\text{step}}$  in the  $(q, \varphi)$  space for  $\varphi^0 = \varphi^\infty \approx 0.2\pi$  and Q = 1and for  $(J, \delta K) = (3, 0.01), (3, 0.005), (3, -0.005), (3, -0.02), and$ (1.5, -0.025) in units of  $(GA/m^2, MJ/m^3)$ . The gray shape in the background (relative to the right axis) shows the x variation of the anisotropy. Black dots and lines correspond to the numerical simulations with a spacing between the dots corresponding to a 1-ns time interval. The colored lines correspond to the numerical integration of the q- $\varphi$  model considering the anisotropy step as a local field  $H_z^K(q)$ . Its color shows whether  $\varphi \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$  in green and  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  in purple. The black arrows indicate the DW propagation direction. (b) Shows the reversal phase diagram in the  $(J, \delta K)$  space. Colored dots indicate the final state of the DW after its interaction with the anisotropy step obtained by the numerical simulations: transmission in green, stoppage in gray, and reflected in purple. The black circles correspond to the configurations shown in (a). The background color shows the same results but obtained by the numerical integration of the q- $\varphi$  model. Black lines show the frontiers between the different behaviors considering an approximated square field as discussed in the main text. (c) Shows a sketch of the different approximations of the effective field  $H_{\tau}^{K}(q)$ : the gray shape in the background (relative to the right axis) shows the variation of the anisotropy, the blue curve (relative to the left axis) shows the variation of  $H_z^K(q)$  (by assuming a rigid DW), and the dashed blue curve shows the square approximation of  $H_z^K(q)$  used for the simplified q- $\varphi$  model.

in the fifth panel of Fig. 5(a), case 4]. For larger current, the DW reverses just one time and the DW is reflected similarly to case 3. These different effects of the anisotropy step are summarized in Fig. 4(b). The colored points correspond to the  $(J, \delta K)$  configurations where the DW is either stopped (gray points), transmitted (green points), or reflected (purple points).

By assuming  $\delta K$  is quite small compared to K, the DW width  $\Delta$  is considered as constant, independent of the anisotropy step [39]. A sharp step of anisotropy at a position  $x_{\text{step}}$  with a magnitude of  $\delta K$  is thus directly associated to an out-of-plane field  $H_{z(q-x_{\text{step}})}^{K} = -\frac{\delta K}{2\mu_0 M_s} \cosh^{-2}(Q\frac{q-x_{\text{step}}}{\Delta})$ , as plotted in Fig. 5(c). By numerically integrating the coupled space and time evolution of q and  $\varphi$  in Eqs. (8) and (9), considering the above  $H_{z(q-x_{\text{step}})}^{K}$ , it is possible to reproduce

the simulated results with a very good agreement. The lines in Fig. 5(a) show the time evolution of q and  $\varphi$  by considering this effective local field with the colors indicating the DW state:  $\varphi \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$  (in green) and  $\varphi \in ]\frac{\pi}{2}, \frac{3\pi}{2}[$  (in purple). The background colors in Fig. 5(b) show the final velocity of the DW obtained with this approach: stopped in gray, transmitted in green, and reflected in purple.

The DW reversal conditions can even be obtained by considering  $H_{\delta K}$  as a uniform field of magnitude  $H_z^K = -\frac{\delta K}{\mu_0 M_s}$ for  $q \in [x_{\text{step}} - \Delta, x_{\text{step}} + \Delta]$  and 0 outside this region [as plotted Fig. 5(c)]. Therefore, the reflection, transmission, or pinning of the DW is given by the DW final state for q = $x_{\text{step}} \pm \Delta$  after the DW interaction with the anisotropy step. Since  $H_{\text{SOT}} \ll H_z^K$  and  $\alpha H_{\text{KIP}} \ll H_z^K$ , Eqs. (8) and (9) can be linearized such as  $\dot{q} \approx \frac{\Delta}{\alpha \tau_0} (-Q\alpha \frac{\delta K}{2K_{IP}} + \frac{\sin 2\varphi}{2})$  and  $\dot{\varphi} \approx$  $-\frac{Q\delta K}{2\alpha K_{IP}\tau_0}$ . The frontiers between the different regions of the diagram in Fig. 5(b) can thus be extracted. For  $\varphi_{(q=x_{step}-\Delta)} =$  $\varphi^{\infty} \in ]-\frac{\pi}{2}, \frac{\pi}{2}[$ , the frontier between the regions 1 and 2 in Fig. 5(b) is given by  $\varphi_{(q=x_{step}+\Delta)} \leq 0$ . This gives  $\delta K_{[1/2]} =$  $QK_{\rm IP}(\frac{\sin^2\varphi^{\infty}}{2+\alpha\varphi^{\infty}})$ . The frontiers between region 2 and regions 3 and 4 is given by  $\varphi_{(q=x_{\text{step}}+\Delta)} \ge \frac{\pi}{2}$  which leads to  $\delta K_{[2/3]} = \delta K_{[2/4]} = -QK_{\text{IP}}(\frac{\cos^2 \varphi^{\infty}}{2-\alpha(\frac{\pi}{2}-\varphi^{\infty})})$ . The frontier between regions 3 and 4 is given by two conditions:  $\varphi_{(q=x_{\text{step}}+\Delta)} \ge \frac{\pi}{2}$  as before, but also  $\varphi_{(q=x_{step}-\Delta)} \leqslant \pi$  corresponding to the two reversal process case. This gives  $\delta K_{[3/4]} = -QK_{\rm IP}(\frac{\sin^2 \varphi^{\infty}}{\alpha(\pi - \varphi^{\infty})})$ . These frontiers are shown by black lines in Fig. 5(b) and match both the simulated and the numerical results with a good agreement. Since these calculations are based on the linearization of Eq. (9), they are more accurate if  $\varphi$  only deviates slightly from  $\varphi_{(q=x_{\text{step}}-\Delta)} = \varphi^{\infty}$ , such as the frontier between 1 and 2 for low current and the one between 2 and 3 for J close to  $J_c$ . These results show that by adapting the anisotropy step  $\delta K$  to the current driving the DW, it is possible to select one of the processes. Such locally variable anisotropy can be controlled by using voltages [48,49], and can lead to a three-state DW transistor.

In the case of a DW between two anisotropy steps corresponding to the region 3 of the diagram 5(b), the DW will be reflected at each of the two steps leading to the oscillations of the DW propagation as shown Fig. 6(a), analogous to confinement in a Fabry-Perot cavity.

## G. Finite magnetic track

A similar effect can be obtained at the extremities of a finite magnetic wire, as shown Figs. 6(b) and 6(c). The black points in Fig. 6(c) correspond to the simulated trajectory of the DW in  $(q, \varphi)$  space and the background color corresponds to the shape of the magnetic element [visible in Fig. 6(b)]. As previously, the extremities of the magnetic wire act on the DW internal angle  $\varphi$ . For low current, the DW stopped in its Bloch configuration (here  $\varphi = 0$ ) just before the end of the wire, as shown in the first case of the Fig. 6(c). If the current increases, the DW goes off the end of the track before being in its Bloch state and the magnetic wire is then fully saturated as shown in the second case of Fig. 6(c). For a sufficiently large current, the end-of-track effect pushes the DW across its reversal points before it leaves the wire and the DW is

![](_page_7_Figure_1.jpeg)

FIG. 6. DW-based oscillators: (a) Shows an example of the DW oscillations for a DW between two anisotropy steps [similar to the case 3 in Fig. 5(a)] with a continuous current of  $J = 3 \text{ GA/m}^2$  and  $\delta K = \pm 0.02 \text{ MJ/m}^3$  and for an initial state Q = 1 and  $\varphi^0 = 0$ . Black dots, black lines, the gray profile, and colored lines have the same meanings as in Fig. 5(a). (b) Shows a sketch of a DW oscillator based on a finite magnetic wire where the continuous electrical current is injected in the bottom HM layer. (c) Shows the different behaviors of the DW in such devices: DW stopped, destroyed, or reflected by the track extremities, depending on the current density for, respectively,  $J = 1.5, 3, 4.5, 7 \text{ GA/m}^2$  in the  $(q, \varphi)$  space. The background indicates the shape of the finite magnetic track. (d) Shows the variation of the DW oscillation frequency for different magnitude of the DC current extracted from (c). The yellow curve corresponds to the expected frequency of these oscillations f = v/2l with  $l = 1 \ \mu m$ above a certain current density  $J_{osc.}$ .

then reflected along the track. A similar process occurs at the other extremity and then the DW oscillates continuously from one to the other extremity, as in the third case of Fig. 6(c). If  $J > J_c$  and the DW is in the middle of the wire, far from the track extremities, the DW is stopped as expected. However, if the DW is close to the track end, it will be attracted and then stopped in its Bloch state after small oscillations of  $\varphi$  around  $\frac{\pi}{2}$  as in the fourth case of Fig. 6(c).

The possibility to make DW oscillate in such small elements driven by a continuous current is also a new way for small magnetic oscillators with a triangular wave time evolution, and for which the frequency f = v/2l, typically in the MHz range, is just governed by the DW velocity vand the track length *l*. Figure 6(d) shows the variation of this frequency versus the magnitude of the current for the magnetic track shown in Fig. 6(b). Interestingly, the nonuniform variation of v with *J* leads to a nonlineal variation of this frequency with the magnitude of the continuous current above a critical current  $J_{\text{osc.}}$  above which the DW oscillates. The shape of the track extremity has only small effects on these results and just modifies  $J_{\text{osc.}}$ .

## **IV. CONCLUSION**

The possibility to stabilize Néel DWs with an achiral mechanism allows for the bistability of these magnetic textures, where both chiralities are energetically degenerate. This gives rise to new forms of SOT-driven DW dynamics. Two propagation directions for such DWs are now possible, only depending on their initial state. By increasing the current density, the DW exhibits a nonmonotonic velocity law with a maximum of velocity and a critical current above which the DW is locked in its pure Bloch state and does not move. This nonuniformity of the velocity law also induces important transient regimes and out-of-equilibrium dynamics. Finally, the possibility of controlled or random reversal of the DW chirality and, therefore, of its propagation direction, has been demonstrated under certain conditions (large current pulses, out-of-plane field, steps of magnetic anisotropy, or the extremities of finite length magnetic tracks). Of particular note are the ability to reflect or transmit DWs at a step in the anisotropy K, with the potential for control through voltage-controlled magnetic anisotropy, and new forms of DW oscillator in which a DW is continuously reflected between anisotropy steps or the ends of a magnetic nanowire. All these completely new behaviors, simulated numerically, have been perfectly reproduced with a suitable analytical model. All these new dynamics offer very interesting possibilities for future DWbased devices that can possibly mix storage and processing.

Data and code associated with this work are available on the University of Leeds Data Repository [50].

## ACKNOWLEDGMENTS

This project has received funding from the EPSRC under Grant No. EP/T006803/1 and the European Unions Horizon 2020 research and innovation program under the Marie Sklodowska-Curie Grant Agreement No. 750147. K.J.A.F. acknowledges support from the Jane and Aatos Erkko Foundation. The main part of these numerical simulations were performed on MAGI, the computing platform of the University Sorbonne Paris Nord, managed by N. Greneche. We thank Y. Roussigné (from the LSPM) for fruitful discussions.

- D. Kumar, T. Jin, R. Sbiaa, M. Kläui, S. Bedanta, S. Fukami, D. Ravelosona, S.-H. Yang, X. Liu, and S. Piramanayagam, Domain wall memory: Physics, materials, and devices, Phys. Rep. 958, 1 (2022).
- [2] S. S. P. Parkin, M. Hayashi, and L. Thomas, Magnetic domainwall racetrack memory, Science 320, 190 (2008).
- [3] D. A. Allwood, G. Xiong, C. C. Faulkner, D. Atkinson, D. Petit, and R. P. Cowburn, Magnetic domain-wall logic, Science 309, 1688 (2005).
- [4] H. Lin, N. Xu, D. Wang, L. Liu, X. Zhao, Y. Zhou, X. Luo, C. Song, G. Yu, and G. Xing, Implementation of highly reliable and energy-efficient nonvolatile in-memory computing using multistate domain wall spin-orbit torque device, Adv. Intell. Syst. 4, 2200028 (2022).
- [5] Z. Luo, T. P. Dao, A. Hrabec, J. Vijayakumar, A. Kleibert, M. Baumgartner, E. Kirk, J. Cui, T. Savchenko, G. Krishnaswamy, L. J. Heyderman, and P. Gambardella, Chirally coupled nano-magnets, Science **363**, 1435 (2019).

- [6] S. Liu, T. P. Xiao, C. Cui, J. A. C. Incorvia, C. H. Bennett, and M. J. Marinella, A domain wall-magnetic tunnel junction artificial synapse with notched geometry for accurate and efficient training of deep neural networks, Appl. Phys. Lett. 118, 202405 (2021).
- [7] J. Williame and J.-V. Kim, A magnetic domain wall Mackey-Glass oscillator, Appl. Phys. Lett. 118, 152404 (2021).
- [8] R. V. Ababei, M. O. A. Ellis, I. T. Vidamour, D. S. Devadasan, D. A. Allwood, E. Vasilaki, and T. J. Hayward, Neuromorphic computation with a single magnetic domain wall, Sci. Rep. 11, 15587 (2021).
- [9] S. A. Siddiqui, S. Dutta, A. Tang, L. Liu, C. A. Ross, and M. A. Baldo, Magnetic domain wall based synaptic and activation function generator for neuromorphic accelerators, Nano Lett. 20, 1033 (2020).
- [10] N. Hassan, X. Hu, L. Jiang-Wei, W. H. Brigner, O. G. Akinola, F. Garcia-Sanchez, M. Pasquale, C. H. Bennett, J. A. C. Incorvia, and J. S. Friedman, Magnetic domain wall neuron with lateral inhibition, J. Appl. Phys. **124**, 152127 (2018).
- [11] J. Shibata, G. Tatara, and H. Kohno, A brief review of field- and current-driven domain-wall motion, J. Phys. D: Appl. Phys. 44, 384004 (2011).
- [12] G. S. D. Beach, C. Nistor, C. Knutson, M. Tsoi, and J. L. Erskine, Dynamics of field-driven domain-wall propagation in ferromagnetic nanowires, Nat. Mater. 4, 741 (2005).
- [13] A. Thiaville, Y. Nakatani, J. Miltat, and Y. Suzuki, Micromagnetic understanding of current-driven domain wall motion in patterned nanowires, Europhys. Lett. 69, 990 (2005).
- [14] A. Manchon, J. Železný, I. M. Miron, T. Jungwirth, J. Sinova, A. Thiaville, K. Garello, and P. Gambardella, Current-induced spin-orbit torques in ferromagnetic and antiferromagnetic systems, Rev. Mod. Phys. **91**, 035004 (2019).
- [15] A. V. Khvalkovskiy, V. Cros, D. Apalkov, V. Nikitin, M. Krounbi, K. A. Zvezdin, A. Anane, J. Grollier, and A. Fert, Matching domain-wall configuration and spin-orbit torques for efficient domain-wall motion, Phys. Rev. B 87, 020402(R) (2013).
- [16] K.-S. Ryu, L. Thomas, S.-H. Yang, and S. Parkin, Chiral spin torque at magnetic domain walls, Nat. Nanotechnol. 8, 527 (2013).
- [17] A. Thiaville, S. Rohart, milie Jué, V. Cros, and A. Fert, Dynamics of Dzyaloshinskii domain walls in ultrathin magnetic films, Europhys. Lett. **100**, 57002 (2012).
- [18] G. Chen, T. Ma, A. T. N'Diaye, H. Kwon, C. Won, Y. Wu, and A. K. Schmid, Tailoring the chirality of magnetic domain walls by interface engineering, Nat. Commun. 4, 2671 (2013).
- [19] J. Torrejon, J. Kim, J. Sinha, S. Mitani, M. Hayashi, M. Yamanouchi, and H. Ohno, Interface control of the magnetic chirality in CoFeB/MgO heterostructures with heavy-metal underlayers, Nat. Commun. 5, 4655 (2014).
- [20] A. Hrabec, N. A. Porter, A. Wells, M. J. Benitez, G. Burnell, S. McVitie, D. McGrouther, T. A. Moore, and C. H. Marrows, Measuring and tailoring the Dzyaloshinskii-Moriya interaction in perpendicularly magnetized thin films, Phys. Rev. B 90, 020402(R) (2014).
- [21] S. Emori, U. Bauer, S.-M. Ahn, E. Martinez, and G. S. D. Beach, Current-driven dynamics of chiral ferromagnetic domain walls, Nat. Mater. 12, 611 (2013).

- [22] K. J. A. Franke, C. Ophus, A. K. Schmid, and C. H. Marrows, Switching between magnetic Bloch and Néel domain walls with anisotropy modulations, Phys. Rev. Lett. **127**, 127203 (2021).
- [23] C. Wu, Y. Huang, Y. Cui, Z. Shen, Y. Ma, S. Xie, H. Du, X. Gao, and S. Li, Film thickness gradient-induced magnetic anisotropy and ferromagnetic resonance in Fe<sub>56</sub> Co<sub>24</sub> B<sub>2</sub> amorphous films prepared by pulse laser deposition, IEEE Trans. Magn. **51**, 1 (2015).
- [24] G. Chen, A. T. N'Diaye, S. P. Kang, H. Y. Kwon, C. Won, Y. Wu, Z. Q. Qiu, and A. K. Schmid, Unlocking Bloch-type chirality in ultrathin magnets through uniaxial strain, Nat. Commun. 6, 6598 (2015).
- [25] M. D. DeJong and K. L. Livesey, Analytic theory for the switch from Bloch to Néel domain wall in nanowires with perpendicular anisotropy, Phys. Rev. B 92, 214420 (2015).
- [26] B. A. Belyaev, A. V. Izotov, P. N. Solovev, and N. M. Boev, Strain gradient induced unidirectional magnetic anisotropy in nanocrystalline thin permalloy films, Phys. Status Solidi RRL 14, 1900467 (2020).
- [27] M. Fattouhi, F. Garcia-Sanchez, R. Yanes, V. Raposo, E. Martinez, and L. Lopez-Diaz, Absence of walker breakdown in the dynamics of chiral Néel domain walls driven by in-plane strain gradients, Phys. Rev. Appl. 18, 044023 (2022).
- [28] K. A. Omari, T. J. Broomhall, R. W. Dawidek, D. A. Allwood, R. C. Bradley, J. M. Wood, P. W. Fry, M. C. Rosamond, E. H. Linfield, M. Y. Im, P. J. Fischer, and T. J. Hayward, Toward chirality-encoded domain wall logic, Adv. Funct. Mater. 29, 1807282 (2019).
- [29] A. Skaugen, P. Murray, and L. Laurson, Analytical computation of the demagnetizing energy of thin-film domain walls, Phys. Rev. B 100, 094440 (2019).
- [30] B. Boehm, A. Bisig, A. Bischof, G. Stefanou, B. J. Hickey, and R. Allenspach, Achiral tilted domain walls in perpendicularly magnetized nanowires, Phys. Rev. B 95, 180406 (2017).
- [31] C. O. Avci, G. S. D. Beach, and P. Gambardella, Effects of transition metal spacers on spin-orbit torques, spin Hall magnetoresistance, and magnetic anisotropy of Pt/Co bilayers, Phys. Rev. B 100, 235454 (2019).
- [32] T. Nan, S. Emori, C. T. Boone, X. Wang, T. M. Oxholm, J. G. Jones, B. M. Howe, G. J. Brown, and N. X. Sun, Comparison of spin-orbit torques and spin pumping across NiFe/Pt and NiFe/Cu/Pt interfaces, Phys. Rev. B 91, 214416 (2015).
- [33] D. X. Chen, E. Pardo, and A. Sanchez, Demagnetizing factors of rectangular prisms and ellipsoids, IEEE Trans. Magn. 38, 1742 (2002).
- [34] A. Mougin, M. Cormier, J. P. Adam, P. J. Metaxas, and J. Ferré, Domain wall mobility, stability and Walker breakdown in magnetic nanowires, Europhys. Lett. 78, 57007 (2007).
- [35] C.-Y. You, Confined magnetic stray field from a narrow domain wall, J. Appl. Phys. 100, 043911 (2006).
- [36] A. Vansteenkiste, J. Leliaert, M. Dvornik, M. Helsen, F. Garcia-Sanchez, and B. Van Waeyenberge, The design and verification of MuMax3, AIP Adv. 4, 107133 (2014).
- [37] T. Devolder, J. V. Kim, L. Nistor, R. Sousa, B. Rodmacq, and B. Diény, Exchange stiffness in ultrathin perpendicularly magnetized CoFeB layers determined using the spectroscopy of electrically excited spin waves, J. Appl. Phys. **120**, 183902 (2016).

- [38] K.-W. Moon, C. Kim, J. Yoon, J. W. Choi, D.-O. Kim, K. M. Song, D. Kim, B. S. Chun, and C. Hwang, A spin torque meter with magnetic facet domains, Nat. Commun. 9, 3788 (2018).
- [39] N. L. Schryer and L. R. Walker, The motion of 180° domain walls in uniform dc magnetic fields, J. Appl. Phys. 45, 5406 (1974).
- [40] S. M. Giani, Micromagnetic study of magnetic domain wall motion: Thermal effects and spin torques, Ph.D. thesis, Universidad de Salamanca, 2017.
- [41] S. Fukami, M. Yamanouchi, S. Ikeda, and H. Ohno, Depinning probability of a magnetic domain wall in nanowires by spinpolarized currents, Nat. Commun. 4, 2293 (2013).
- [42] M. Hayashi, L. Thomas, C. Rettner, R. Moriya, and S. S. P. Parkin, Dynamics of domain wall depinning driven by a combination of direct and pulsed currents, Appl. Phys. Lett. 92, 162503 (2008).
- [43] K. Yue, Y. Liu, R. K. Lake, and A. C. Parker, A brain-plausible neuromorphic on-the-fly learning system implemented with magnetic domain wall analog memristors, Sci. Adv. 5, eaau8170 (2019).
- [44] T. Blachowicz and A. Ehrmann, Magnetic elements for neuromorphic computing, Molecules 25, 2550 (2020).

- [45] D. Marković, A. Mizrahi, D. Querlioz, and J. Grollier, Physics for neuromorphic computing, Nat. Rev. Phys. 2, 499 (2020).
- [46] M. Toda, On the theory of the brownian motion, J. Phys. Soc. Jpn. 13, 1266 (1958).
- [47] P. Diaconis, S. Holmes, and R. Montgomery, Dynamical bias in the coin toss, SIAM Rev. 49, 211 (2007).
- [48] S. Li, Q. Xue, H. Du, J. Xu, Q. Li, Z. Shi, X. Gao, M. Liu, T. Nan, Z. Hu, N. X. Sun, and W. Shao, Large E-field tunability of magnetic anisotropy and ferromagnetic resonance frequency of co-sputtered Fe<sub>50</sub> Co<sub>50</sub>-B film, J. Appl. Phys. **117**, 17D702 (2015).
- [49] W. Lin, N. Vernier, G. Agnus, K. Garcia, B. Ocker, W. Zhao, E. E. Fullerton, and D. Ravelosona, Universal domain wall dynamics under electric field in Ta/CoFeB/MgO devices with perpendicular anisotropy, Nat. Commun. 7, 13532 (2016).
- [50] https://doi.org/10.5518/1474.

*Correction:* An editorial processing error caused the images for Figures 3, 4, 5, and 6 to appear with the incorrect captions. The figures now appear in the correct locations.