

Transverse spin freezing in ruthenium-doped a -Fe₉₀Zr₁₀

D. H. Ryan

*Physics Department and Centre for the Physics of Materials, McGill University, 3600 University Street,
Montreal, Quebec, Canada H3A 2T8*

J. M. Cadogan

School of Physics, The University of New South Wales, Sydney NSW 2052, Australia

J. van Lierop

*Physics Department and Centre for the Physics of Materials, McGill University, 3600 University Street,
Montreal, Quebec, Canada H3A 2T8*

(Received 2 May 2000)

Muon spin relaxation (μ SR) has been used to study the ferromagnet to spin glass crossover in a -Fe_{90-x}Ru_xZr₁₀. We find clear evidence of two magnetic transitions in both the dynamic and static behavior of the muon polarization decay: a ferromagnetic phase transition at T_c , followed by transverse spin freezing at T_{xy} . Comparison with earlier Mössbauer data shows that the break in $B_{\text{hf}}(T)$ is indeed due to transverse spin freezing, and that both Mössbauer spectroscopy and μ SR yield the same values for T_{xy} .

I. INTRODUCTION

Of all transition metals (TM) surveyed, ruthenium leads to the most rapid destruction of ferromagnetic order in a -Fe_{90-x}TM_xZr₁₀ alloys.¹ Ruthenium is nonmagnetic, and forms a stable ternary a -Fe-Ru-Zr glass over a very wide composition range;² it therefore provides an ideal system in which to study the ferromagnet (FM) to spin glass (SG) crossover. Mössbauer³ and neutron depolarisation⁴ measurements have shown that there is a complete loss of long-range FM order by a critical doping level of $x_c \sim 2.5$. Since the loss of order in the binary a -Fe-Zr system is due to the development of exchange frustration,⁵ we would expect the same mechanism to be active in the Ru-doped system and therefore transverse spin freezing should occur below T_c in those alloys that are close to the FM-SG crossover.⁶

The defining characteristic of transverse spin freezing is the appearance of SG order at a well defined temperature (T_{xy}), and in the plane perpendicular to the axis defined by the existing FM order. The SG order is in addition to, and coexists with, the FM order throughout the material. The local moment increases, but the system becomes non-collinear and so the magnetization is unaffected. This behavior is most easily observed using Mössbauer spectroscopy in an applied field of several tesla where spin components are seen to develop perpendicular to the applied field on cooling through T_{xy} .⁵ An alternative signature has been provided by numerical simulations,⁷ which showed that although the freezing of transverse spin components does not represent a phase transition, it should be accompanied by significant, but noncritical, magnetic fluctuations. This prediction was recently confirmed by μ SR measurements on binary a -Fe_xZr_{100-x} alloys where the dynamic signature of transverse spin freezing was clearly observed and shown to coincide with an increase in the static order.⁸ The systematic deviation between the applied field Mössbauer values for T_{xy} and those derived from zero-field μ SR indicates that the sys-

tem is severely perturbed by an applied field and emphasises the need to use zero-field methods to follow the ordering at T_{xy} .

Doping a -Fe₉₀Zr₁₀ with ruthenium leads to a rapid reduction in T_c and magnetization while the local Fe moment is largely unaffected.^{1,4} Behavior that suggests increasing frustration. However, only indirect evidence has been presented for transverse spin freezing in a -Fe_{90-x}Ru_xZr₁₀. The temperature dependence of the average hyperfine field (B_{hf}) shows a break in slope well below T_c , at a temperature labeled T_{br} . The composition dependence of T_{br} is consistent with the expected behavior of T_{xy} .⁴ Such a break in slope could be associated with the increase in local moment that occurs when the transverse spin components order; however we observed no such break in the binary a -Fe-Zr system.⁵ By contrast, the a -(Fe_{1-x}Mn_x)₇₈Sn₂Si₆B₁₄ system exhibits a striking break in slope at T_{xy} .⁹

In order to confirm that transverse spin freezing does indeed occur, and to compare the static and dynamic behavior in this system with that observed in the binary a -Fe-Zr system, we have made μ SR measurements through the FM-SG crossover region in a -Fe_{90-x}Ru_xZr₁₀. We show that the dynamic and static signatures of transverse spin freezing are present, and coincide in temperature. The results are also compared with zero field Mössbauer data and confirm that the break in $B_{\text{hf}}(T)$ is associated with transverse spin freezing.

II. EXPERIMENTAL METHODS

Ribbons of a -Fe_{90-x}Ru_xZr₁₀ were prepared by arc-melting followed by melt-spinning.⁴ Cu $K\alpha$ x-ray diffraction and room temperature ⁵⁷Fe Mössbauer spectra were used to confirm the absence of crystalline contamination. Basic magnetic characterization was carried out on a commercial susceptometer/magnetometer. Sample compositions were checked by electron microprobe analysis and some loss of

ruthenium (typically 0.1–0.4 at. %) was noted. All compositions quoted here are actual, rather than nominal values.

Mössbauer measurements were obtained on a constant-acceleration spectrometer using a 1 GBq $^{57}\text{CoRh}$ source. Temperatures between 12 K and room temperature were achieved using a vibration-isolated closed-cycle refrigerator. Spectra were fitted using Window's method.¹⁰

Zero-field μSR measurements were made on the M20 beamline at TRIUMF. Sample temperature was controlled between 5 K and 300 K in a He-flow cryostat.¹¹ Field zero was set to better than 0.1 mT using a Hall probe and confirmed using the μ^+ precession signal in a pure silver blank. Samples were 170–200 mg cm^{-2} thick over a 16 mm diameter active area. Histograms containing $(1-4)\times 10^7$ events were acquired with a timing resolution of 0.8 ns.

As before,⁸ data above T_c were fitted using a stretched exponential,

$$A_d = A_o \exp(-(\lambda t)^\beta),$$

while below T_c the presence of static order required the inclusion of a Kubo-Toyabe (KT) function¹²

$$G_z^G(\Delta, t) = \frac{1}{3} + \frac{2}{3}(1 - (\Delta t)^\alpha) \exp\left(-\frac{(\Delta t)^\alpha}{\alpha}\right)$$

and the data were fitted as the product,

$$A = A_d G_z^G,$$

a procedure that is valid as long as $f_L \gg \lambda$.¹³

III. RESULTS AND DISCUSSION

Typical μSR patterns for $a\text{-Fe}_{89.2}\text{Ru}_{0.8}\text{Zr}_{10}$ are shown in Fig. 1 at 220 K (above T_c), 180 K (below T_c but above T_{xy}) and 45 K (below T_{xy}). Above T_c there is no static order, but magnetic fluctuations couple to the muon spin and cause an exponential decay in the observed polarization. The inset shows that the exponential continues to the earliest time measured (~ 1.5 ns), and no static contribution is apparent. Below T_c , fluctuations (e.g. magnons) continue to depolarize the muons, but the characteristic KT minimum is observed at early times (inset), indicating the presence of static magnetic order. Finally, below T_{xy} , fluctuations are still present and the KT minimum due to static order has moved to still earlier time, indicating an increase in the local field at the muon sites. The static relaxation rate at 45 K is 260 MHz, however it is clear from the inset to Fig. 1, that our resolution is more than adequate to provide reliable values at far greater relaxation rates. Figure 1 also serves to demonstrate a major advantage of the zero-field μSR technique: static and dynamic effects can both be studied in a single measurement, but their signatures in the data are completely independent, and therefore do not interfere. The static contributions in Fig. 1 are complete by 40 ns, whereas the dynamic exponential decay extends across the remaining 4 μs .

Values for static relaxation rates in the samples studied here are shown in Fig. 2. The most immediate observation is that as the ruthenium content, x , is increased, the temperature at which static magnetic order develops moves down rapidly. A second feature is apparent below T_c in most of the curves: there is a distinct break in the temperature dependence for




FIG. 1. Typical μSR patterns for $a\text{-Fe}_{89.2}\text{Ru}_{0.8}\text{Zr}_{10}$ at 220 K (above T_c), 180 K (below T_c but above T_{xy}), and 45 K (below T_{xy}). Insets show the early time region of the data where, for $T < T_c$, the static KT minimum is observed. Solid lines are fits to functions described in the text.

$x \leq 2.0$. $\Delta(T)$ was fitted using the sum of two Brillouin functions (modified to allow for a distribution of exchange¹⁴) each with different onset temperatures and saturation values. These fits are shown as solid lines in Fig. 2. This behavior is consistent with transverse spin freezing, and matches that seen previously in $a\text{-Fe-Zr}$.⁸

Localizing a break in slope is not always easy, nor does it provide a convincing demonstration that a significant change in magnetic order has occurred. The behavior of the dynamic relaxation rate, also shown in Fig. 2, is far clearer. Above T_c , the muons are depolarized by dynamic fluctuations in the local magnetization. These fluctuations diverge at T_c . We found that a simple Curie-Weiss function [$\lambda \propto (T - T_c)^{-1}$] gave a good description of $\lambda(T)$ as we approached T_c from above. This served to locate T_c , however no attempt was made to determine the critical exponent, nor were the data adequate for such an analysis. Below T_c magnon-muon interactions serve to depolarize the muons. As the temperature is lowered, these freeze out and λ should fall to zero.




FIG. 2. Temperature dependence of the static (Δ) and dynamic (λ) relaxation rates in $a\text{-Fe}_{90-x}\text{Ru}_x\text{Zr}_{10}$ showing the steady reduction in ordering temperature with increasing ruthenium content, and the effects of transverse spin freezing for $x \leq 2.75$. Solid lines are fits described in the text. Note, by $x=4$, $\Delta(T)$, and $\lambda(T)$ show only a single ordering event.

This was observed in $a\text{-Fe}_{89}\text{Zr}_{11}$,⁸ which does not exhibit transverse spin freezing, and was only seen here for $x > 3$ where we are fully in the spin glass regime and transverse spin freezing is also absent. For the other samples, the steady decline in $\lambda(T)$ is interrupted by a broad peak (right-hand side of Fig. 2). This peak was most easily fitted as a Gaussian with a width of $\sim 20\text{--}25$ K. This peak clearly reflects a substantial increase in the fluctuation rate [at least two orders of magnitude above the background in the equivalent region in $a\text{-Fe}_{89}\text{Zr}_{11}$ (Ref. 8)], however it is equally clearly not divergent. This observation is in striking agreement with the predictions of numerical simulation work,⁷ where T_{xy} was shown to be associated with a *noncritical* peak in the fluctuation rate.

Transition temperatures are summarized in the phase diagram shown as Fig. 3. The basic pattern is exactly that expected for a partially frustrated magnetic system exhibiting transverse spin freezing.^{5-7,15} T_c falls, and T_{xy} rises to meet it as the frustration level (in this case controlled by the ruthenium content) is increased. One key result is the close agreement between the transition temperatures derived from the static and dynamic effects in the μSR signal. Both T_c and T_{xy} are clearly associated with fluctuations and with a




FIG. 3. Magnetic phase diagram for $a\text{-Fe}_{90-x}\text{Ru}_x\text{Zr}_{10}$ showing transition temperatures derived from static and dynamic μSR data and χ_{ac} measurements. T_c and T_{xy} obtained on an independently prepared series of alloys using zero-field Mössbauer spectroscopy are also shown. All compositions derived from electron microprobe analysis.

marked change in the local, static order. There is no evidence for further transitions below T_{xy} . There is however, one interesting difference between the theoretical predictions and the phase diagram presented in Fig. 3. $T_c(x)$ and $T_{xy}(x)$ are




FIG. 4. Comparison of Mössbauer hyperfine fields (B_{hf}) and static relaxation rates (Δ) for Top: $x=1.0$ (B_{hf}) and $x=0.8$ (Δ); bottom: $x=1.6$ (B_{hf}) and $x=1.7$ (Δ). Each data set has been normalized to its value extrapolated to $T=0$ K.

usually shown as having a constant slope until they meet, then the spin glass transition $T_{sg}(x)$ continues horizontally.^{5-7,15} Here we see that $T_{xy}(x)$ levels off and $T_c(x)$ drops abruptly by nearly a factor of 2 in the last 0.5 at. % to join it. This observation indicates that the region close to the FM-SG crossover would bear closer theoretical investigation.

Since the static rate (Δ) and B_{hf} both exhibit a break in slope, and both reflect local static order, it is of interest to compare their behavior. Figure 4 shows the temperature dependences of Δ and B_{hf} for $x \sim 1.0$ and ~ 1.6 , with each data set normalized to its value extrapolated to $T=0$ K. In each case the two measurements track reasonably closely, but the behavior of $B_{hf}(T)$ is generally smoother, with a less well-defined break at T_{xy} . Despite the operational simplicity of the Mössbauer measurements, it is clear that μ SR provides clearer insight into the static behavior, and in addition dynamics can be probed independently.

The solid symbols in Fig. 3 summarize the results of zero-field Mössbauer measurements of T_c and T_{br} .⁴ The consistency between T_{br} from $B_{hf}(T)$, and T_{xy} from $\Delta(T)$ and $\lambda(T)$, confirms that the break in slope in the Mössbauer data is indeed due to transverse spin freezing. Furthermore, the agreement here is far better and more consistent than that found when T_{xy} values from μ SR and applied field Mössbauer data were compared for a -Fe_xZr_{100-x}.⁸ There, a substantial deviation was observed, and the gap grew as the crossover region was approached. These two data sets taken together strongly suggest that the transverse spin freezing transition is suppressed by an external applied field, and

serve to emphasize the need to use zero-field techniques in its determination.

IV. CONCLUSIONS

μ SR provides clear evidence of two, and only two, magnetic transitions in a -Fe_{90-x}Ru_xZr₁₀. The two transitions are observed in both the dynamic and static behavior of the muon polarization decay. The results are in perfect agreement with the description of the ordering in terms of a FM phase transition followed by transverse spin freezing. We have confirmed the presence of a noncritical peak in the fluctuations at T_{xy} predicted by numerical simulations. The decline in T_c on approaching x_c is more rapid than simple models predict, and suggests that the collapse of long-ranged order may be more abrupt than previously expected. Comparison with earlier Mössbauer data shows that the break in $B_{hf}(T)$ is due to transverse spin freezing, and the consistent agreement between these two zero-field measurements, in contrast with those made in an applied field, suggests that transverse spin freezing is significantly suppressed by an external field.

ACKNOWLEDGMENTS

The authors would like to acknowledge assistance from the TRIUMF muon group during the acquisition of these data. This work was supported by grants from the Natural Sciences and Engineering Research Council of Canada, Fonds pour la formation de chercheurs et l'aide à la recherche, Québec, the Australian Research Council, and the Australian Nuclear Science and Technology Organization.

¹D.H. Ryan and J.M. Cadogan, *J. Magn. Magn. Mater.* **213**, 111 (2000).

²V. Nagarajan, P.L. Paulose, and R. Vijayaraghavan, *J. Phys. Colloq.* **49**, C8-1135 (1988); P.L. Paulose, V. Nagarajan, R. Krishnan, J. Voiron, H. Lassri, R. Nagarajan, and R. Vijayaraghavan, *J. Magn. Magn. Mater.* **140-44**, 301 (1995).

³D.H. Ryan, J.M. Cadogan, and Zin Tun, *J. Appl. Phys.* **81**, 4407 (1997).

⁴D.H. Ryan, Zin Tun, and J.M. Cadogan, *J. Magn. Magn. Mater.* **177-81**, 57 (1998).

⁵H. Ren and D.H. Ryan, *Phys. Rev. B* **51**, 15 885 (1995).

⁶D.H. Ryan, in *Recent Progress in Random Magnets*, edited by D.H. Ryan (World Scientific, Singapore, 1992), pp. 1-40.

⁷J.R. Thomson, Hong Guo, D.H. Ryan, M.J. Zuckermann, and M. Grant, *Phys. Rev. B* **45**, 3129 (1992).

⁸D.H. Ryan, J.M. Cadogan, and J. van Lierop, *Phys. Rev. B* **61**, 6816 (2000).

⁹A. Kuprin, D. Wiarda, and D.H. Ryan, *Phys. Rev. B* **61**, 1267 (2000).

¹⁰B. Window, *J. Phys. E* **4**, 401 (1971).

¹¹We confirmed that the silver used gave no time-dependent μ SR signal down to 5 K.

¹²R. Kubo, *Hyperfine Interact.* **8**, 731 (1981); R. Kubo and T. Toyabe, in *Magnetic Resonance and Relaxation*, edited by R. Blinc (North-Holland, Amsterdam, 1967), p. 810.

¹³R.S. Hayano, Y.J. Uemura, J. Imazato, N. Nishida, T. Yamazaki, and R. Kubo, *Phys. Rev. B* **20**, 850 (1979).

¹⁴K. Handrich, *Phys. Status Solidi* **32**, K55 (1969).

¹⁵M. Gabay and G. Toulouse, *Phys. Rev. Lett.* **47**, 201 (1981).