

***Ab initio* calculation of resonant x-ray scattering in manganites**Patrizia Benedetti,¹ Jeroen van den Brink,^{2,3} Eva Pavarini,^{2,4} Assunta Vigliante,¹ and Peter Wochner¹¹Max-Planck-Institut für Metallforschung, Heisenbergstrasse 1, D-70569 Stuttgart, Germany²Max-Planck-Institut für Festkörperforschung, Heisenbergstrasse 1, D-70569 Stuttgart, Germany³Faculty of Applied Physics and MESA⁺ Institute, University of Twente, Box 217, 7500 AE Enschede, The Netherlands⁴INFN, Dipartimento di Fisica A. Volta, Via Bassi 6, I-27100 Pavia, Italy

(Received 8 September 2000; published 22 January 2001)

We study the origin of the resonant x-ray signal in manganites and generalize the resonant cross section to the band-structure framework. With *ab initio* LSDA and LSDA+*U* calculations we determine the resonant x-ray spectrum of LaMnO₃. The calculated spectrum and azimuthal angle dependence at the Mn *K* edge reproduce the measured data without adjustable parameters. The intensity of this signal is directly related to the orthorhombicity of the lattice. We also predict a resonant x-ray signal at the La *L* edge, caused by the tilting of the MnO₆ octahedra. This shows that the resonant x-ray signal in the hard x-ray regime can be understood in terms of the band structure of a material and is sensitive to the fine details of crystal structure.

DOI: 10.1103/PhysRevB.63.060408

PACS number(s): 75.30.Vn, 61.10.Dp, 71.15.Ap, 78.70.Ck

In strongly correlated 3*d* transition-metal oxides (TMO's) orbital degeneracy and orbital order have a large effect on magnetic, structural, and electronic properties. The discovery of a Colossal Magneto-Resistance in perovskite manganites¹ has intensified experimental and theoretical efforts to understand and quantify the repercussions of orbital degeneracy on the physical properties of TMO's. An orbitally degenerate ground state is unstable and different mechanisms have been proposed for the lifting of the orbital degeneracy of the 3*d* electrons. One possible mechanism was implicitly provided by Goodenough and Kanamori,² who realized that superexchange interactions, which are due to the strong Coulomb interactions between electrons, depend on the orbitals the spins actually occupy. This implies that magnetic and orbital order are directly related to each other, and ordering of the orbitals, induced by the magnetic exchange, can lift the orbital degeneracy.³ On the other hand the lifting of the orbital degeneracy can also be induced by lattice distortions: this is the well-known Jahn-Teller effect.⁴ In order to infer the actual orbital order in TMO's one can therefore make use of indirect information coming from the magnetic and (Jahn-Teller distorted) crystal structure. For instance in vanadates [V₂O₃ (Ref. 5) and LiVO₂ (Ref. 6)], cuprates (KCuF₃)³ and manganites (LaMnO₃)^{7,2} the orbital order can be traced in this way. The orbital structure is very important as it strongly affects the low-energy and low-temperature behavior of these systems. The description of the metal-insulator transition in V₂O₃ in terms of a spin 1/2 Hubbard model,⁸ the magnon dispersion in (doped) manganites⁹ and charge-order in half-doped manganites¹⁰ are all related to the underlying orbital structure of the material.

X-ray techniques, which could in principle serve as an independent direct probe of the orbital order of the *d* electrons, are under normal conditions not very sensitive to the distribution of valence electrons. Nevertheless, it was recently demonstrated on perovskite manganites that the use of hard x-rays corresponding to the Mn *K* edge, greatly enhances the sensitivity to the valence electron distribution and is related to the orbital order.¹¹ This type of experiment is now widely used to probe orbital and charge order in various

TMO's.¹² The question is, however, where the sensitivity to the valence electrons comes from. Essentially three models have been proposed. Fabrizio *et al.*¹³ suggest that for the manganites an 1*s* electron, excited at the *K*-edge resonance, makes an optically forbidden quadrupole transition into the 3*d* valence band and directly probes the empty and occupied Mn *e_g* orbitals. Ishihara *et al.*¹⁴ argue that the transition is of dipolar character, into the Mn 4*p* states. The sensitivity to the 3*d* states is then caused by the Coulomb repulsion between a 4*p* and 3*d* electron, which depends on the symmetry of the orbital that is occupied. Finally, Elfmov *et al.*¹⁵ suggest that the transition is dipolar, but that the signal is mainly due to the inequivalence of the 4*p* bands due to the Jahn-Teller distortion and therefore not directly sensitive to the Mn 3*d* states.

The aim of this paper is to clarify which physical effects contribute to the resonant x-ray scattering (RXS) signal in manganites. In order to do this, it is necessary to make firm theoretical predictions for the RXS signal within a chosen model on a specific compound. We adopt the model of Elfmov *et al.* and generalize the resonant cross section to the band-structure picture. By means of *ab initio* LSDA and LSDA+*U* calculations for LaMnO₃ we determine the RXS spectrum and show that the calculated spectrum at the Mn-edge agrees in detail with experiment and reproduces the measured data without adjustable parameters. This implies that the Jahn-Teller distortion is the main cause of the RXS signal. Via a tight-binding description of the bandstructure, we show that the intensity of the RXS signal is directly related to the orthorhombicity of the lattice. We also predict a resonant signal at the La *L* edge, which was recently observed in experiment.¹⁶ The presence of a signal on the La edge is a consequence of the tilting of the MnO₆ octahedra and, to a lesser extent, of the Jahn-Teller distortion of the MnO₆ octahedra in the crystal and is independent of the electronic configuration of the Mn 3*d* levels. This shows that the RXS signal is sensitive to the fine details of the crystal structure of a material.

LaMnO₃ is a prototypical orbital ordered compound. The Mn³⁺ ion is in a high spin *d*⁴ configuration, where three




FIG. 1. Schematic representation of the crystal distortions of LaMnO_3 . Manganese atoms are denoted by the small filled circles, the oxygen by the large open circles and the lanthanum by the hatched circles. Left: projection on the ac plane of the tilted octahedra. Right: projection on the ab plane of the Jahn-Teller distorted octahedra with the occupied $3x^2-r^2$ and $3y^2-r^2$ orbitals.

electrons are in the t_{2g} and one electron in the e_g orbitals. The orthorhombic $Pbnm$ crystal structure can be considered as a cubic perovskite with two types of distortions: first a tilting of the MnO_6 octahedra, so that the Mn-O-Mn angles become less than 180° , and second a cooperative Jahn-Teller distortion (shortening of four Mn-O bonds and elongation of the other two, see Fig. 1). The twofold degeneracy of the e_g orbital, occupied by one electron, is lifted by the Jahn-Teller distortion. Due to these distortions two neighboring Mn atoms are inequivalent: on one Mn-site mainly the $3x^2-r^2$ orbital is occupied, while on the neighboring site the occupied orbital has mainly $3y^2-r^2$ character. We show below that the inequivalence of the local environment of neighboring Mn atoms (and also of the La atoms) gives rise to a large signal in a RXS experiment. In order to calculate the RXS signal from first principles, we first present the formulas for the RXS cross section, that we use later on to obtain the resonant spectra and azimuthal angle dependencies from the local-density calculations. We adopt the notation introduced by Ishihara and Maekawa¹⁴ and define the structure factor

$$F_{i,\alpha\beta}^{\mathbf{k}-\mathbf{k}'} = e^{i(\mathbf{k}-\mathbf{k}')\cdot\mathbf{R}_i} \sum_{b,\mathbf{q}} \frac{\langle 0|P_{i,\alpha}|\psi_{\mathbf{q}}^b\rangle\langle\psi_{\mathbf{q}}^b|P_{i,\beta}|0\rangle}{\omega - E_{\mathbf{q}}^b + E_0 + i\eta}, \quad (1)$$

where \mathbf{k} (\mathbf{k}') is the incident (outgoing) momentum of the light, $P_{i,\alpha}$ is the dipole operator with polarization $\alpha, \beta = x, y, z$ on site i with lattice vector \mathbf{R}_i , $|0\rangle$ (E_0) is the groundstate wave function (energy), $|\psi_{\mathbf{q}}^b\rangle$ an excited state with momentum \mathbf{q} , energy $E_{\mathbf{q}}^b$ and band index b . To be specific we consider the (3,0,0) reflection for the undoped manganite LaMnO_3 in the experimental setup¹¹ at the Mn K edge and assume that the incoming light is fully σ polarized. At the K edge the relevant dipole operator is

$$P_{i,\alpha} = p_{i,\alpha}^\dagger s_i + s_i^\dagger p_{i,\alpha}, \quad (2)$$

where s_i creates a $1s$ core hole on the Mn and $p_{i,\alpha}^\dagger$ creates an electron in the Mn $4p$ shell with $\alpha = x, y, z$ symmetry. A detailed derivation of the cross-section in the $\sigma \rightarrow \pi$ channel, where the polarization state of the photon is rotated by $\pi/2$ on scattering, shows that the intensity is given by

$$I_{\sigma \rightarrow \pi} = \text{const} |A_{21}(\phi) \sin \theta - A_{31}(\phi) \cos \theta|^2, \quad (3)$$

where θ is the scattering angle, which is fixed in experiment at approximately $\pi/6$, and ϕ the azimuthal angle which describes the rotation around the scattering vector,

$$A_{21}(\phi) = \cos^2 \phi (F_{xz} + F_{yz}) - \sin^2 \phi (F_{zx} + F_{zy}) - \sin \phi \cos \phi (F_{xx} + F_{yy} + F_{xy} + F_{yx} - 2F_{zz}) / \sqrt{2}, \quad (4)$$

and

$$A_{31}(\phi) = \cos \phi (F_{xz} - F_{yz}) - \sin \phi (F_{xx} - F_{yy} + F_{xy} - F_{yx}) / \sqrt{2}. \quad (5)$$

In LaMnO_3 the orbital ordered state consists of two Mn sublattices, where on sublattice A (B) presumably mostly the $3x^2-r^2$ ($3y^2-r^2$) orbital is occupied, see Fig. 1. The RXS cross section is exactly sensitive to the difference between the two sublattices, as

$$F_{\alpha\beta} = \sum_{i \in A} F_{i,\alpha\beta}^0 - \sum_{i \in B} F_{i,\alpha\beta}^0. \quad (6)$$

From this expression it is easy to deduce the physical interpretation of RXS cross section in the band picture. F_{xx} , for instance, is simply proportional to the difference of the Mn $4p_x$ projected density of states (DOS) on sublattice A and the Mn $4p_x$ projected DOS on sublattice B . The RXS intensity is proportional to the square of this difference. Note that off-diagonal elements of the structure factor tensor are nonzero due to the tilting of the octahedra.

The electronic structure is calculated with the LMTO ASA LSDA method¹⁸ and with the LSDA+ U method,¹⁹ that incorporates a mean-field treatment of the strong correlations of the e_g electrons. All the *ab-initio* calculations are based on the Stuttgart TBLMTO47 code. We perform the calculations on a set of different (virtual) crystal structures for LaMnO_3 . First of all the RXS signal is calculated for the real lattice structure, including the tilting (T) and Jahn-Teller (JT) distortion, both with and without the on-site Coulomb interaction U . In order to study the effect of tilting and Jahn-Teller distortion separately, we do the same calculations for LaMnO_3 in the not Jahn-Teller distorted (but tilted) $\text{Pr}_{1/2}\text{Sr}_{1/2}\text{MnO}_3$ structure and for a virtual crystal structure that is Jahn-Teller distorted, but not tilted. We first present the results for the Mn K -edge in Fig. 2, calculated with Eqs. (1)–(6), where the core hole potential is neglected, and the core-hole lifetime leads to a broadening of the signal with a half width at half maximum of 1.2 eV.¹⁵ In LSDA+ U calculations we use $U = 8$ eV.²⁰ The spectrum for the full calculation (JT+T+ U) shows that at 10 eV above the absorption edge there is a strong satellite (experimentally 12 eV)^{11,21} and weak satellites 23 and 27 eV above the edge, that are also found experimentally at the same energies.²¹ The calculation for the JT+T system ($U=0$) agrees with the result of Takahashi *et al.*²² and is very similar to the JT+T+ U result, with a slight shift of spectral weight from the main peak to the satellite. Electron correlations, that are responsible for the orbital dependent superexchange and a possible driving force for orbital order,³ therefore make a neg-




FIG. 2. Resonant x-ray scattering intensity at the Mn edge from LSDA(+ U) calculations for different crystal structures. JT+T: experimental Jahn-Teller distorted and tilted $Pbnm$ crystal structure of LaMnO_3 , JT (T): virtual crystal structure with only the Jahn-Teller distortion (tilting of the MnO_6 octahedra). The Fermi-level is chosen as the zero of energy. Inset: azimuthal angle dependence of the main edge from the JT+T+ U calculation normalized to the maximum intensity.

ligible contribution to the RXS intensity at the Mn K edge, as is suggested by Elfimov *et al.*¹⁵ and in agreement with multiple scattering cluster calculations.¹⁷ The azimuthal angle dependence at the main peak shows that the signal follows closely a $\sin^2\phi$ behavior, in accordance with experiment,¹¹ with a phase factor that is slightly shifted by 0.059π . This indicates that the main contribution is due to the term $F_{xx} - F_{yy}$ in Eq. (5), which comes from the difference in p_x (p_y) projected density of states on the two sublattices and is obviously connected to the JT distortion. This assignment is supported by the calculation for the system without Jahn-Teller distortion shown in Fig. 2. In the T+ U system the signal is broad, featureless, an order of magnitude weaker and almost entirely due to the tilting. From the calculation for the JT+ U system we conclude that the tilting of the octahedra is responsible for the observed satellites, but has only a moderate effect on the total intensity of the RXS signal at the Mn K edge. An interesting question is how the RXS signal actually depends on the strength of the Jahn-Teller distortion. From the LSDA calculation we obtain the parameters for a tight-binding (TB) description of the electronic structure for a lattice without tilting and JT distortion, in accordance with previously published results.²³ The RXS intensity for the undistorted lattice and $U=0$ is of course vanishing because all neighboring Mn atoms are equivalent. A JT distortion modifies the TB parameters, whose distance dependence is given by Harrison²⁴ and allows the resonant scattering at (3,0,0). In Fig. 3 the total RXS intensity is shown as a function of the orthorhombicity. The JT distortion gives rise to a long (l) and short (s) manganese-oxygen bondlength in the ab plane and we define the orthorhombicity as $\delta=(l-s)/(l+s)$ so that for the cubic perovskite $\delta=0$. The experimental value for the orthorhombicity at low




FIG. 3. Total resonant x-ray intensity as a function of the Jahn-Teller distortion strength calculated within a tight-binding framework, normalized to the total intensity at the experimental value for the orthorhombicity (defined in the text) $\delta=0.130$ (dashed line).

temperature is $\delta=0.130$.⁹ The resonant intensity smoothly depends on δ and is approximately proportional to $\delta^{3/2}$. This supports the suggestion that the temperature dependence of the RXS is closely related to the temperature dependence of the lattice parameters.²¹ Finally we present the results for the RXS signal at the La L edge. Figure 1 shows that due to the lattice distortions also neighboring La atoms have locally different surroundings. We calculate the RXS intensity for the (3,0,0) reflection in the $\sigma \rightarrow \pi$ channel, for different (virtual) lattice structures, as we did for the Mn edge. We find a signal at the La edge, shown in Fig. 4, that is mainly due to the tilting. From the JT+ U calculation we see that the combined contribution of the other two symmetry breaking effects is small. For the crystal structure that only has the tilting distortion we find a signal that is comparable to the JT+T+ U calculation both in intensity and shape. This result is not unexpected as the tilting of the MnO_6 octahedra modifies the local environment of La atoms: the apical oxygen atoms are displaced towards the La atoms on one sublattice and away from them on the other sublattice so that neighboring lanthanum atoms have inequivalent oxygen surroundings.

We determined, in conclusion, with *ab initio* LSDA and LSDA+ U calculations the resonant x-ray spectrum (RXS) of LaMnO_3 . The calculated spectrum and azimuthal angle




FIG. 4. Resonant x-ray scattering intensity at the La edge from LSDA(+ U) calculations for different crystal structures. JT+T: experimental Jahn-Teller distorted and tilted crystal structure, T: crystal structure with only the tilting of the MnO_6 octahedra.

dependence at the Mn edge reproduce the measured data without adjustable parameters. Spectra for different (virtual) crystal structures show that the RXS intensity at the Mn *K* edge is mainly due to the Jahn-Teller distortion¹⁵ and that the tilting of the MnO₆ octahedra causes the strong satellite structure in the spectrum. We find that the intensity of the resonant x-ray signal at the Mn edge is directly related to the orthorhombicity of the lattice. We also predict a RXS signal at the La *L* edge, which is a consequence of the tilting of the MnO₆ octahedra in the crystal. This shows that the resonant

signal at different edges in the hard x-ray regime can be understood and predicted by calculations in the band-structure framework and is sensitive to the fine details of lattice distortions, but does not *directly* probe the orbital order of the 3*d* states. Orbital order, of large enough periodicity to satisfy Bragg conditions, might however be visible in resonant experiments with soft x-rays, where direct transitions into the 3*d* states are allowed.

We thank I. Elfimov, G. Sawatzky, and P. J. Kelly for useful discussions.

-
- ¹R. von Helmolt *et al.*, Phys. Rev. Lett. **71**, 2331 (1993); S. Jin *et al.*, Science **264**, 413 (1994).
- ²J.B. Goodenough, *Magnetism and Chemical Bond* (Interscience, New York, 1963).
- ³K.I. Kugel and D.I. Khomskii, Zh. Éksp. Teor. Fiz. **64**, 1429 (1973) [Sov. Phys. JETP **37**, 725 (1973); Usp. Fiz. Nauk **136**, 621 (1982) [Sov. Phys. Usp. **25**, 231 (1982), and references therein].
- ⁴H.A. Jahn and E. Teller, Proc. R. Soc. London, Ser. A **161**, 220 (1937).
- ⁵C. Castellani, C.R. Natoli, and J. Ranninger, Phys. Rev. B **18**, 4945 (1978).
- ⁶H.F. Pen *et al.*, Phys. Rev. Lett. **78**, 1323 (1997).
- ⁷Z. Jirac *et al.*, J. Magn. Magn. Mater. **53**, 153 (1985).
- ⁸D.B. MacWhan, T.M. Rice, and J.P. Remeika, Phys. Rev. Lett. **23**, 1384 (1969); S.Y. Ezhov *et al.*, *ibid.* **83**, 4136 (1999).
- ⁹F. Moussa *et al.*, Phys. Rev. B **54**, 15 149 (1996); R. Kilian and G. Khaliullin, *ibid.* **61**, 3494 (2000).
- ¹⁰J. van den Brink and D. Khomskii, Phys. Rev. Lett. **82**, 1016 (1999); I.V. Solovyev and K. Terakura, *ibid.* **83**, 2825 (1999); J. van den Brink, G. Khaliullin, and D. Khomskii, *ibid.* **83**, 5118 (1999).
- ¹¹Y. Murakami *et al.*, Phys. Rev. Lett. **80**, 1932 (1998); Y. Murakami *et al.*, *ibid.* **81**, 582 (1998).
- ¹²M.v. Zimmermann *et al.*, Phys. Rev. Lett. **83**, 4872 (1999); Y. Endoh *et al.*, *ibid.* **82**, 4328 (1999); L. Paolasini *et al.*, *ibid.* **82**, 4719 (1999); A. Stunault *et al.*, Phys. Rev. B **60**, 10 170 (1999); K. Nakamura *et al.*, *ibid.* **60**, 2425 (1999).
- ¹³M. Fabrizio, M. Altarelli, and M. Benfatto, Phys. Rev. Lett. **80**, 3400 (1998).
- ¹⁴S. Ishihara and S. Maekawa, Phys. Rev. Lett. **80**, 3799 (1998); S. Ishihara and S. Maekawa, Phys. Rev. B **58**, 13 442 (1998).
- ¹⁵I.S. Elfimov, V.I. Anisimov, and G.A. Sawatzky, Phys. Rev. Lett. **82**, 4264 (1999).
- ¹⁶M.v. Zimmermann, J.P. Hill, D. Gibbs, Y. Murakami, C.-C. Kao, Y. Tomioka, and Y. Tokura (unpublished).
- ¹⁷M. Benfatto, Y. Joly, and C.R. Natoli, Phys. Rev. Lett. **83**, 636 (1999).
- ¹⁸O.K. Andersen and O. Jepsen, Phys. Rev. Lett. **53**, 2571 (1984).
- ¹⁹V.I. Anisimov, J. Zaanen, and O.K. Andersen, Phys. Rev. B **44**, 943 (1991).
- ²⁰S. Satpathy, Z.S. Popovic, and F.R. Vukajlovic, Phys. Rev. Lett. **76**, 960 (1996).
- ²¹P. Wochner *et al.* (unpublished).
- ²²M. Takahashi, J. Igarashi, and P. Fulde, J. Phys. Soc. Jpn. **68**, 2530 (1999).
- ²³D.A. Papaconstantopoulos and W.E. Pickett, Phys. Rev. B **57**, 12 751 (1998).
- ²⁴W.A. Harrison, *Electronic Structure and the Properties of Solids* (Freeman, San Francisco, 1980).