

^{19}F NMR investigation of the iron pnictide superconductor $\text{LaFeAsO}_{0.89}\text{F}_{0.11}$ K. Ahilan,¹ F. L. Ning,¹ T. Imai,^{1,2} A. S. Sefat,³ R. Jin,³ M. A. McGuire,³ B. C. Sales,³ and D. Mandrus³¹*Department of Physics and Astronomy, McMaster University, Hamilton, Ontario, Canada L8S4M1*²*Canadian Institute for Advanced Research, Toronto, Ontario, Canada M5G1Z8*³*Materials Science and Technology Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831, USA*

(Received 24 April 2008; revised manuscript received 31 July 2008; published 3 September 2008)

We report on ^{19}F nuclear magnetic resonance (NMR) investigation of the high-temperature superconductor $\text{LaFeAsO}_{0.89}\text{F}_{0.11}$ ($T_c \sim 28$ K). We demonstrate that low-frequency spin fluctuations exhibit pseudogap behavior above T_c . We also deduce the London penetration depth λ from NMR line broadening below T_c .

DOI: 10.1103/PhysRevB.78.100501

PACS number(s): 74.70.-b, 76.60.-k

The recent discovery of an iron pnictide superconductor $\text{LaFeAsO}_{1-x}\text{F}_x$ ($x=0.05 \sim 0.12$) with a high transition temperature $T_c \sim 26$ K by Kamihara *et al.*¹ has generated tremendous interest in the condensed-matter and materials physics communities. When La^{3+} ions are replaced by Nd^{3+} ions, T_c exceeds 50 K.² The key building blocks of the $R\text{FeAsO}_{1-x}\text{F}_x$ system ($R=\text{La}, \text{Nd}, \text{etc.}$) are two-dimensional sheets of Fe square lattice as shown in Fig. 1. $\text{RO}_{1-x}\text{F}_x$ charge reservoir layers donate electrons into the superconducting Fe sheets and become spectators of the latter. Unlike the CuO_2 sheets in high- T_c cuprate superconductors, the Fe sheets do not require O^{2-} ions to become superconducting. In fact, $\text{Ba}_{1-x}\text{K}_x\text{Fe}_2\text{As}_2$ is also a high- T_c superconductor with $T_c \sim 38$ K.³ On the other hand, the ground state of the undoped LaFeAsO is magnetically ordered.⁴ This suggests that the mechanism of superconductivity in $\text{LaFeAsO}_{1-x}\text{F}_x$ may be unconventional, and electron-electron correlation effects may be playing a major role, in analogy with high- T_c cuprates.⁵ More experimental and theoretical efforts are necessary to understand the properties of these fascinating iron pnictides.

In this Rapid Communication, we provide a microscopic look at the local electronic properties of $\text{LaFeAsO}_{1-x}\text{F}_x$ using nuclear magnetic resonance (NMR). It is worth recalling that NMR techniques are capable of probing a variety of physical properties of superconductors.⁶ As a start, our present work focuses on the ^{19}F NMR properties of a polycrystalline sample of $\text{LaFeAsO}_{1-x}\text{F}_x$ with the nominal composition $x=0.11$ and $T_c \sim 28$ K. See Refs. 5 and 7 for comprehensive bulk characterization of the same batch of the sample. From the measurement of the nuclear-spin-lattice relaxation rate $1/T_1$, we will demonstrate that low-frequency spin fluctuations *decrease* as the temperature is lowered toward T_c . The observed behavior is qualitatively similar to that in the *pseudogap* regime of underdoped high-temperature cuprate superconductors.^{8,9} From NMR line broadening induced by vortices in the mixed state below T_c , we will also deduce the London penetration depth λ .

In Fig. 1, we present typical line shapes of ^{19}F NMR observed in an external magnetic field $B=1.11$ T. ^{19}F has nuclear spin $I=\frac{1}{2}$ and is free from complications caused by nuclear quadrupole interactions. We will take full advantage of the inherently narrow line shapes to deduce the temperature dependence of λ and the intrinsic electron-spin susceptibility χ . Quite generally, one can express the resonance

frequency of ^{19}F NMR as $f=(1+K)\gamma_n B$, where $\gamma_n=2\pi \times 40.262$ MHz/T is the nuclear gyromagnetic ratio of the ^{19}F nuclear spin and K is the NMR Knight shift

$$K = A_{\text{hf}}\chi + K_{\text{chem}}. \quad (1)$$

A_{hf} represents the hyperfine coupling constant between the ^{19}F nuclear spin and the electron spins and K_{chem} is a small temperature-independent chemical shift. From the peak position of the ^{19}F NMR line shapes, we deduced the temperature dependence of K as summarized in Fig. 2(a). Superconducting diamagnetic effects and line broadening in the mixed state caused by vortices prevented us from deducing the temperature dependence of K below T_c . $K \leq 100$ ppm observed above T_c is comparable to that observed for ^{89}Y NMR in $\text{YBa}_2\text{Cu}_3\text{O}_x$.⁹ The small magnitude of K implies that spin transfer from the Fe sheets to the $\text{LaO}_{0.89}\text{F}_{0.11}$ layers is small, and it provides evidence for the highly two-dimensional nature of the electronic properties.^{10,11} Also shown in Fig. 2(b) is the temperature dependence of $1/T_1 T$, the ^{19}F nuclear-spin-lattice relaxation rate $1/T_1$ divided by temperature T ,

$$\frac{1}{T_1 T} \propto |A_{\text{hf}}|^2 \sum_{\mathbf{k}} \frac{\chi''(\mathbf{k}, f)}{f}. \quad (2)$$

$\chi''(\mathbf{k}, f)$ represents the imaginary part of the dynamical electron-spin susceptibility at the NMR frequency f and the \mathbf{k} summation is taken over the Brillouin zone. (^{19}F nuclear-spin recovery after saturation always shows a single expo-




FIG. 1. (Color online) Left: Crystal structure of $\text{LaFeAsO}_{0.89}\text{F}_{0.11}$. Right: Representative ^{19}F NMR line shapes for a randomly oriented polycrystalline sample. Curves represent a Gaussian fit.




FIG. 2. (a) Temperature dependence of the NMR Knight shift K . (b) Spin-lattice relaxation rate divided by T , $1/T_1T$. Inset in (b) $1/T_1T$ vs K with temperature as the implicit parameter. The linear fit suggests that $1/T_1T$ and K exhibit the same temperature dependence and $K_{\text{chem}}=30$ ppm. The solid curves in (a) and (b) represent empirical parabolic fits with the same curvature and $K_{\text{chem}}=30$ ppm.

nential behavior above T_c .) The ^{19}F site is located directly above/below the Fe sites, and there is no accidental cancellation of antiferromagnetic spin fluctuations for any \mathbf{k} modes due to the geometrical form factor (i.e., $|A_{\text{hf}}|^2$ is independent of \mathbf{k}). This means that $1/T_1T$ at the ^{19}F site probes various \mathbf{k} modes of low-frequency spin fluctuations with equal weight.

A striking feature of Fig. 2(b) is that $1/T_1T$ monotonically decreases with T from room temperature to T_c . Without relying on any assumptions or model-dependent analysis, we conclude that *the low-frequency spectral weight of spin fluctuations is gradually suppressed with decreasing temperature down to T_c , i.e., the observed suppression establishes the pseudogap behavior. Similar pseudogap was observed by NMR and other techniques in the underdoped regime of high- T_c cuprate superconductors,^{8,9,12} and its possible relation to the superconducting mechanism has been at the focus of intense debate. Our observation suggests that analogous exotic state of electrons may exist in iron pnictide above T_c .*

Equally interesting is the fact that the Knight shift K in Fig. 2(a) shows nearly identical temperature dependence as $1/T_1T$ in Fig. 2(b). The inset in Fig. 2(b) presents a plot of $1/T_1T$ vs K with temperature as the implicit parameter. The linear fit suggests that $K_{\text{chem}} \sim 30$ ppm and $1/T_1T \propto K_{\text{spin}} = K - K_{\text{chem}} = A_{\text{hf}}\chi$. This simple dynamical scaling behavior implies $A_{\text{hf}} > 0$ and is consistent with (but does not necessarily prove) a decreasing χ with temperature toward T_c .

Next, we turn our attention to the NMR measurements below T_c . As noted above, we are unable to deduce the intrinsic behavior of K below T_c because superconducting vor-




FIG. 3. (Color online) Temperature dependence of the broadening of the Gaussian linewidth Δf below T_c . The right axis shows the conversion to λ^{-2} (see main text). Curves represent a theoretical fit to an energy gap with d -wave symmetry, without disorder (solid curve) and with a mild disorder $\Gamma/T_c=0.01$ (dashed curve) and $\Gamma/T_c=0.05$ (dotted curve), where Γ is the scattering rate (Ref. 19).

tices induce a distribution of the *local* magnetic field B_{local} inside the sample, and the broadening of the NMR line shape overwhelms the temperature dependence of K . Nevertheless, one can deduce valuable information about the superconducting state based on this very line broadening through the measurement of the London penetration depth λ as follows.¹³ When our superconducting sample enters the mixed state below T_c in applied magnetic field B , quantized magnetic flux $\phi_o = \frac{2h}{e} = 2.07 \times 10^{-7}$ Oe/cm² forms an Abrikosov lattice. B_{local} takes the largest value in the vortex cores and decays with a characteristic length scale set by λ . One can express the resulting distribution ΔB_{local} of the local field as¹⁴

$$\Delta B_{\text{local}} \sim 0.0609 \frac{\phi_o}{\lambda^2}, \quad (3)$$

when $B_{c1} \ll B \ll B_{c2}$ is satisfied. [The lower critical field B_{c1} and upper critical field B_{c2} are estimated to be ~ 0.005 (Ref. 15) and ~ 60 T,⁷ respectively.] When λ begins to decrease from $\lambda = \infty$ below T_c , ΔB_{local} becomes nonzero and induces a temperature-dependent broadening of the NMR linewidth $\Delta f = \gamma_n \Delta B_{\text{local}}$. Δf is the NMR analog of the Gaussian relaxation rate σ measured in μSR experiments within the time domain^{16,17} and represents the same physical process.

Experimentally, it is well known that ΔB_{local} in the superconducting state of polycrystalline samples can be approximated by a Gaussian distribution.^{17,18} In fact, we found that ^{19}F NMR line shapes fit quite well to Gaussians as shown in Fig. 1. We deduced Δf below T_c from the fit and used $\Delta f = \gamma_n \Delta B_{\text{local}}$ and Eq. (3) to convert Δf to $\lambda^{-2} (\propto \Delta f)$. In Fig. 3, we summarize the temperature dependence of Δf and λ^{-2} . One of the most important findings of the present work is that λ^{-2} does not saturate down to the lowest temperature we have reached, $T=2\text{K} \sim 0.1T_c$. If $\text{LaFeAsO}_{0.89}\text{F}_{0.11}$ was a conventional BCS s -wave superconductor, λ^{-2} would saturate below $T \sim 0.4T_c$ because λ would asymptote exponentially to a constant value $\lambda(0)$ below $T \sim 0.4T_c$, where $\lambda(0)$ is the $T=0$ limit. Instead, λ^{-2} continues to grow roughly linearly.

Similar T -linear behavior of the Gaussian relaxation rate σ was observed by μ SR for clean polycrystalline samples of high- T_c superconductors, and it is known to be an indication of the presence of *line nodes* in the superconducting energy gap $\Delta(\mathbf{k})$.¹⁷ The underlying physics of such T -linear behavior is easily understandable from the following considerations. When there are line nodes in $\Delta(\mathbf{k})$ at certain wave vector \mathbf{k} , the density of states of superconducting carriers averaged over \mathbf{k} increases linearly with energy, $D_s(E-E_F) \sim |E-E_F|$. For this reason, the superconducting carrier density n_s decreases linearly above $T=0$. In the London theory, n_s and λ^{-2} are proportional to each other,

$$n_s = \frac{m^* c^2}{4\pi e^2 \lambda^2}, \quad (4)$$

where m^* is the effective mass of the carrier. Equation (4) indicates that λ^{-2} shows a T -linear behavior near $T=0$ if $\Delta(\mathbf{k})$ has line nodes.

Close inspection of our λ^{-2} data in Fig. 3 reveals a small negative curvature. It is known that disorder tends to smear out the line nodes and λ^{-2} begins to deviate from T -linear behavior, crossing over to T^2 behavior when the sample is strongly disordered.¹⁹ We find similarity between the temperature dependence of our λ^{-2} data and theoretical calculations based on a d -wave model with mild disorder as shown in Fig. 3. We emphasize, however, that this qualitative agreement does not necessarily mean that the superconducting energy gap in LaFeAsO_{0.89}F_{0.11} has d -wave symmetry. Our results for λ^{-2} alone cannot discern²⁰ d -wave symmetry from extended s wave²¹ or p wave.²²

By smoothly extrapolating the temperature dependence of λ^{-2} to $T=0$, we estimate the $T=0$ limit as $\lambda(0)^{-2} \sim 7 \mu\text{m}^{-2}$ or, equivalently, $\lambda(0) \sim 378$ nm. Our estimation of the London penetration depth $\lambda(0)$ is averaged over all possible orientations. As noted above, however, LaFeAsO_{1-x}F_x should be considered a highly anisotropic system; hence, we expect an anisotropic penetration depth $\lambda_{ab} \ll \lambda_c$. Theoretically, the in-plane penetration depth λ_{ab} and the powder-averaged penetration depth λ satisfy a simple relation $\lambda_{ab} \sim \lambda/1.23$;²³ hence, we arrive at $\lambda_{ab}(0) \sim 308$ nm. This is comparable to $\lambda_{ab}(0)=250$ nm observed for the high- T_c cuprate La_{1.85}Sr_{0.15}CuO₄ with comparable $T_c=38$ K.¹⁷

The observed value of $\lambda(0)$ also provides additional insight into the electronic properties of the LaFeAsO_{1-x}F_x sys-

tem. First, combined with the superconducting correlation length $\xi(0) \sim 4$ nm deduced from the zero-temperature limit of the upper critical field $B_{c2}(0)$,⁷ we arrive at the Ginzburg-Landau parameter $\kappa = \lambda(0)/\xi(0) \sim 77$. Second, within the London relation, Eq. (3), and ignoring possible mass enhancement for m^* , we estimate the density of superconducting carriers as $n_s \sim 0.3 \times 10^{21} \text{ cm}^{-3}$. This is comparable to the carrier density estimated by Hall voltage measurements in the normal state above T_c , $n_H \sim 1.0 \times 10^{21} \text{ cm}^{-3}$ (Ref. 5). As already noted in Ref. 5, the LaFeAsO_{1-x}F_x system is indeed a low carrier density superconductor.

Given the extraordinarily fast progress of research into iron pnictide systems, it would be useful to compare our findings with those by other experimental techniques and put our results into perspective. During the course of the present study, measurements of the field dependence of the specific heat,²⁴ tunneling conductance,²⁵ lower critical field B_{c1} ,¹⁵ and μ SR (Ref. 26) were independently reported, all pointing toward the presence of line nodes in the energy gap, in agreement with our conclusion. In particular, Ren *et al.*¹⁵ reported a linear temperature dependence of B_{c1} below $T \sim 0.5T_c$. Within the Ginzburg-Landau theory, $\lambda^{-2} \propto B_{c1}$; hence, the B_{c1} and NMR measurements are fully consistent. The penetration depth $\lambda_{ab}(0)=254$ nm as measured by μ SR (Ref. 26) is also in good agreement with our finding. Very recently, ¹³⁹La NMR,²⁷ ⁷⁵As NMR,^{27,28} and photoemission experiments²⁹ confirmed the pseudogap behavior above T_c . Moreover, $1/T_1T$ data at ⁷⁵As and ¹³⁹La sites show an absence of the Hebel-Slichter coherence peak just below T_c and exhibit a power-law temperature dependence well below T_c .^{27,28} These results are consistent with the presence of line nodes in $\Delta(\mathbf{k})$.

To summarize, we have reported a microscopic investigation of the local electronic properties of the LaFeAsO_{0.89}F_{0.11} superconductor based on ¹⁹F NMR techniques. Our observations indicate that LaFeAsO_{0.89}F_{0.11} is a highly unconventional system.

T.I. thanks G. M. Luke and A. J. Berlinsky for the helpful discussions. The work at McMaster was supported by NSERC and CIFAR. Research sponsored by the Division of Materials Science and Engineering, Office of Basic Sciences, Oak Ridge National Laboratory is managed by UT-Battelle, LLC for the U.S. Department of Energy under Contract No. DE-AC-05-00OR22725.

¹Y. Kamihara, T. Watanabe, M. Hirano, and H. Hosono, *J. Am. Chem. Soc.* **130**, 3296 (2008).

²Z. A. Ren *et al.*, *Europhys. Lett.* **82**, 57002 (2008).

³M. Rotter, M. Tegel, and D. Johrendt, arXiv:0805.4630 (unpublished).

⁴C. de la Cruz *et al.*, *Nature (London)* **453**, 899 (2008).

⁵A. S. Sefat, M. A. McGuire, B. C. Sales, R. Jin, J. Y. Howe, and D. Mandrus, *Phys. Rev. B* **77**, 174503 (2008).

⁶D. E. MacLaughlin, *Solid State Physics* (Academic Press, New York, 1976), Vol. 31, p. 1.

⁷F. Hunte, J. Jaroszynski, A. Gurevich, D. C. Larbalestier, R. Jin, A. S. Sefat, M. A. McGuire, B. C. Sales, D. K. Christen, and D. Mandrus, *Nature (London)* **453**, 903 (2008).

⁸M. Takigawa, A. P. Reyes, P. C. Hammel, J. D. Thompson, R. H. Heffner, Z. Fisk, and K. C. Ott, *Phys. Rev. B* **43**, 247 (1991).

⁹H. Alloul, T. Ohno, and P. Mendels, *Phys. Rev. Lett.* **63**, 1700 (1989).

¹⁰D. J. Singh and M. H. Du, *Phys. Rev. Lett.* **100**, 237003 (2008).

¹¹K. Haule, J. H. Shim, and G. Kotliar, *Phys. Rev. Lett.* **100**, 226402 (2008).

- ¹²T. Timusk and B. W. Statt, *Rep. Prog. Phys.* **62**, 61 (1999).
- ¹³P. Pincus, A. C. Gossard, V. Jaccarino, and J. H. Wernick, *Phys. Lett.* **13**, 21 (1964).
- ¹⁴E. H. Brandt, *Phys. Rev. B* **37**, 2349 (1988).
- ¹⁵C. Ren, Z. S. Wang, H. Yang, X. Zhu, L. Fang, G. Mu, L. Shan, and H. H. Wen, arXiv:0804.1726 (unpublished).
- ¹⁶Y. J. Uemura, G. M. Luke, B. J. Sternlieb, J. Brewer *et al.*, *Phys. Rev. Lett.* **62**, 2317 (1989).
- ¹⁷J. E. Sonier, J. Brewer, and R. F. Kiefl, *Rev. Mod. Phys.* **72**, 769 (2000).
- ¹⁸A. Maisuradze, R. Khasanov, A. Shengelaya, and H. Keller, arXiv:0805.3646 (unpublished).
- ¹⁹P. J. Hirschfeld and N. Goldenfeld, *Phys. Rev. B* **48**, 4219 (1993).
- ²⁰S. Graser, G. R. Boyd, C. Cao, H. P. Cheng, P. J. Hirschfeld, and D. J. Scalapino, *Phys. Rev. B* **77**, 180514(R) (2008).
- ²¹I. I. Mazin, D. J. Singh, M. D. Johannes, and M. H. Du, *Phys. Rev. Lett.* **101**, 057003 (2008).
- ²²P. A. Lee and X. G. Wen, arXiv:0804.1739 (unpublished).
- ²³W. Barford and J. M. F. Gunn, *Physica C* **156**, 515 (1988).
- ²⁴G. Mu, X. Zhu, L. Fang, L. Shan, C. Ren, and H. Wen, *Chin. Phys. Lett.* **25**, 2221 (2008).
- ²⁵L. Shan, Y. Wang, X. Zhu, G. Mu, L. Fang, and H.-H. Wen, arXiv:0803.2405 (unpublished).
- ²⁶H. Luetkens *et al.*, arXiv:0804.3115 (unpublished).
- ²⁷Y. Nakai, K. Ishida, Y. Kamihara, A. Hirano, and H. Hosono, *J. Phys. Soc. Jpn.* **77**, 073701 (2008).
- ²⁸H. J. Grafe, D. Paar, G. Lang, N. J. Curro, G. Behr, J. Werner, J. Hamann-Borrero, C. Hess, N. Leps, R. Klingeler, and B. Büchner, *Phys. Rev. Lett.* **101**, 047003 (2008).
- ²⁹T. Sato, S. Souma, K. Nakayama, K. Terashima, K. Sugawara, T. Takahashi, Y. Kamihara, M. Hirano, and H. Hosono, *J. Phys. Soc. Jpn.* **77**, 063708 (2008).