

First-principles investigation of magnetism and electronic structures of substitutional 3d transition-metal impurities in bcc Fe

Gul Rahman and In Gee Kim*

Graduate Institute of Ferrous Technology, Pohang University of Science and Technology, Pohang 790-784, Republic of Korea

H. K. D. H. Bhadeshia

Graduate Institute of Ferrous Technology, Pohang University of Science and Technology, Pohang 790-784, Republic of Korea and Department of Materials Science and Metallurgy, University of Cambridge, Cambridge CB2 3QZ, United Kingdom

Arthur J. Freeman

Department of Physics and Astronomy, Northwestern University, Evanston, Illinois 60208, USA

(Received 28 October 2009; revised manuscript received 23 February 2010; published 20 May 2010)

The magnetic and electronic structures of 3d impurity atoms from Sc to Zn in ferromagnetic body-centered-cubic iron are investigated using the all-electron full-potential linearized augmented plane-wave method based on the generalized gradient approximation (GGA). We found that, in general, the GGA results are closer to the experimental values than those of the local spin density approximation. The calculated formation enthalpy data indicate the importance of a systematic study on the ternary Fe-C-X systems rather than the binary Fe-X systems in steel design. The lattice parameters are optimized and the conditions for spin polarization at the impurity sites are discussed in terms of the local Stoner model. Our calculations, which are consistent with previous work, imply that the local spin polarizations at Sc, Ti, V, Cu, and Zn are induced by the host Fe atoms. The early transition-metal atoms couple antiferromagnetically, while the late transition-metal atoms couple ferromagnetically to the host Fe atoms. The calculated total magnetization (M) of bcc Fe is reduced by impurity elements from Sc to Cr as a result of the antiferromagnetic interaction, with the opposite effect for solutes which couple ferromagnetically. The changes in M are attributed to nearest neighbor interactions, mostly between the impurity and host atoms. The atom averaged magnetic moment is shown to follow generally the well-known Slater-Pauling curve, but our results do not follow the linearity of the Slater-Pauling curve. We attribute this discrepancy to the weak ferromagnetic nature of bcc Fe. The calculated Fermi contact hyperfine fields follow the trend of the local magnetic moments. The effect of spin-orbit coupling is found not to be significant although it comes into prominence at locations far from the impurity sites.

DOI: [10.1103/PhysRevB.81.184423](https://doi.org/10.1103/PhysRevB.81.184423)

PACS number(s): 75.50.Bb, 71.70.Ej, 71.20.Be

I. INTRODUCTION

Each of the three allotropes of iron possess interesting magnetic properties which have a profound influence on their stability.¹ The body-centered-cubic (bcc) form is ferromagnetic;² the face-centered-cubic (fcc) Fe at low temperatures is antiferromagnetic,³ but its higher energy ferromagnetic state can be thermally excited with complex variations in magnetic structure as a function of temperature.^{4,5} Ferromagnetism is eliminated when bcc iron transforms into the hexagonal close-packed (hcp) crystal structure at high pressures of ~ 29.5 GPa.⁶

Density-functional theory has been proven to be reliable in estimating the magnetic properties of iron-based transition-metal alloys, for example, the pioneering work by Akai *et al.*⁷ who used the Korringar-Kohn-Rostoker (KKR) Green's function method based on the local spin density approximation (LSDA), and Anisimov *et al.*,⁸ who used the linear muffin-tin orbital (LMTO) Green's function method to obtain a consistent picture of the electronic and magnetic structures of 3d impurities in bcc Fe. However, the LSDA is known to underestimate exchange effects,^{9,10} which are crucial for determining magnetism. Furthermore, lattice optimization, which may affect the electronic and magnetic structures of the impurity and host, was not taken into account in

these previous calculations. Lattice optimization may not change the general conclusions drawn previously but can give more quantitative information. The relative stability of 3d impurities in bcc Fe is also important for practical implementations in the steel industry which can be precisely calculated at the optimized lattice parameters and for this purpose, the lattice parameters of the 3d impurities are also optimized. We focus also on the magnetic interactions between impurity and the host element which can give a detailed picture of the magnetism of impurities in bcc Fe. The purpose of the present work was to use the highly precise all-electron full-potential linearized augmented plane-wave (FLAPW) method¹¹ based on the generalized gradient approximation (GGA) (Ref. 12) to study the magnetic and electronic structures and hyperfine fields of Fe where it is substitutionally alloyed with the 3d transition metals. The longer term aim is to be able to contribute to the development of the so-called electrical steels, which are used in the manufacture of motors and transformers.

II. CALCULATION METHOD

A $3 \times 3 \times 3$ supercell of the primitive bcc cell containing 27 Fe atoms (Fig. 1) was used with 3d solute atoms ($X=\text{Sc-Zn}$) substituting a body-centered iron atom, giving a




FIG. 1. (Color online) The model of $3 \times 3 \times 3$ supercell of the primitive cell of bcc Fe, which contains 27 atoms. The Fe1, Fe2, and Fe3 atoms are represented by black, white, and gray spheres, respectively, while the impurity atom (corner atom) is marked with X.

composition $X_1\text{Fe}_{26}$ equivalent to a concentration of 3.7 at.%, which is consistent with the levels of solute added to steels. The impurity atom X has first, second, and third nearest neighbors designated Fe1, Fe2, and Fe3, respectively.

The Kohn-Sham equations¹³ were solved in the framework of the FLAPW (Ref. 11) method under the GGA.¹² An energy cutoff at $4(2\pi/a)$, where a is the lattice parameter of each calculation, employed for expanding the linearized augmented plane wave (LAPW) basis set, corresponding to ~ 2350 LAPWs per \mathbf{k} point and spin. A $16.1245(2\pi/a)$ cutoff was used for the star functions depicting the charge density and potential in the interstitial regions. Lattice harmonics with $l \leq 8$ were employed to expand the charge density, potential, and wave functions inside each muffin-tin (MT) sphere of radius of 2.2 a.u. for all the atoms. Integrations inside the Brillouin zone (BZ) were performed using the improved tetrahedron method¹⁴ over a $13 \times 13 \times 13$ mesh within the three-dimensional (3D) BZ, corresponding to 84 \mathbf{k} points inside the irreducible wedge of the 3D-BZ. All core electrons were at first treated fully relativistically and valence states scalar relativistically, i.e., without spin-orbit coupling (SOC).¹⁵ For spin-orbit coupling on valence states, we employed the second variation method¹⁶ with the spin diag-




FIG. 2. Calculated optimized lattice constant a (in units of Å) and bulk modulus B (in units of GPa) of $X_1\text{Fe}_{26}$. Filled squares (circles) on the left (right) axis show lattice constant (bulk modulus).

onal parts of the density subjected to a self-consistency loop. During the second variation procedure, integrations inside the 3D-BZ were done in the full-BZ, i.e., 1099 \mathbf{k} points. The explicit orthogonalization (XO) scheme was employed to ensure the orthogonality between the core and valence states.¹⁷

All atoms were fully relaxed at each lattice volume until the atomic forces on each atom were less than 2 mRy/a.u. The equilibrium lattice constants and bulk moduli B were determined by fitting the total energy and volume to the Birch-Murnaghan equation of states.¹⁸ Using the optimized lattice constants, further calculations were carried out in the spin-unpolarized and spin-polarized states with and without SOC. Self-consistency was assumed when the difference between input and output charge densities became less than 1.0×10^{-4} electrons/a.u.³ Note that all the computational parameters used in the present calculations satisfy the convergence test.¹⁹

III. RESULTS AND DISCUSSIONS

A. Structural properties

Table I and Fig. 2 show the optimized lattice parameters a (in units of Å) and bulk moduli B (in units of GPa) of $X_1\text{Fe}_{26}$ supercell at zero kelvin. The optimized lattice constant of pure bcc Fe is 2.83 Å, which is only 1.4% smaller than that of the finite temperature experimental value 2.87 Å.²⁰ It is interesting to find out that the all the substitutional $3d$ impurities in bcc Fe increases the lattice parameter. The calculated

TABLE I. Calculated lattice parameters a (in units of Å), bulk moduli B (in units of GPa), and formation enthalpy per atom (ΔH in units of eV/atom) of $X_1\text{Fe}_{26}$. Numbers in the parentheses are the formation enthalpy in units of kJ/atom-mol.

X	Sc	Ti	V	Cr	Mn	Fe	Co	Ni	Cu	Zn
a	8.556	8.534	8.518	8.516	8.510	8.499	8.508	8.518	8.522	8.528
B	180.54	188.26	186.52	179.58	162.73	175.75	184.40	176.68	166.35	167.06
ΔH	0.034 (3.26)	-0.011 (-1.04)	-0.004 (-0.40)	0.018 (1.71)	0.038 (3.68)	0.000 (0.00)	0.020 (1.91)	0.029 (2.83)	0.053 (5.14)	0.038 (3.68)

bulk modulus of bcc Fe, 175.5 GPa is also comparable with the experimentally observed value.²¹ We can see B has minimum when the d band is half filled, i.e., Mn. We also analyzed the local lattice expansion/contraction around the X impurities and we arrive at a conclusion that the lattice distortions around the X impurities are negligible. However, one can easily calculate the bond lengths of Fe- X using the lattice parameters given in Table I.

The relative stability of X in bcc Fe can be understood through the formation enthalpy ΔH per atom of $X_1\text{Fe}_{26}$, which was calculated as follows:

$$\Delta H = \frac{H(X_n\text{Fe}_m) - mH(\text{Fe}) - nH(X)}{m+n}, \quad (1)$$

where $H(X_n\text{Fe}_m)$ is the enthalpy of $X_n\text{Fe}_m$ for $m=26$ and $n=1$, and $H(\text{Fe})$ and $H(X)$ are the total energy/atom of bcc Fe and X at their ground state structures, respectively. For ΔH , the optimized lattice parameters of the impurity X crystals were also calculated, e.g., bcc Cr (2.88 Å) and hcp Co ($a=2.51$ Å, $c=4.0$ Å), which are close to the experimental values. Using the optimized lattice parameters, ΔH was calculated by the above equation and the results are shown in Table I. Note that ΔH of a system is nothing more than the total energy of the system at zero pressure and 0 K at the corresponding equilibrium lattice parameter and is an enthalpy change for the synthesis of the composition from the component elements. It is interesting to find that ΔH values of all the $3d$ elements are positive, except the Ti and V cases.

A category of the solution atoms in Fe-C system is available:²² Ni and Cu are considered as the elements, which enter only the ferrite phase, while Ti, V, Cr, and Mn are considered as the elements, which form stable carbides and also enter the ferrite phase. It seems in this Fe- X system that there is no strong significant relationship between ΔH and the solubilities of the elements. Many noble properties found during the alloy design for steels are able to be contributed by the characters of the ternary Fe-C- X systems rather than the binary Fe- X ones in thermodynamic point of view.

B. Local Stoner criterion

It is known that bcc Fe is a ferromagnetic metal which will be shown using spin-polarized (magnetic) calculations. The spin-unpolarized (nonmagnetic) state of bcc Fe is higher in energy than the magnetic one, but a knowledge of spin-unpolarized calculations is necessary to find out the condition for the formation of local magnetic moment at the impurity site using the Stoner criterion.²³ The calculated spin-unpolarized impurity-site-projected local density of states (LDOS) for the solutes in bcc Fe are shown in Fig. 3, where the contribution from the d states are decomposed into the e_g and t_{2g} states. The Fermi levels (E_F) were set to zero. Pure bcc Fe exhibits the typical three-peak structure of $3d$ bcc metals. The positions of the bonding and antibonding states relative to E_F depend on the number of electrons of the impurity atoms. When a Sc atom substitutes for a centered Fe atom, the lowest lying unoccupied d states are the t_{2g} states. The addition of one valence $3d$ electron, i.e., when the impurity Sc is replaced by Ti, causes the unoccupied t_{2g} states




FIG. 3. (Color online) Calculated spin-unpolarized impurity-atom-projected local density of states of $X_1\text{Fe}_{26}$. Solid (dotted) lines represent the t_{2g} (e_g) states, whereas the thin solid (dotted) lines show the s (p) states, which are multiplied by a factor 20, of Zn impurity at the left bottom. First (second) column shows early (late) transition metals. The Fermi energy (E_F) is set to zero.

to shift toward E_F . For Sc and Ti impurities the lowest lying unoccupied states are mainly the t_{2g} states. In contrast, with V the corresponding unoccupied states become sharp and are dominated by the e_g states.

For the other impurities, the antibonding states form virtual bound states (VBSs) (Ref. 24) near E_F are dominated by the e_g states. The $3d$ impurities also affect the LDOS of the neighboring atoms through bonding with the host atoms (not shown). For pure bcc Fe, one can see the dominant Fe1- e_g states just above E_F . On adding $3d$ electrons using appropriate solutes, these Fe1 e_g states become narrow and their density is changed. After the d bands are filled, the p electrons will hybridize with the host Fe and this happens with the Zn




FIG. 4. Calculated local density of states at the Fermi energy, $n(E_F)$, for the 3d impurities in nonmagnetic bcc Fe. The dotted horizontal line represents the Stoner limits for the local spin polarization.

impurity, where one can expect the sp - d hybridization rather than the d - d hybridization.

Figure 4 we show the calculated X atom projected LDOS at the Fermi energy, denoted by $n(E_F)$. The condition for the formation of local spin polarization at the X atom in bcc Fe can be determined approximately by adapting the Stoner criterion,²³ i.e., $In(E_F) > 1$, where I is the well-known atomic exchange parameter equal to 0.925 eV for bcc Fe.²⁵ The critical value of $n(E_F)$ above, which an intrinsic local magnetic moment arises on the impurity atom in bcc Fe was estimated to be ~ 1.081 states/eV atom, shown in Fig. 4 as a dotted horizontal line. It is found that the condition for the local spin polarization is not satisfied for the Sc, Ti, V, Cu, and Zn impurities. In other words, the calculated local magnetic moments of impurity atoms which do not satisfy the local Stoner criterion are induced by the surrounding magnetic Fe atoms.

The elements from Cr to Ni, which satisfy the local Stoner criterion, induce the t_{2g} and e_g states to move closer to E_F . For the early 3d impurities, $n(E_F)$ is mainly contributed by the t_{2g} states, while for the late 3d transition-metal impurities $n(E_F)$ is contributed by the e_g states. Once these 3d impurity bands cross E_F , i.e., when the d bands are completely filled, the electronic structures and the magnetism of the impurity atoms will be determined by the sp electrons as seen, for example, in the LDOS of Zn in Fig. 3.

C. Magnetism

Figure 5 shows the calculated local magnetic moment (m) within each MT sphere of the 3d impurity sites. Solutes from Sc to Cr are associated with negative values of m with antiferromagnetic coupling with the host Fe atoms. It is noticeable that Sc, Ti, and V atoms have significant magnetic moments, even though these elements are not magnetic elements—this is because the 3d magnetism, according to the local Stoner criterion (Fig. 4), is not intrinsic but is induced via the host iron atoms. It is considered that the largely




FIG. 5. Calculated local magnetic moment of the 3d impurities in bcc Fe. Filled circles show our calculated local magnetic moment (in units of μ_B) at the X site, filled triangles show the previously calculated values (Other) (Ref. 8), and open triangles show the experimental (Expt.) values taken from Refs. 20 and 26–31.

induced m of the impurities from Sc to V are due to the fact that their 3d states are induced.

Cr and Mn, which satisfy the Stoner criterion and are antiferromagnetically and ferromagnetically coupled to the iron respectively, have intrinsically large magnetic moments which are not attributed to the neighboring iron atoms. In the case of Co and Ni, the local magnetic moments are positive and are coupled ferromagnetically to the host Fe. In contrast to the induced m of the early transition-metal impurities from Sc to V, the calculated m for Cu and Zn impurities, which have complete d shell occupation, are very small. Especially, the Zn impurity shows local diamagnetism. We may say that Sc to Cr might not be useful due to antiferromagnetic coupling when designing iron alloys where a high-saturation magnetization is required.

It seems that as a general principle, similar to Hund's rules, impurity atoms with 3d states less than half-filled will tend to couple antiferromagnetically with iron and ferromagnetic coupling occurs when the atoms have more than half-filled states, and this statement was also confirmed by spin-density contours. Figure 5 also shows published data^{8,20,26–31} which seem to be consistent with the trends illustrated in Fig. 4.

The case of Mn impurity attracts attention, because the local magnetic moments of Mn are very sensitive to volume. Our analysis showed that Mn can couple antiferromagnetically as well as ferromagnetically depending on the lattice volume. For example, at the experimental lattice constant of bcc Fe (5.4169 a.u.), Mn couples antiferromagnetically with the host Fe atoms but couples ferromagnetically at the optimized lattice constant of Fe_{26}Mn (5.3608 a.u.). The unstable behavior of local magnetic moments of Mn may cause disagreement between experiments and theoretical calculations. There is a significant discrepancy with the experimental data for Mn; spin-unpolarized neutron diffraction measurements of FeMn alloys gave values of a Mn local moment from $0.0 \pm 0.2\mu_B$ (Ref. 32) to $1.0 \pm 0.2\mu_B$,²⁶ while polarized neutron diffraction measurements give $0.77\mu_B$ for parallel³³ and




FIG. 6. Calculated total magnetization M of $X_1\text{Fe}_{26}$ (in units of T). Open squares show M without spin-orbit coupling (SOC) and filled squares show M with SOC. The horizontal dotted line shows M of pure Fe without SOC. The inset shows the atom averaged magnetic moment (\bar{m}) (open circles) in units of μ_B without SOC versus the number of electrons per atom of $X_1\text{Fe}_{26}$. The filled circles show the experimental values taken from Ref. 37.

$-0.82\mu_B$ for antiparallel²⁷ to the orientation of m of Mn. The previously calculated m of Mn in Fe are $0.6\mu_B$,⁷ $1.6\mu_B$,³⁴ and $-2.30\mu_B$ and $1.6\mu_B$.³⁵ The discrepancies between the individual calculations are due to the use of different computational methods and the exchange-correlation potentials. The KKR-Green's function method by Akai *et al.*⁷ showed that the variation of m with the impurity nonintegral nuclear charges Z , leads m with negative values for $Z \leq 25$, but that the sign is reversed beyond $Z=25$.¹⁷ This implies that the m of Mn is not only susceptible to nuclear charges but also to volumes. On the other hand, recent calculations indicate the noncollinear magnetic structures for FeMn.³⁶ The discrepancies between the calculated and the experimental values of m of Mn shows that the exact experimental determination of the value of the Mn impurity magnetic moment might be complicated by its pronounced concentration²⁷ and temperature dependence²⁶ in FeMn alloys.

Judging from the dependence of local magnetic moments, one can expect that solutes from Sc to Cr will decrease the magnetization M of bcc Fe due to antiferromagnetic coupling, while Co to Ni will have the opposite effect based on ferromagnetic coupling to the host Fe atoms. This is indeed observed as shown in Fig. 6, where the calculations are presented with and without SOC. M is seen to vary linearly with the atomic number from Sc to Mn with a large increase from Mn to Fe. The Mn case is quite different because the sign of m of Mn is very sensitive to external perturbation (volume in this case) around the equilibrium volume. Therefore, there are two competing factors that determine the change in M with respect to pure bcc Fe, i.e., nearest-neighbor (NN) interaction and lattice volume. The lattice volume of X (Sc-Mn) is larger than bcc Fe, so one can expect small M , and at the same time the nearest-neighbor interactions favor the AFM coupling between X (Sc-Cr) and Fe atoms and decreases M .

For Co and Ni impurities, although the lattice volume is larger but the NN interactions favor FM coupling and in-

creases M . From Fe to Ni, M increases linearly and we already discussed the enhanced M of Ni in bcc Fe due to the spin-flip of Fe1 d states.³⁸ On the other hand, M decreased sharply for Cu and Zn, because as stated previously, their $3d$ bands are fully occupied and hence are not susceptible to magnetic interactions with the host atoms. The calculated magnetic moment of bcc Fe is found to be $2.22\mu_B$, the same as that observed experimentally.²⁰ The calculated trend that solutes from Sc to Mn decrease the total magnetization of the system has been observed experimentally.³⁹⁻⁴¹ Co and Ni enhance the magnetization of Fe and this compares well with experimental measurements.^{29,30,42}

Before going into the microscopic description of the magnetic interaction of an X impurity with the neighboring Fe atoms, our calculated trends of M can be compared with the Slater-Pauling curve,^{43,44} which is a plot of atom averaged magnetic moment (\bar{m}) of ferromagnets versus the electron-to-atom ratio. Here, we used \bar{m} to distinguish it from the magnetization M . Bcc iron as a weak ferromagnet and alloys based on bcc iron can form the left branch of the Slater-Pauling curve. Our calculated \bar{m} of $X_1\text{Fe}_{26}$ can follow the simple phenomenological relation discussed in Ref. 23, i.e.,

$$\bar{m} = m_A^0 + x(Z_B - Z_A) \quad (2)$$

for the left branch, i.e., \bar{m} increasing branch,

$$\bar{m} = m_A^0 - x(Z_B - Z_A), \quad (3)$$

for the right branch, i.e., \bar{m} decreasing branch, where m_A^0 is the magnetic moment of the host atom, x is the solute concentration, and Z_A and Z_B are the valences of the host and the solute atoms, respectively. The inset of Fig. 6 shows \bar{m} versus the number of electrons per atom. The \bar{m} curve shows a local maximum at about 26.074 electrons per atom, which is approximately similar to the other bcc alloys on the Slater-Pauling curve. However, it is noticeable that the left branch does not follow the simple linear relation in Eq. (2). We attribute that this offset from the linear behavior is caused by the weak ferromagnetic nature of bcc Fe, discussed in the following.

Figure 7 and the results in Table II show that it is the interaction of $X=\text{Sc-Mn}$ with first neighbor Fe1 atoms that is most responsible for the reduction in M of the alloy. With Cr and Mn, which exhibit local intrinsic spin polarizations, the reduction in M is caused mainly by the interaction with the Fe2 atoms. The importance of Fe2 can be understood in terms of the local symmetry of the Cr and Mn atoms in bcc Fe. The width of the splitting of the bonding and antibonding states usually depends on the spatial separation of the atoms, and becomes large if the atoms are close together. The Cr and Mn atoms, surrounded by the nearest eight Fe1 atoms, are located at the corners of a cube at a distance of $\sqrt{3}a/2$. The atomic wave-functions of Cr or Mn e_g and Fe1 t_{2g} overlap strongly and form hybrid orbitals. The impurity atoms are also surrounded by six next-nearest neighboring Fe2 atoms, which form an octahedral cage around Cr and Mn atoms at a distance of a . Consequently, the hybridization is smaller and, hence, so is the resulting splitting of the hybrid orbitals. Due




FIG. 7. Calculated local magnetic moments (in units of μ_B) of Fe1, Fe2, and Fe3 atoms. Filled squares and triangles represent the local magnetic moments of Fe1 and Fe3 atoms, respectively, whereas the open circles represent Fe2 atoms.

to the weak antiferromagnetic interaction between the Cr (or Mn) and the Fe2 atoms, the magnetic moment of the Fe2 atom is smaller than that of the Fe1 atom.

The variation in m of Fe1, Fe2, and Fe3 atoms is not monotonic for solutes with $d > 5$. The Fe1 atoms have a much larger m than those of Fe2 and Fe3 atoms for the late transition-metal solutes. The enhancement of magnetization due to the late transition-metal impurities in bcc Fe is caused mainly by the Fe1 atoms. The origin of such an enhanced magnetization in bcc Fe was already discussed in Ref. 38 where we found strong interactions between the Fe1 t_{2g} and Ni e_g states, through the VBS.

For further insight, it is useful to compare the spin-unpolarized LDOS in Fig. 3 and the spin-polarized one in Fig. 8. Considering bcc Fe, or the Fe impurity case, the e_g majority spins are almost completely occupied, but the t_{2g}

majority spins are partially filled. Due to this latter property, bcc Fe is so-called a weak ferromagnet.⁴⁵ This makes the magnetic moment of bcc Fe sensitive to perturbations due to X impurities.

With the substitution of Sc, the valence 3d electron is accommodated in the minority t_{2g} states; if instead Ti is added, its additional 3d electron occupies the minority t_{2g} states with both the latter and e_g states shifting toward lower energy. Thus, by adding electrons, the unoccupied states move closer to E_F . Therefore, the spin-polarized LDOS indicates that for the impurities from Sc to Cr all the 3d electrons occupy in the local minority spin bands to achieve charge neutrality and consequently to align the impurity magnetic moments in an opposite sense to the host magnetic moments. For Mn impurity, the majority e_g spin states also become occupied. We verified that the local DOS at Mn site depends on the volume.

The t_{2g} minority spin states are filled beyond Mn so that further additional 3d electrons are forced to enter the t_{2g} majority spin states and couple ferromagnetically to the host Fe atoms. It follows that from Mn to Cu the impurity magnetic moments are parallel to those of the host, whereas for Sc to Cr they are coupled antiparallel to the Fe host. The transition from antiferromagnetic to ferromagnetic coupling occurs when the VBS in the majority spin band crosses E_F , i.e., the majority spin d bands being occupied⁴⁶ (see Figs. 3 and 8).

The effects of 3d impurities on the electronic structures of Fe1, Fe2, and Fe3 atoms (not shown here) are generally that the minority spin e_g states at ~ 2.0 eV above E_F are not strongly affected by the 3d impurity atoms. The hybridization between X and the host Fe become important when the d bands of impurity atoms are more than half filled, e.g., see the Ni and Cu where the additional peaks at Fe1 are caused by the hybridization of the X impurities with the host Fe, through the location of the VBS.

TABLE II. Calculated site-projected local spin magnetic moments (in units of μ_B) of $X_1\text{Fe}_{26}$ inside each muffin-tin (MT) sphere with and without spin-orbit coupling (SOC). M is the total magnetization in units of T . The lower portion of the table shows the effect of SOC.

Site	Sc	Ti	V	Cr	Mn	Fe	Co	Ni	Cu	Zn
M	2.059	2.088	2.103	2.120	2.172	2.235	2.271	2.287	2.188	2.168
Without SOC										
X	-0.251	-0.628	-1.173	-1.727	0.440	2.237	1.802	0.999	0.150	-0.053
Fe1	2.160	2.194	2.244	2.288	2.266	2.237	2.387	2.463	2.360	2.311
Fe2	2.271	2.271	2.253	2.262	2.204	2.237	2.256	2.283	2.223	2.240
Fe3	2.207	2.234	2.261	2.300	2.263	2.237	2.261	2.301	2.266	2.276
With SOC										
Site	Sc	Ti	V	Cr	Mn	Fe	Co	Ni	Cu	Zn
M	2.056	2.083	2.101	2.116	2.173	2.234	2.268	2.283	2.186	2.164
X	-0.251	-0.628	-1.171	-1.723	0.470	2.235	1.797	0.996	0.151	-0.052
Fe1	2.156	2.189	2.242	2.285	2.264	2.235	2.382	2.458	2.357	2.306
Fe2	2.267	2.265	2.251	2.259	2.205	2.235	2.252	2.280	2.221	2.236
Fe3	2.203	2.229	2.258	2.295	2.262	2.235	2.259	2.298	2.263	2.272




FIG. 8. (Color online) Calculated spin-polarized impurity-site-projected local density of states of $X_1\text{Fe}_{26}$. The upper (lower) panels show majority (minority) spin states. Solid (dotted) lines show the t_{2g} (e_g) states, whereas for the Zn impurity at the left bottom the thin solid and dotted lines show the s and p states, which are multiplied by a factor 20. First (second) column shows early (late) transition metals. The Fermi levels (E_F) are set to zero.

The above mentioned facts can also be confirmed by using the calculated spin density contours. Representative cases (Cr, Mn, and Fe impurities in bcc Fe) are shown in Fig. 9. The interstitial regions are negatively polarized. The spin density contours of pure bcc Fe show considerable magnetic interaction with its first neighbor, Fe1 and one can also examine the interactions with Fe2 and Fe3 atoms. This magnetic interaction is not a surprise, because the distance between the Fe1 and Fe2 atoms and Fe2 and Fe3 atoms is the same, i.e., $\sqrt{3}a/2$. Very recently, such kinds of interactions were also observed even for monatomic bcc Fe, when examined in the (110) plane.⁴⁷




FIG. 9. Calculated spin density contour plots in the (110) plane for (a) Cr, (b) Mn, and (c) Fe impurities in bcc Fe. Solid lines represent the spin up whereas dotted lines represent the spin-down densities. The lowest contour starts from 2×10^{-4} electrons/a.u.³ and the subsequent lines differ by a factor $\sqrt{2}$. The Fe1, Fe2, and Fe3 atoms are also shown.

The spin density at Cr site is negatively polarized and the sign reversal of the local impurity moments was also observable at the Mn-Cu impurity sites, which show positive spin polarization and couple ferromagnetically to the host Fe. When the d bands of the impurity atom are filled, it not only affects the neighboring Fe atoms but also its local impurity magnetic moment, and this is the case of the Zn impurity which has a small negative spin polarization (not shown here), the sp diamagnetism.




FIG. 10. Calculated Fermi contact hyperfine fields (in units of kG) of the $3d$ impurities in bcc Fe. The filled circles represent the total hyperfine field. The open circles and triangles represent the valence and core contributions, respectively. The inset shows the variation of $B_{\text{hf}}^{\text{core}}$ and $B_{\text{hf}}^{\text{val}}$ with the local magnetic moment of the impurity atoms.

We did not find any significant effects of SOC on M as well as on the spin density contour plots in Fig. 9. The calculated M of pure bcc Fe is ~ 2.22 T and upon SOC, M is found to be 2.20 T. Table II shows that the effect of SOC is not very affective at the impurity sites but slightly affects m at the Fe1, Fe2, and Fe3 atoms. This feature is well understood by the concept of the orbital quenching, along with the fact of no significant Jahn-Teller distortion; i.e., the interatomic distortions of the neighboring Fe atoms are negligible.²⁰

D. Fermi contact hyperfine fields

The hyperfine fields in bcc iron are dominated by the Fermi contact term, which depends essentially on the s -electron spin density at the nucleus. Figure 10 shows both the core ($B_{\text{hf}}^{\text{core}}$) and valence ($B_{\text{hf}}^{\text{val}}$) state contributions to the fields. For the impurities considered, $B_{\text{hf}}^{\text{core}}$ and $B_{\text{hf}}^{\text{val}}$ are opposite in sign with magnitudes increasing from Sc to Cr and then decreasing from Co to Zn. As a consequence there is a change in sign for the total hyperfine field in going from Mn to Fe.

The trend of $B_{\text{hf}}^{\text{total}}$ is similar to that for the local impurity magnetic moments. Generally, $B_{\text{hf}}^{\text{core}}$ is proportional to the local impurity magnetic moment, as shown in the inset of Fig. 10, and its sign is negative for a parallel moment and vice versa, as seen in Fig. 10. This linear dependence is due to the exchange interaction of the polarized d shell with the s orbitals of the core. As a result, a weak s polarization is induced at the nuclear position, which is typically opposite to the local magnetic moment. Since the exchange interaction is weak, the core hyperfine field $B_{\text{hf}}^{\text{core}}$ is expected to scale with the local moment. The behavior of $B_{\text{hf}}^{\text{val}}$ is more complicated—it scales approximately with the local magnetic moments but in an opposite sense to $B_{\text{hf}}^{\text{core}}$. The two major contributions to $B_{\text{hf}}^{\text{val}}$ are (a) from the polarization of the outer s orbitals of the impurity by its own local moment




FIG. 11. Calculated Fermi contact hyperfine field changes ΔB_n normalized by the host Fermi contact hyperfine field B_{host} in the first, second, and third shells around the $3d$ impurities in bcc Fe. Here n represents the first, second, and third Fe atoms. The filled squares, triangles, and circles represent ΔB_1 , ΔB_3 , and ΔB_2 respectively, whereas open symbols represent the experimental values taken from Ref. 50.

and (b) polarization of valence electrons due to the magnetic moments of the neighboring atoms, which is usually proportional to the magnetic moment of the surrounding host atoms. The proportionality constants for the linear relationships described are the hyperfine coupling constants, calculated from Fig. 10 to be $C_{\text{core}} \sim -145$ kG/ μ_B and $C_{\text{val}} \sim 119$ kG/ μ_B . These values are comparable to the results reported for $3d$ impurities in Cr, Fe, and Ni hosts.^{48,49}

Figure 11 illustrates the changes, ΔB_1 , ΔB_2 , and ΔB_3 , in the Fermi contact hyperfine fields of the Fe1, Fe2, and Fe3 atoms, respectively, with the normalization by the host Fermi contact hyperfine field, B_{host} . Positive values imply that the hyperfine field of Fe n neighbor is smaller than that of the host and vice versa. The calculated ΔB_1 for Ni and Co are negative, in agreement with experiments,⁵⁰ whereas ΔB_1 is inconsistent with the calculations done by Dederichs *et al.*,⁵⁰ who found a zero value for ΔB_1 . This discrepancy is due to partly the different computational method. Our calculated GGA trend of ΔB_n can be compared with the experimental observations and the other previous calculations.⁵⁰

The B_{hf} results in Table III show that $B_{\text{hf}}^{\text{val}}$ of Fe1 is negative for all the $3d$ impurities except for Cr, and these positive quantities increase the transfer field of the Fe1 atoms through its proportionality to the magnetic moment of the surrounding atoms, i.e., the Fe1, Fe2, and Fe3 atoms. Hence, the transfer field of the Fe2 atom is smaller than that of the Fe1 atom and this supports the notion that the reduced M of bcc Fe alloyed with Cr and Mn is caused mainly by the Fe2 atoms.

Reported B_{hf} values for pure bcc Fe calculated using LSDA and GGA are, without SOC, -278 and -298 kG, respectively, and, with SOC, -253 and -276 kG, respectively.⁵¹ Our GGA result is -371 kG (and -364 kG with SOC), which is close to the experimental value of -339.0 kG.⁵² The somewhat larger values obtained here are consistent with FLAPW-LSDA value of -366.0 kG reported by Ohnishi.⁵³ Table III shows again that SOC does not sig-

TABLE III. Calculated Fermi contact hyperfine fields in units of kG. The left (right) column shows the Fermi contact field without (with) spin-orbit coupling (SOC).

Atom	Without SOC			With SOC		
	Total	Valence	Core	Total	Valence	Core
Sc	-164.2	-209.42	54.22	-163.9	-209.17	45.31
Fe1	-357.3	-41.95	-315.34	-356.3	-41.51	-314.82
Fe2	-346.6	-14.21	-332.35	-345.7	-13.93	-331.74
Fe3	-359.3	-36.44	-322.86	-358.3	-36.05	-322.23
Ti	-167.3	-267.54	100.21	-166.6	-266.98	104.41
Fe1	-348.4	-27.43	-320.93	-347.2	-26.96	-320.24
Fe2	-340.6	-8.84	-331.80	-339.6	-8.60	-331.01
Fe3	-360.9	-34.25	-326.66	-359.7	-33.90	-325.81
V	-164.9	-334.54	169.60	-164.2	-333.61	169.45
Fe1	-337.4	-8.86	-328.56	-336.4	-8.23	-328.14
Fe2	-334.9	-6.08	-328.83	-334.0	-5.54	-328.46
Fe3	-361.6	-30.95	-330.66	-360.5	-30.35	-330.17
Cr	-157.0	-395.25	238.25	-156.2	-394.07	237.84
Fe1	-326.3	8.21	-334.52	-325.1	8.98	-334.11
Fe2	-333.1	-3.51	-329.54	-332.1	-3.21	-328.91
Fe3	-363.0	-26.74	-336.28	-362.0	-26.42	-335.56
Mn	-269.2	-202.41	66.82	-269.7	-198.83	-70.90
Fe1	-334.5	-3.19	-331.29	-337.7	-2.73	-330.95
Fe2	-360.7	-38.69	-322.04	-360.0	-37.99	-322.03
Fe3	-363.1	-32.20	-330.87	-362.1	-31.43	-330.66
Fe	-362.0	-34.84	-327.12	-360.2	-33.48	-326.74
Fe1	-361.9	-35.01	-326.88	-360.3	-33.80	-326.53
Fe2	-361.8	-34.80	-327.03	-360.3	-33.79	-326.55
Fe3	-361.8	-44.74	-327.02	-360.3	-33.73	-326.61
Co	-394.4	-120.87	-273.52	-493.2	-120.45	-272.72
Fe1	-374.4	-25.19	-349.26	-373.7	-25.18	-348.53
Fe2	-358.2	-28.75	-329.44	-354.4	-28.58	-328.86
Fe3	-366.4	-35.65	-330.75	-365.7	-35.46	-330.24
Ni	-389.0	-225.99	-163.02	-387.4	-225.01	-162.38
Fe1	-375.7	-15.49	-360.25	-374.8	-15.29	-359.48
Fe2	-359.0	-26.40	-332.65	-358.1	-25.89	-332.17
Fe3	-370.2	-33.71	-336.48	-369.1	-33.13	-335.96
Cu	-321.3	-284.25	-37.01	-321.1	-284.00	-37.07
Fe1	-366.2	-20.74	-345.44	-365.9	-20.79	-345.11
Fe2	-374.6	-49.30	-325.24	-374.2	-49.33	-324.88
Fe3	-361.9	-30.76	-331.13	-361.6	-30.76	-330.81
Zn	-304.2	-297.77	-6.48	-303.3	-296.85	-6.46
Fe1	-363.1	-24.89	-338.23	-362.1	-24.56	-337.55
Fe2	-374.4	-46.13	-328.23	-373.4	-45.81	-327.62
Fe3	-362.9	-29.95	-332.96	-362.0	-29.67	-332.34

nificantly affect the calculations because of the localization of the impurity.

Finally, some test calculations were also carried out for big and small supercells of $\text{Fe}_{52}\text{Ni}_2$ and Fe_{15}Ni and the local properties around Ni were similar to Fe_{26}Ni . This indicates that $3 \times 3 \times 3$ supercell of the primitive bcc cell as discussed

in Sec. II is sufficient for 3.7 at.% impurities in bcc Fe but may not be sufficient for the other host, e.g., bcc Cr.⁴⁸

IV. SUMMARY

The magnetism and electronic structures of $3d$ impurities in body-centered iron have been investigated in terms of the

FLAPW method based on the generalized gradient approximation. The results compare favorably with existing experimental data and have been contrasted with published calculations where available.

The lattice parameters were optimized and it is shown that the lattice constant decreases with the atomic number of the impurity X (Sc-Fe), whereas it increases for Co-Zn. The calculated formation energy results are in good agreement with the alloying experiences in steels design. It is found that iron induces a magnetic moment at the Sc, Ti, V, Cu, and Zn atoms substituted into the iron lattice; Sc, Ti, V, Cr, and Zn couple antiferromagnetically with iron, resulting in an overall reduction in the saturation magnetization relative to pure iron. In contrast, Co and Ni couple ferromagnetically with iron and resulting in increase in saturation magnetization. The trend of the atom averaged magnetic moment versus effective atomic number is shown to lie on the left branch of the well-known Slater-Pauling curve, but it is not simply linear—the deviation from the standard Slater-Pauling curve is attributed by the nature of the weak ferromagnetism of bcc iron. These results have been interpreted by examining in detail the local density of states, near neighbor interactions, and other features of the electronic structure of the alloys resulting from the substitution of impurity atoms into iron.

An important outcome is that calculations of the type reported here are not significantly influenced by spin-orbit cou-

pling. The calculated Fermi contact hyperfine fields also support this conclusion. In the light of previous theoretical calculations, where LSDA was used our calculations showed that although LSDA cannot describe the correct magnetic properties of bcc Fe, but can describe the correct magnetic properties (qualitatively) of bcc Fe because our GGA results are close to the previous LSDA results. Comparing the LSDA and GGA, we showed that the GGA results are closer to the experimental data.

ACKNOWLEDGMENTS

This work was supported by the Steel Innovation Program by POSCO, the WCU (World Class University) program (Project No. R32-2008-000-10147-0), and the Basic Science Research Program (Grant No. 2009-0088216) through the National Research Foundation funded by the Ministry of Education, Science and Technology of Republic of Korea. The present work was also funded by office of Scientific Research (Grant No. FA9550-07-1-0013) and in part by the U.S. Air Force. We are grateful to Hae-Geon Lee for the provision of laboratory facilities at POSTECH. Finally, I.G.K. thanks Sam Kyu Chang for encouraging the initiation of this work.

*Corresponding author; igkim@postech.ac.kr

- ¹L.-G. Liu and W. A. Basset, *J. Geophys. Res.* **80**, 3777 (1975).
- ²H. Hasegawa and D. G. Pettifor, *Phys. Rev. Lett.* **50**, 130 (1983).
- ³J. H. Park, S. K. Kwon, B. I. Min, and H. S. Cho, *J. Korean Phys. Soc.* **37**, 109 (2000).
- ⁴M. Uhl, L. M. Sandratskii, and J. Kübler, *J. Magn. Magn. Mater.* **103**, 314 (1992).
- ⁵V. M. García-Suárez, C. J. Lambert, J. M. Pruneda, and J. Ferrer, *J. Phys.: Condens. Matter* **16**, 5453 (2004).
- ⁶Z.-Y. Zeng, C.-E. Hu, X.-R. Chen, L.-C. Cai, and F.-Q. Jing, *J. Phys.: Condens. Matter* **20**, 425217 (2008).
- ⁷H. Akai, M. Akai, and J. Kanamori, *J. Phys. Soc. Jpn.* **54**, 4257 (1985).
- ⁸V. I. Anisimov, V. P. Antropov, A. I. Liechtenstein, V. A. Gubanov, and A. V. Postnikov, *Phys. Rev. B* **37**, 5598 (1988).
- ⁹H. J. F. Jansen, K. B. Hathaway, and A. J. Freeman, *Phys. Rev. B* **30**, 6177 (1984).
- ¹⁰C. S. Wang, B. M. Klein, and H. Krakauer, *Phys. Rev. Lett.* **54**, 1852 (1985).
- ¹¹E. Wimmer, H. Krakauer, M. Weinert, and A. J. Freeman, *Phys. Rev. B* **24**, 864 (1981), and references therein; M. Weinert, E. Wimmer, and A. J. Freeman, *ibid.* **26**, 4571 (1982).
- ¹²J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996); **78**, 1396(E) (1997).
- ¹³P. Hohenberg and W. Kohn, *Phys. Rev.* **136**, B864 (1964); W. Kohn and L. J. Sham, *ibid.* **140**, A1133 (1965).
- ¹⁴J.-H. Lee, T. Shishidou, and A. J. Freeman, *Phys. Rev. B* **66**, 233102 (2002).
- ¹⁵D. D. Koelling and B. N. Harmon, *J. Phys. C* **10**, 3107 (1977).
- ¹⁶R. Wu, D. Wang, and A. J. Freeman, *J. Magn. Magn. Mater.* **132**, 103 (1994).
- ¹⁷M. Weinert, G. Schneider, R. Podloucky, and J. Redinger, *J. Phys.: Condens. Matter* **21**, 084201 (2009).
- ¹⁸F. Birch, *Phys. Rev.* **71**, 809 (1947); F. D. Murnaghan, *Proc. Natl. Acad. Sci. U.S.A.* **30**, 244 (1944).
- ¹⁹S.-W. Seo, Y.-Y. Song, G. Rahman, I. G. Kim, M. Weinert, and A. J. Freeman, *J. Magn.* **14**, 137 (2009).
- ²⁰C. Kittel, *Introduction to Solid State Physics*, 7th ed. (Wiley, New York, 1996).
- ²¹O. L. Andersen, in *Physical Acoustics*, edited by W. P. Mason (Academic, New York, 1965), Vol. III-B, pp. 77–95.
- ²²H. K. D. H. Bhadeshia and R. W. K. Honeycombe, *Steels: Microstructure and Properties*, 3rd ed. (Elsevier, Amsterdam, 2006), Chap. 4.
- ²³J. Kübler, *Theory of Itinerant Electron Magnetism* (Oxford, New York, 2000).
- ²⁴V. A. Gubanov, A. L. Liechtenstein, and A. V. Postnikov, *Magnetism and the Electronic Structure of Crystals* (Springer, Berlin, 1992).
- ²⁵T. Beuerle, K. Hummler, C. Elsässer, and M. Fähnle, *Phys. Rev. B* **49**, 8802 (1994).
- ²⁶H. R. Child and J. W. Cable, *Phys. Rev. B* **13**, 227 (1976).
- ²⁷F. Kajzar and G. Parette, *Phys. Rev. B* **22**, 5471 (1980).
- ²⁸A. T. Aldred, B. D. Rainford, J. S. Kouvel, and T. J. Hicks, *Phys. Rev. B* **14**, 228 (1976).
- ²⁹M. F. Collins and J. B. Forsyth, *Philos. Mag.* **8**, 401 (1963).
- ³⁰J. Crangle and G. C. Hallam, *Proc. R. Soc. London, Ser. A* **272**, 119 (1963).
- ³¹F. Kajzar and G. Parette, *J. Appl. Phys.* **50**, 1966 (1979).

- ³²M. F. Collins and G. G. Low, *Proc. Phys. Soc. London* **86**, 535 (1965).
- ³³P. Radhakrishna and F. Livet, *Solid State Commun.* **25**, 597 (1978).
- ³⁴H. Akai, M. Akai, S. Blügel, R. Zeller, and P. H. Dederichs, *J. Magn. Magn. Mater.* **45**, 291 (1984).
- ³⁵C. Koenig and E. Daniel, *J. Phys. (Paris)* **42**, 1015 (1981).
- ³⁶K. Nakamura, T. Ito, A. J. Freeman, L. Zhong, and J. Fernandez-de-Castro, *Phys. Rev. B* **67**, 014405 (2003).
- ³⁷T. Mashimo, X. Huang, X. Fan, K. Koyama, and M. Motokawa, *Phys. Rev. B* **66**, 132407 (2002).
- ³⁸G. Rahman and I. G. Kim, *J. Magn.* **13**, 124 (2008).
- ³⁹A. T. Aldred, *J. Phys. C* **1**, 244 (1968).
- ⁴⁰M. V. Nevitt and A. T. Aldred, *J. Appl. Phys.* **34**, 463 (1963).
- ⁴¹C. Paduani, E. Galvão da Silva, and G. A. Perez-Alcazar, *J. Appl. Phys.* **70**, 7524 (1991).
- ⁴²D. I. Bardos, *J. Appl. Phys.* **40**, 1371 (1969).
- ⁴³J. C. Slater, *Phys. Rev.* **49**, 537 (1936).
- ⁴⁴L. Pauling, *Phys. Rev.* **54**, 899 (1938).
- ⁴⁵P. Mohan, *Magnetism in the Solid State* (Springer, Berlin, 2003).
- ⁴⁶J. Friedel, *Nuovo Cimento* **7**, 287 (1958).
- ⁴⁷T. E. Jones, M. E. Eberhart, and D. P. Clougherty, *Phys. Rev. Lett.* **100**, 017208 (2008).
- ⁴⁸S. N. Mishra, *Phys. Rev. B* **77**, 224402 (2008).
- ⁴⁹H. Akai, M. Akai, S. Blügel, B. Drittler, H. Ebert, K. Terakura, R. Zeller, and P. H. Dederichs, *Prog. Theor. Phys. Suppl.* **101**, 11 (1990).
- ⁵⁰P. H. Dederichs, B. Drittler, R. Zeller, H. Ebert, and M. Weinert, *Hyperfine Interact.* **60**, 547 (1990) and references therein.
- ⁵¹C. O. Rodriguez, M. V. Ganduglia-Pirovano, E. L. Peltzer y Blancá, M. Petersen, and P. Novák, *Phys. Rev. B* **63**, 184413 (2001).
- ⁵²J. I. Budnick, L. J. Bruner, R. J. Blume, and E. L. Boyd, *J. Appl. Phys. Suppl.* **32**, 120S (1961).
- ⁵³S. Ohnishi, A. J. Freeman, and M. Weinert, *Phys. Rev. B* **28**, 6741 (1983).