# Physical and magnetic properties of $Ba(Fe_{1-x}Ru_x)_2As_2$ single crystals

A. Thaler, N. Ni, A. Kracher, J. Q. Yan, S. L. Bud'ko, and P. C. Canfield

Ames Laboratory and Department of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, USA

(Received 16 June 2010; revised manuscript received 13 July 2010; published 30 July 2010)

Single crystals of Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>, x < 0.37, have been grown and characterized by structural, magnetic, and transport measurements. These measurements show that the structural/magnetic phase transition found in pure BaFe<sub>2</sub>As<sub>2</sub> at 134 K is suppressed monotonically by Ru doping but, unlike doping with TM=Co, Ni, Cu, Rh, or Pd, the coupled transition seen in the parent compound does not detectably split into two separate ones. Superconductivity is stabilized at low temperatures for x > 0.2 and continues through the highest doping levels we report. The superconducting region is domelike, with maximum  $T_c(\sim 16.5 \text{ K})$  found around  $x \sim 0.29$ . A phase diagram of temperature versus doping, based on electrical transport and magnetization measurements, has been constructed and compared to those of the Ba(Fe<sub>1-x</sub> $TM_x$ )<sub>2</sub>As<sub>2</sub> (TM=Co, Ni, Rh, and Pd) series as well as to the temperature-pressure phase diagram for pure BaFe<sub>2</sub>As<sub>2</sub>. Suppression of the structural/magnetic phase transition as well as the appearance of superconductivity is much more gradual in Ru doping, as compared to Co, Ni, Rh, and Pd doping, and appears to have more in common with BaFe<sub>2</sub>As<sub>2</sub> tuned with pressure; by plotting  $T_S/T_m$  and  $T_c$  as a function of changes in unit-cell dimensions, we find that changes in the c/a ratio, rather than changes in c, a, or V, unify the T(p) and T(x) phase diagrams for BaFe<sub>2</sub>As<sub>2</sub> and Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>, respectively.

DOI: 10.1103/PhysRevB.82.014534

PACS number(s): 74.10.+v, 74.25.Dw, 74.62.Bf, 74.62.Dh

## I. INTRODUCTION

The discovery of superconductivity in F-doped LaFeAsO (Ref. 1) and K-doped BaFe<sub>2</sub>As<sub>2</sub> (Ref. 2) in 2008 led to extensive interest in these families of FeAs-based compounds. The superconducting critical temperature,  $T_c$ , has risen as high as 56 K for F-doped RFeAsO (Ref. 3) and as high as 38 K in K- and Na-doped  $AEFe_2As_2$  systems (AE=Ba, Sr, and Ca).<sup>2</sup> Superconductivity was also found in Co-doped AEFe<sub>2</sub>As<sub>2</sub> (Ref. 4) and RFeAsO.<sup>5</sup> More recently, superconductivity has been found in other 3d, 4d, and 5d transition metal, electron-doped BaFe<sub>2</sub>As<sub>2</sub> systems,<sup>6-14</sup> as well as SrFe<sub>2</sub>As<sub>2</sub> and CaFe<sub>2</sub>As<sub>2</sub>. Although the electron doped  $AEFe_2As_2$  systems have lower  $T_c$  values than the hole-doped ones,<sup>10-14</sup> they have been studied extensively because doping is more homogeneous in these systems and single crystals can be more easily and reproducibly grown. In order to understand the conditions for superconductivity in these systems, temperature versus doping phase diagrams must first be constructed. Detailed studies have been made for TM-doped BaFe<sub>2</sub>As<sub>2</sub> (TM=Co, Ni, Cu, Rh, Pd, Pt, and Ir).<sup>6,10–16</sup> For Co, Ni, Cu, Rh, and Pd, temperature vs doping concentration, x, and temperature vs electron count, e, phase diagrams show similar properties, with the temperature of the structural/magnetic transition,  $T_S/T_m$ , seen in the parent compound being suppressed and separated in a similar manner with x, and  $T_c$  evolving in a similar manner with e, especially on the overdoped side of the superconducting dome.<sup>6,10,14,17</sup> Although TM doping of the  $BaFe_2As_2$  system is convenient-providing large homogeneous crystals-it is not unique in tuning  $T_S/T_m$  and  $T_c$ . Pressure can also be used to suppress  $T_S/T_m$  and stabilize a low-temperature superconducting state.<sup>18-20</sup>

In contrast with its 4*d* neighbors Rh and Pd, Ru doping provides no extra electrons to the bands. However, recent polycrystalline studies in both the  $SrFe_2As_2$  (Refs. 21 and

22) and BaFe<sub>2</sub>As<sub>2</sub> (Ref. 7) systems show that Ru substitution on the Fe site suppresses the structural/magnetic phase transition and leads to superconductivity, indicating that this system may allow a direct comparison of nominally isovalent doping and electron doping TM substitution as well as pressure studies. Isovalent doping induced superconductivity, as pressure before it, indicates that whereas x and e are important parameters in parametrizing the phase transitions in these systems, changes in the unit-cell parameter may be important as well.

Based on this, we have studied Ru-doped  $BaFe_2As_2$  single crystals in order to compare the effects of isoelectronic doping to 3d and 4d transition metal, electron-doped compounds. As we wrote this work up, a similar, complimentary, study was posted;<sup>23,24</sup> comparison to these data will be made as well.

#### **II. EXPERIMENTAL METHODS**

Single crystals of  $Ba(Fe_{1-x}Ru_x)_2As_2$  were grown out of self-flux using conventional high-temperature solution growth techniques.<sup>10,25</sup> FeAs and RuAs were synthesized in the same manner as in Ref. 10. Small Ba chunks and FeAs/ RuAs powder were mixed together in a ratio of Ba: TMAs =1:4. The mixture was then placed in an alumina crucible with a "catch" crucible filled with quartz wool placed on top. Both crucibles were sealed in a silica tube under 1/6 atmosphere of Ar gas. The sealed tube was heated up to 1180 °C over 12 h, held at 1180 °C for 8-12 h and then cooled over 45-65 h. The final temperature varied between 1050 and 1100 °C, increasing with the Ru-doping level. Once the furnace reached the final temperature, the excess FeAs/RuAs liquid was decanted, leaving the single crystals behind. Unfortunately, this increasing decanting temperature made doping levels above x=0.37 difficult to produce.

$Ba(Fe_{1-x}Ru_x)_2As_2$											
Ν	14	16	12	12	11	19	18	13	14	15	25
<i>x<sub>nominal</sub></i>	0.05	0.1	0.125	0.15	0.175	0.2	0.225	0.25	0.265	0.27	0.3
$x_{\rm WDS}$	0.021	0.048	0.073	0.092	0.126	0.161	0.210	0.24	0.29	0.29	0.36
$2\sigma$	0.001	0.001	0.001	0.003	0.003	0.005	0.013	0.05	0.05	0.05	0.05

TABLE I. WDS data for Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>. N is the number of points measured in each batch,  $x_{WDS}$  is the average x value for that batch, and  $2\sigma$  is twice the standard deviation of the N values measured.

Powder x-ray diffraction (XRD) measurements with a Si standard, were performed using a Rigaku Miniflex diffractometer with Cu  $K\alpha$  radiation at room temperature. Diffraction patterns were taken on ground single crystals from each batch. Only very small FeAs impurity peaks were found as a secondary phase. The unit-cell parameters were refined by "RIETICA" software. Elemental analysis of single-crystal samples was used to determine the actual percentage of the dopant in the lattice as opposed to the nominal doping level. This was performed using wavelength dispersive x-ray spectroscopy (WDS) in a JEOL JXA-8200 electron microprobe. Magnetization data were collected in a Quantum Design (QD) Magnetic Properties Measurement System (MPMS). Temperature-dependent ac electrical resistance data (f=16 Hz, I=3 mA) was collected using either a QD MPMS with a LR700 resistance bridge or a QD Physical Properties Measurement System (PPMS). Electrical contact was made to the sample using Epotek H20E silver epoxy to attach Pt wires in a four-probe configuration.

### **III. RESULTS**

A summary of the WDS measurement data is presented in Table I. For each batch, between 1 and 5 crystal surfaces were measured. The table shows the number of points measured, the nominal x value measured, the average x value, and two times the standard deviation of the x values measured.



FIG. 1. Experimentally determined Ru concentration,  $x_{\text{WDS}}$ , vs nominal Ru concentration. Error bars are  $\pm 2\sigma$  (values from Table I).

sured. All x values given in this paper are the average  $x_{WDS}$  values determined by WDS. Figure 1 shows the measured vs nominal Ru concentration, as well as the error bars on the measured values. For  $x_{WDS} \le 0.21$  the variation in Ru content within a batch is small, in the range of 1-5 % of the x value. Such variation is similar to what is found for other 3*d*- and 4*d*-doping series.<sup>6,10,14,17</sup> For  $x \ge 0.24$  there is a sudden and rather dramatic increase in the variation in the Ru concentration within a single batch (and even a single sample). It is not clear what the origin of the change in homogeneity is but it is also noted, in a qualitative manner, in Ref. 23 as well.

Powder x-ray diffraction measurements confirm that  $Ba(Fe_{1-x}Ru_x)_2As_2$  forms in the I4/mmm,  $ThCr_2Si_2$  structure and that impurities are minimal (Fig. 2). Rietveld refinement of the XRD data gives the *a* and *c* lattice parameters, which are plotted, along with the unit-cell volume, as a function of  $x_{WDS}$  in Fig. 3.

Figure 4 shows the normalized electrical resistance data of the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> series from 5 to 300 K. Normalized resistance is plotted instead of resistivity because of the tendency of these samples to exfoliate or crack.<sup>10,26,27</sup> The anomaly in normalized resistance at 134 K for pure BaFe<sub>2</sub>As<sub>2</sub> is associated with a first-order phase transition into an orthorhombic antiferromagnetic state.<sup>28</sup> As in the case of Co, Ni, Cu, Rh, and Pd substitution,<sup>6,10,14,17</sup> the temperature of the resistive anomaly is suppressed monotonically and the shape is changed from the sharp loss of resistance on cooling



FIG. 2. Powder x-ray pattern for Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>, x=0.073, with Si standard. Open symbols are measured data, closed ones are fit, the line shows the difference.  $\times$ , |, and + symbols are calculated peak positions for Si, FeAs, and the sample.



FIG. 3. (Color online) Lattice parameters for Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>, compared to BaFe<sub>2</sub>As<sub>2</sub>, for which  $a_0=3.96$  Å,  $c_0=13.0$  Å, and  $V_0=204$  Å<sup>3</sup>. The slopes are  $a/a_0:(3.7\pm0.1)\times10^{-4}/\text{Ru}$  atom,  $c/c_0:(-4.9\pm0.1)\times10^{-4}/\text{Ru}$  atom, and  $V/V_0:(2.4\pm0.2)\times10^{-4}/\text{Ru}$  atom. The trend lines are determined by a least-squares fit. The error in the slope is the standard error from this fit.

through  $T_S/T_m$  seen in pure BaFe<sub>2</sub>As<sub>2</sub> to a broader increase in resistance on cooling through  $T_S/T_m$  for intermediate xvalues. For  $x \ge 0.29$ , anomalies associated with  $T_S/T_m$  are no longer detectable. Superconductivity begins to appear above x=0.161 (resistive onset only) and is fully manifested (R=0) by x=0.210. A maximum  $T_c$  of 16.5 K is achieved at  $x \approx 0.29$ .  $T_c$  is suppressed for higher values of x. The superconducting transition is quite broad compared to other TMdopings: more than 7 K wide for  $x_{WDS}=0.210$  compared with a 3 K width for a Co-doping level of x=0.038.<sup>10</sup> Such a wide transition is more typical of pressure induced superconductivity rather than chemical doping.<sup>20</sup>

Figure 5(a) shows high-field (H=70 kOe) M/H data for representative members of the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> series. At high temperatures the M(T)/H ratio is roughly linear and



FIG. 4. (Color online) Temperature-dependent resistance, normalized to the room-temperature value, for select  $Ba(Fe_{1-x}Ru_x)_2As_2$ doping levels. Inset shows low-temperature behavior.



FIG. 5. (Color online) (a) Temperature-dependent magnetization, scaled by applied field H=70 kOe, for Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>. (b) Low-temperature, low-field, zero-field cooled and field-cooled magnetization for several superconducting members of the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> family.  $H \perp c$  for all data sets. The relatively large, low temperature, diamagnetic shielding in the zero-field cooled measurements approaches that found for Co, Ni, Rh, and Pd doping (Refs. 6, 10, 14, and 17).

decreases with decreasing temperature with a slope that decreases with increasing Ru doping. As with normalized resistance, the magnetization of the parent compound manifests a clear change at 134 K, correlated with the structural/magnetic phase transition.<sup>28</sup> As x is increased up to x = 0.126, this transition is suppressed and broadened without qualitative change. Starting with x=0.161 the transition becomes much flatter and broader, and by x=0.24 it is barely visible. At x=0.29 it has completely vanished.

Figure 5(b) shows the low-field (50 Oe) M/H data for the superconducting members of the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> series. These samples show a clear diamagnetic signal in the zero-field cooled (ZFC) data, as well as some Meissner expulsion. It is worth noting that whereas the ZFC diamagnetic signal for Co, Ni, Rh, Pd, and Cu/Co dopings are all similar and close to  $-1/4\pi$ , <sup>6,10,14,17,29</sup> the low-temperature values for Ru doping [Fig. 5(b)] are smaller in amplitude and vary more.



FIG. 6. (Color online) (a) Magnetization and (b) normalized resistance, along with derivatives, for Ba $(Fe_{1-x}Ru_x)_2As_2(x=0.073)$ . Vertical arrows show the criteria for determination of the transition temperature. (c) shows normalized resistance derivative data for Co doping (x=0.024) and Rh doping (x=0.012) with similar transition temperatures.

### **IV. DISCUSSION**

Figures 6 and 7 show normalized resistance and magnetization data, along with their derivatives, for x=0.073 and x=0.16 samples, respectively. These figures show the criteria used for determining the structural/magnetic phase-transition temperatures for these materials.

Figures 6(c) and 7(c) show comparisons of normalized resistance derivatives for Ru-, Co-, and Rh-doped BaFe<sub>2</sub>As<sub>2</sub> with similar  $T_S/T_m$  values. In the Co and Rh series, a clear splitting of the two transitions is visible. (At the same temperatures, the derivatives of magnetization and heat capacity show split features as well.<sup>6,10,14,17</sup>) By contrast, we do not see these separated features in the derivatives of the normalized resistance from the Ru system. These features have been shown to correspond to a splitting of the joint transition into two transitions, one structural the other magnetic.<sup>6,14,16,17,30</sup> Although the authors of Ref. 23 claim to see a split transition, it appears to be a subtle feature compared to Co or Rh data. The single feature in the Ru-doped series dR/dT data suggests that either the splitting is much smaller, or absent, in this system or that the resistive feature associated with  $T_S$ is much weaker in this system. It is possible that the splitting is caused by the extra electrons provided by other TM doping (e.g., Co, Ni, Cu, Rh, and Pd).

Onset and offset criteria were used to determine  $T_c$  from this resistance data.  $T_c$  was determined from the magnetization data by extrapolating the maximum slope of the ZFC data back to the normal state. There is fair agreement be-



FIG. 7. (Color online) (a) Magnetization and (b) normalized resistance, along with derivatives, for  $Ba(Fe_{1-x}Ru_x)_2As_2(x=0.16)$ . Vertical arrows show the criteria for determination of the transition temperature. (c) shows normalized resistance derivative data for Co doping (x=0.038) and Rh doping (x=0.039) with similar transition temperatures.

tween  $T_c^{offset}$  determined from normalized resistance and  $T_c$  determined from magnetization. It should be noted, though, that (i) superconductivity primarily occurs in the region where the spread in  $x_{\text{WDS}}$  is large and (ii) the superconducting transition is broad in R(T) and both ZFC and field cooled Meissner data are somewhat lower than for other *TM*-doped series.

Using these criteria, the data presented in Figs. 4 and 5 are summarized in a *T*-*x* phase diagram shown in Fig. 8. Overall, the phase diagram for the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> series is qualitatively quite similar to that of the Co, Ni, Rh, and Pd diagrams: increasing *x* suppresses the structural/magnetic phase transition, a superconducting dome appears above some critical *x* value and this dome has a maximum near the point where  $T_S/T_m$  extrapolates to zero. However, there is a key difference: suppression of  $T_S/T_m$  is much slower than for other *TM* dopings (Co, Ni, Cu, Rh, and Pd).<sup>6,10,14,17,29</sup> In previous comparisons of 3*d* and 4*d TM* dopings,<sup>6,14,17</sup> we showed that suppression of  $T_S/T_m$  occurs at roughly the same rate regardless of differences in size and electron count between dopants; the suppression of  $T_S/T_m$  in Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> is about three times slower.

As in the case of Rh- and Pd-doped BaFe<sub>2</sub>As<sub>2</sub>,<sup>6</sup> with Ru doping the *c*-lattice parameter shrinks compared to the parent BaFe<sub>2</sub>As<sub>2</sub> while the *a*-lattice parameter and the unit-cell volume, *V*, grow. (This is in contrast to the 3*d* TM dopings, where all three shrink with increasing *x*.) By way of comparison: a Ru-doping level of  $x_{WDS}$ =0.175 has a=1.002 $a_0$  and c=0.995 $c_0$ , and a Rh doping level of x=0.171 has *a* 



FIG. 8. (Color online) x dependent phase diagram, showing T for salient features in Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub>.

=1.007 $a_0$  and c=0.988 $c_0$ .<sup>6</sup> Because the crystallographic trends of all three 4*d* TM dopant series (Ru, Rh, and Pd) are similar, the major differences in their T-x phase diagrams suggest that steric effects alone are not enough to explain the differences in behavior of this system with doping (i.e., the extra electrons in Rh and Pd are responsible for the much more rapid effects of doping).

Although the maximum superconducting critical temperature,  $T_c^{max}$ , is significantly lower in the Ru-doped system, there is a clear similarity between the Ru-doped *T*-*x* phase diagram and the pressure dependent, *T*-*p*, phase diagram of the parent BaFe<sub>2</sub>As<sub>2</sub> compound,<sup>20</sup> as can be seen in Fig. 9. The similarity of the phase diagrams suggests that changes in the unit-cell dimensions may be playing a large role in determining the superconducting behavior with the effects of Ru substitution in this system being similar to physical pressure in the undoped BaFe<sub>2</sub>As<sub>2</sub> system. The difference in  $T_c^{max}$ is most likely caused by the Ru dopant disordering the Fe plane whereas pressure induces no such distortion.

Whereas the agreement between the T-x and T-p phase diagrams in Fig. 9 is good, the scaling between x and p was



FIG. 9. (Color online) Comparison of Ru-doping phase diagram with that of the parent  $BaFe_2As_2$  compound under applied pressure.



FIG. 10. (Color online) Phase diagrams of  $Ba(Fe_{1-x}Ru_x)_2As_2$ and of parent  $BaFe_2As_2$  under pressure, scaled by lattice parameters. (a) is scaled by  $\Delta c/c_0$ . (b) is scaled by  $\Delta (c/c_0)/(a/a_0)$ .

arbitrarily chosen to optimize the overlap of the two data sets. Using our data on the x-dependence of the unit-cell parameters (Fig. 3) in combination with the data from Ref. 31 on the pressure dependence of the unit-cell parameters of BaFe<sub>2</sub>As<sub>2</sub>, we can make this comparison more quantitative. Of the four combinations of the unit-cell parameters: a, c, V, and c/a, only c and c/a show similar responses to pressure and doping; a and V both increase with doping whereas they decrease with p. Figures 10(a) and 10(b) present our Rudoping data as well as the pressure data from Ref. 20 plotted as functions of the changes in c and c/a. A comparison of these two figures clearly indicates that c/a rather than c better parametrizes the effects of doping and pressure. This result means that, based on these two isoelectronic perturbations (pressure and Ru doping), changes in the c/a ratio appear to be more physically important than changes in calone.

The other isoelectronic substitution which produces superconductivity in BaFe<sub>2</sub>As<sub>2</sub> is P doping on the As site.<sup>32,33</sup> Although the maximum  $T_c$  in the BaFe<sub>2</sub>(As<sub>1-x</sub>P<sub>x</sub>)<sub>2</sub> system is quite a bit higher than in the Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> system (~30 K), several key properties are similar.  $T_S/T_m$  is suppressed in a relatively gradual manner and the maximum  $T_c$ 

value occurs at a comparably high doping level ( $x_{Ru} = 0.29$ ,  $x_P = 0.32$ ) and extends over a much wider range than in any of the electron doped *TM* series.<sup>32,33</sup> Furthermore, both Ru doping and underdoping of P produce wider transitions than other *TM* dopings (e.g., Co, Ni, Rh, and Pd).<sup>6,10,33,34</sup> On the other hand, taking changes in *c* and *a* with P doping into account,  $T_S/T_m$  and  $T_c$  for P-doped and Ru-doped BaFe<sub>2</sub>As<sub>2</sub> scale better with changes in *c* than with changes in *c*/*a*.<sup>33</sup> This means that, if we include P doping as a third isoelectronic perturbation, then neither changes in *c* nor *c*/*a* universally describe the *T*-*x* and *T*-*p* phase diagrams.

### V. SUMMARY

Single crystals of Ba(Fe<sub>1-x</sub>Ru<sub>x</sub>)<sub>2</sub>As<sub>2</sub> can be grown for x < 0.37, although Ru homogeneity becomes less well controlled for x > 0.21. The structural and magnetic phase-transition temperature,  $T_S/T_m$ , is suppressed as x increases but does not clearly split, as it does for TM=Co, Ni, Cu, Rh,

and Pd doping. As  $T_S/T_m$  is suppressed superconductivity appears, reaching a maximum  $T_c$  value of 16.5 K for x = 0.29, near the point that  $T_S/T_m$  extrapolates to T=0 K. Whereas the suppression of  $T_S/T_m$  and the stabilization of  $T_c$ occur at a much slower rate for Ru doping than they do for doping with TM=Co, Ni, Cu, Rh, or Pd, indicating that the additional electrons brought by these dopants play a significant role in tuning of this system, there is a remarkable agreement between two isoelectronic phase diagrams (Ru doping and pressure) of BaFe<sub>2</sub>As<sub>2</sub> when plotted as T(c/a)but not when plotted as T(c).

### ACKNOWLEDGMENTS

Work at the Ames Laboratory was supported by the Department of Energy, Basic Energy Sciences under Contract No. DE-AC02-07CH11358. We would like to thank E. D. Mun, S. Kim, X. Lin, R. Gordon, R. Fernandes, A. Kreyssig, R. Roggers, and J. Brgoch for help and useful discussions.

- <sup>1</sup>Y. Kamihara, T. Watanabe, M. Hirano, and H. Hosono, J. Am. Chem. Soc. **130**, 3296 (2008).
- <sup>2</sup>M. Rotter, M. Tegel, and D. Johrendt, Phys. Rev. Lett. **101**, 107006 (2008).
- <sup>3</sup>R. Zhi-An, L. Wei, Y. Jie, Y. Wei, S. Xiao-Li, Zheng-Cai, C. Guang-Can, D. Xiao-Li, S. Li-Ling, Z. Fang, and Z. Zhong-Xian, Chin. Phys. Lett. **25**, 2215 (2008).
- <sup>4</sup>A. S. Sefat, R. Jin, M. A. McGuire, B. C. Sales, D. J. Singh, and D. Mandrus, Phys. Rev. Lett. **101**, 117004 (2008).
- <sup>5</sup>A. S. Sefat, A. Huq, M. A. McGuire, R. Jin, B. C. Sales, D. Mandrus, L. M. D. Cranswick, P. W. Stephens, and K. H. Stone, Phys. Rev. B 78, 104505 (2008).
- <sup>6</sup>N. Ni, A. Thaler, A. Kracher, J. Q. Yan, S. L. Bud'ko, and P. C. Canfield, Phys. Rev. B **80**, 024511 (2009).
- <sup>7</sup>S. Sharma, A. Bharathi, S. Chandra, V. R. Reddy, S. Paulraj, A. T. Satya, V. S. Sastry, A. Gupta, and C. S. Sundar, Phys. Rev. B 81, 174512 (2010).
- <sup>8</sup>X. L. Wang, H. Y. Shi, X. W. Yan, Y. C. Yuan, Z.-Y. Lu, X. Q. Wang, and T.-S. Zhao, Appl. Phys. Lett. **96**, 012507 (2010).
- <sup>9</sup>S. R. Saha, T. Drye, K. Kirshenbaum, N. P. Butch, P. Y. Zavalij, and J. Paglione, J. Phys.: Condens. Matter **22**, 072204 (2010).
- <sup>10</sup>N. Ni, M. E. Tillman, J.-Q. Yan, A. Kracher, S. T. Hannahs, S. L. Bud'ko, and P. C. Canfield, Phys. Rev. B 78, 214515 (2008).
- <sup>11</sup>J.-H. Chu, J. G. Analytis, C. Kucharczyk, and I. R. Fisher, Phys. Rev. B **79**, 014506 (2009).
- <sup>12</sup>F. Ning, K. Ahilan, T. Imai, A. S. Sefat, R. Jin, M. A. McGuire, B. C. Sales, and D. Mandrus, J. Phys. Soc. Jpn. **78**, 013711 (2009).
- <sup>13</sup>L. Fang, H. Luo, P. Cheng, Z. Wang, Y. Jia, G. Mu, B. Shen, I. I. Mazin, L. Shan, C. Ren, and H.-H. Wen, Phys. Rev. B 80, 140508 (2009).
- <sup>14</sup>P. C. Canfield, S. L. Bud'ko, N. Ni, J. Q. Yan, and A. Kracher, Phys. Rev. B **80**, 060501 (2009).
- <sup>15</sup>C. Lester, J.-H. Chu, J. G. Analytis, S. C. Capelli, A. S. Erickson, C. L. Condron, M. F. Toney, I. R. Fisher, and S. M. Hayden, Phys. Rev. B **79**, 144523 (2009).

- <sup>16</sup>D. K. Pratt, W. Tian, A. Kreyssig, J. L. Zarestky, S. Nandi, N. Ni, S. L. Bud'ko, P. C. Canfield, A. I. Goldman, and R. J. McQueeney, Phys. Rev. Lett. **103**, 087001 (2009).
- <sup>17</sup>P. Canfield and S. Bud'ko, arXiv:1002.0858, Condens. Matter Phys. (to be published).
- <sup>18</sup>M. S. Torikachvili, S. L. Bud'ko, N. Ni, and P. C. Canfield, Phys. Rev. B **78**, 104527 (2008).
- <sup>19</sup>P. L. Alireza, Y. T. C. Ko, J. Gillett, C. M. Petrone, J. M. Cole, G. G. Lonzarich, and S. E. Sebastian, J. Phys.: Condens. Matter 21, 012208 (2009).
- <sup>20</sup>E. Colombier, S. L. Bud'ko, N. Ni, and P. C. Canfield, Phys. Rev. B **79**, 224518 (2009).
- <sup>21</sup>W. Schnelle, A. Leithe-Jasper, R. Gumeniuk, U. Burkhardt, D. Kasinathan, and H. Rosner, Phys. Rev. B 79, 214516 (2009).
- <sup>22</sup> Y. Qi, L. Wang, Z. Gao, D. Wang, X. Zhang, and Y. Ma, Physica C 469, 1921 (2009).
- <sup>23</sup>F. Rullier-Albenque, D. Colson, A. Forget, P. Thuéry, and S. Poissonnet, Phys. Rev. B 81, 224503 (2010).
- <sup>24</sup> V. Brouet, F. Rullier-Albenque, M. Marsi, B. Mansart, J. Faure, L. Perfetti, A. Taleb-Ibrahimi, P. Le Fevre, F. Bertran, A. Forget, and D. Colson, arXiv:1002.4952 (unpublished).
- <sup>25</sup>P. C. Canfield and Z. Fisk, Philos. Mag. B **65**, 1117 (1992).
- <sup>26</sup>M. A. Tanatar, N. Ni, C. Martin, R. T. Gordon, H. Kim, V. G. Kogan, G. D. Samolyuk, S. L. Bud'ko, P. C. Canfield, and R. Prozorov, Phys. Rev. B **79**, 094507 (2009).
- <sup>27</sup>M. A. Tanatar, N. Ni, G. D. Samolyuk, S. L. Bud'ko, P. C. Canfield, and R. Prozorov, Phys. Rev. B **79**, 134528 (2009).
- <sup>28</sup>M. Rotter, M. Tegel, D. Johrendt, I. Schellenberg, W. Hermes, and R. Pottgen, Phys. Rev. B 78, 020503 (2008).
- <sup>29</sup>N. Ni, Ph.D. thesis, Iowa State University, 2009.
- <sup>30</sup> A. Kreyssig, M. G. Kim, S. Nandi, D. K. Pratt, W. Tian, J. L. Zarestky, N. Ni, A. Thaler, S. L. Bud'ko, P. C. Canfield, R. J. McQueeney, and A. I. Goldman, Phys. Rev. B **81**, 134512 (2010).
- <sup>31</sup>S. A. J. Kimber, A. Kreyssig, Y.-Z. Zhang, H. O. Jeschke, R. Valentí, F. Yokaichiya, E. Colombier, J. Yan, T. C. Hansen,

T. Chatterji, R. J. McQueeney, P. C. Canfield, A. I. Goldman, and D. N. Argyriou, Nature Mater. 8, 471 (2009).

- <sup>32</sup>S. Jiang, H. Xing, G. Xuan, C. Wang, Z. Ren, C. Feng, J. Dai, Z. Xu, and G. Cao, J. Phys.: Condens. Matter **21**, 382203 (2009).
- <sup>33</sup>S. Kasahara, T. Shibauchi, K. Hashimoto, K. Ikada, S. Tone-

gawa, R. Okazaki, H. Shishido, H. Ikeda, H. Takeya, K. Hirata, T. Terashima, and Y. Matsuda, Phys. Rev. B **81**, 184519 (2010).

<sup>34</sup>L. J. Li, Y. K. Luo, Q. B. Wang, H. Chen, Z. Ren, Q. Tao, Y. K. Li, X. Lin, M. He, Z. W. Zhu, G. H. Cao, and Z. A. Xu, New J. Phys. **11**, 025008 (2009).