

Magnetoresistance of two-dimensional and three-dimensional electron gas in $\text{LaAlO}_3/\text{SrTiO}_3$ heterostructures: Influence of magnetic ordering, interface scattering, and dimensionality

X. Wang,^{1,2} W. M. Lü,^{1,3} A. Annadi,^{1,2} Z. Q. Liu,^{1,2} K. Gopinadhan,^{1,3} S. Dhar,^{1,3} T. Venkatesan,^{1,2,3} and Ariando^{1,2,*}

¹NUSNNI-Nanocore, National University of Singapore, 117411 Singapore

²Department of Physics, National University of Singapore, 117542 Singapore

³Department of Electrical and Computer Engineering, National University of Singapore, 117576 Singapore

(Received 17 May 2011; published 8 August 2011)

Magnetoresistance (MR) anisotropy in $\text{LaAlO}_3/\text{SrTiO}_3$ interfaces is compared between samples prepared in high-oxygen partial-pressure (P_{O_2}) of 10^{-4} mbar exhibiting quasi-two-dimensional (quasi-2D) electron gas and low P_{O_2} of 10^{-6} mbar exhibiting 3D conductivity. While the 3D interfaces show positive MR for all temperatures, the quasi-2D interfaces show negative MR below 30 K, suggesting the presence of magnetic centers in the quasi-2D system. Interestingly, a linear relation between MR and applied magnetic fields was observed in the 3D interfaces for an in-plane field, while in the quasi-2D interfaces for an out-of-plane field, demonstrating the dominant effect of the interface and substrate's vicinal step scattering, respectively. Furthermore, the MR with the out-of-plane field is always larger compared to the MR with in-plane field, suggesting lower dissipation of electrons from interface than defect scattering. Our study demonstrates that MR can be used to distinguish the dimensionality of the charge transport and various (defect, magnetic center, and interface boundary) scattering processes in this system.

DOI: 10.1103/PhysRevB.84.075312

PACS number(s): 73.40.Rw, 73.50.Gr, 73.20.Hb

I. INTRODUCTION

With the recent observation of electronic phase separation, strong negative magnetoresistance (MR) and room-temperature ferromagnetism at the $\text{LaAlO}_3/\text{SrTiO}_3$ interface prepared at higher P_{O_2} of $\sim 1 \times 10^{-2}$ mbar,¹ understanding the role of magnetic ordering and various scattering processes in the transport of quasi-two-dimensional (quasi-2D) electron gas has become important in addition to the variety of fascinating transport properties observed such as superconductivity, Kondo, and field effects.^{2–6}

In various material systems, the behavior of the MR has been studied as a function of field and the angle between the current and field direction in order to distinguish between various possible magnetic states.^{7–9} For example, MR anisotropy measurements have been used to distinguish between weak localization and Kondo scattering.¹⁰ In the case of the $\text{LaAlO}_3/\text{SrTiO}_3$ interfaces, several MR studies^{11–15} have been done to study interface anisotropy, long-range magnetism, magnetic inhomogeneities, and spin-orbit scattering. Based on the observation of negative MR, Shalom *et al.*¹⁴ proposed the existence of magnetic ordering below 35 K for the samples prepared at the canonical P_{O_2} of 10^{-4} – 10^{-3} mbar where quasi-2D electron gas is dominant. However, there has not been any study of the comparison of MR between the quasi-2D and the 3D conductivity cases or the angular dependence of the MR as a function of field and the angle between the current and field direction. Such MR anisotropy measurements would be able to give us further information about magnetic ordering, transport dimensionality and various (interface) scattering processes that can exist in electronic transport of a confined system.

In this paper, we report on temperature-dependent MR anisotropy measurement for atomically sharp interfaces between LaAlO_3 and SrTiO_3 not only for the quasi-2D electron gas prepared under the conditions of $P_{\text{O}_2} = 10^{-4}$ mbar, but

also the 3D electron gas at $P_{\text{O}_2} = 10^{-6}$ mbar. Fundamental differences were observed in MR behavior of high P_{O_2} samples, where a quasi-2D electron gas is expected, compared to those of low P_{O_2} samples, where the electronic transport is 3D. In samples prepared at high P_{O_2} , the MR behavior is strongly influenced by the existence of magnetic scattering centers near the interfaces (a magnetic scattering plane), too small to be detected by other means which accounts for a negative low-temperature MR, and the scattering most probably due to the vicinal steps of the substrate which accounts for the linear MR observed even for out-of-plane configuration.

II. EXPERIMENTAL

In our experiment, samples of 26 unit cells (uc) LaAlO_3 were grown layer by layer on atomically flat TiO_2 terminated SrTiO_3 , under two different P_{O_2} of 10^{-4} and 10^{-6} mbar. Reflection high-energy electron diffraction (RHEED) oscillations obtained from both types of interface samples during growth are shown in Figs. 1(a) and 1(b). These oscillations indicate good layer-by-layer growth up to the 26-uc-thick LaAlO_3 . The electrical measurement was done by linear four-probe geometry.

III. RESULTS AND DISCUSSION

Figure 1(c) shows the resistances of the two types of interfaces. A large difference (of 2 orders of magnitude) in resistance values between the 2D and 3D samples was observed at room temperature, which increases to 4 orders at 2 K. As commonly believed, the resistance difference is one of the key parameters to differentiate between the quasi-2D and 3D interfaces with the carriers in the latter case arising from mainly oxygen vacancies. Furthermore, the growth pressure of 10^{-4} mbar also matches well with reported critical P_{O_2} , above




FIG. 1. (Color online) RHEED oscillation for samples prepared in (a) high P_{O_2} and (b) low P_{O_2} . Clear layer-by-layer growth was observed in both cases. (c) Large transport resistance difference for samples processed under different P_{O_2} .

which SrTiO_3 , when annealed, will remain an insulator, and thus the conduction can only be from interface.¹⁶

MR anisotropy investigation was done in linear geometry with two different directions of magnetic field applied, namely, out-of-plane MR and in-plane MR, as shown in Figs. 2(a) and 2(b). Note that the magnetic fields were always applied perpendicular to current: The field was in the plane of the film for 0° and normal to the film for 90° .

For the oxygen-vacancies-dominated 3D interfaces, a very large out-of-plane MR of $\sim 1500\%$ [Fig. 2(c)] and an order of magnitude lower in-plane MR of $\sim 100\%$ [Fig. 2(d)] were observed when magnetic field was increased up to 9 T at 2 K. While the out-of-plane MR has a quadratic relation, the in-plane MR has a linear relation with applied magnetic field. The behavior of the out-of-plane MR (quadratic dependence) is understood as due to increased defect scattering resulting from enhanced transit path of electrons.¹⁷ On the other hand, the in-plane MR is mainly dominated by interface scattering, primarily at the $\text{LaAlO}_3/\text{SrTiO}_3$ interface as the estimated cyclotron radius for the electron is of the order of a few micrometers (at 1 T applied magnetic field), which is significantly larger than the thickness of the LaAlO_3 layer. As a result the frequency of the interface scattering will be proportional to the cyclotron frequency which has a linear dependence on magnetic field. Further, the reduced magnitude of the MR indicates that the interface scattering is significantly less dissipative (elastic scattering) than the defect scattering.

The MR at 2 K for the quasi-2D interfaces shows much more interesting phenomena. The out-of-plane MR in quasi-2D interfaces is linear instead of quadratic [Fig. 2(e)]. Under 9 T applied magnetic field, the magnitude of the MR is also an order of magnitude smaller compared to those for the out-of-plane 3D case and comparable to those for the in-plane 3D case. Both observations support the idea of the 2D electrons scattering from the vicinal steps in SrTiO_3 which have a width of the order of 200 nm, significantly smaller than the cyclotron radius. Surprisingly, a negative MR [Fig. 2(f)] is observed for the in-plane geometry, in contrast to all the other cases.




FIG. 2. (Color online) Comparison on magnetoresistance between high P_{O_2} and low P_{O_2} with magnetic field applied at different directions. Illustration for (a) out-of-plane and (b) in-plane linear measurement geometry. (c) Low- P_{O_2} $\text{LaAlO}_3/\text{SrTiO}_3$ interfaces out-of-plane MR. (d) Low- P_{O_2} $\text{LaAlO}_3/\text{SrTiO}_3$ interface in-plane MR. (e) High- P_{O_2} interfaces out-of-plane MR. (f) High- P_{O_2} interfaces in-plane MR.

The negative MR could be an indication of onset of magnetic centers as the scattering becomes more coherent. The origin of magnetic scattering has been seen before in the form of Kondo scattering⁴ and also in the extreme case of interfaces grown under higher oxygen pressures exhibiting electronic phase separation.¹ The origin of the magnetic centers is most likely from cationic defects at the $\text{LaAlO}_3/\text{SrTiO}_3$ interface in the form of Ti vacancies or Ti^{3+} . Nakagawa *et al.*¹⁸ have used electron energy loss spectroscopy measurement of the interface to show the existence of Ti^{3+} . Thus, one expects a quasi-2D plane of magnetic centers near the interface responsible for the negative MR.

To sum up, there are three kinds of MR relations observed at 2 K: quadratic positive MR arising from enhanced electron transit path (out-of-plane MR in a low- P_{O_2} sample), linear MR arising from interface scattering (in-plane MR in a low- P_{O_2} sample and out-of-plane MR in a high- P_{O_2} sample), and negative MR arising from coherent scattering (in-plane MR in a high- P_{O_2} sample).

The anisotropy features could already been observed from Fig. 2. In order to check the detailed features of those anisotropies, the MR under 9 T for both the quasi-2D and 3D interfaces are measured at different angles and different temperatures and are shown in Fig. 3. The MR and the




FIG. 3. (Color online) Resistance under 9 T magnetic field with respect to different angles for two types of interfaces.

anisotropy for both quasi-2D and 3D interfaces are suppressed at temperatures above ~ 100 K. At lower temperatures, for the 3D interfaces, the resistance exhibits a cosine relationship with respect to measured angle and the out-of-plane (0°) resistance is about 4 times larger than in-plane (90°) resistance at 9 T and 2 K. In the quasi-2D interface the functional form of the angular dependence shows the formation of a deep cusp at 90° and 270° , which is characteristic of a 2D electron transport.¹⁹

Figure 4 shows a closer comparison of the angular dependence of the 2D and the 3D cases at 2 K and 9 T field. In the quasi-2D interfaces, a negative MR is observed in in-plane geometry (90°) and positive MR in out-of-plane geometry (0°). To vividly demonstrate the MR anisotropy of different types of interfaces, two different plots can be used to present the MR anisotropy at 2 K under 9 T. As can be seen in Fig. 4, the negative MR in-plane geometry for quasi-2D interfaces is very obvious. The shape differences and amplitude differences between quasi-2D and 3D interfaces could be clearly observed in these plots.

The observed different scattering mechanisms have also temperature dependences as illustrated in in-plane resistance and in-plane MR shown in Fig. 5 for the 2D interface. For the 2D samples prepared at higher pressures of 10^{-3} mbar the Kondo effect has been clearly seen but not at 10^{-4} mbar as the concentration of the magnetic centers is too low. However, a magnetic field can align these residual centers, which induces a more coherent scattering and results in a negative MR. Thus, the negative MR is an even more sensitive probe for the presence of magnetic centers than Kondo scattering. This negative MR vanishes beyond 20 K turning progressively positive at higher temperatures due to the disruption of the




FIG. 4. (Color online) Various plots for magnetoresistance of different interfaces under 9 T magnetic field at 2 K. Normal plot for (a) quasi-2D interfaces and (b) 3D interfaces. (c) Polar plot for quasi-2D interfaces and (d) 3D interfaces.

exchange interaction between the magnetic centers by thermal excitations. This accounts for the downward trend of the MR signal with decreasing temperature that originates at 30 K and becomes negative below 20 K. However, the abruptness of the MR transition at 30 K tends to suggest the role of the SrTiO_3 phase transition (orthorhombic to rhombohedral) on the observed change in the MR behavior.




FIG. 5. (Color online) Temperature dependence for in-plane resistance (a) and in-plane magnetoresistance (b),(c) for high- P_{O_2} $\text{LaAlO}_3/\text{SrTiO}_3$ interfaces.

IV. CONCLUSION

In summary, we present a comparison of MR anisotropy in $\text{LaAlO}_3/\text{SrTiO}_3$ interfaces prepared under different P_{O_2} . Large anisotropies were found in both 2D and 3D interface samples and three distinct scattering mechanisms were observed in this system. The observed anisotropy features and temperature dependence suggest the role of interface scattering in addition to enhanced electron paths under a magnetic field and in the case of 2D electron gas the role of a magnetic plane that is effective at low temperatures in introducing a coherent scattering process leading to negative MR. This study supports the formation of a magnetic scattering plane near the 2D electron interface. The study also brings out the lower dissipation of scattering at interfaces as opposed to defect losses due to

enhanced electron transit paths. Thus, MR anisotropy is a sensitive technique for understanding the role of magnetic ordering and various scattering processes in the transport of quasi-2D electron gas.

ACKNOWLEDGMENTS

We thank J. Huijben and H. Hilgenkamp for experimental help and discussions and the National Research Foundation (NRF) Singapore under the Competitive Research Program (CRP) ‘Tailoring Oxide Electronics by Atomic Control’ NRF2008NRF-CRP002-024, National University of Singapore (NUS) cross-faculty grant and FRC (ARF Grant No. R-144-000-278-112) for financial support.

*ariando@nus.edu.sg

¹Ariando *et al.*, *Nat. Commun.* **2**, 188 (2011).

²A. Ohtomo and H. Y. Hwang, *Nature (London)* **427**, 423 (2004).

³N. Reyren *et al.*, *Science* **317**, 1196 (2007).

⁴A. Brinkman *et al.*, *Nat. Mater.* **6**, 493 (2007).

⁵S. Thiel, G. Hammerl, A. Schmehl, C. W. Schneider, and J. Mannhart, *Science* **313**, 1942 (2006).

⁶A. D. Caviglia *et al.*, *Nature (London)* **456**, 624 (2008).

⁷S. Jin *et al.*, *Science* **264**, 413 (1994).

⁸G. J. C. L. Bruls, J. Bass, A. P. van Gelder, H. van Kempen, and P. Wyder, *Phys. Rev. Lett.* **46**, 553 (1981).

⁹G. J. C. L. Bruls, J. Bass, A. P. van Gelder, H. van Kempen, and P. Wyder, *Phys. Rev. B* **32**, 1927 (1985).

¹⁰S. Zhang *et al.*, *Adv. Mater.* **21**, 2282 (2009).

¹¹S. Seri *et al.*, *IEEE Trans. Magn.* **46**, 1630 (2010).

¹²S. Seri and L. Klein, *Phys. Rev. B* **80**, 180410(R) (2009).

¹³F. J. Wong, R. V. Chopdekar, and Y. Suzuki, *Phys. Rev. B* **82**, 165413 (2010).

¹⁴M. Ben Shalom, C. W. Tai, Y. Lereah, M. Sachs, E. Levy, D. Rakhmilevitch, A. Palevski, and Y. Dagan, *Phys. Rev. B* **80**, 140403(R) (2009).

¹⁵J. H. Ngai, Y. Segal, F. J. Walker, and C. H. Ahn, *Phys. Rev. B* **83**, 045304 (2011).

¹⁶A. Kalabukhov, R. Gunnarsson, J. Borjesson, E. Olsson, T. Claesson, and D. Winkler, *Phys. Rev. B* **75**, 121404(R) (2007).

¹⁷O. N. Tufte and E. L. Stelzer, *Phys. Rev.* **173**, 775 (1968).

¹⁸N. Nakagawa, H. Y. Hwang, and D. A. Muller, *Nat. Mater.* **5**, 204 (2006).

¹⁹P. H. Kes, J. Aarts, V. M. Vinokur, and C. J. van der Beek, *Phys. Rev. Lett.* **64**, 1063 (1990).