

Coexistence of antiferromagnetic and ferromagnetic spin correlations in SrCo₂As₂ revealed by ⁵⁹Co and ⁷⁵As NMR

P. Wiecki,^{1,2} V. Ogloblichev,^{1,3} Abhishek Pandey,^{1,2} D. C. Johnston,^{1,2} and Y. Furukawa^{1,2}

¹The Ames Laboratory, Ames, Iowa 50011, USA

²Department of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, USA

³Institute of Metal Physics, Ural Division of Russian Academy of Sciences, Ekaterinburg 620990, Russia

(Received 26 February 2015; revised manuscript received 3 May 2015; published 15 June 2015)

In nonsuperconducting, metallic paramagnetic SrCo₂As₂, inelastic neutron scattering measurements have revealed strong stripe-type $\mathbf{q} = (\pi, 0)$ antiferromagnetic (AFM) spin correlations. Here, using nuclear magnetic resonance (NMR) measurements on ⁵⁹Co and ⁷⁵As nuclei, we demonstrate that stronger ferromagnetic (FM) spin correlations coexist in SrCo₂As₂. Our NMR data are consistent with density functional theory (DFT) calculations which show enhancements at both $\mathbf{q} = (\pi, 0)$ and the in-plane FM $\mathbf{q} = 0$ wave vectors in static magnetic susceptibility $\chi(\mathbf{q})$. We suggest that the strong FM fluctuations prevent superconductivity in SrCo₂As₂, despite the presence of stripe-type AFM fluctuations. Furthermore, since DFT calculations have consistently revealed similar enhancements of the $\chi(\mathbf{q})$ at both $\mathbf{q} = (\pi, 0)$ and $\mathbf{q} = 0$ in the iron-based superconductors and parent compounds, our observation of FM correlations in SrCo₂As₂ calls for detailed studies of FM correlations in the iron-based superconductors.

DOI: [10.1103/PhysRevB.91.220406](https://doi.org/10.1103/PhysRevB.91.220406)

PACS number(s): 74.70.Xa, 75.40.Gb, 76.60.-k

The interplay between magnetism and superconductivity is one of the central issues in unconventional superconductors (SCs) such as high- T_c cuprates and iron-pnictide-based SCs. Among the iron-pnictide-based SCs, the “122” class of compounds, AFe₂As₂ ($A = \text{Ca, Ba, Sr, Eu}$), has been one of the most widely studied systems in recent years [1–7]. These systems undergo coupled structural and magnetic phase transitions at a system-dependent Néel temperature T_N , below which long-range stripe-type antiferromagnetic (AFM) order emerges. Suppression of the AFM order by doping or pressure results in a SC ground state with T_c ranging from a few Kelvin to more than 50 K. Continued doping ultimately results in the suppression of the stripe-type AFM spin fluctuations, which correlates with the suppression of SC [1–7]. Although the Cooper pairing is widely believed to originate from the residual stripe-type AFM spin fluctuations, the origin of the large variability of T_c is still not well understood.

Tetragonal, metallic paramagnetic (PM) SrCo₂As₂ is the end member of the electron-doped Sr(Fe_{1-x}Co_x)₂As₂ family of compounds, which displays superconductivity in the range from $x = 0.07$ to $x = 0.17$ with a maximum T_c of 19 K [8,9]. The $x = 0$ parent compound, SrFe₂As₂, is an AFM showing stripe-type spin density wave order below 220 K [10,11]. In SrCo₂As₂, on the other hand, no long-range magnetic ordering is observed down to 1.8 K [12]. The Sommerfeld coefficient ($\gamma = 37.8 \frac{\text{mJ}}{\text{mol K}^2}$) is significantly enhanced relative to SrFe₂As₂ in the stripe AFM state [12]. Angle-resolved photoemission spectroscopy and electronic structure calculations show no clear nesting features of the Fermi surface which drive the stripe-type AFM order and SC in the parent and modestly doped compounds [12]. Nevertheless, AFM spin correlations are suggested from the temperature (T) dependence of magnetic susceptibility χ which exhibits a broad maximum around 115 K, a characteristic of short-range dynamic AFM correlations in low-dimensional spin systems [12]. Subsequent inelastic neutron scattering (INS) measurements on SrCo₂As₂ revealed strong AFM spin fluctuations at the stripe-type wave vector [13]. Similar

physical properties are reported in the SC compound KFe₂As₂, the end member of the hole-doped Ba_{1-x}K_xFe₂As₂ family. This compound also has an enhanced $\gamma = 103 \frac{\text{mJ}}{\text{mol K}^2}$ and a broad peak in χ around 100 K [14], along with strong stripe-type AFM fluctuations [15]. The similarity between SC KFe₂As₂ and non-SC SrCo₂As₂ raises the important question of why superconductivity does not arise in SrCo₂As₂.

In this Rapid Communication, we report ⁵⁹Co and ⁷⁵As nuclear magnetic resonance (NMR) measurements to examine the local microscopic properties of SrCo₂As₂. Our analysis, based on the modified Korringa relation, reveals strong ferromagnetic (FM) spin fluctuations within the Co layer coexisting with the stripe-type AFM fluctuations observed by INS. Based on these results, we suggest that the low-energy FM fluctuations observed by NMR compete with the stripe-type AFM fluctuations, resulting in the suppression of SC in SrCo₂As₂. Furthermore, our observation of coexisting stripe AFM and FM fluctuations in SrCo₂As₂ is consistent with density functional theory (DFT) calculations which show peaks in the static susceptibility, $\chi(\mathbf{q})$, at both the FM and stripe AFM in-plane wave vectors [13]. This theoretically predicted enhancement of $\chi(\mathbf{q})$ at both wave vectors is not unique to SrCo₂As₂ but in fact applies more generally to iron-pnictide-based superconductors and parent compounds [1,16–20]. Our NMR data provide microscopic confirmation of spin susceptibility enhanced at both wave vectors in the iron-pnictide family, indicating that FM fluctuations may play an important role in determining T_c in iron-pnictide-based SCs.

NMR measurements were performed on ⁷⁵As ($I = 3/2$, $\gamma/2\pi = 7.2919$ MHz/T) and ⁵⁹Co ($I = 7/2$, $\gamma/2\pi = 10.03$ MHz/T) using a homemade phase-coherent spin-echo pulse spectrometer. The ⁵⁹Co and ⁷⁵As spin-lattice relaxation rates ($1/T_1$) were measured with a recovery method using a single $\pi/2$ saturation pulse [21]. The single crystal used in this study was grown with Sn flux and is the same as that in our previous study [12] where preliminary ⁷⁵As-NMR results were reported.




FIG. 1. (Color online) (a) Field-swept ^{59}Co -NMR spectra at frequency $f = 66.3$ MHz for magnetic fields $H \parallel c$ axis (black) and $H \parallel ab$ plane (red) at various values of T . The vertical dashed line represents the zero-shift position ($K = 0$). (b) T dependence of the ^{59}Co -NMR shifts K_c and K_{ab} . The black and red dashed lines correspond to K_0 for K_c and K_{ab} , respectively. Inset: K vs χ plots for each field direction where we used χ data reported in Ref. [12]. The thick solid lines are fitting results and two thin lines above and below the thick line give an error for our estimate of K_0 for each H direction. (c) T dependence of the FWHM of the spectra for each field direction.

Figure 1(a) shows field-swept ^{59}Co -NMR spectra at various values of T for magnetic fields parallel to the c axis ($H \parallel c$ axis) and to the ab plane ($H \parallel ab$ plane). The typical spectrum for a nucleus with spin $I = 7/2$ with Zeeman and quadrupolar interactions can be described by a nuclear spin Hamiltonian $\mathcal{H} = -\gamma\hbar\mathbf{I} \cdot \mathbf{H}_{\text{eff}} + \frac{h\nu_Q}{6}[3I_z^2 - I(I+1)]$, where \mathbf{H}_{eff} is the effective field at the nuclear site and h is Planck's constant. The nuclear quadrupole frequency for $I = 7/2$ nuclei is given by $\nu_Q = e^2QV_{ZZ}/14h$, where Q is the nuclear quadrupole moment and V_{ZZ} is the electric field gradient at the nuclear site. For $I = 7/2$ nuclei, this Hamiltonian produces a spectrum with a sharp central transition line flanked by three satellite peaks on either side. The observed ^{59}Co NMR spectra, however, do not show the seven distinct lines but rather exhibit a single broad line due to inhomogeneous broadenings. From the linewidth, we estimate $\nu_Q \sim 0.14$ MHz at 4.2 K with V_{ZZ} parallel to the c axis, close to the value of 0.13 MHz for ^{59}Co in $\text{Ba}(\text{Fe}_{1-x}\text{Co}_x)_2\text{As}_2$ with $x = 0.02$ and 0.04 [22].

Figure 1(b) shows the T dependence of the NMR shift for $H \parallel c$ axis (K_c) and $H \parallel ab$ plane (K_{ab}). The NMR shift has contributions from the T -dependent spin part K_{spin} and a T -independent orbital part K_0 . K_{spin} is proportional to the spin susceptibility χ_{spin} through the hyperfine coupling constant A_{hf} giving $K(T) = K_0 + \frac{A_{\text{hf}}}{N_A}\chi_{\text{spin}}(T)$, where N_A is Avogadro's number. The anisotropic spin susceptibilities χ_{ab} and χ_c in SrCo_2As_2 were reported in Ref. [12]. The inset of Fig. 1(b) plots K_{ab} and K_c against χ_{ab} and χ_c , respectively, with T as an implicit parameter. T is chosen to be above 20 K to avoid upturns in χ due to impurities [12]. K_{ab} and K_c vary with the corresponding χ as expected, although one can see a slight deviation from the linear relationship. We estimated

the hyperfine coupling constants $A_c = (-110 \pm 5)$ kOe/ μ_B and $A_{ab} = (-22.9 \pm 1.0)$ kOe/ μ_B by fitting the data (shown by the thick lines in the inset). A_c is comparable to the value of -105 kOe/ μ_B for isotropic d electron core polarization, while A_{ab} is much smaller. The small value of A_{ab} could be due to anisotropic and positive orbital and/or dipolar hyperfine coupling contributions which cancel a part of the negative core polarization hyperfine field. Similar reductions in the hyperfine coupling constant have been observed in several Co compounds, which have been well explained by taking the orbital contributions into consideration [23–25]. The orbital shifts $K_{0,ab} = (1.31 \pm 0.10)\%$ and $K_{0,c} = (1.51 \pm 0.13)\%$ were estimated from the fittings. In order to estimate the error in K_0 , we change the K_0 while keeping the same slope to cover all data points. The two thin lines correspond to the fitting lines with minimum and maximum K_0 for each H direction. The T dependencies of K_{ab} and K_c are similar to the behaviors reported for ^{75}As -NMR in Ref. [12], which show broad maxima at $T \sim 115$ K. These maxima are observed as minima in the ^{59}Co NMR shift data due to the negative hyperfine coupling constant. The broad minima in K_{ab} and K_c suggest the presence of low-dimensional dynamic short-range AFM correlations below 115 K. In Fig. 1(c), we plot the full width at half maximum (FWHM) of the spectra as a function of T for $H \parallel c$ axis and $H \parallel ab$ plane. With decreasing T , the FWHM decreases gradually and starts to increase below ~ 30 K where χ shows T -independent behavior, suggesting inhomogeneities of the dynamic short-range AFM order below 30 K.

To investigate the dynamical magnetic properties, we have measured $1/T_1$ versus T (Fig. 2). In both field directions $1/(T_1T)$ is roughly constant over the entire temperature range. The inset shows nuclear magnetization recovery curves for the two magnetic field directions together with fitting results. To examine the character of the spin fluctuations in more detail, we perform a modified Korringa relation analysis. Within a




FIG. 2. (Color online) T dependence of $1/T_1T$ for both magnetic field directions, $H \parallel c$ axis [$1/(T_1T)_{H\parallel c}$] and $H \parallel ab$ plane [$1/(T_1T)_{H\parallel ab}$]. Inset: Recovery curves at $T = 2.4$ K for both H directions. The solid lines are fits by the relaxation function described in the text.




FIG. 3. (Color online) Top panel: T dependence of the Korringa ratios $1/T_{1,\perp} T K_{\text{spin},ab}^2$ (red) and $1/T_{1,\parallel} T K_{\text{spin},c}^2$ (black) for spin correlations in the ab plane and along the c axis, respectively. The solid lines are guides to the eye. Lower panel: T dependence of the parameter α_{\perp} for spin correlations in the ab plane (red) and α_{\parallel} along the c axis (black).

Fermi liquid picture, $1/T_1 T$ is proportional to the square of the density of states at the Fermi energy $\mathcal{D}(E_F)$ and $K_{\text{spin}} (\propto \chi_{\text{spin}})$ is proportional to $\mathcal{D}(E_F)$. In particular, $T_1 T K_{\text{spin}}^2 = \frac{\hbar}{4\pi k_B} \left(\frac{\gamma_e}{\gamma_N}\right)^2 = S$, which is the Korringa relation. Deviations from S can reveal information about electron correlations in the material [26,27], which are expressed via the parameter $\alpha = S/(T_1 T K_{\text{spin}}^2)$. For instance, enhancement of $\chi(\mathbf{q} \neq 0)$ increases $1/T_1 T$ but has little or no effect on K_{spin} , which probes only the uniform χ with $\mathbf{q} = 0$. Thus $\alpha > 1$ for AFM correlations and $\alpha < 1$ for FM correlations.

Application of the Korringa relation to SrCo_2As_2 requires some care due to the anisotropy of K_{spin} and $1/T_1 T$. Since $1/T_1 T$ probes magnetic fluctuations perpendicular to the magnetic field [26], it is natural to consider the Korringa ratio $1/T_{1,\perp} T K_{\text{spin},ab}^2$ where $1/T_{1,\perp} T = 1/(T_1 T)_{H \parallel c}$, when examining the character of magnetic fluctuations in the ab plane. Similarly, we consider the Korringa ratio $1/T_{1,\parallel} T K_{\text{spin},c}^2$ for magnetic fluctuations along the c axis. Here $1/(T_{1,\parallel} T)$ is estimated from $2/(T_1 T)_{H \parallel ab} - 1/(T_1 T)_{H \parallel c}$.

In the top panel of Fig. 3, we show the T dependence of the Korringa ratios for magnetic fluctuations in the ab plane and along the c axis, along with the corresponding values of the parameter α in the bottom panel. We find that $\alpha \ll 1$ in each case, with the value of α remaining constant throughout the range of T . The low values of α indicate that the fluctuations have predominantly FM character. It should be emphasized that the α values strongly depend on K_{spin} and the α_{\perp} greater than α_{\parallel} could be due to the small K_{spin} values arising from the small A_{ab} . In addition, it should be noted that the observed $1/T_1 T$ is the sum of four contributions: the s electron Fermi contact, d orbital, d core polarization, and d dipole relaxation rates. As a result, the estimated values for α for both directions can be considered to be upper limits on α , indicating even stronger FM fluctuations in SrCo_2As_2 than expected from the above α values. On the other hand, the




FIG. 4. (Color online) (a) T dependence of the ^{75}As NMR shift for both field directions in SrCo_2As_2 (black) and BaCo_2As_2 (red) [28]. (b) T dependence of $1/T_1 T$ at the ^{75}As sites for both field directions in SrCo_2As_2 (black) and BaCo_2As_2 (red).

increase of $1/T_{1,\parallel} T K_{\text{spin},c}^2$ below 50 K clearly indicates the presence of AFM correlations along the c axis coexisting with the dominant FM fluctuations.

The suggested FM spin correlations can be confirmed by ^{75}As NMR in SrCo_2As_2 . In Fig. 4(a), we show the T dependence of the ^{75}As NMR shifts K_{ab} and K_c . For comparison, Fig. 4 also shows our analogous data from isostructural BaCo_2As_2 reported in Ref. [28], which are in agreement with those reported in Ref. [29]. The NMR shifts measured at the ^{75}As sites of SrCo_2As_2 display broad maxima at $T \sim 115$ K, consistent with the NMR shift measured at the ^{59}Co sites, although with opposite sign of the hyperfine coupling. The broad peak observed in SrCo_2As_2 contrasts sharply with the NMR shift in BaCo_2As_2 , which increases with decreasing T and then levels off at low T .

The T dependence of $1/T_1 T$ of ^{75}As , measured in both field directions, is shown in Fig. 4(b) for both SrCo_2As_2 and BaCo_2As_2 . For SrCo_2As_2 , $1/T_1 T$ for both field directions shows a broad peak around $T \sim 115$ K. This T dependence is very similar to that of the NMR shift. Also in BaCo_2As_2 , $1/T_1 T$ shows a very similar T dependence to that of the corresponding NMR shift. This similar T dependence of $1/T_1 T$ and K for BaCo_2As_2 was also noted in Ref. [29]. Ahilan *et al.* contrasted this behavior to that of the PM state in optimally doped $\text{Ba}(\text{Fe}_{1-x}\text{Co}_x)_2\text{As}_2$, where $1/T_1 T$ increases with decreasing T below 100 K, while K slowly decreases [29]. This behavior is clear evidence for the presence of fluctuations with $\mathbf{q} \neq 0$. In contrast, the similar T dependence of $1/T_1 T$ and K in BaCo_2As_2 rules out strong fluctuations with $\mathbf{q} \neq 0$, since these would increase $1/T_1 T$ but




FIG. 5. (Color online) Top panel: T dependence of the Korringa ratios $1/T_{\perp}TK_{\text{spin},ab}^2$ (open symbols) and $1/T_{\parallel}TK_{\text{spin},c}^2$ (closed symbols) for spin correlations in the ab plane and along the c axis, respectively, for SrCo_2As_2 (black) and BaCo_2As_2 (red). Lower panel: T dependence of α_{\perp} and α_{\parallel} for SrCo_2As_2 and BaCo_2As_2 .

not K . Ahilan *et al.* therefore concluded the correlations in BaCo_2As_2 are primarily FM in nature. By a similar argument, our data on SrCo_2As_2 offer clear evidence for dominant FM fluctuations. In fact, the FM fluctuations can be shown by the modified Korringa relation analysis using the ^{75}As NMR data. Figure 5 shows the Korringa ratios for both field directions in SrCo_2As_2 and BaCo_2As_2 along with the corresponding Korringa parameters α . In each case we find $\alpha \ll 1$, again consistent with strong FM fluctuations in both materials, consistent with dominant FM correlations as found above for ^{59}Co in SrCo_2As_2 . The slightly higher value of the α_{\parallel} for SrCo_2As_2 than the other three cases suggests that the c axis component of the magnetic fluctuations in SrCo_2As_2 would be less FM than in BaCo_2As_2 . The above analysis is based on a simple model that the nuclear relaxation is due to the local $\mathcal{D}(E_F)$ at the As sites, through on-site hyperfine interactions, where As- $4p$ bands hybridize with Fe- $3d$ bands. On the other hand, if the relaxations are induced by only localized Fe electronic spins through isotropic transferred hyperfine interactions, the α value would be modified by a factor of 4 due to the q -dependent hyperfine form factor [30]; FM spin correlations would then be expected for $\alpha < 0.25$. Regardless of the model, the α values in both systems are consistent with FM spin correlations.

According to DFT calculations in Ref. [13], the $\chi(\mathbf{q})$ in SrCo_2As_2 shows enhancements of similar strength at both

the FM and stripe AFM wave vectors. Furthermore, the DFT results indicate that the stripe-type AFM fluctuations have a higher energy scale than the FM fluctuations, suggesting that FM fluctuations may be dominant at low energies. From the NMR point of view, which probes energies very near the ground state, we find that the fluctuations are indeed predominantly FM in character. We also find evidence for weak AFM fluctuations coexisting with the dominant FM fluctuations, which can be attributed to the contribution in $\chi(\mathbf{q})$ at the stripe AFM wave vector revealed by the DFT calculations and INS measurements.

In summary, our ^{59}Co and ^{75}As NMR data demonstrate that the low-energy spin fluctuations in paramagnetic SrCo_2As_2 , the end member of the electron-doped $\text{Sr}(\text{Fe}_{1-x}\text{Co}_x)_2\text{As}_2$ family, are predominantly FM in character. We also found clear evidence of coexisting weak stripe-type AFM fluctuations that also appear at the higher INS energy scale. In the standard phenomenology of the iron-arsenide SCs, optimum SC is expected if strong stripe-type AFM fluctuations are present in the absence of long-range AFM order. We suggest that the competing low-energy FM fluctuations interfere with the stripe-type AFM fluctuation-based pairing mechanism, thus suppressing superconductivity in SrCo_2As_2 even though the standard requirements are satisfied. Finally, several theoretical calculations have shown enhancements of $\chi(\mathbf{q})$ at both the FM and stripe-type AFM wave vectors in iron-based superconductors and parent compounds, similar to the case of SrCo_2As_2 . Experimentally, a Korringa parameter α from ^{77}Se -NMR data on the iron-chalcogenide superconductor $\text{K}_{0.8}\text{Fe}_2\text{Se}_2$ seems to be consistent with FM fluctuations in the high- T paramagnetic phase [31]. These results suggest that strong FM correlations and fluctuations may be important to determining T_c in the iron-based superconductors. Due to the partial cancellation of the influences of FM and AFM fluctuations in NMR measurements, polarized inelastic neutron scattering measurements are needed to definitively measure the relative strengths of FM and AFM fluctuations in SrCo_2As_2 and other iron-based superconductors.

We thank Alan Goldman and Andreas Kreyssig for helpful discussions. The research was supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering. Ames Laboratory is operated for the U.S. Department of Energy by Iowa State University under Contract No. DE-AC02-07CH11358. V.O. thanks the Ames Laboratory and U.S. DOE for providing him the opportunity to be a visiting scientist at the Ames Laboratory and also thanks the Russian Foundation for Basic Research (Grant No. 15-02-02000) for support.

- [1] D. C. Johnston, *Adv. Phys.* **59**, 803 (2010).
- [2] N. Ni, S. Nandi, A. Kreyssig, A. I. Goldman, E. D. Mun, S. L. Bud'ko, and P. C. Canfield, *Phys. Rev. B* **78**, 014523 (2008).
- [3] M. Rotter, M. Tegel, and D. Johrendt, *Phys. Rev. Lett.* **101**, 107006 (2008).
- [4] A. S. Sefat, R. Jin, M. A. McGuire, B. C. Sales, D. J. Singh, and D. Mandrus, *Phys. Rev. Lett.* **101**, 117004 (2008).

- [5] P. C. Canfield and S. L. Bud'ko, *Annu. Rev. Condens. Matter Phys.* **1**, 27 (2010).
- [6] G. R. Stewart, *Rev. Mod. Phys.* **83**, 1589 (2011).
- [7] N. Ni, M. E. Tillman, J. Q. Yan, A. Kracher, S. T. Hannahs, S. L. Bud'ko, and P. C. Canfield, *Phys. Rev. B* **78**, 214515 (2008).
- [8] A. Leithe-Jasper, W. Schnelle, C. Geibel, and H. Rosner, *Phys. Rev. Lett.* **101**, 207004 (2008).

- [9] R. Hu, S. L. Bud'ko, W. E. Straszheim, and P. C. Canfield, *Phys. Rev. B* **83**, 094520 (2011).
- [10] C. Krellner, N. Caroca-Canales, A. Jesche, H. Rosner, A. Ormeci, and C. Geibel, *Phys. Rev. B* **78**, 100504(R) (2008).
- [11] J. Zhao, D.-X. Yao, S. Li, T. Hong, Y. Chen, S. Chang, W. Ratcliff, II, J. W. Lynn, H. A. Mook, G. F. Chen, J. L. Luo, N. L. Wang, E. W. Carlson, J. Hu, and P. Dai, *Phys. Rev. Lett.* **101**, 167203 (2008).
- [12] A. Pandey, D. G. Quirinale, W. Jayasekara, A. Sapkota, M. G. Kim, R. S. Dhaka, Y. Lee, T. W. Heitmann, P. W. Stephens, V. Ogloblichev, A. Kreyssig, R. J. McQueeney, A. I. Goldman, A. Kaminski, B. N. Harmon, Y. Furukawa, and D. C. Johnston, *Phys. Rev. B* **88**, 014526 (2013).
- [13] W. Jayasekara, Y. Lee, A. Pandey, G. S. Tucker, A. Sapkota, J. Lamsal, S. Calder, D. L. Abernathy, J. L. Niedziela, B. N. Harmon, A. Kreyssig, D. Vaknin, D. C. Johnston, A. I. Goldman, and R. J. McQueeney, *Phys. Rev. Lett.* **111**, 157001 (2013).
- [14] F. Hardy, A. E. Böhmer, D. Aoki, P. Burger, T. Wolf, P. Schweiss, R. Heid, P. Adelman, Y. X. Yao, G. Kotliar, J. Schmalian, and C. Meingast, *Phys. Rev. Lett.* **111**, 027002 (2013).
- [15] M. Hirano, Y. Yamada, T. Saito, R. Nagashima, T. Konishi, T. Toriyama, Y. Ohta, H. Fukazawa, Y. Kohori, Y. Furukawa, K. Kihou, C.-H. Lee, A. Iyo, and H. Eisaki, *J. Phys. Soc. Jpn.* **81**, 054704 (2012).
- [16] D. J. Singh and M. H. Du, *Phys. Rev. Lett.* **100**, 237003 (2008).
- [17] I. I. Mazin, D. J. Singh, M. D. Johannes, and M. H. Du, *Phys. Rev. Lett.* **101**, 057003 (2008).
- [18] J. Dong, H. J. Zhang, G. Xu, Z. Li, G. Li, W. Z. Hu, D. Wu, G. F. Chen, X. Dai, J. L. Luo, Z. Fang, and N. L. Wang, *Europhys. Lett.* **83**, 27006 (2008).
- [19] A. N. Yaresko, G.-Q. Liu, V. N. Antonov, and O. K. Andersen, *Phys. Rev. B* **79**, 144421 (2009).
- [20] M. Neupane, P. Richard, Y.-M. Xu, K. Nakayama, T. Sato, T. Takahashi, A. V. Federov, G. Xu, X. Dai, Z. Fang, Z. Wang, G.-F. Chen, N.-L. Wang, H.-H. Wen, and H. Ding, *Phys. Rev. B* **83**, 094522 (2011).
- [21] $1/T_1$ at each T was determined by fitting the nuclear magnetization M versus time t using the exponential functions $1 - M(t)/M(\infty) = 0.1e^{-t/T_1} + 0.9e^{-6t/T_1}$ for ^{75}As and $1 - M(t)/M(\infty) = 0.012e^{-t/T_1} + 0.068e^{-6t/T_1} + 0.206e^{-15t/T_1} + 0.714e^{-28t/T_1}$ for ^{59}Co , where $M(t)$ is the nuclear magnetization at time t after saturation and $M(\infty)$ is the equilibrium nuclear magnetization at $t \rightarrow \infty$.
- [22] F. L. Ning, K. Ahilan, T. Imai, A. S. Sefat, R. Jin, M. A. McGuire, B. C. Sales, and D. Mandrus, *Phys. Rev. B* **79**, 140506(R) (2009).
- [23] T. Tsuda, A. Hirai, and H. Abe, *Phys. Lett. A* **26**, 463 (1968).
- [24] T. Fukai, Y. Furukawa, S. Wada, and K. Miyatani, *J. Phys. Soc. Jpn.* **65**, 4067 (1996).
- [25] B. Roy, Abhishek Pandey, Q. Zhang, T. W. Heitmann, D. Vaknin, D. C. Johnston, and Y. Furukawa, *Phys. Rev. B* **88**, 174415 (2013).
- [26] T. Moriya, *J. Phys. Soc. Jpn.* **18**, 516 (1963).
- [27] A. Narath and H. T. Weaver, *Phys. Rev.* **175**, 373 (1968).
- [28] V. K. Anand, D. G. Quirinale, Y. Lee, B. N. Harmon, Y. Furukawa, V. V. Ogloblichev, A. Huq, D. L. Abernathy, P. W. Stephens, R. J. McQueeney, A. Kreyssig, A. I. Goldman, and D. C. Johnston, *Phys. Rev. B* **90**, 064517 (2014).
- [29] K. Ahilan, T. Imai, A. S. Sefat, and F. L. Ning, *Phys. Rev. B* **90**, 014520 (2014).
- [30] P. Jeglič, A. Potočnik, M. Klanjšek, M. Bobnar, M. Jagodič, K. Koch, H. Rosner, S. Margadonna, B. Lv, A. M. Guloy, and D. Arčon, *Phys. Rev. B* **81**, 140511(R) (2010).
- [31] H. Kotegawa, Y. Hara, H. Nohara, H. Tou, Y. Mizuguchi, H. Takeya, and Y. Takano, *J. Phys. Soc. Jpn.* **80**, 043708 (2011).