

Magnetic fluctuations and superconducting properties of CaKFe₄As₄ studied by ⁷⁵As NMRJ. Cui,^{1,2} Q.-P. Ding,¹ W. R. Meier,^{1,3} A. E. Böhmer,¹ T. Kong,^{1,3,*} V. Borisov,⁴ Y. Lee,¹ S. L. Bud'ko,^{1,3}
R. Valentí,⁴ P. C. Canfield,^{1,3} and Y. Furukawa^{1,3}¹Ames Laboratory, U.S. DOE, Ames, Iowa 50011, USA²Department of Chemistry, Iowa State University, Ames, Iowa 50011, USA³Department of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, USA⁴Institute of Theoretical Physics, Goethe University Frankfurt am Main, D-60438 Frankfurt am Main, Germany

(Received 5 July 2017; revised manuscript received 30 August 2017; published 25 September 2017)

We report ⁷⁵As nuclear magnetic resonance (NMR) studies on a new iron-based superconductor, CaKFe₄As₄, with $T_c = 35$ K. ⁷⁵As NMR spectra show two distinct lines corresponding to the As(1) and As(2) sites close to the K and Ca layers, respectively, revealing that K and Ca layers are well ordered without site inversions. We found that nuclear quadrupole frequencies ν_Q of the As(1) and As(2) sites show an opposite temperature T dependence. Nearly T independent behavior of the Knight shifts K is observed in the normal state, and a sudden decrease in K in the superconducting (SC) state suggests spin-singlet Cooper pairs. ⁷⁵As spin-lattice relaxation rates $1/T_1$ show a power-law T dependence with different exponents for the two As sites. The isotropic antiferromagnetic spin fluctuations characterized by the wave vector $\mathbf{q} = (\pi, 0)$ or $(0, \pi)$ in the single-iron Brillouin zone notation are revealed by $1/T_1T$ and K measurements. Such magnetic fluctuations are necessary to explain the observed temperature dependence of the ⁷⁵As quadrupole frequencies, as evidenced by our first-principles calculations. In the SC state, $1/T_1$ shows a rapid decrease below T_c without a Hebel-Slichter peak and decreases exponentially at low T , consistent with an s^\pm nodeless two-gap superconductor.

DOI: [10.1103/PhysRevB.96.104512](https://doi.org/10.1103/PhysRevB.96.104512)**I. INTRODUCTION**

Following the discovery of unconventional superconductivity (SC) in the so-called 1111 and 122 systems exemplified by LaFeAsO [1] and BaFe₂As₂ [2], respectively, many pnictides have been investigated in the search for unconventional superconductivity and other novel properties [3–7]. Quite recently, a new Fe-based SC, CaKFe₄As₄ (in short, CaK1144), with a transition temperature of $T_c \sim 33.1$ K has been discovered [8]. In CaK1144, Ca²⁺ and K¹⁺ occupy different atomic positions in its crystal structure due to the different ionic radii, forming alternating Ca and K planes along the crystallographic c axis separated by FeAs layers [8]. This is contrary to the doped 122 system such as Ba_{1-x}K_xFe₂As₂, where alkaline-earth metal and alkaline ions occupy randomly the same atomic position. The ordering of the K and Ca ions changes the space group from the $I4/mmm$ system to $P4/mmm$. Consequently, as shown in the inset of Fig. 1(a), there are two different As sites: As(1) and As(2) sites close to the K and Ca layers, respectively.

Soon after the discovery of CaK1144, thermodynamic and transport measurements on single crystals revealed that CaK1144 is an ordered stoichiometric superconductor with $T_c \sim 35$ K and a very high upper critical field of 92 T [9] with no other phase transition from 1.8 K to room temperature and shows physical properties similar to those of the optimally doped (Ba_{1-x}K_x)Fe₂As₂. Muon spin rotation and relaxation (μ SR) measurements show two nodeless gaps in CaK1144 with gap sizes of 2.5 and 8.6 meV [10], consistent with tunnel-diode resonator (TDR) and scanning tunneling microscope (STM) measurements [11]. The multiple

superconducting gaps in CaK1144 are also revealed by high-resolution angle-resolved photoemission spectroscopy (ARPES) measurements and density functional theory (DFT) calculations [12]. However, studies of magnetic fluctuations in CaK1144 have not been carried out yet. Since the magnetic fluctuations are considered to be one of the keys in driving SC in iron pnictide superconductors [3,13–16], it is important to characterize the dynamical properties of the Fe moments.

Nuclear magnetic resonance (NMR) is a microscopic probe suitable for investigating static spin susceptibility and low-energy spin excitations for pnictide superconductors [3,13]. The temperature T dependence of the nuclear spin-lattice relaxation rate ($1/T_1$) is known to reflect the wave-vector q -summed dynamical susceptibility. On the other hand, NMR spectrum measurements, in particular the Knight shift K , give us information on static magnetic susceptibility χ . Thus from the T dependence of $1/T_1T$ and K , one can obtain valuable insights about magnetic fluctuations in materials. Furthermore, $1/T_1$ measurements in the SC state provide important information for understanding the gap structure in SCs.

In this paper, we carried out ⁷⁵As NMR measurements to investigate the electronic and magnetic properties of single-crystalline CaKFe₄As₄ with $T_c = 35$ K. We observed two ⁷⁵As NMR signals corresponding to the two different As sites in the crystal structure, showing the ordering of Ca and K ions on each layer. The antiferromagnetic (AFM) spin fluctuations are clearly evidenced by ⁷⁵As spin-lattice relaxation rate $1/T_1$ and Knight shift K measurements. *Ab initio* density functional theory calculations of the ⁷⁵As nuclear quadrupole frequency ν_Q confirm the importance of such fluctuations for the description of the observed temperature evolution of ν_Q . In the superconducting state, $1/T_1$ shows a rapid decrease below T_c without showing a Hebel-Slichter coherence peak and decreases exponentially at low temperatures, which

*Present address: Department of Chemistry, Princeton University, Princeton, New Jersey 08544, USA.

is explained by a two-nodeless-gap model, consistent with previous reports.

II. EXPERIMENTAL METHODS

The single crystals of $\text{CaKFe}_4\text{As}_4$ for NMR measurements were grown by high-temperature solution growth out of FeAs flux [9] and were extensively characterized by thermodynamic and transport measurements [9]. NMR measurements were carried out on ^{75}As ($I = 3/2$, $\gamma/2\pi = 7.2919$ MHz/T, $Q = 0.29$ barns) by using a laboratory-built, phase-coherent, spin-echo pulse spectrometer. The ^{75}As NMR spectra were obtained by sweeping the magnetic field at a fixed frequency $f = 53$ MHz. The magnetic field was applied parallel to either the crystalline c axis or the ab plane. The ^{75}As $1/T_1$ was measured with a recovery method using a single $\pi/2$ saturation pulse. In the normal state above T_c , the $1/T_1$ at each T was determined by fitting the nuclear magnetization M versus time t using the exponential function $1 - M(t)/M(\infty) = 0.1e^{-t/T_1} + 0.9e^{-6t/T_1}$ for ^{75}As NMR, where $M(t)$ and $M(\infty)$ are the nuclear magnetization at time t after the saturation and the equilibrium nuclear magnetization at $t \rightarrow \infty$, respectively. In the SC state, the function could not reproduce the M versus t data. Then we fitted the data with the two- T_1 component function $1 - M(t)/M(\infty) = M_S[0.1e^{-t/T_{1S}} + 0.9e^{-6t/T_{1S}}] + M_L[0.1e^{-t/T_{1L}} + 0.9e^{-6t/T_{1L}}]$, where $M_S + M_L = 1$. M_S and M_L correspond to the fractions for the short relaxation time T_{1S} and the long relaxation time T_{1L} , respectively. M_L is estimated to be ~ 0.5 in the temperature range of 4.3–25 K and then starts to increase slowly up to 1 at T_c . T_{1S} and T_{1L} could be attributed to T_1 for the As(2) and As(1) sites, respectively, in the SC state.

III. RESULTS AND DISCUSSION

A. ^{75}As NMR spectrum

Figure 1(a) shows typical field-swept ^{75}As NMR spectra of the $\text{CaKFe}_4\text{As}_4$ single crystal at $T = 36$ K for the two magnetic field directions: $H \parallel c$ axis and $H \parallel ab$ plane. The typical spectrum for a nucleus with spin $I = 3/2$ with Zeeman and quadrupolar interactions can be described by a nuclear spin Hamiltonian $\mathcal{H} = -\gamma\hbar(1 + K)HI_z + \frac{h\nu_Q}{6}[3I_z^2 - I(I + 1) + \frac{1}{2}\eta(I_+^2 + I_-^2)]$, where K is the Knight shift, h is Planck's constant, and $\hbar = h/2\pi$. The nuclear quadrupole frequency for $I = 3/2$ nuclei is given by $\nu_Q = eQV_{ZZ}/2h\sqrt{1 + \eta^2/3}$, where Q is the nuclear quadrupole moment, V_{ZZ} is the electric field gradient (EFG) along z at the As site, and $\eta = (V_{YY} - V_{XX})/V_{ZZ}$ is the in-plane asymmetry of the EFG tensor. For $I = 3/2$ nuclei, when the Zeeman interaction is much greater than the quadrupole interaction, this Hamiltonian produces a spectrum with a sharp central transition line flanked by a single satellite peak on each side for each equivalent As site. As shown in the crystal structure [inset of Fig. 1(a)], $\text{CaKFe}_4\text{As}_4$ has two inequivalent As sites: As(1) and As(2) close to the K and Ca layers, respectively. As seen in Fig. 1(a), we indeed observe two sets of $I = 3/2$ quadrupole split lines corresponding to the two As sites for each H direction. The observed ^{75}As NMR spectra are well reproduced by simulated spectra [the red and blue lines in Fig. 1(a)] from the above




FIG. 1. (a) Field-swept ^{75}As NMR spectra at $f = 53$ MHz for magnetic fields $H \parallel ab$ plane and $H \parallel c$ axis at $T = 36$ K. The red and blue lines are simulated spectra for the As(1) and As(2) sites, respectively. The inset shows the crystal structure of $\text{CaKFe}_4\text{As}_4$. (b) Temperature dependence of the central transition lines of ^{75}As NMR spectra for the As(1) and As(2) sites for $H \parallel c$ axis.

simple Hamiltonian where the Zeeman interaction is greater than the quadrupole interaction. Since the distance between the As(1) and Fe ions is $2.395(2)$ Å, which is slightly greater than $2.387(2)$ Å for the As(2) sites at 300 K [12], the As(1) site is expected to be less strongly coupled to the Fe ions than the As(2) sites. Thus we assign the lower-field central peak with the greater Knight shift K to the As(2) site and the higher-field central peak with the smaller K to the As(1) site [see Fig. 1(b)]. The well-separated As(1) and As(2) lines indicate that K and Ca ions are not randomly distributed but are well ordered, making the Ca and K layers without a significant site inversion.

The full width at half maximum (FWHM) of each satellite line is estimated to be 1.35 and 1.40 kOe for the As(1) and As(2) sites at 36 K and $H \parallel ab$ plane, respectively. Since the FWHM of the satellite line is proportional to the distribution of ν_Q and thus V_{ZZ} , the results indicate no large difference in inhomogeneity for the local As environments, again consistent with the ordering of the Ca and K ions for each plane. It is noted that these values are greater than ~ 0.75 kOe for the satellite line of ^{75}As NMR at 200 K and $H \parallel ab$ plane in CaFe_2As_2 , which exhibits a stripe-type antiferromagnetic order below $T_N \sim 170$ K [17], and are also greater than ~ 0.4 kOe at 10 K in the superconductor KFe_2As_2 with $T_c = 3.5$ K [18]. On the other hand, these values are smaller than the K-doped BaFe_2As_2 case, for example, ~ 2.5 kOe at 50 K in $\text{Ba}_{0.42}\text{K}_{0.58}\text{Fe}_2\text{As}_2$ [19].

The T dependence of the central transition lines of the As(1) and As(2) sites under H parallel to the c axis is shown in Fig. 1(b), where no obvious change in the spectra is observed down to $T_c = 33$ K, which is slightly reduced from the zero-field transition temperature due to the application of $H \sim 7.23$ T. The FWHM of the central line is nearly




FIG. 2. (a) Temperature dependences of the ^{75}As NMR shifts K_c and K_{ab} for the As(1) and As(2) sites. (b) Temperature dependences of quadrupole frequency ν_Q for the As(1) and As(2) sites, estimated from NMR and NQR spectra measurements. The ν_Q above 205 K were not determined due to poor signal intensity. ^{75}As ν_Q data for KFe_2As_2 [18] and CaFe_2As_2 [20] are also plotted for comparison.

independent of T , with ~ 46 and ~ 85 Oe for the As(1) and As(2) sites, respectively, in the normal state, indicating no magnetic and structural phase transitions above T_c . The difference in FWHM originates from the distribution of the hyperfine field at the As sites. The small hump between the As(1) and As(2) lines is not intrinsic, probably due to an unknown impurity, since no angle and temperature dependences are observed. Below T_c , the two intrinsic peaks shift to higher magnetic field, and at the same time, the lines become broad due to the SC transition. Even at 30 K, just 3 K below T_c , the two lines are smeared out, and no clear separation of the two lines is observed, as seen in Fig. 1(b). Despite a very low signal intensity, we were able to measure the spectrum at 4.2 K, which is very broad but still allows us to determine the peak position.

Figure 2(a) shows the T dependence of NMR shifts K_{ab} ($H \parallel ab$ plane) and K_c ($H \parallel c$ axis) for the two As sites. For both As sites, K are nearly independent of T above ~ 130 K and decrease very slightly down to T_c upon cooling. Similar weak T dependence of K is observed in $(\text{Ba}_{1-x}\text{K}_x)\text{Fe}_2\text{As}_2$ [19]. Below T_c , K_c for both the As sites show a sudden drop, indicating spin-singlet Cooper pairing.

B. ^{75}As quadrupole frequency

Figure 2(b) shows the T dependence of ν_Q for the two As sites estimated from the fit of the NMR spectra, together with the ^{75}As ν_Q data in KFe_2As_2 and CaFe_2As_2 . The ν_Q for the As(1) and As(2) sites are also obtained by nuclear quadrupole resonance (NQR) measurements under zero magnetic field. For the As(2) site, with decreasing T , ν_Q increases from 13.8 MHz at 205 K to 14.8 MHz at 36 K, while for the As(1) site an opposite trend is observed and ν_Q decreases from 13.2 MHz at 205 K to 12.2 MHz at 36 K with decreasing T . It is interesting to note that the T dependences of ν_Q of As(1) and As(2) are similar to those of ν_Q of the As site in KFe_2As_2 [18] and CaFe_2As_2 [20], respectively, as shown in Fig. 2(b). These results are also consistent with our site assignment.

In order to understand the peculiar temperature dependence of ν_Q for As(1) and As(2), we have performed a density functional study of the electric-field gradients in $\text{CaKFe}_4\text{As}_4$ under different assumptions concerning the structural and spin degrees of freedom.

By making use of the experimental lattice parameters measured between 6 and 300 K [9], two types of structures were created due to the present lack of knowledge of the internal positions of As and Fe; one type was obtained by fixing z_{Fe} and z_{As} to their values known for the 300 K structure ($z_{\text{Fe}} = 0.2319$; As: $z_{\text{Ca}} = 0.1235$ and $z_{\text{K}} = 0.3415$) and the volume adapted to the experimental data at each temperature. This procedure is equivalent to a uniform stretching of the crystal when going to higher temperatures. The second type of crystal structure was obtained by fixing the volume given at each temperature and relaxing the internal atomic positions. Magnetic fluctuations are taken into account, in a first approximation, by imposing different types of *frozen* magnetic order. This approach has been successfully applied to the recently discovered half-collapse transition in $\text{CaKFe}_4\text{As}_4$, where a specific type of spin configuration reproduces the structural behavior under external pressure [21]. In the present study, we analyze the effect of such (fluctuating) spin configurations on the EFGs V_{ZZ} on As sites. The latter were calculated fully relativistically in the generalized gradient approximation using the projector augmented wave pseudopotential method of the Vienna Ab initio Simulation Package (VASP) [22–26]. The integration over the irreducible Brillouin zone was realized on the Γ -centered $(10 \times 10 \times 10)$ k mesh. The V_{ZZ} values are converted to the quadrupole frequencies using the relation $\nu_Q = eQV_{ZZ}/2h\sqrt{1 + \eta^2}/3$, discussed already in Sec. III A. For clarity, we first consider here in detail the spin-vortex hedgehog phase [27] and compare its behavior to the purely nonmagnetic case. This type of order has one of the lowest energies among the configurations preserving the C_4 symmetry and has been determined already to play a role in pressure-induced structural collapse transitions in $\text{CaKFe}_4\text{As}_4$ [21], as well as in Co- and Ni-doped CaK1144 where a hedgehog long-range order has been identified [27].

Calculations of ν_Q in the hedgehog phase for both sets of structures show the same temperature trend as observed in our measurements [compare Fig. 3(b) with Fig. 2(b)]. The first set of structures [z_{As} fixed structures, solid lines in Fig. 3(b)] indicates a significantly nonzero splitting between the two As frequencies at low temperature [$\Delta\nu_Q = 2.5$ MHz




FIG. 3. (a) Sketches of (i) the spin-vortex hedgehog and (ii) the stripe spin structures of $\text{CaKFe}_4\text{As}_4$. Theoretical estimates of the As quadrupole frequencies ν_Q vs temperature (b) assuming an underlying spin-vortex hedgehog magnetic configuration (Fe spins in one of the FeAs layers are shown in the inset) compared to (c) the nonmagnetic phase. As(1) and As(2) stand for As sites near the K and Ca layers. Solid lines in (b) and (c) represent simulations with structures where the two As positions z_{As} are fixed at the experimental values at room temperature, while the dashed lines correspond to the z_{As} optimized in each case [with magnetism in (b) and without it in (c)]. (d) Calculated ν_Q for the stripe order with fixed and optimized As positions.

at 6 K and $\nu_Q(\text{Ca}) > \nu_Q(\text{K})$], while the splitting is almost zero in the room-temperature structure [$\nu_Q(\text{Ca}) \approx \nu_Q(\text{K})$]. Our low-temperature estimate of $\Delta\nu_Q$ is in good agreement with the experimental result $\Delta\nu_Q = 2.5$ MHz, although both calculated frequencies are ~ 2.5 MHz lower than in experiment. The second set of structures (z_{As} relaxed structures; see Table I) shows that relaxation of the internal positions induces slight changes of z_{As} for As(1) and As(2) which translate into a shortening of the As-As bonds across the Ca layer and their

TABLE I. Temperature dependence of Fe magnetic moments for the $\text{CaKFe}_4\text{As}_4$ hedgehog structures depicted in Fig. 3(a), sketch (i), with optimized Fe and As positions compared with the Fe moments for the case when the internal positions are fixed at their room-temperature values ($z_{\text{Fe}} = 0.2319$; As: $z_{\text{Ca}} = 0.1235$ and $z_{\text{K}} = 0.3415$). The measured lattice parameters a and c from Ref. [9] are given at each temperature.

T (K)	Fixed z_{As}		Optimized z_{As}			
	$m_{\text{Fe}} (\mu_B)$	$m_{\text{Fe}} (\mu_B)$	z_{Ca}	z_{K}	a (Å)	c (Å)
6	1.51	1.32	0.12318	0.33286	3.861	12.675
50	1.51	1.32	0.12319	0.33276	3.862	12.682
100	1.52	1.33	0.12320	0.33251	3.862	12.705
150	1.55	1.33	0.12323	0.33213	3.864	12.737
200	1.57	1.34	0.12325	0.33169	3.866	12.773
250	1.58	1.36	0.12325	0.33130	3.867	12.802
300	1.62	1.36	0.12325	0.33081	3.870	12.838

stretching across the K layer. Accordingly, in the optimized structures, the Fe magnetic moment is slightly diminished compared to the nonrelaxed structures, which is correlated to the overall smaller Fe-As distances (Table I). As a function of temperature, the relaxed Fe-As distances barely change, which is in contrast to the case of fixed z_{As} , where these distances decrease upon cooling. Upon structure optimization, ν_Q for the Ca layer is almost uniformly increased by ~ 1.4 – 1.8 MHz at all temperatures [compare dashed and solid lines for As(2) in Fig. 3(b)], while ν_Q for the K layer [As(1)] is much less affected. The effect of z_{As} optimization on the NQR properties can be interpreted in terms of the Fe moments, which change by only $0.04\mu_B$ with temperature, while they increase by $0.11\mu_B$ and have, in general, a larger magnitude when z_{As} is fixed at all temperatures, as highlighted in Table I. Furthermore, the Fe-As and As-As bonding certainly affects the size and ordering of ν_Q , but it is not the only determining factor.

Illustrative of the role of magnetic degrees of freedom is a comparison with the results for the truly nonmagnetic state with zero Fe local moments [Fig. 3(c)]. The order of the quadrupole frequencies is reversed, leading to $\nu_Q(\text{Ca}) < \nu_Q(\text{K})$, and no crossing is observed at higher temperatures, which contradicts the experimental observations. Optimizing z_{As} for this nonmagnetic state restores the correct order $\nu_Q(\text{Ca}) > \nu_Q(\text{K})$, but the splitting $\Delta\nu_Q$ is severely overestimated compared to the spin-polarized calculations and experiment. In addition, one of the quadrupole frequencies is significantly underestimated by a factor of 2 compared to the measured values of ν_Q . Finally, from Fig. 3(d), we see that the stripe configuration provides values of the quadrupole frequencies similar to those of the hedgehog order. The stripe order is close in energy to the hedgehog order, which is discussed in detail in Ref. [27]. The quadrupole frequencies resulting from the magnetic fluctuations may be approximated by an average of the data shown in Figs. 3(b) and 3(d). Such an average would stay in good agreement with the measured ν_Q .

These results show that both temperature-dependent structural features, nonzero Fe moment, and the type of magnetic fluctuations shape the temperature evolution of NQR in $\text{CaKFe}_4\text{As}_4$. In this respect, different temperature behavior of the quadrupole frequencies for the two crystallographically inequivalent As sites might indicate the presence of C_4 -type magnetic fluctuations competing with the usual stripe fluctuations, as suggested by the first-principles analysis. Additional calculations (not shown here) suggest that the splitting between the quadrupole frequencies of As(1) and As(2) is sensitive to pressure, especially near the half-collapse transition around 4 GPa [21]. Finally, it is noted that the origin of the opposite T dependence of ν_Q in CaFe_2As_2 and KFe_2As_2 is still an open question. It is interesting to see that our approach based on the first-principles calculation explains this behavior; however, disentangling the details of the various trends requires further investigations that are beyond the scope of the present study.

C. ^{75}As spin-lattice relaxation rate $1/T_1$

In order to investigate magnetic fluctuations in CaK1144 , we measured $1/T_1$ at various temperatures. Figure 4 shows the T dependences of $1/T_1$ of both As sites for magnetic field




FIG. 4. Temperature dependences of $1/T_1$ of both As sites for $H \parallel c$ axis and $H \parallel ab$ plane. The black and red lines show the power-law temperature dependence with an exponent of 0.6 and 0.2 for the As(2) and As(1) sites, respectively. The blue lines are calculated $1/T_1$ with a two-full gapped s model using the SC gap parameters of $\Delta = 2.0 \pm 0.4$ and 20 ± 9 meV for $1/T_{1L}$ and $\Delta = 1.9 \pm 0.4$ and 16 ± 8 meV for $1/T_{1S}$. The inset shows the semilog plots of $1/T_{1S}$ and $1/T_{1L}$ vs $1/T$ in the SC state.

directions $H \parallel c$ axis and $H \parallel ab$ plane. The $1/T_1$ of the As(2) sites is nearly T independent above $T^* \sim 130$ K for both H directions. Below T^* , $1/T_1$ decreases with a power-law T dependence of $1/T_1 \propto T^{0.6}$, as shown by the black line in Fig. 4. A similar T dependence of ^{75}As $1/T_1$ has been reported in AFe_2As_2 ($A = \text{K, Rb, Cs}$), where $1/T_1$ increases with a power law $1/T_1 \propto T^{0.75}$ and levels off above $T^* \sim 165, 125,$ and 85 K for $A = \text{K, Rb, and Cs}$, respectively [28]. Such a characteristic T dependence of $1/T_1$ is often observed in heavy-fermion systems where the exponent strongly depends on the type of quantum criticality nearby, such as 1 for URu_2Si_2 [29], 0.25 for CeCoIn_5 [30], and 0 for YbRh_2Si_2 [31].

As for the As(1) sites, a similar T dependence is also observed, but the exponent is found to be ~ 0.2 , which is smaller than 0.6 for the As(2) sites. Since As(1) and As(2) are expected to probe the same spin dynamics from the Fe layers, one naively expects a similar T dependence of $1/T_1$ for both sites, although the magnitude can be different due to different hyperfine coupling constants. The results suggest that the Fe spins produce different magnetic fluctuations at the As(1) and As(2) sites in CaK1144 , and a possible origin of the different T dependences of $1/T_1$ is discussed later.

In the SC state below $T_c \sim 33$ K, we attempted to measure $1/T_1$ at the As(1) site for $H \parallel c$ axis. As described above, however, we could not distinguish the two As sites due to the broadening of the spectra. Therefore $1/T_1$ is measured at the peak position of the spectrum at low T . Because of the overlap of the spectra, we found two T_1 components: short (T_{1S}) and long (T_{1L}) relaxation times, which could be attributed to T_1 for the As(2) and As(1) sites, respectively. Just below T_c , both $1/T_{1L}$ and $1/T_{1S}$ decrease rapidly without any coherence peak, consistent with an s^\pm model. With further decrease of T , both $1/T_{1L}$ and $1/T_{1S}$ show broad humps around ~ 15 K and exponential decreases at lower T , which can be clearly seen in the semilog plot of $1/T_1$ vs $1/T$ shown in the inset of Fig. 4. Similar behavior of $1/T_1$ in the SC state has been observed in $\text{LaFeAsO}_{1-x}\text{F}_x$ [32] and $\text{K-doped BaFe}_2\text{As}_2$ superconductors [33,34]. These results suggest a SC state with multiple full gaps, consistent with previous measurements. In fact, the T dependence of $1/T_1$ is roughly reproduced by a two-full-gap model with superconducting gap parameters $\Delta = 2.0 \pm 0.4$ and 20 ± 9 meV for $1/T_{1L}$ and $\Delta = 1.9 \pm 0.4$ and 16 ± 8 meV for $1/T_{1S}$, as shown by the solid lines. The smaller gap of ~ 2.0 meV is not far from the 2.5 meV obtained from the μSR measurements [10] and in good agreement with the 1–4 meV from the TDR and STM measurements [11]. On the other hand, the larger gaps of 20 ± 9 and 16 ± 8 meV seem to be greater than the 6–9 meV from the other measurements [11]. However, it should be noted that our estimates of the larger gap have a large uncertainty due to the poor statistical accuracy and relatively narrow T range for the fit; therefore it should be regarded as a tentative estimate.

Now we discuss magnetic fluctuations in the normal state. Figures 5(a) and 5(b) show the T dependences of $1/T_1 T$ for $H \parallel c$ and $H \parallel ab$ in CaK1144 . For comparison, we also plot the T_1 data of KFe_2As_2 ($T_c = 3.5$ K) [19], $\text{Ba}_{0.45}\text{K}_{0.55}\text{Fe}_2\text{As}_2$ ($T_c = 34$ K) [19], and $\text{Ba}_{0.68}\text{K}_{0.32}\text{Fe}_2\text{As}_2$ ($T_c = 38.5$ K) [33]. The $1/T_1 T$ at the As(1) site is comparable to those of $\text{Ba}_{0.45}\text{K}_{0.55}\text{Fe}_2\text{As}_2$ and $\text{Ba}_{0.68}\text{K}_{0.32}\text{Fe}_2\text{As}_2$, while for the As(2) sites $1/T_1 T$ is larger than in the KFe_2As_2 case. All $1/T_1 T$ show a monotonic increase down to T_c with decreasing T except for $\text{Ba}_{0.45}\text{K}_{0.55}\text{Fe}_2\text{As}_2$, where $1/T_1$ decreases at low T , showing gaplike behavior [19]. In general, $1/T_1 T$ is related to the dynamical magnetic susceptibility as $\frac{1}{T_1 T} = \frac{2\gamma_N^2 k_B}{N_A} \sum_{\vec{q}} |A(\vec{q})|^2 \frac{\chi''(\vec{q}, \omega_0)}{\omega_0}$, where $A(\vec{q})$ is the wave-vector- \vec{q} -dependent form factor and $\chi''(\vec{q}, \omega_0)$ is the imaginary part of the dynamic susceptibility at the Larmor frequency ω_0 . Although the exponents of the power-law behavior of $1/T_1$ for As(1) and As(2) are different, we can attribute the increase of $1/T_1 T$ to the growth of AFM spin fluctuations at $q \neq 0$ since both K_c and K_{ab} , reflecting $\chi'(q = 0, \omega_0 = 0)$, are nearly independent of T .

In order to see the nature of spin correlations, we plotted the ratio of $1/T_1$ for the two field directions, $r \equiv T_{1,c}/T_{1,ab}$. According to previous NMR studies performed on Fe pnictides and related materials [19,35–37], the ratio r depends on AFM spin correlation modes as

$$r = \begin{cases} 0.5 + \left(\frac{S_{ab}}{S_c}\right)^2 & \text{for } \mathbf{q} = (\pi, 0) \text{ or } (0, \pi), \\ 0.5 & \text{for } \mathbf{q} = (\pi, \pi), \end{cases} \quad (1)$$




FIG. 5. Temperature dependence of $1/T_1T$ in $\text{CaKFe}_4\text{As}_4$, together with those in $\text{Ba}_{1-x}\text{K}_x\text{Fe}_2\text{As}_2$ ($x = 0.32, 0.55$, and 1). (a) $H \parallel c$ axis. (b) $H \parallel ab$ plane.

where \mathcal{S}_α is the amplitude of the spin-fluctuation spectral density at the NMR frequency along the α direction. The wave vectors are given in the single-iron Brillouin zone notation.

As plotted in Fig. 6(a), the ratios for both the As(1) and As(2) sites are close to $r \sim 1.5$. This indicates that the spin fluctuations in $\text{CaKFe}_4\text{As}_4$ are characterized by the AFM spin fluctuations with $q = (\pi, 0)$ or $(0, \pi)$ and $\mathcal{S}_c \sim \mathcal{S}_{ab}$ indicating the isotropic spin fluctuations. In order to confirm the AFM spin correlations, we have calculated $\chi(q)$ [38] using the full-potential linearized augmented plane-wave method [39] with a generalized gradient approximation [40]. The calculated $\chi(q)$ is shown in the inset of Fig. 6(a), which actually exhibits the AFM spin correlations where a peak around the wave vector $\mathbf{q} = (\pi, 0)$ or $(0, \pi)$ is observed with a small structure. A similar structure in $\chi(q)$ was reported in CaFe_2As_2 [41].

In most of the Fe pnictide SCs, the AFM fluctuations are described in terms of the stripe-type spin fluctuations. Recently, another possible AFM fluctuation with q vectors $[(\pi, 0)$ and $(0, \pi)]$ was proposed in the spin-vortex crystal state where Fe spins are noncollinear and form spin vortices staggered across the iron square lattices [42]. Since the stripe- and spin-vortex-type states produce the AFM spin correlations with the same q , in general, it would be difficult




FIG. 6. (a) Temperature dependence of $r \equiv T_{1,c}/T_{1,ab}$ for the As(1) and As(2) sites. The horizontal dashed lines at $r = 1.5$ and 0.5 correspond to the ratios for the AFM spin fluctuations with $q = (\pi, 0)$ [or $(0, \pi)$] and (π, π) , respectively. The inset shows the calculated $\chi(q)$ vs q . (b) Temperature dependences of $T_1[\text{As}(2)]/T_1[\text{As}(1)]$ for $H \parallel c$ and $H \parallel ab$.

to distinguish between the two different spin correlations from the T_1 measurements. However, $\text{CaKFe}_4\text{As}_4$ provides us with a special occasion to distinguish between them. In the hedgehog vortex ordered state, the internal fields at As(1) are calculated to be finite along the c axis, while the internal field at As(2) is zero due to a cancellation originating from the characteristic spin structure [27]. Therefore one expects that $1/T_1T$ for As(1) is more enhanced than that for As(2) if the AFM spin fluctuations originate from the spin-vortex hedgehog-type spin correlations. On the other hand, in the case of stripe-type AFM fluctuations, the temperature dependence of $1/T_1T$ for As(1) should scale to that of $1/T_1T$ for As(2) sites since there is no cancellation of the internal field at both As sites [27]. The $1/T_1T$ for As(1) divided by $1/T_1T$ for As(2) for $H \parallel c$ and $H \parallel ab$ are shown in Fig. 6(b), where clear enhancements are observed below ~ 150 K. Above ~ 150 K, the ratios of $T_1[\text{As}(2)]/T_1[\text{As}(1)]$ show a nearly temperature independent value of ~ 0.35 , which could be determined by the different hyperfine coupling constants for the As(1) and As(2) sites. The increases below ~ 150 K indicate that the As(1) sites pick up the AFM spin fluctuations more strongly than the As(2) sites, consistent with the case of hedgehog-type spin

fluctuations. Our *ab initio* DFT total energy calculations show that both stripe order and spin-vortex order are energetically competing in $\text{CaKFe}_4\text{As}_4$, and the temperature dependence of ν_Q , as presented above, is well described by assuming a hedgehog spin-vortex order. Furthermore, a hedgehog spin-vortex order was recently observed in Co-doped and Ni-doped $\text{CaKFe}_4\text{As}_4$ [27]. Therefore our results strongly indicate the existence of the spin-vortex hedgehog-type spin correlations in the paramagnetic state. Further experimental and theoretical studies are important to elucidate more details of the characteristics of the hedgehog-type spin correlations and also their relationship to superconductivity in $\text{CaKFe}_4\text{As}_4$ and the carrier-doped $\text{CaKFe}_4\text{As}_4$.

IV. SUMMARY

In conclusion, we have carried out ^{75}As NMR measurements in the single-crystalline $\text{CaKFe}_4\text{As}_4$. The observation of two distinct ^{75}As NMR lines indicates that K and Ca ions are not randomly distributed but are well ordered, forming the Ca and K layers without a significant site inversion. We found that ν_Q of the As(1) and As(2) sites show an opposite T dependence. Based on our *ab initio* density functional theory calculations, this behavior might originate from the presence of spin-vortex hedgehog-type spin fluctuations which represent a superposition of $(\pi, 0)$ and $(0, \pi)$ stripe fluctuations. We found that the calculated quadrupole frequencies are comparably affected by the Fe-As and As-As bonding, nonzero Fe

moments, and the underlying magnetic order which simulates the spin fluctuations to a first approximation. In the normal state, we also observed evidence of the enhancement of isotropic AFM spin fluctuations with wave vector $\mathbf{q} = (\pi, 0)$ or $(0, \pi)$ in the T dependences of $1/T_1 T$ and K . It is suggested that the different T dependences of $1/T_1$ for the As(1) and As(2) sites are explained by the peculiar spin fluctuations due to the spin-vortex hedgehog-type spin correlations. In the SC state, we observed a sudden decrease in K , indicating spin-singlet Cooper pairs. The $1/T_1$ shows a rapid decrease below T_c without showing a Hebel-Slichter peak and decreases exponentially at low temperatures. These results indicate an s^\pm nodeless two-gap SC state.

ACKNOWLEDGMENTS

The authors would like to thank K. Rana for his assistance with NQR experiments. We also thank P. Wiecki, R. Fernandes, P. Orth, I. Mazin, and A. Kreyssig for helpful discussions. The research was supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering. Ames Laboratory is operated for the U.S. Department of Energy by Iowa State University under Contract No. DE-AC02-07CH11358. W.R.M. was supported by the Gordon and Betty Moore Foundation's EPiQS Initiative through Grant No. GBMF4411. V.B. and R.V. are supported by the Deutsche Forschungsgemeinschaft through Grant No. SFB/TRR 49, and the computer time was allotted by the center for supercomputing (CSC) in Frankfurt.

-
- [1] Y. Kamihara, T. Watanabe, M. Hirano, and H. Hosono, *J. Am. Chem. Soc.* **130**, 3296 (2008).
- [2] M. Rotter, M. Tegel, and D. Johrendt, *Phys. Rev. Lett.* **101**, 107006 (2008).
- [3] D. C. Johnston, *Adv. Phys.* **59**, 803 (2010).
- [4] P. C. Canfield and S. L. Bud'ko, *Annu. Rev. Condens. Matter Phys.* **1**, 27 (2010).
- [5] N. Ni, S. Nandi, A. Kreyssig, A. I. Goldman, E. D. Mun, S. L. Bud'ko, and P. C. Canfield, *Phys. Rev. B* **78**, 014523 (2008).
- [6] C. W. Chu, F. Chen, M. Gooch, A. M. Guloy, B. Lorenz, B. Lv, K. Sasmal, Z. J. Tang, J. H. Tapp, and Y. Y. Xue, *Phys. C (Amsterdam, Neth.)* **469**, 326 (2009).
- [7] G. R. Stewart, *Rev. Mod. Phys.* **83**, 1589 (2011).
- [8] A. Iyo, K. Kawashima, T. Kinjo, T. Nishio, S. Ishida, H. Fujihisa, Y. Gotoh, K. Kihou, H. Eisaki, and Y. Yoshida, *J. Am. Chem. Soc.* **138**, 3410 (2016).
- [9] W. R. Meier, T. Kong, U. S. Kaluarachchi, V. Taufour, N. H. Jo, G. Drachuck, A. E. Böhrer, S. M. Saunders, A. Sapkota and A. Kreyssig, M. A. Tanatar, R. Prozorov, A. I. Goldman, F. F. Balakirev, A. Gurevich, S. L. Bud'ko, and P. C. Canfield, *Phys. Rev. B* **94**, 064501 (2016).
- [10] P. K. Biswas, A. Iyo, Y. Yoshida, H. Eisaki, K. Kawashima, and A. D. Hillier, *Phys. Rev. B* **95**, 140505 (2017).
- [11] K. Cho, A. Fente, S. Teknowijoyo, M. A. Tanatar, K. R. Joshi, N. M. Nusran, T. Kong, W. R. Meier, U. Kaluarachchi, I. Guillamón, H. Suderow, S. L. Bud'ko, P. C. Canfield, and R. Prozorov, *Phys. Rev. B* **95**, 100502 (2017).
- [12] D. Mou, T. Kong, W. R. Meier, F. Lochner, L.-L. Wang, Q. Lin, Y. Wu, S. L. Bud'ko, I. Eremin, D. D. Johnson, P. C. Canfield, and A. Kaminski, *Phys. Rev. Lett.* **117**, 277001 (2016).
- [13] K. Ishida, Y. Nakai, and H. Hosono, *J. Phys. Soc. Jpn.* **78**, 062001 (2009).
- [14] J. Paglione and R. L. Greene, *Nat. Phys.* **6**, 645 (2010).
- [15] P. Wiecki, B. Roy, D. C. Johnston, S. L. Bud'ko, P. C. Canfield, and Y. Furukawa, *Phys. Rev. Lett.* **115**, 137001 (2015).
- [16] J. Cui, P. Wiecki, S. Ran, S. L. Bud'ko, P. C. Canfield, and Y. Furukawa, *Phys. Rev. B* **94**, 174512 (2016).
- [17] Y. Furukawa, B. Roy, S. Ran, S. L. Bud'ko, and P. C. Canfield, *Phys. Rev. B* **89**, 121109 (2014).
- [18] P. Wiecki, P. C. Canfield, and Y. Furukawa (unpublished).
- [19] M. Hirano, Y. Yamada, T. Saito, R. Nagashima, T. Konishi, T. Toriyama, Y. Ohta, H. Fukazawa, Y. Kohori, Y. Furukawa, K. Kihou, C.-H. Lee, A. Iyo, and H. Eisaki, *J. Phys. Soc. Jpn.* **81**, 054704 (2012).
- [20] J. Cui, B. Roy, M. A. Tanatar, S. Ran, S. L. Bud'ko, R. Prozorov, P. C. Canfield, and Y. Furukawa, *Phys. Rev. B* **92**, 184504 (2015).
- [21] U. S. Kaluarachchi, V. Taufour, A. Sapkota, V. Borisov, T. Kong, W. R. Meier, K. Kothapalli, B. G. Ueland, A. Kreyssig, R. Valentí, R. J. McQueeney, A. I. Goldman, S. L. Bud'ko, and P. C. Canfield, *arXiv:1702.06622*.
- [22] G. Kresse and J. Hafner, *Phys. Rev. B* **47**, 558 (1993).
- [23] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [24] G. Kresse and J. Furthmüller, *Comput. Mater. Sci.* **6**, 15 (1996).
- [25] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).

- [26] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- [27] W. R. Meier, Q.-P. Ding, A. Kreyssig, S. L. Bud'ko, A. Sapkota, K. Kothapalli, V. Borisov, R. Valentí, C. D. Batista, P. P. Orth, R. M. Fernandes, A. I. Goldman, Y. Furukawa, A. E. Böhmer, and P. C. Canfield, [arXiv:1706.01067](https://arxiv.org/abs/1706.01067).
- [28] Y. P. Wu, D. Zhao, A. F. Wang, N. Z. Wang, Z. J. Xiang, X. G. Luo, T. Wu, and X. H. Chen, *Phys. Rev. Lett.* **116**, 147001 (2016).
- [29] T. Kohara, Y. Kohori, K. Asayama, Y. Kitaoka, M. B. Maple, and M. S. Torikachvili, *Solid State Commun.* **59**, 603 (1986).
- [30] Y. Kohori, Y. Yamato, Y. Iwamoto, T. Kohara, E. D. Bauer, M. B. Maple, and J. L. Sarrao, *Phys. Rev. B* **64**, 134526 (2001).
- [31] K. Ishida, K. Okamoto, Y. Kawasaki, Y. Kitaoka, O. Trovarelli, C. Geibel, and F. Steglich, *Phys. Rev. Lett.* **89**, 107202 (2002).
- [32] T. Oka, Z. Li, S. Kawasaki, G. F. Chen, N. L. Wang, and G.-Q. Zheng, *Phys. Rev. Lett.* **108**, 047001 (2012).
- [33] Z. Li, D. L. Sun, C. T. Lin, Y. H. Su, J. P. Hu, and G.-Q. Zheng, *Phys. Rev. B* **83**, 140506 (2011).
- [34] K. Matano, Z. Li, G. L. Sun, D. L. Sun, C. T. Lin, M. Ichioka, and G.-Q. Zheng, *Europhys. Lett.* **87**, 27012 (2009).
- [35] K. Kitagawa, N. Katayama, K. Ohgushi, and M. Takigawa, *J. Phys. Soc. Jpn.* **78**, 063706 (2009).
- [36] S. Kitagawa, Y. Nakai, T. Iye, K. Ishida, Y. Kamihara, M. Hirano, and H. Hosono, *Phys. Rev. B* **81**, 212502 (2010).
- [37] A. Pandey, D. G. Quirinale, W. Jayasekara, A. Sapkota, M. G. Kim, R. S. Dhaka, Y. Lee, T. W. Heitmann, P. W. Stephens, V. Ogloblichev, A. Kreyssig, R. J. McQueeney, A. I. Goldman, A. Kaminski, B. N. Harmon, Y. Furukawa, and D. C. Johnston, *Phys. Rev. B* **88**, 014526 (2013).
- [38] To obtain self-consistent charge density, we employed $R_{\text{MT}k_{\text{max}}} = 8.0$ and muffin-tin radii $R_{\text{MT}} = 2.0$ a.u. for all atoms. We selected 364 \mathbf{k} points in the irreducible Brillouin zone (BZ) and calculated the band structure with 67,626 \mathbf{k} points, which resulted from a $100 \times 100 \times 100$ division of the whole BZ.
- [39] P. Blaha, K. Schwarz, G. K. H. Madsen, D. Kvasnick, and J. Luitz, WIEN2K, an augmented plane wave + local orbitals program for calculation crystal properties, Technical Universität Wien, Vienna, 2001.
- [40] J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [41] A. I. Goldman, A. Kreyssig, K. Prokeš, D. K. Pratt, D. N. Argyriou, J. W. Lynn, S. Nandi, S. A. J. Kimber, Y. Chen, Y. B. Lee, G. D. Samolyuk, J. B. Leão, S. J. Poulton, S. L. Bud'ko, N. Ni, P. C. Canfield, B. N. Harmon, and R. J. McQueeney, *Phys. Rev. B* **79**, 024513 (2009).
- [42] R. M. Fernandes, S. A. Kivelson, and E. Berg, *Phys. Rev. B* **93**, 014511 (2016).