Scattering of phonons by quantum-dislocation segments in an elastic continuum

Fernando Lund^{1,2,*} and Bruno Scheihing H.¹

¹Departamento de Física, Facultad de Ciencias Físicas y Matemáticas, Universidad de Chile, Santiago 8370448, Chile ²CIMAT, Facultad de Ciencias Físicas y Matemáticas, Universidad de Chile, Santiago 8370448, Chile

(Received 20 March 2019; revised manuscript received 30 April 2019; published 5 June 2019)

A canonical quantization procedure is applied to elastic waves interacting with pinned dislocation segments ("strings") of length L via the Peach-Koehler force. The interaction Hamiltonian, derived from an action principle that classically generates the Peach-Koehler force, is a power series of creation and annihilation operators. The leading term is quadratic, and keeping only this term the observable quantities of scattering processes are computed to all orders in perturbation theory. The resulting theory is characterized by the magnitude of kL, with k the wave number of an incident phonon. The theory is solved for arbitrary kL, and different limits are explored. A significant result at this level is the scattering cross section for phonons by dislocation segments. As a function of frequency, this cross section has a much richer structure than the linear-in-frequency behavior that is inferred from scattering by an infinite, static, dislocation. The rate of spontaneous phonon emission by an excited dislocation is computed as well. When many dislocations are present, an effective mass operator is computed in the weak and independent scattering approximation. The contribution of the cubic terms is computed to leading order in perturbation theory. They allow for a comparison of the scattering of a phonon by a string and the three-phonon scattering, as well as studying the dependence of scattering amplitudes on the temperature of the solid. It is concluded that the effect of dislocations of Burgers vector 0.5 nm and length 50 nm will dominate for relatively modest dislocation densities: 10^8 cm⁻². Finally, the full power series of the interaction Hamiltonian is considered. The effects of quantum corrections, i.e., contributions proportional to Planck's constant, are estimated, and found to be controlled by another wave-number-dependent parameter kd_a , where d_q is a length proportional to \sqrt{h} . The possibility of using the results of this paper in the study of the phononic thermal properties of two- and three-dimensional materials is noted and discussed.

DOI: 10.1103/PhysRevB.99.214102

I. INTRODUCTION

The interaction of phonons with dislocations has long been a subject of concern. Thermal transport, particularly in insulators, and thermoelectric materials are two overlapping perspectives where this concern is of central importance. In a classic paper, Klemens [1] computed the scattering of low-frequency (so that dispersion effects could be neglected) phonons by a number of static imperfections, including infinitely long, straight dislocations. This configuration was also considered by Carruthers [2], who considered a modified version of the potential energy. One important insight that came out of this very simplified approach is that dislocations should be far more efficient scattering phonons that travel perpendicular, rather than parallel, to the dislocation line. Another is that phonon scattering by the strain field of a static dislocation is characterized by a relaxation time inversely proportional to frequency. To this day, these works appear to be the main source of information to analyze the role of dislocations in thermal transport experimental data [3-5].

Quite recently, it has become possible to bring out the contribution of dislocations to thermal transport: Kim *et al.* [6,7] obtained a significant lowering of thermal conductivity in $Bi_{0.5}Sb_{1.5}Te_3$ through the introduction of dense dislocation arrays within grain boundaries. Xie *et al.* [8] report a 50%

reduction in lattice thermal conductivity due to dislocations in Si-based thermoelectric composites. Chen *et al.* [9] have obtained very low values of lattice thermal conductivity in $Pb_{1-x}Sb_{2x/3}Se$ solid solutions, by way of generating dense arrays of uniformly distributed dislocations in the grains. Zhou *et al.* [10] have rationally included point defects, vacancy driven dense dislocations, and nanoprecipitates in a *n*-type PbSe thermoelectric material to obtain a lattice thermal conductivity approaching that of the amorphous limit. A precise, quantitative, appraisal of the dislocation contribution to thermal conductivity still faces considerable challenges, however, as emphasized by Wang *et al.* [11]. The classical models are simply not able to cope with the data and there is a clear need for better models. This paper aims at filling this gap.

An interesting step has been taken by Sun *et al.* [12], who have measured a significant thermal transport anisotropy in micron-thick, single-crystal InN films with highly oriented dislocation arrays. The influence of dislocations in these results is quite unambiguous, and points to the very real possibility of engineering defects, particularly dislocations, to obtain desired thermal performances. The theoretical framework currently available is, again, not enough to rationalize these measurements and improvements are needed.

A dislocation that is hit by a phonon will typically respond by bowing out, oscillating, and reradiating secondary phonons. This process can lead to resonances which may affect the scattering cross section, and the resulting relaxation time, considerably. At first sight, one could think that

^{*}Corresponding author: flund@cimat.cl

resonance would be effective only for phonons whose wavelength is comparable to the distance between pinning points for a pinned dislocation, say tens of nanometers, and hence not relevant at most working temperatures when the dominant phonon wavelength is much shorter. A closer look, however, reveals that, thinking of the dislocation as an elastic string, there will be resonant scattering not only when the phonon frequency coincides with the fundamental mode of vibration of the string, but also when it coincides with any of the higherorder modes of vibration. This dynamical mechanism was tackled by Ninomiya [13,14] for an infinitely long dislocation line that can oscillate around a straight equilibrium position, coupled to phonons through the kinetic-energy terms but not through the potential-energy terms. Building on the work of Ninomiya [13,14], Li et al. [15-17] have recently developed a theory of phonons, and electrons, in interaction with the quantum normal modes (termed "dislons") of an infinitely long straight dislocation. The question that naturally arises is: what is the quantum description of dislocation segments of finite length interacting with phonons? In this paper we address this issue.

The interaction of classical elastic waves with infinitely thin dislocations segments of finite length—the "string model"—has been a topic of active research for decades [18,19]. A comparatively recent result is the computation of the scattering cross section for classical elastic waves by pinned dislocation segments [20], as well as by prismatic dislocation loops [21]. Use of the formalism developed therein, together with multiple-scattering theory, has enabled the computation of an effective, complex, index of refraction for the propagation of coherent elastic waves in a medium filled with randomly distributed and oriented, pinned dislocation segments [22,23]. In turn, this has led to nonintrusive acoustic characterization tools to describe the plasticity of metals and alloys [24–26].

The quantum theory of elastic waves in interaction with dislocations has been far less studied. In addition to the analytical work of Ninomiya [13,14] and Li *et al.* [15–17] already mentioned, Wang *et al.* [27] have performed a numerical *ab initio* calculation of phonon scattering by a dipole of edge dislocations in silicon. They infer, from their calculation, that high but realistic dislocation concentrations can significantly influence thermal conductivity at room temperature and above. Also, their results are qualitatively at variance with the classic ones [1,2]

This paper is organized as follows: Section II has a brief review of the classical theory that we shall quantize. Section III describes the canonical quantization of the free theory. The interaction term involves polynomial interactions between phonons and quantum strings. Section IV solves the quantum theory retaining only the quadratic interactions but to all orders in perturbation theory, which turns out to be equivalent to have a solution for arbitrary phonon wavelengths: short, comparable, and long compared to string length *L*. Sections IV A and IV B provide the scattering cross section for phonons by dislocations, while Sec. IV C gives the mass operator when many dislocations are present in the weak and independent scattering approximation. Section V computes the contribution of cubic terms in the interaction, to leading order in perturbation theory. This allows for a comparison of phonon-dislocation scattering with three-phonon processes, including the effect of temperature. Finally, Sec. VI solves the theory for the full polynomial interaction, to leading order in perturbation theory in which a characteristic length proportional to the square root of Planck's constant emerges. Section VII has concluding remarks. A number of technical computations are provided in four Appendixes.

II. CLASSICAL ACTION

In this paper we work out the quantum theory of oscillating dislocation segments, of length L, in interaction with elastic waves in three dimensions.

We consider a homogeneous, isotropic, elastic, continuum solid of density ρ and elastic constants c_{pqmr} , (p, q = 1, 2, 3)within which there is a stringlike dislocation line. The variables describing the solid are the displacements $\mathbf{u}(\mathbf{x}, t)$, at time t, of a point whose equilibrium position is \mathbf{x} . In addition, there is a string described by a vector $\mathbf{X}(s, t)$, where 0 < s < tL is a position parameter along the string whose ends are fixed. The fact that the string is a dislocation is implemented through the fact that the displacements $\mathbf{u}(\mathbf{x}, t)$ are multivalued functions: They have a discontinuity equal to the Burgers vector **b** when crossing a surface, part of whose boundary includes the string with fixed ends. In addition to this geometrical fact, the coupling between elastic displacements and elastic string is given by standard conservation of energy and momentum arguments. When dislocation velocities are small compared to the speed of sound, an assumption we shall make throughout this paper, this leads to the well-known Peach-Koehler force [28]. In the time-dependent case, and for string velocities small compared to the speed of sound, the dynamics is described by the following classical action [29]:

$$S = S_{\rm ph} + S_{\rm string} + S_{\rm int} + S_0,$$

(1)

where

$$S_{\rm ph} = \frac{1}{2} \int dt \int d^3x \left(\rho \dot{\mathbf{u}}^2 - c_{pqmr} \frac{\partial u_m}{\partial x_q} \frac{\partial u_p}{\partial x_r} \right) + \cdots \quad (2)$$

$$S_{\text{string}} = \frac{1}{2} \int dt \int_0^L ds (m \dot{\mathbf{X}}^2 - \Gamma \mathbf{X}'^2) + \cdots$$
(3)

$$S_{\rm int} = -b_i \int dt \int_{\delta S} dS^j \sigma_{ij}, \qquad (4)$$

where the ellipses " \cdots " refer to higher-order terms in the phonon or string actions, and S_0 involves the interaction of the elastic displacements with a static dislocation, part of whose boundary is the straight line \mathbf{X}_0 (1). This is the interaction that was considered by Klemens [1] when \mathbf{X}_0 is an infinite line and will not be discussed further in this paper.

Let us start by describing the phonon action S_{ph} : Clearly, S_{ph} describes elastic waves in an elastic continuum, wherein the quadratic terms will lead to free phonons and the higher-order terms will lead to phonon-phonon interactions. In the isotropic case $c_{pqmr} = \lambda \delta_{pq} \delta_{mr} + \mu (\delta_{pm} \delta_{qr} + \delta_{pr} \delta_{mq})$ where λ and μ are the Lamé constants.

Classically, and in the absence of the interaction term, the free phonon theory has simple solutions in terms of plane waves for the elastic displacement (phonons) and normal modes for the pinned string. In the case of



FIG. 1. The dislocation line has a static part \mathbf{X}_0 , a portion of which is a straight line segment. Oscillations about this straight line segment are described by $\mathbf{X}(s, t)$, where *s* is a position parameter and *t* is time.

phonons, they are characterized by two different modes of propagation: transversal waves of speed $c_T = \sqrt{\mu/\rho}$ with two allowed polarizations, and longitudinal waves of speed $c_L = \sqrt{(\lambda + 2\mu)/\rho}$ with one polarization. For future usage, we define $\gamma \equiv c_L/c_T > 1$.

On the other hand, we have a string described by a vector $\mathbf{X}(s, t)$, where 0 < s < L is a position parameter along the string (see Fig. 1). We consider small deviations from a straight equilibrium position \mathbf{X}_0 , the ends of which are pinned to their positions. S_{string} describes oscillations (normal modes) of an elastic string of finite length with fixed ends; higher-order terms describe anharmonic effects on these oscillations, which we will not address in this paper. The parameters *m* and Γ characterize the dislocation segment. In this paper we shall consider segments of edge dislocations only, in which case they may be written in terms of the Burgers vector **b** as [29]

$$m = \frac{\rho b^2}{4\pi} (1 + \gamma^{-4}) \ln(\delta/\delta_0),$$
 (5)

where δ and δ_0 are long- and short-distance cutoff lengths, and

$$\Gamma = \frac{\mu b^2}{2\pi} (1 - \gamma^{-2}) \ln(\delta/\delta_0). \tag{6}$$

m defines a mass per unit of length and Γ is the line tension. The logarithmic cutoff is a dimensionless parameter of order 1; it has no influence on the results of this paper.

In the same manner as classically the phonons have plane waves solutions, this term of the action has oscillatory solutions that may be expanded in Fourier series $\operatorname{Re}\{\sum_{n} a_{n}e^{-i\omega_{n}t}\sin(n\pi s/L)\}\)$, where $\omega_{n} = \frac{n\pi}{L}\sqrt{\frac{\Gamma}{m}}$ is the frequency of each normal mode. We take the string to have one degree of freedom (i.e., one direction orthogonal to its equilibrium position over which to oscillate) defined by the direction of the Burgers vector **b**, the glide plane. For most of our results, the generalization to more directions of oscillation is straightforward. In the Debye model, the Debye frequency is fixed by imposing that the total number of normal modes of vibration of the continuum must equal 3N, where N is the number of atoms. In the present approach, we are not changing this way of mode counting, and the string modes are simply added up to the expected 3N modes. However, for a fairly high dislocation density, say 10^{12} cm⁻², and a 0.3-nm interatomic distance, the number of additional degrees of freedom will be about one-tenth of one percent. We shall neglect this small overcounting.

Finally, S_{int} describes the interaction between these two sectors. It is given by the well-known Peach-Koehler force: b_i is the *i*th component of the Burgers vector, σ_{ij} is the elastic stress tensor, evaluated at the current position of the dislocation line, and the surface δS describes the region bounded by the string and its equilibrium position. As mentioned in the Introduction, the classical scattering of phonons by dislocations using this interaction term has already been dealt with [22,23].

Having this realized, we now turn to quantize the theory by introducing canonical commutation relations.

III. CANONICAL QUANTIZATION OF THE FREE FIELDS

We commence this section by implementing the correspondence of the Poisson brackets to commutators $\{\cdot, \cdot\} \rightarrow -\frac{i}{\hbar}[\cdot, \cdot]$. According to standard practice [30], the mode coefficients of the classical solutions are promoted to creation and annihilation operators, in terms of which we may write the displacement field as

$$\mathbf{u}(\mathbf{x},t) = \sqrt{\frac{\hbar}{\rho}} \int \frac{d^3k}{(2\pi)^3} \sum_{\iota \in \{\text{pol.}\}} \left[\frac{\boldsymbol{\varepsilon}_{\iota}^*(\mathbf{k}) a_{\iota}(\mathbf{k}) e^{i\mathbf{k}\cdot\mathbf{x} - i\omega_{\iota}(\mathbf{k})t}}{\sqrt{2\omega_{\iota}(\mathbf{k})}} + \frac{\boldsymbol{\varepsilon}_{\iota}(\mathbf{k}) a_{\iota}^{\dagger}(\mathbf{k}) e^{-i\mathbf{k}\cdot\mathbf{x} + i\omega_{\iota}(\mathbf{k})t}}{\sqrt{2\omega_{\iota}(\mathbf{k})}} \right]$$
(7)

and the string displacement as

$$X(s,t) = \sqrt{\frac{\hbar}{mL}} \sum_{n=1}^{n_D} \left(\frac{a_n e^{-i\omega_n t}}{\sqrt{\omega_n}} + \frac{a_n^{\dagger} e^{i\omega_n t}}{\sqrt{\omega_n}} \right) \sin\left(\frac{n\pi s}{L}\right), \quad (8)$$

where n_D is a cutoff for the string wave number, as an oscillating string with the action S_{string} can only represent the physical setting down to a given length where the idealization breaks down. When comparing with experiments, if possible, this number should be left as a free parameter to be fixed by the actual results. In condensed matter a natural cutoff is provided by the Debye frequency. However, as we will comment in Sec. IV B 3, the precise value of the cutoff n_D is irrelevant for phonon frequencies well below the frequency cutoff ω_{n_D} .

Now we proceed to impose canonical commutation relations:

$$[u_i(\mathbf{x},t),\,\rho\dot{u}_j(\mathbf{y},t)] = i\hbar\delta_{ij}\delta^{(3)}(\mathbf{x}-\mathbf{y}),\tag{9}$$

$$[X(s,t), m\dot{X}(s',t)] = i\hbar\delta(s-s'), \tag{10}$$

$$[u_i(\mathbf{x}, t), u_j(\mathbf{y}, t)] = 0, \ [X(s, t), X(s', t)] = 0, \ (11)$$

which fully define the quantum theory in the noninteracting case. These relations in turn require

$$[a_{\iota}(\mathbf{k}), a_{\iota'}(\mathbf{k}')] = [a_{\iota}^{\dagger}(\mathbf{k}), a_{\iota'}^{\dagger}(\mathbf{k}')] = 0, \qquad (12)$$

$$[a_{\iota}(\mathbf{k}), a_{\iota'}^{\dagger}(\mathbf{k})] = (2\pi)^{3} \delta^{(3)}(\mathbf{k} - \mathbf{k}') \delta_{\iota\iota'}, \qquad (13)$$

$$[a_n, a_m] = [a_n^{\dagger}, a_m^{\dagger}] = 0, \quad [a_n, a_m^{\dagger}] = \delta_{nm}.$$
(14)

In the preceding expressions, ι is an index that runs over the possible polarizations for the phonons: two transversal modes and a longitudinal mode. The corresponding frequencies satisfy $\omega_t(\mathbf{k}) = c_t k$, where $\iota = L, T$ for the phonons (denoting longitudinal and transverse propagation respectively), and $\omega_n = \frac{n\pi}{L} \sqrt{\frac{\Gamma}{m}}$ for the string. Finally, $\boldsymbol{\varepsilon}_t(\mathbf{k})$ represents the polarization vector associated to each mode of propagation. These vectors satisfy

$$\boldsymbol{\varepsilon}_{\iota}(\mathbf{k}) \cdot \boldsymbol{\varepsilon}_{\iota'}^{*}(\mathbf{k}) = \delta_{\iota\iota'}, \qquad (15)$$

$$\sum_{\iota=T_1,T_2} \varepsilon_{\iota}^*(\mathbf{k})_i \varepsilon_{\iota}(\mathbf{k})_j = \delta_{ij} - \frac{k_i k_j}{k^2}, \qquad (16)$$

$$\varepsilon_L^*(\mathbf{k})_i \varepsilon_L(\mathbf{k})_j = \frac{k_i k_j}{k^2},\tag{17}$$

where T_1, T_2 denote the two transversal polarizations and *L* is the longitudinal polarization. The Hamiltonian of the free theory is

$$H = H_{\rm ph} + H_{\rm string} \tag{18}$$

with phonon and string terms given, respectively, by

$$H_{\rm ph} = \int \frac{d^3k}{(2\pi)^3} \sum_{\iota \in \{\rm pol.\}} \hbar \omega_\iota(\mathbf{k}) a_\iota^\dagger(\mathbf{k}) a_\iota(\mathbf{k}), \qquad (19)$$

$$H_{\text{string}} = \sum_{n=1}^{n_D} \hbar \omega_n a_n^{\dagger} a_n.$$
 (20)

In characterizing the free theory, a fundamental object is the two-point function, or more commonly known as the *propagator*. Let *T* be the time-ordering symbol, instructing operators evaluated at a later time to be placed at the left, and let $|0\rangle$ be the vacuum state of the quantum-mechanical system, with no excitations of the elastic displacements nor the string. For the dislocation, it reads

$$\Delta(s, s', t - t') \equiv \langle 0 | TX(s, t)X(s', t') | 0 \rangle$$

= $\frac{\hbar}{mL} \sum_{n=1}^{n_D} \frac{e^{-i\omega_n |t - t'|}}{\omega_n} \sin\left(\frac{n\pi s}{L}\right) \sin\left(\frac{n\pi s'}{L}\right).$ (21)

Even though we can do the same for the elastic displacement field, it turns out to be more useful for subsequent computations to write down the propagator for its spatial derivative:

$$\begin{aligned} \Delta_{iji'j'}(\mathbf{x} - \mathbf{x}', t - t') \\ &\equiv \langle 0|T\frac{\partial u_i}{\partial x_j}(\mathbf{x}, t)\frac{\partial u_{i'}}{\partial x_{j'}}(\mathbf{x}', t')|0\rangle \\ &= \frac{\hbar}{\rho} \int \frac{d^3k}{(2\pi)^3} k_j k_{j'} \left[\left(\delta_{ii'} - \frac{k_i k_{i'}}{k^2} \right) \frac{e^{-i\omega_T(\mathbf{k})|t - t'|}}{2\omega_T(\mathbf{k})} \right] \\ &+ \frac{k_i k_{i'}}{k^2} \frac{e^{-i\omega_L(\mathbf{k})|t - t'|}}{2\omega_L(\mathbf{k})} \right] e^{i\mathbf{k}\cdot(\mathbf{x} - \mathbf{x}')}. \end{aligned}$$
(22)

The reason behind writing down time-ordered quantities is that when we compute scattering amplitudes in the interacting theory, the *S* matrix will be given by [30]

$$\langle \Psi_{\text{out}} | \operatorname{Texp} \left[-\frac{i}{\hbar} \int_{-\infty}^{\infty} H_I(t) dt \right] | \Psi_{\text{in}} \rangle ,$$
 (23)

where H_I is the quantum-mechanical interaction picture Hamiltonian operator, and thus the time-ordered quantities will have a central role.

In the sections that follow, we will take the string to have its equilibrium position along the $\hat{z} = \hat{e}_3$ axis, and the Burgers vector to be written as $\mathbf{b} = b\hat{e}_1 = b\hat{x}$.

IV. THE QUADRATIC INTERACTIONS: A SINGLE STRING

The lowest-order interaction, which classically means to consider small strains, and small string excursions, away from the equilibrium position, is given by

$$S_{\text{int}} = -\mu b \int dt \int_0^L ds \, \mathbf{M}_{kl} \frac{\partial u_k}{\partial x_l} (\mathbf{x}_0 + (0, 0, s), t) X(s, t),$$
(24)

which is quadratic in the fluctuations. With our choice of coordinates, $\mathbf{M}_{kl} = (\hat{e}_1)_k (\hat{e}_2)_l + (\hat{e}_2)_k (\hat{e}_1)_l$. This interaction will give rise to the scattering of phonons by the strings, which is described by

$$\langle f|i\rangle = \langle 0|a_i(\mathbf{k})\mathrm{T}\exp\left[-\frac{i}{\hbar}\int_{-\infty}^{\infty}H_I(t)dt\right]a_{i'}^{\dagger}(\mathbf{k}')|0\rangle,$$
 (25)

where

$$H_I(t) = \mu b \int_0^L ds \, \mathbf{M}_{kl} \frac{\partial u_k^I}{\partial x_l} (\mathbf{x}_0 + (0, 0, s), t) X^I(s, t).$$
(26)

For completeness, we also write down the Hamiltonian in the Heisenberg picture (where it is naturally constant) in terms of creation and annihilation operators:

$$H_{\text{int}} = \frac{\hbar}{\sqrt{mL}} \int \frac{d^3k}{(2\pi)^3} \sum_{n=1}^{n_D} \sum_{\iota \in \{\text{pol.}\}} \left(\frac{a_n + a_n^{\dagger}}{\sqrt{\omega_n}} \right) \\ \times \left(\frac{in\pi E(\mathbf{k};\iota)a_\iota(\mathbf{k})}{L} \frac{e^{iL(\mathbf{k}\cdot\hat{e}_3) - in\pi} - 1}{(\mathbf{k}\cdot\hat{e}_3)^2 - (n\pi/L)^2} + \text{H.c.} \right),$$
(27)

where H.c. stands for Hermitian conjugate. Furthermore, we have defined $\omega \equiv \omega_l(\mathbf{k}) = \omega_{l'}(\mathbf{k}')$,

$$E(\mathbf{k};\iota) \equiv \frac{\mu b}{\sqrt{2\rho\omega_{\iota}(\mathbf{k})}} k_{l} \mathbf{M}_{kl} \varepsilon_{\iota}^{*}(\mathbf{k})_{k} e^{i\mathbf{x}_{0}\cdot\mathbf{k}}, \qquad (28)$$

and we will denote its complex conjugate by E^* . Here we have denoted $k_l = (\mathbf{k} \cdot \hat{e}_l)$ and $\varepsilon_l(\mathbf{k})_k = (\boldsymbol{\epsilon}_l(\mathbf{k}) \cdot \hat{e}_k)$.

In Eq. (26), u^{I} and X^{I} are the operator fields of the interaction picture, i.e., they evolve as free fields. As a reminder to the reader, the passage to the Heisenberg picture is implemented through

$$u(\mathbf{x},t) = U^{\dagger}(t,t_0)u_I(\mathbf{x},t)U(t,t_0)$$
(29)

with

$$U(t, t_0) = \operatorname{Texp}\left[-i \int_{t_0}^t H_I(t') dt'\right],$$
(30)

where t_0 is the time at which both operators coincide (typically it is taken to be $-\infty$).

One may ask what is the nature of the approximation involved in considering only the quadratic interaction terms for the quantum theory. Since the only way to be sure of the answer is to compute the subleading terms, we will leave this question unanswered until the last section, where we study explicitly the higher-order corrections.

For the moment, we can start with the leading contribution to the phonon-phonon amplitude.

A. Lowest-order contribution in the phonon-string coupling

Given that we are interested in phonon-phonon amplitudes, in order to have a nonvanishing contribution from (25) we need to expand the time-ordered exponential up to quadratic order. Employing our definition for the string propagator and performing the relevant contractions, we see that

$$\langle f|i\rangle|_{\mathcal{O}(b^2)} = -\frac{b^2\mu^2}{\hbar^2} \int_{-\infty}^{\infty} dt \int_{-\infty}^{\infty} dt' \int_{0}^{L} ds \int_{0}^{L} ds' \mathbf{M}_{kl} \mathbf{M}_{k'l'} \Delta(s, s', t - t') \\ \times \left\langle 0|a_i(\mathbf{k}) \frac{\partial u_k^I}{\partial x_l} (\mathbf{x}_0 + (0, 0, s), t)|0 \right\rangle \left\langle 0|\frac{\partial u_{k'}^I}{\partial x_{l'}} (\mathbf{x}_0 + (0, 0, s'), t') a_{i'}^{\dagger} (\mathbf{k}')|0 \right\rangle.$$
(31)

If we define the \mathcal{T} matrix through

$$\langle f|i\rangle \equiv 2\pi \,\delta[\omega_t(\mathbf{k}) - \omega_{t'}(\mathbf{k}')] \,\mathcal{T},\tag{32}$$

then Eq. (31) yields, using (7),

$$\mathcal{T} = \frac{2iE^{*}(\mathbf{k};\iota)E(\mathbf{k}';\iota')}{mL} \sum_{n=1}^{n_{D}} \frac{(n\pi/L)^{2}}{\omega_{n}^{2} - \omega^{2}} \frac{e^{iL(\mathbf{k}'\cdot\hat{e}_{3}) - in\pi} - 1}{(\mathbf{k}'\cdot\hat{e}_{3})^{2} - (n\pi/L)^{2}} \frac{e^{-iL(\mathbf{k}\cdot\hat{e}_{3}) + in\pi} - 1}{(\mathbf{k}\cdot\hat{e}_{3})^{2} - (n\pi/L)^{2}}.$$
(33)

An interesting feature of this result is that it is independent of b, as we have $m \propto b^2$; that is, the mass per unit length of the dislocation is proportional to the square of the Burgers vector. While it is too soon to make a definitive statement about the actual perturbative parameter of the problem, this suggests that b per se does not play that role, contrary to what one could at first think.

The observable that may be derived from the \mathcal{T} matrix is the scattering cross section. As we are interested in the outgoing flux, i.e., the angular distribution of phonons, given an incident phonon with well-defined momentum \mathbf{k}' , one obtains

$$\frac{d\sigma}{d\Omega} = \frac{\omega^2 |\mathcal{T}|^2}{4\pi^2 c_i^3 c_{i'}}.$$
(34)

This dependence of the cross section on the scattering amplitude holds independently of the order to which we compute observables in perturbation theory, which is exactly our next order of business.

B. Phonon scattering by dislocation segments to all orders in the coupling

Now we turn to solving for the scattering amplitude to all orders in the interaction Hamiltonian (26), that is, the computation of all terms in the power series development of the exponential that appears in (25). The object of interest is the same as before (25), so we may proceed order by order and then sum the terms to reconstruct the result. It turns out that it will be sufficient to evaluate the fully connected parts of the amplitude, i.e., those which cannot be separated into independent factors, and that a power series results, that can be summed. Because the expressions involved in the derivation are quite lengthy, we shall present those details in Appendix B, and here we will discuss the results.

In a very similar manner to the classical case [23], the T matrix one obtains is given by

$$\mathcal{T} = \mathbf{v}^{\dagger}(\mathbf{k}) \cdot \frac{iE^{*}(\mathbf{k};\iota)E(\mathbf{k}';\iota')}{1 - \mathbf{T}(\omega)} \cdot \mathbf{v}(\mathbf{k}').$$
(35)

The precise definitions of **v** and $\mathbf{T}(\omega)$ are listed in Appendix **B**. For the purposes with which we concern ourselves, **v** may be seen as an n_D -dimensional vector that contains information on how an incident wave interacts with each mode of the string, to first order. This is readily seen by noticing that the amplitude to lowest order (33) is given by $iE^*(\mathbf{k}, \iota)E(\mathbf{k}', \iota')\mathbf{v}^{\dagger}(\mathbf{k}) \cdot \mathbf{v}(\mathbf{k}')$.

On the other hand, $\mathbf{T}(\omega)$ may be regarded as an $n_D \times n_D$ symmetric matrix quantifying the internal structure of the theory, being the object wherein to look for a perturbative parameter. This object has a rich structure, which we will study thoroughly in the following subsections.

1. Finiteness of the theory

In previous works studying the problem of phonon scattering by dislocations [23], a renormalization procedure was necessary to guarantee a finite result at every order in perturbation theory. Specifically, one may be worried that the integral (B6) involved in the definition of **T** may diverge:

$$F(n, n') \equiv \frac{\mu b \mathbf{M}_{kl}}{\sqrt{\rho}} \int \frac{d^3 k}{(2\pi)^3} k_l k_{l'} \int_0^L ds \sin\left(\frac{n\pi s}{L}\right) e^{ik_{3}s} \\ \times \left[\frac{\delta_{kk'} - \hat{k}_k \hat{k}_{k'}}{\omega_T(\mathbf{k})^2 - \omega^2 - i\epsilon} + \frac{\hat{k}_k \hat{k}_{k'}}{\omega_L(\mathbf{k})^2 - \omega^2 - i\epsilon}\right] \\ \times \int_0^L ds' \sin\left(\frac{n'\pi s'}{L}\right) e^{-ik_{3}s'} \frac{\mu b \mathbf{M}_{k'l'}}{\sqrt{\rho}}, \quad (36)$$

where ϵ is a positive infinitesimal and $k_i \equiv \mathbf{k} \cdot \hat{e}_i$. This object may be regarded as a correction to the propagator of the string modes, as it only involves indices labeling these states.

It turns out that one can perform the integration over $|\mathbf{k}|$ by employing the prescription defined by ϵ . After doing some residue calculus and performing the integral over the azimuthal angle, one finds

$$F(n,n') = i\omega^{3} \frac{\mu^{2} b^{2}}{8\pi\rho} \int_{0}^{L} ds \int_{0}^{s} ds' \int_{0}^{1} du (1-u^{2})$$

$$\times \left[\sin\left(\frac{n\pi s}{L}\right) \sin\left(\frac{n'\pi s'}{L}\right) + (n \leftrightarrow n') \right]$$

$$\times \left[\frac{1+u^{2}}{c_{T}^{5}} e^{i(s-s')\omega u/c_{T}} + \frac{1-u^{2}}{c_{L}^{5}} e^{i(s-s')\omega u/c_{L}} \right].$$
(37)

As expected [23], the real part of (37) vanishes as $\omega \to 0$ faster than the imaginary part, which goes as ω^3 at low frequencies. Furthermore, it is manifestly finite at all frequencies, as every piece of the integrand is bounded.

2. Low- and high-frequency behavior

It is instructive to explore the behavior of the preceding formulas in the low-frequency limit $\omega L/c \propto kL \ll 1$ to see whether this result is consistent with previous findings. As *F* is finite and nonzero for small ω , we may simply evaluate it at $\omega = 0$ and only keep the leading factor ω^3 . To further simplify matters, we will only take into account the dominant contribution to scattering at large wavelengths: n = n' = 1. We then obtain

$$\mathbf{T}_{\omega \ll c_T/L} \simeq i\omega^3 \frac{\mu^2 b^2 L}{m\rho \omega_1^2 c_T^5} \frac{4}{5\pi^3} \bigg[1 + \frac{2}{3\gamma^5} \bigg], \qquad (38)$$

where we have also approximated $\omega_1^2 - \omega^2 \approx \omega_1^2$ in the denominator. This is exactly what was inferred in previous papers [23] for the value of this operator, thus verifying that **T** is purely imaginary at low frequencies.

Now we may infer the perturbative parameter involved in expression (35) at low frequencies. As it turns out, Eq. (38) is proportional to $(\omega L/c_T)^3$. Although it might not be the fundamental constant we could have hoped for (analogous to the fine-structure constant), it is physically sound: the larger

the characteristic wavelength of a wave packet, the less it is affected by dislocations.

On the other hand, in the high-frequency limit the integrals in (37) vanish as the integrand turns highly oscillatory. This result is generically known as the Riemann-Lebesgue lemma. If one performs a change of variables s = xL and then takes $L \rightarrow \infty$, one concludes that the integrals should vanish on the same grounds. However, this assumes that we leave n, n'as constants, which is not of much physical interest. If we instead take $k_z \equiv n\pi/L$ fixed when L goes to infinity, we recover a continuum of modes in an infinitely long string, and as the system gains a translation symmetry along the z axis, wave-number conservation along this direction emerges in the scattering amplitudes. Mathematically, this feature arises, again, due to the Riemann-Lebesgue lemma, as the integrand becomes highly oscillatory unless the wave numbers $\omega u/c_{i}$ are equal. A detailed study of this regime will be undertaken in future work.

3. Intermediate region: A numerical analysis

To study the behavior of the amplitude (35), or equivalently the cross section, in the regime where the frequency ω is close to the resonant frequencies of the string we will resort to numerical computations. For these purposes, we find it more instructive to define a dimensionless frequency $v \equiv \omega L/c_T$ and write T as

$$\mathcal{T} = \frac{\rho b^2 L^2 c_T^3}{m c_l c_{l'}} \mathbf{w}^{\dagger}(\mathbf{k}) \cdot \frac{i \nu}{1 - \mathbf{T}(\omega)} \cdot \mathbf{w}(\mathbf{k}')$$
$$\times \hat{k}_l \mathbf{M}_{kl} \varepsilon_l(\mathbf{k})_k \hat{k'}_{l'} \mathbf{M}_{k'l'} \varepsilon_{l'}(\mathbf{k}')_{k'} e^{i(\mathbf{k}' - \mathbf{k}) \cdot \mathbf{x}_0}, \quad (39)$$

where \mathbf{w} is a n_D -dimensional vector with entries

$$[\mathbf{w}(\mathbf{k})]_n \equiv \frac{n\pi}{\frac{L}{c_T}\sqrt{\omega_n^2 - \omega^2}} \frac{e^{iL(\mathbf{k}\cdot\hat{e}_3) + in\pi} - 1}{(L\mathbf{k}\cdot\hat{e}_3)^2 - (n\pi)^2}.$$
 (40)

Thus, we see that the usual scattering amplitude f such that $d\sigma/d\Omega = |f|^2$ is given by

$$f(\omega, \mathbf{k}, \mathbf{k}') \equiv \frac{\rho b^2 L c_T^4}{2\pi m \sqrt{c_i^5 c_{i'}^3}} \mathbf{w}^{\dagger}(\mathbf{k}) \cdot \frac{i\nu^2}{1 - \mathbf{T}(\omega)} \cdot \mathbf{w}(\mathbf{k}')$$
$$\times \hat{k}_l \mathbf{M}_{kl} \varepsilon_{\iota}(\mathbf{k})_k \hat{k'}_{l'} \mathbf{M}_{k'l'} \varepsilon_{\iota'}^*(\mathbf{k}')_{k'} e^{i(\mathbf{k}' - \mathbf{k}) \cdot \mathbf{x}_0}, \quad (41)$$

where the vectors \mathbf{k} , \mathbf{k}' satisfy $\omega = |\mathbf{k}|c_i = |\mathbf{k}'|c_{i'}$.

To show an example of this, Fig. 2 shows the absolute value of the longitudinal to longitudinal scattering amplitude for a range of frequencies in a typical scattering event. From low frequencies until the first resonance ω_1 the angular distribution is concentrated around the $\hat{e}_1 - \hat{e}_2$ plane. However, after the first resonance the cross section starts experiencing the effects of the incident direction, obtaining asymmetric patterns with respect to \hat{e}_3 . Similar results can be obtained for cross sections involving transverse polarization; the main difference is that the angular distribution changes because of the different polarization directions of the incident wave.

Having the differential scattering cross section for the scattering of phonons by dislocation segments, the next step is to compute the total cross section for a given mode of transmission. This is obtained by integrating over all outgoing modes of polarization and momenta consistent with the



FIG. 2. Absolute value of the scattering amplitude |f| for phonons by dislocation segments for $n_D = 10$, $\gamma = 2$, $\ln(\delta/\delta_0) = 3$, with both incident and outgoing phonons having longitudinal polarization, as a function of the outgoing direction \hat{k} . The ingoing direction was set to $\hat{k}' = (1/2, 1/2, 1/\sqrt{2})$. Different values for the incident frequency are shown in different plots. The coordinates (x, y) correspond to the directions (\hat{e}_1, \hat{e}_2) respectively. The plots are to scale with respect to each other. Note that at low frequencies there is an up-down symmetry that is lost when ν is gradually increased above $\approx 2\pi$, that is, at frequencies higher than the second string resonance, which is the first that can distinguish \hat{e}_3 from $-\hat{e}_3$ and is thus sensitive to the direction of incidence \hat{k}' .

kinematical restrictions. In this case, these restrictions amount to energy conservation. However, the resulting cross section depends on the incident distribution of polarization, which is particularly relevant in the case of transverse polarization. In a general situation, given an initial density matrix $\hat{\rho}_{\mathbf{k},T}^0$ for the transverse modes of wave number **k**, we can compute the fraction of scattered phonons as

$$\operatorname{tr}\left(U\hat{\rho}_{\mathbf{k},T}^{0}U^{\dagger}P_{\{\mathbf{k}':\mathbf{k}'\neq\mathbf{k}\}}\right),\tag{42}$$

where $P_{\{\mathbf{k}':\mathbf{k}'\neq\mathbf{k}\}}$ is an orthogonal projector to the space of all single-particle states with wave number different than \mathbf{k} , which plays the role of selecting the scattered piece of the time-evolved state.

Dividing the result by the incident flux, it is not difficult to see that for an unpolarized incident beam of transversepolarized phonons, the total cross section is given by

$$\sigma_{T}(\mathbf{k}) = \frac{\pi L^{2}}{2} \left(\frac{\rho b^{2}}{2\pi m} \right)^{2} (|\hat{k} \times \hat{e}_{3}|^{2} - 4(\hat{k} \cdot \hat{e}_{1})^{2} (\hat{k} \cdot \hat{e}_{2})^{2}) \\ \times \int_{-1}^{1} du \left[(1 - u^{4}) \left| \mathbf{w}_{T}^{\dagger}(u, v) \frac{v^{2}}{1 - \mathbf{T}(\omega)} \mathbf{w}_{T}(\hat{k} \cdot \hat{e}_{3}, v) \right|^{2} \right] \\ + \frac{(1 - u^{2})^{2}}{\gamma^{5}} \left| \mathbf{w}_{L}^{\dagger}(u, v) \frac{v^{2}}{1 - \mathbf{T}(\omega)} \mathbf{w}_{T}(\hat{k} \cdot \hat{e}_{3}, v) \right|^{2} \right],$$
(43)

where $\{\hat{e}_i\}_i$ is the orthonormal basis used to describe the string, and we have defined

$$[\mathbf{w}_{T}(u,v)]_{n} \equiv \frac{n\pi}{\frac{L}{c_{T}}\sqrt{\omega_{n}^{2} - v^{2}c_{T}^{2}/L^{2}}} \frac{e^{iuv + in\pi} - 1}{u^{2}v^{2} - (n\pi)^{2}}, \quad (44)$$

$$[\mathbf{w}_{L}(u,v)]_{n} \equiv \frac{n\pi}{\frac{L}{c_{T}}\sqrt{\omega_{n}^{2} - v^{2}c_{T}^{2}/L^{2}}} \frac{e^{iuv/\gamma + in\pi} - 1}{u^{2}v^{2}/\gamma^{2} - (n\pi)^{2}}$$
(45)

as a function of the dimensionless frequency v and the angle of the corresponding wave number \mathbf{k}' with respect to the axis of the string $u = \hat{k}' \cdot \hat{e}_3$. Similarly, in the case of longitudinal polarization we have

$$\sigma_{L}(\mathbf{k}) = \frac{\pi L^{2}}{\gamma^{3}} \left(\frac{\rho b^{2}}{2\pi m}\right)^{2} (4(\hat{k} \cdot \hat{e}_{1})^{2}(\hat{k} \cdot \hat{e}_{2})^{2}) \\ \times \int_{-1}^{1} du \left[(1 - u^{4}) \left| \mathbf{w}_{T}^{\dagger}(u, v) \frac{v^{2}}{1 - \mathbf{T}(\omega)} \mathbf{w}_{L}(\hat{k} \cdot \hat{e}_{3}, v) \right|^{2} \right] \\ + \frac{(1 - u^{2})^{2}}{\gamma^{5}} \left| \mathbf{w}_{L}^{\dagger}(u, v) \frac{v^{2}}{1 - \mathbf{T}(\omega)} \mathbf{w}_{L}(\hat{k} \cdot \hat{e}_{3}, v) \right|^{2} \right].$$
(46)

Plots of these results are shown in Fig. 3.



FIG. 3. Surface plot of the scattering cross sections σ_T and σ_L in log-linear scale, as a function of frequency and angle of incidence, for phonons by oscillating dislocation segments of finite length. In the figure, $n_D = 10$, $\gamma = 2$, and $\ln(\delta/\delta_0) = 3$. Furthermore, we have defined $\cos \theta = \hat{k} \cdot \hat{e}_3$ and chosen $|\hat{k} \cdot \hat{e}_1| = |\hat{k} \cdot \hat{e}_2|$ as a representative instance of these quantities. Note the rich behavior of the cross sections as a function of frequency, in contrast with the linear-in-frequency behavior inferred from the scattering by an infinitely long, static, dislocation [1,2].

It is important to stress that the cross section for transverse polarization is dependent on the particular polarization of the incident wave, as both the polarization vector $\boldsymbol{\varepsilon}$ and the wave number **k** must have projections over \hat{e}_1 or \hat{e}_2 to get a nonzero result. This can be readily appreciated by

looking at the scattering amplitude (41). For now, and for all forthcoming purposes, we will proceed using the average cross section for transverse modes, which is exactly what one obtains with circular polarization, or with unpolarized phonons. As a final note on this section, let us comment on the role of the cutoff n_D . Typically, it should be chosen so that the wave number $n_D \pi / L$ matches the Debye wavelength. However, if one is interested in making predictions at frequencies below a given eigenfrequency of the string ω_{n^*} , it is possible to choose the cutoff as n^* without losing predictive power because the coupling to distant frequencies ω_n in the scattering amplitude (39) is suppressed by a factor of $(\omega_n^2 - \omega^2)^{-1}$, making them irrelevant if the frequency of interest is well below ω_n . In this sense, the results shown in the plots of Figs. 2 and 3 always hold (independently of our choice $n_D = 10$), provided that, roughly speaking, $\nu < 30$.

4. Resonances and decay rates

A recurring feature within the expressions for the phononphonon scattering amplitude we have written down so far is the apparent existence of poles at specific frequencies, namely at the natural frequencies of oscillation of the string. However, none of these creates any singularity, as should be obvious from Fig. 2: the width and height of the peaks in the cross section is finite. This is related to the fact that phonons at these frequencies can decay into excited string states, thus avoiding the resonant behavior of the interaction and giving the peak a finite width.

Indeed, the interaction between the string and a phonon with coinciding eigenfrequency will generate asymptotic states (i.e., those that result from a scattering process) that assign some probability to having an excited string. Conversely, an initially excited string is also an unstable particle, and it will have a decay rate by emission of phonons, with a probability amplitude equal to the phonon-string decay up to an overall sign.

For instance, the decay rate of an excited string may be evaluated by the same means that we evaluated the phononphonon cross sections. The object of interest is

$$\langle f|i\rangle = \langle 0|a_{\iota}(\mathbf{k})\mathrm{T}\exp\left[-\frac{i}{\hbar}\int_{-\infty}^{\infty}H_{I}(t)dt\right]a_{n}^{\dagger}|0\rangle,$$
 (47)

which after a completely analogous process, in terms of the \mathcal{T} matrix $\langle f | i \rangle = (2\pi) \delta(\omega_l - \omega_n) \mathcal{T}$, gives

$$\mathcal{T} = (iE(\mathbf{k};\iota)\mathbf{v}(\mathbf{k}))^{\dagger} \cdot \frac{\mathbf{T}(\omega)}{1 - \mathbf{T}(\omega)} \cdot (G_n \mathbf{e}_n), \qquad (48)$$

where we have defined $G_n \equiv n\pi/\sqrt{mL^3\omega_n}$ and \mathbf{e}_n as a unit vector in the n_D -dimensional space on which **T** acts, with a nonzero component for the *n*th mode only. Since $\mathbf{T}(\omega)$ commutes with $[1 - \mathbf{T}(\omega)]^{-1}$, we can write unambiguously $\frac{\mathbf{T}(\omega)}{1 - \mathbf{T}(\omega)} \equiv \mathbf{T}(\omega)[1 - \mathbf{T}(\omega)]^{-1} = [1 - \mathbf{T}(\omega)]^{-1}\mathbf{T}(\omega)$. The amplitude of the inverse process (phonon to string) is given by interchanging the roles of *iE***v** and $G_n \mathbf{e}_n$.

Finally, the rate of spontaneous emission for excitations of the string in its mode n is given by

$$\Gamma_n = \frac{\omega_n^2}{4\pi^2} \sum_{\iota} \frac{1}{c_\iota^3} \int d\Omega |\mathcal{T}|^2, \qquad (49)$$

with \mathcal{T} given by (48), which gives the typical lifetime of an excited string.

The converse process, i.e., the absorption of a phonon by a dislocation segment, is also allowed, and as such it contributes

to the total cross section of a phonon traveling through the solid. However, since this scattering process will be subject to energy conservation, the corresponding amplitude will be either zero or formally infinite via the presence of the Dirac delta. Therefore, it will not contribute to the bulk thermal conductivity: if the amplitude is zero, the total cross section will be described purely by phonon-phonon processes, and if it is infinite, then that specific mode channel will contribute zero, which renders it irrelevant as we have a continuum of modes of transmission available, although the situation should change in the presence of a continuous distribution of lengths, because in this situation absorption to a continuum of modes will be possible, and thus the macroscopic observables, such as the thermal conductivity, should be modified.

C. Dislocations in a mesoscopic medium

In this section we discuss some methods and approximations that should be useful for dealing with a dislocation-filled medium from a mesoscopic perspective. First we will write down an expression useful in situations where the scattering is well approximated by a single interaction with a dislocation, imposing that these interactions should, on average, behave as if the medium were homogeneous and isotropic. We also present a compact expression for the propagator in this approximation. Then we proceed to outline the general situation, where this approximation may or may not hold true.

1. An effective mass operator for weak and independent scattering

In many realistic situations, we will have randomly distributed dislocations within the solid. Therefore, if we want to make practical predictions on phonon scattering within a solid, we must account for this in some way. The *weak and independent scattering approximation* [31] provides a solution to this problem: average the \mathcal{T} matrix over the internal degrees of freedom of the system. In this case, we will average over the dislocation position \mathbf{x}_0 and orientation $(\hat{e}_1, \hat{e}_2, \hat{e}_3)$. For computational simplicity, however, we will keep a unique string length.

It should be clear from Eq. (33) that averaging over the position \mathbf{x}_0 of the string will give a Dirac delta in momentum space, thus enforcing momentum conservation by demanding the sample to have a homogeneous distribution of dislocations. The result of averaging over dislocation directions should then yield an isotropic result, and since δ_{ij} and $\hat{k}_i \hat{k}_j$ are the only rank-2 tensors available, it should be possible to express the average \mathcal{T} matrix, $\tilde{\mathcal{T}}$, as

$$\bar{\mathcal{T}} = i(2\pi)^{3} \delta^{(3)}(\mathbf{k} - \mathbf{k}') \varepsilon_{\iota}(\mathbf{k})_{i} \varepsilon_{\iota'}(\mathbf{k}')_{j} \frac{n_{d} L \mu^{2} b^{2} k^{2}}{8m \rho \omega}$$

$$\times \left((\delta_{ij} - \hat{k}_{i} \hat{k}_{j}) \operatorname{tr}_{n_{D}} \left[\frac{\mathbf{F}_{T}(k, \omega)}{1 - \mathbf{T}(\omega)} \right] + \hat{k}_{i} \hat{k}_{j} \operatorname{tr}_{n_{D}} \left[\frac{\mathbf{F}_{L}(k, \omega)}{1 - \mathbf{T}(\omega)} \right] \right), \tag{50}$$

where n_d is the dislocation number density and tr_{n_D} stands for taking the trace over the different modes of excitation of the

$$[\mathbf{F}_{T}]_{n'n} = \frac{nn'\pi^{2}}{\sqrt{\omega_{n}^{2} - \omega^{2}}\sqrt{\omega_{n'}^{2} - \omega^{2}}} \int_{-1}^{1} du(1 - u^{4}) \\ \times \frac{e^{ikLu}(-1)^{n'} - 1}{(kLu)^{2} - (n'\pi)^{2}} \frac{e^{-ikLu}(-1)^{n} - 1}{(kLu)^{2} - (n\pi)^{2}}$$
(51)

and

$$[\mathbf{F}_{L}]_{n'n} = \frac{nn'\pi^{2}}{\sqrt{\omega_{n}^{2} - \omega^{2}}\sqrt{\omega_{n'}^{2} - \omega^{2}}} \int_{-1}^{1} du \, 2(1 - u^{2})^{2} \\ \times \frac{e^{ikLu}(-1)^{n'} - 1}{(kLu)^{2} - (n'\pi)^{2}} \frac{e^{-ikLu}(-1)^{n} - 1}{(kLu)^{2} - (n\pi)^{2}}.$$
 (52)

The details of these computations are presented in Appendix A. These results are consistent with those of previous works [20,22,23] in the large wavelength limit $kL \ll 1$, and furthermore completely define the scattering amplitude.

Now we may derive a macroscopic mass operator for the phonon dispersion relation from this effective scattering amplitude. Usually one defines the mass operator Σ as the operator that solves the Dyson equation:

$$\langle G \rangle = [(G^0)^{-1} - \Sigma]^{-1},$$
 (53)

where G^0 is the Green's function for the elastic continuum without dislocations, which (up to normalization) we write as

$$(G^{0})_{ij}^{-1} = -\omega^{2}\delta_{ij} + c_{T}^{2}k^{2}(\delta_{ij} - \hat{k}_{i}\hat{k}_{j}) + c_{L}^{2}k^{2}\hat{k}_{i}\hat{k}_{j}, \qquad (54)$$

and $\langle G \rangle$ is an effective Green's function, that results from performing the averages just described. By inspecting the time-ordered two-point function associated to the amplitude (25) we find that if we define a reduced amplitude \overline{T}_{ij} through

$$\bar{\mathcal{T}} = i(2\pi)^3 \delta^{(3)}(\mathbf{k} - \mathbf{k}') \frac{\varepsilon_i(\mathbf{k})_i \varepsilon_{i'}^*(\mathbf{k}')_j}{2\omega} \bar{\mathcal{T}}_{ij}$$
(55)

then the effective Green's function is given by

$$\langle G \rangle_{ij} = G^0_{ij} + G^0_{ik} \bar{\mathcal{T}}_{kl} G^0_{lj}.$$
 (56)

However, this considers single scattering through a single mesoscopic region in space. If we take this, as we stated earlier, to represent a single (effective) scattering process, this would just be the first term for a macroscopic Born series, which would read

$$\langle G \rangle_{ij} = G_{ik}^0 \sum_{n=0}^\infty [(\bar{\mathcal{T}} G^0)^n]_{kj}$$

= $[(G^0)^{-1} - \bar{\mathcal{T}}]^{-1},$ (57)

from where we get the macroscopic mass operator as

$$\Sigma_{ij} = \bar{\mathcal{T}}_{ij}$$

$$= \frac{n_d L \mu^2 b^2 k^2}{4m\rho} \left((\delta_{ij} - \hat{k}_i \hat{k}_j) \operatorname{tr}_{n_D} \left[\frac{\mathbf{F}_T(k, \omega)}{1 - \mathbf{T}(\omega)} \right] + \hat{k}_i \hat{k}_j \operatorname{tr}_{n_D} \left[\frac{\mathbf{F}_L(k, \omega)}{1 - \mathbf{T}(\omega)} \right] \right),$$
(58)

which represents, as the name suggests, a frequencydependent mass term to be added to the Green's function. It should be noted that it also includes dissipative terms coming from the interaction with the strings.

In order to illustrate this result, and given that the spirit of the approximation is to model an elastic medium at a mesoscopic scale, let us take $n_D = 1$. This is justified as long as the elastic waves of interest have wavelengths larger than L, or equivalently frequencies below c_T/L .

The dispersion relation that determines how elastic waves propagate is given by the poles of the effective Green's function $\langle G \rangle$. Because \mathbf{F}_T , \mathbf{F}_L , and \mathbf{T} are generically complexvalued, one can expect dissipative effects to emerge. Moreover, by simple inspection one can determine that the presence of dislocations changes the sound speed at arbitrarily low wave number/frequency. The effective sound speeds at very long wavelengths $kL \ll 1$ are given by

$$c_{T,\text{eff}}^2 = c_T^2 \left(1 - \frac{8}{5\pi^2} \frac{n_d L c_T^2}{\omega_1^2} \frac{\rho b^2}{m} \right), \tag{59}$$

$$c_{L,\text{eff}}^{2} = c_{L}^{2} \left(1 - \frac{32}{15\pi^{2}} \frac{n_{d} L c_{L}^{2}}{\gamma^{4} \omega_{1}^{2}} \frac{\rho b^{2}}{m} \right), \tag{60}$$

which are exactly those found with the classical theory in previous works [22] in the $\omega \rightarrow 0$ limit.

To find the full dispersion relation, we solve for the location of the poles numerically, and present the results in Fig. 4. These were computed searching for the propagative solution of the poles, i.e., that with the lowest value for $\text{Im}[k(\omega)]$. The curves shown have been smoothed by a Savitzky-Golay filter. In the case of transverse wave propagation, we also present, with discontinuous lines, the dispersion relation for evanescent waves that appear because of having a complex dispersion relation.

We start discussing the propagative solutions. Qualitatively speaking, at frequencies below the first resonance the sound speed of the medium decreases and the medium gets increasingly dissipative as the frequency is increased. A maximum is reached in the imaginary part of the wave number at a frequency close to that of the first resonance peak of the scattering amplitude, at which point the real part of the wave number crosses the line of the free theory dispersion relation, and then starts moving away from the resonant behavior, reapproaching the free theory behavior at larger frequencies. However, if the frequency is further increased, one should expect the effects of the next resonance peaks to kick in.

At first sight in Fig. 4, the group velocity $\partial \omega / \partial k$ appears to exceed the free theory sound speed at frequencies close to the resonance peak. However, as Jackson points out in his classic textbook [32], the notion of group velocity through $\partial \omega / \partial k$ is well defined when the variation of the refraction index $n(\omega)$ is small, a condition that is utterly demolished in regions of anomalous dispersion, which is exactly the case at hand. Therefore, one should not worry about the apparently causality-violating behavior of $\text{Re}[k(\omega)]$ that would appear around the resonance peak if one took the group velocity definition as meaningful for all frequencies.

Finally, we point out that the presence of evanescent waves for transverse polarization and not for longitudinal polarization in the range of frequencies/wave numbers explored in the plots is mostly due to the dislocations having combinations



FIG. 4. Numerical solution of the dispersion relation $k(\omega)$ for the propagation of phonons through a medium with many, randomly located and oriented, dislocation segments for different values of the dislocation density n_D . In the plots, we have set $\gamma = 2$ and $\ln(\delta/\delta_0) = 3$. Note that shear phonons are more strongly affected that longitudinal phonons. The propagative solutions are plotted with continuous lines and the evanescent waves with discontinuous lines. See text for a discussion.

of eigenfrequencies/eigenstates that resemble more closely $\omega = kc_T$ than $\omega = kc_L$. This is because in $\omega_n = \frac{n\pi}{L}c_d$, we can identify $\frac{n\pi}{L}$ as the wave number, and c_d will always satisfy $c_d < \sqrt{2}c_T$ (in the plot, $c_d \approx 1.18c_T$). Therefore, for longitudinal waves it is less common to satisfy $\omega \sim \omega_n$ and $\mathbf{k} \cdot \hat{e}_3 \sim \frac{n\pi}{L}$ simultaneously than for transverse waves. Thus, as longitudinal waves will consequently have fewer interactions with the dislocations, their dispersion relation is less affected. Nonetheless, evanescent solutions should also exist, albeit with a shorter decay length. In this sense, increasing the dislocation density makes it possible to have states that are more extended throughout the solid, as one might have intuited from the beginning.

Further analysis of the critical dislocation density $n_d L^3$, at which the propagating waves' dispersion relation intersects with that of evanescent waves, remains pending for future projects. It would be of interest to explore links, if any, and possible research directions, with metamaterials, by trying to tune the mass operator we have just derived to serve a specific purpose. On the other hand, it is possible that in such contexts, or in the present context, the weak and independent scattering starts to deviate from the physical phenomena, precisely because of a high dislocation density that makes independent scattering unfeasible.

Therefore, we feel compelled to at least outline what a more general situation would be, and how the quantities that previously led to the mass operator would be computed.

2. Many dislocations: General case

Formally, we may write the interaction Hamiltonian for a medium with many dislocations as

$$H_{I} = \int_{\mathbf{x}_{0},L,b,\triangleleft} f(\mathbf{x}_{0},L,b,\triangleleft) \int_{0}^{L} ds \,\mu b \mathbf{M}_{kl}(\triangleleft)$$
$$\times \frac{\partial u_{k}^{I}}{\partial x_{l}} (\mathbf{x}_{0} + s\hat{e}_{3}(\triangleleft), t) X^{I}(s,t;\mathbf{x}_{0},L,b,\triangleleft), \qquad (61)$$

where $f(\mathbf{x}_0, L, b, \triangleleft)$ is some distribution of positions \mathbf{x}_0 , lengths *L*, Burgers vector magnitude *b*, and orientation \triangleleft characterizing the triad defined by the equilibrium position of the string and the direction of the Burgers vector \hat{b} . This translates into new commutation relations for the mode operators of the string, which now are also a function of $\mathbf{x}_0, L, b, \triangleleft$:

$$[a_n(\mathbf{x}_0, L, b, \triangleleft), a_m^{\dagger}(\mathbf{x}'_0, L', b', \triangleleft')] = \delta_{nm} \delta^{(3)}(\mathbf{x}_0 - \mathbf{x}'_0) \delta(L - L') \delta(b - b') \delta(\triangleleft - \triangleleft') \quad (62)$$

with the other commutators vanishing.

In this setting, we now have a dislon field $X(s, t; \mathbf{x}_0, L, b, \triangleleft)$ over the parameters of the string, with $f(\mathbf{x}_0, L, b, \triangleleft)$ describing how the field is arranged and how the positions \mathbf{x}_0 are correlated with the other variables.

Even though this may seem to be significantly more complicated than what we have previously studied, some generalities are at hand. For instance, it is fairly easy to see that the effective propagator F(n, n') is now promoted to a function of not only the mode of each interacting string, but also of their position, orientation, and characteristic lengths. Concretely, we have

$$F = i\omega^{3} \frac{\mu^{2} bb' \mathbf{M}_{ik}(\triangleleft) \mathbf{M}_{jl}(\triangleleft')}{4\pi^{2}\rho} f(\mathbf{x}_{0}, L, b, \triangleleft) f(\mathbf{x}_{0}', L', b', \triangleleft')$$

$$\times \int d\Omega_{+} \hat{k}_{k} \hat{k}_{l} \int_{0}^{L} ds \int_{0}^{L'} ds' \sin\left(\frac{n\pi s}{L}\right) \sin\left(\frac{n'\pi s'}{L'}\right)$$

$$\times \left[\frac{\delta_{ij} - \hat{k}_{i} \hat{k}_{j}}{c_{T}^{5}} e^{i|\mathbf{x}_{0} - \mathbf{x}_{0}' + s\hat{n}(\triangleleft) - s'\hat{n}'(\triangleleft')|\omega\cos\theta/c_{T}} + \frac{\hat{k}_{i} \hat{k}_{j}}{c_{L}^{5}} e^{i|\mathbf{x}_{0} - \mathbf{x}_{0}' + s\hat{n}(\triangleleft) - s'\hat{n}'(\triangleleft')|\omega\cos\theta/c_{L}}\right]$$

$$(63)$$

as a function of all the aforementioned variables. Here the unit vectors \hat{n}, \hat{n}' point along the direction in which the

string is laid out. The differential $d\Omega_+$ indicates to integrate over the upper hemisphere $\cos \theta > 0$ only, and \hat{k} is the unit vector that spans the surface of the corresponding sphere. The integrals are less manageable than before because there is no particular alignment between the direction defined by $\mathbf{x}_0 - \mathbf{x}'_0 + s\hat{n}(\triangleleft) - s'\hat{n}'(\triangleleft')$ and the local orientation matrices $\mathbf{M}_{ik}(\triangleleft)$.

The complexity in dealing with this object resides in that the product of operators that we used earlier was a standard matrix product. However, now we have to deal with degrees of freedom that are continuous, and thus these products are, in general, operations of the sort

$$F_3(\mathbf{x}, \mathbf{y}) = \int_{\mathbf{z}} F_1(\mathbf{x}, \mathbf{z}) F_2(\mathbf{z}, \mathbf{y}), \tag{64}$$

and thus the inverse operation appearing in the final scattering amplitude, $[1 - \mathbf{T}(\omega)]^{-1}$, must be taken with respect to all the operations that are involved in taking products between effective propagators *F*. Finding analytic expressions for these objects is highly nontrivial in general.

Nonetheless, if we consider a situation with a finite number of dislocations, each with its own properties, the situation becomes somewhat more tractable: the products between $T(\omega)$ again reduce to matrix products, in a vectorial space of dimension $n_D \times N$ with N the number of dislocations in the solid.

All computations in this section have been performed with the interaction (26), which is quadratic in the fields. We now go to the next level.

V. CUBIC INTERACTIONS

Even though the quadratic term in S_{int} fully captures the usual Peach-Koehler force, the fact that this comes from an action principle naturally suggests higher-order couplings. As a starting point, in this section we consider the cubic interactions, which give rise to scattering of phonons by strings with an energy transfer from one to the other. These are given by

$$H_{I}^{(3)}(t) = \mu b \int_{0}^{L} ds \, \mathbf{M}_{kl} \frac{\partial^{2} u_{k}^{I}}{\partial x_{l} \partial x_{l}} ((0, 0, s), t) [X^{I}(s, t)]^{2}.$$
(65)

Even though one could also study the corrections to the mass operator that arise from these terms, we shall postpone that discussion for Sec. VI, where we will treat them inside a broader context of quantum-mechanical corrections.

For simplicity, we shall take $\mathbf{x}_0 = 0$ throughout this section, and denote $\omega_t \equiv \omega_t(\mathbf{k})$ where a prime on the polarization index will also imply a prime on the wave number. Since the final purpose of this section will be to study in what regime one would expect the interactions of phonons by dislocations to compete with the cubic self-interactions of phonons, we will include the quadratic theory only to the lowest comparable order in the perturbative expansion that generates the processes of interest. The complete result, however, will include (at least once per process) a $[1 - \mathbf{T}(\omega)]^{-1}$ factor for each external particle (be it a phonon or a dislon) involved in the corresponding scattering process, accounting for the full extent of the quadratic interactions.

We now proceed to examine the processes of phonon scattering by excited strings and compare them to the effects

of cubic elastic nonlinearities. In between, we will take the opportunity to explore what the scattering cross sections look like in the presence of a thermal distribution for one of the particles involved in each process.

A. Scattering of a phonon by an excited string

Consider the process of an ingoing elastic wave with wave number \mathbf{k}' scattering with the string and producing an outgoing elastic wave with wave number \mathbf{k} , but this time accounting for an excitation of the string in the initial state. This is described by

$$\langle f|i\rangle = \langle 0|a_{\iota}(\mathbf{k})\mathrm{T}\exp\left(-\frac{i}{\hbar}\int_{-\infty}^{\infty}dt\,H_{I}(t)\right)a_{\iota'}^{\dagger}(\mathbf{k}')a_{n}^{\dagger}|0\rangle\,.$$
 (66)

We can now repeat the process of computing the scattering amplitude as before by expanding the *S* matrix in powers of *b*. The result is found to be given by $\langle f | i \rangle = 2\pi \, \delta(\omega_t - \omega_{t'} - \omega_n) \mathcal{T}$, with

$$\mathcal{T} = -iE^*(\mathbf{k};\iota)E(\mathbf{k}';\iota')\sqrt{\frac{\hbar}{(mL)^3\omega_n}}$$

$$\times \sum_{n'=1}^{n_D} \frac{4\pi^3 n'^3}{L^3} \left[\frac{(\mathbf{k}\cdot\hat{e}_1)/(\mathbf{k}\cdot\hat{e}_3)}{\omega_{n'}^2 - \omega_{\iota'}^2} \frac{e^{iL(\mathbf{k}'\cdot\hat{e}_3)-in'\pi} - 1}{(\mathbf{k}'\cdot\hat{e}_3)^2 - (\frac{\pi n'}{L})^2} \right]$$

$$\times \frac{e^{-iL(\mathbf{k}\cdot\hat{e}_3)} - 1}{(\mathbf{k}\cdot\hat{e}_3)^2 - (\frac{2\pi n'}{L})^2} + (\mathbf{k}\leftrightarrow -\mathbf{k}') \left].$$
(67)

Just as the mass operator of the phonon exhibits resonances at the natural frequencies of the string, resonant scattering of a phonon by a string through cubic interactions is also possible. One only needs to notice the $(\omega_{n'}^2 - \omega_{i'}^2)$ factor in the denominator of the previous amplitude, which provides a distinctive signal to compare with other types of scattering. However, it is possible to argue that the exact result, in analogy with what we obtained for the quadratic theory, will have resonance peaks of finite width.

Let us note that the opposite process, i.e., having a phonon lose energy to a string, is also possible and has a scattering amplitude with similar behavior. The corresponding amplitude is given by

$$\langle f|i\rangle = \langle 0|a_n a_i(\mathbf{k}) \operatorname{Texp}\left(-\frac{i}{\hbar} \int_{-\infty}^{\infty} dt \, H_I(t)\right) a_{i'}^{\dagger}(\mathbf{k}')|0\rangle \,, \quad (68)$$

and analogously the \mathcal{T} matrix is given by

$$\mathcal{T} = iE^*(\mathbf{k};\iota)E(\mathbf{k}';\iota')\sqrt{\frac{\hbar}{(mL)^3\omega_n}}$$

$$\times \sum_{n'=1}^{n_D} \frac{4\pi^3 n'^3}{L^3} \left[\frac{(\mathbf{k}'\cdot\hat{e}_1)/(\mathbf{k}'\cdot\hat{e}_3)}{\omega_{n'}^2 - \omega_{\iota}^2} \frac{e^{-iL(\mathbf{k}\cdot\hat{e}_3)-in'\pi} - 1}{(\mathbf{k}\cdot\hat{e}_3)^2 - (\frac{\pi n'}{L})^2} \right]$$

$$\times \frac{e^{iL(\mathbf{k}'\cdot\hat{e}_3)} - 1}{(\mathbf{k}'\cdot\hat{e}_3)^2 - (\frac{2\pi n'}{L})^2} + (\mathbf{k} \leftrightarrow -\mathbf{k}') \left]. \tag{69}$$

Nonetheless, for the preceding computations to be of interest in a typical setting, we should compare the typical magnitude of the cross section for phonon scattering by a string versus phonon scattering by phonons, given by the cubic term in the energy density of a continuous elastic medium.

B. Phonon-phonon-phonon scattering

Let us recall [33] that the cubic term in the energy density of a continuous solid may be written as

$$H_{\text{elastic}}^{(3)} = \int d^3x \, c_{pqmrst} \frac{\partial u_m}{\partial x_q} \frac{\partial u_p}{\partial x_r} \frac{\partial u_s}{\partial x_t}.$$
 (70)

Using the standard techniques employed so far, a quick computation for the amplitude of two incident phonons with wave number \mathbf{k}_1 , \mathbf{k}_2 and an outgoing phonon with wave number \mathbf{k} yields

$$\langle f | i \rangle_{\text{ph}^{3}} = (2\pi)^{4} \delta^{(4)} (k - k_{1} - k_{2}) \sqrt{\frac{\hbar}{8\rho^{3}\omega_{\iota}\omega_{\iota_{1}}\omega_{\iota_{2}}}} \times 6c_{pqmrst} (\mathbf{k} \cdot \hat{e}_{q}) (\mathbf{k}_{1} \cdot \hat{e}_{r}) (\mathbf{k}_{2} \cdot \hat{e}_{t}) \times \varepsilon_{\iota} (\mathbf{k})_{m} \varepsilon^{*}_{\iota_{1}} (\mathbf{k}_{1})_{p} \varepsilon^{*}_{\iota_{2}} (\mathbf{k}_{2})_{s},$$
(71)

where $\delta^{(4)}(k - k_1 - k_2) = \delta(\omega_l - \omega_{l_1} - \omega_{l_2})\delta^{(3)}(\mathbf{k} - \mathbf{k}_1 - \mathbf{k}_2)$ enforces overall energy-momentum conservation. In what follows, we will use $\mathcal{T}_{\text{ph}^3}$ defined implicitly through $\langle f | i \rangle_{\text{ph}^3} = (2\pi)^4 \delta^{(4)}(k - k_1 - k_2) \mathcal{T}_{\text{ph}^3}$.

However, in order to make a comparison with the scattering amplitude by a string it is necessary to include a distribution of phonons to scatter against, as the dimensionality of the Dirac delta prevents us from making a direct comparison between the constants of the problem. Even though we could simply substitute it with a volume factor, this presents us with the opportunity to write down cross sections through thermal distributions.

C. Behavior at finite temperature

Although our present interests encourage us to explore scattering of phonons through some distribution, the prospect of writing down the cross section of an incident wave on a solid at finite temperature T should be rather attractive. Let us take an initial state characterized by a density matrix of thermodynamic equilibrium at chemical potential $\bar{\mu}$ in the grand canonical ensemble for the strings

$$\hat{\rho}^{0} = \frac{a_{\iota'}^{\dagger}(\mathbf{k}')|0\rangle\langle 0|a_{\iota'}(\mathbf{k}')}{\langle 0|a_{\iota'}(\mathbf{k}')a_{\iota'}^{\dagger}(\mathbf{k}')|0\rangle} \otimes \frac{e^{-\beta\sum_{n=1}^{n_{D}}(\hbar\omega_{n}-\bar{\mu})a_{n}^{\dagger}a_{n}}}{\operatorname{tr}[e^{-\beta\sum_{n=1}^{n_{D}}(\hbar\omega_{n}-\bar{\mu})a_{n}^{\dagger}a_{n}}]}, \quad (72)$$

where $\beta = (k_B T)^{-1}$, and \otimes is the tensor product between the Hilbert spaces of the string and phonon states. To make progress, it is helpful to write the exponential in terms of the string eigenstates:

$$e^{-\beta \sum_{n=1}^{n_D} (\hbar \omega_n - \bar{\mu}) a_n^{\dagger} a_n} = \sum_{\{N_i\}_{i=1}^{n_D}} e^{-\beta \sum_{n=1}^{n_D} (\hbar \omega_n - \bar{\mu}) N_n} \times |N_1, \dots, N_{n_D}\rangle \langle N_1, \dots, N_{n_D}|, \quad (73)$$

where the sum over $\{N_i\}_{i=1}^{n_D}$ represents the sum over all occupation numbers N_i for each mode of the string $i \in \{1, ..., n_D\}$. Proceeding as we did before, the cross section for outgoing phonons scattered through a process with scattering amplitude (67) will be given by

$$d\sigma = \frac{d^3k}{c_{\iota'}(2\pi)^3} \operatorname{tr} \left(U \hat{\rho}^0 U^{\dagger} | \mathbf{k}, \iota \rangle \langle \mathbf{k}, \iota | \otimes \mathcal{I}_{n_D} \right), \quad (74)$$

where \mathcal{I}_{n_D} is the identity operator on the Hilbert space of the string. This in turn implies

$$d\sigma = \frac{d^{3}k}{c_{\iota'}(2\pi)^{3}} \operatorname{tr}_{\text{string}} \left[\sum_{\{N_{i}\}_{i=1}^{n_{D}}} e^{-\beta \sum_{n=1}^{n_{D}} (\hbar\omega_{n} - \bar{\mu})N_{n}} \right. \\ \left. \times \left\langle \mathbf{k}, \iota | U | N_{1}, \ldots, N_{n_{D}} \right\rangle \otimes |\mathbf{k}', \iota' \rangle \right. \\ \left. \times \left\langle N_{1}, \ldots, N_{n_{D}} \right| \otimes \left\langle \mathbf{k}', \iota' | U^{\dagger} | \mathbf{k}, \iota \right\rangle \right]$$
(75)

and thus, if we only keep track of the processes that originate by (67), we get

$$\frac{d\sigma}{d\Omega} = \sum_{\{N_i\}_{i=1}^{n_D}} e^{-\beta \sum_{n=1}^{n_D} (\hbar\omega_n - \bar{\mu})N_n} \\
\times \sum_{i=1}^{n_D} N_i \frac{(\omega_{i'} + \omega_i)^2}{4\pi^2 c_{i'} c_i^3} |\mathcal{T}|^2_{\omega_i = \omega_{i'} + \omega_n},$$
(76)

where the N_i factor comes from selecting one of the creation operators in the states

$$|N_1, \dots, N_{n_D}\rangle \equiv \frac{(a_1^{\dagger})^{N_1} \dots (a_{n_D}^{\dagger})^{N_{n_D}}}{\sqrt{N_1! \dots N_{n_D}!}} |0\rangle$$
(77)

and normalizing appropriately when taking the trace.

Now one may execute the sum over the occupation numbers as usual in statistical mechanics. The resulting cross section would be

$$\frac{d\sigma}{d\Omega} = \sum_{n=1}^{n_D} \frac{|\mathcal{T}|^2_{\omega_i = \omega_{l'} + \omega_n}}{e^{(\hbar\omega_n - \bar{\mu})/k_B T} - 1} \frac{(\omega_{l'} + \omega_n)^2}{4\pi^2 c_{l'} c_l^3}$$
(78)

with \mathcal{T} given by (67). Here we have assumed that the dislocations are in thermodynamic equilibrium with some reservoir at temperature T and chemical potential $\bar{\mu}$, but not with the phonons. That is, we have neglected the effects of the interaction for this estimate.

On the other hand, the scattering of phonons under similar assumptions gives

$$\frac{d\sigma}{d\Omega}\Big|_{\rm ph^3} = \frac{|\mathcal{T}_{\rm ph^3}|^2}{e^{\hbar(\omega_l - \omega_{l_1})/k_BT} - 1} \frac{\mathbf{k}_2 = \mathbf{k} - \mathbf{k}_1}{4\pi^2 c_{l_1} c_l^3} K(\mathbf{k}, \mathbf{k}_1; \{c_{l_i}\}),$$
(79)

where $K(\mathbf{k}, \mathbf{k}_1; c_{i_i})$ is a kinematical factor arising from the restrictions imposed by energy-momentum conservation (details are given in Appendix C), and V is the volume of the solid. Given that the volume of the solid is an extensive quantity that does not depend on the specific constitution of the solid, if there is only one dislocation present we could always consider a "large volume" limit and neglect the effects of the dislocation. Therefore, a meaningful comparison will arise only if we let the dislocations increase in number with the volume of the solid. Thus, the appropriate comparison

between \mathcal{T} matrices is \mathcal{T}_{ph^3} versus $\sqrt{n_d}\mathcal{T}$, where n_d is the dislocation number density.

To compare them, we will assume c_{pqmrst} to be of the same order as μ , and take a situation in which the incident and outgoing frequencies are not too close to the resonances ω_n , so that (67) holds as written. This is because the exact result will contain higher-order terms that after resummation should render the peaks at ω_n finite, in analogy with what happens in (35).

Given that the temperature enters the differential cross sections in the same manner in both (78) and (79), we can take the corresponding factors to be equal as long as we are interested in asymptotic states with the same ingoing and outgoing frequencies in both situations. A rough estimate gives

$$\mathcal{T}_{\mathrm{ph}^3} \sim \mu k^3 \sqrt{\frac{\hbar}{\rho^3 \omega_\iota \omega_{\iota_1} \omega_{\iota_2}}}$$
 (80)

and, assuming that the preponderant eigenfrequency of the string in the scattering process is ω_1 ,

$$\mathcal{T} \sim \sqrt{\frac{\hbar n_d}{(mL)^3 \omega_\iota \omega_{\iota'} \omega_n}} \frac{\mu^2 b^2 L^2}{\rho} \frac{k^3}{\omega_1^2},\tag{81}$$

one thus obtains that the scattering by excited strings should dominate provided that

$$n_d L^3 \gg b^2 / L^2. \tag{82}$$

Note that this estimate depends only on the intrinsic characteristics of the dislocation: their "aspect ratio" b/L and density completely determine whether scattering by dislocations should dominate or not. This can be traced back to the fact that the characteristic time scales of dislocations are not independent of the properties of the elastic medium. In fact, a close look at the eigenfrequencies of the string reveals that $\omega_n = \frac{n\pi c_T}{L} \mathcal{O}(1)$, where the $\mathcal{O}(1)$ number is given by $\sqrt{2(1-\gamma^{-2})/(1+\gamma^{-4})}$. Thus, the only sensitivity of (82) on the characteristics of the material is, aside from *b*, through γ , and is a rather weak one.

Therefore, if there is a high density of scatterers compared to the aspect ratio of the dislocations, it would be expectable that string dislocations represent the dominant contribution to the phonon cross section, without a strong dependence on the material at hand (apart from the value of *b*). For example, if we take a Burgers vector b = 0.5 nm and a dislocation length L = 50 nm, we have that phonon-dislocation scattering will dominate over phonon-phonon scattering for dislocation densities $\Lambda = n_d L \sim 10^8$ cm⁻², which is, in the opinion of the authors, a very modest bound.

All of the previous results could have been obtained through a careful classical analysis of the original action integral *S*. Now we turn to some intrinsically quantummechanical effects that may be reflected on different observable quantities.

VI. QUANTUM CORRECTIONS

As was mentioned earlier, the action integral S_{int} discussed prior to Sec. V only includes quadratic terms. However, the

starting point is

$$S_{\rm int} = -b_i \int dt \int_{\delta S} dS^j \sigma_{ij}.$$
 (83)

If we perform a Taylor expansion of $\sigma_{ij}(s\hat{\tau} + r\vec{X})$ about the equilibrium position of the string r = 0 (*r*, *s* being the coordinates parametrizing δS), we obtain

$$S_{\text{int}} = -b_i \int dt \int_{\delta S} dS^j \left[\sum_{n=0}^{\infty} c_{ijkl} \frac{\partial^{n+1} u_k}{\partial x_1^n \partial x_l} \frac{r^n}{n!} X^n \right]$$
$$= -\mu b \mathbf{M}_{kl} \int dt \int_0^L ds \left[\sum_{n=0}^{\infty} \frac{\partial^{n+1} u_k}{\partial x_1^n \partial x_l} \frac{X^{n+1}}{(n+1)!} \right], \quad (84)$$

which gives further couplings between phonons and string dislocations. These terms will make a phonon be able to interact with several modes of the dislocation in a singlescattering event at the same time.

For the moment we will only deal with the effects of these additional terms in action integral on the scattering of phonons by a string to lowest order in the amplitude of the interaction, which schematically would be $\mathcal{O}(b^2)$ (as we have shown earlier that this is not the true perturbative parameter, at least in the quadratic theory). The main difference of this section with our earlier computations is that now the internal structure of the scattering will get richer. Namely, "loop" contributions, as one would call them in quantum field theory, will emerge when performing "contractions" (i.e., pairings through Wick's theorem when computing the quantum expectation value) of fields in the interaction Hamiltonians with themselves.

A. Phonon-phonon amplitude

The object of interest is the same as in Sec. IV, and given by Eq. (25),

$$\langle f|i\rangle = \langle 0|a_{\iota}(\mathbf{k})\mathrm{T}\exp\left[-\frac{i}{\hbar}\int_{-\infty}^{\infty}H_{I}(t)dt\right]a_{\iota'}^{\dagger}(\mathbf{k}')|0\rangle,$$

only now we have a more complex Hamiltonian H_I . However, it is still linear in **u**, and therefore the factors $E(\mathbf{k}; \iota)$ are still present. This only leaves the aforementioned loop contributions yet to be accounted for. If n, n' denote indices in the sum of the interaction picture Hamiltonian derived from (84), we are left with terms proportional to

$$\frac{(-i\mathbf{k}\cdot\hat{e}_{1})^{n}}{(n+1)!}\frac{(+i\mathbf{k}'\cdot\hat{e}_{1})^{n'}}{(n'+1)!}\left\langle 0|TX_{I}^{n+1}(s,t)X_{I}^{n'+1}(s',t')|0\right\rangle, \quad (85)$$

in which the unraveling of the products of creation and annihilation operators may be performed as a combinatorial exercise. After doing so, the expressions may be summed back to obtain

$$\mathcal{T} = -\frac{E^*(\mathbf{k}; \iota)E(\mathbf{k}'; \iota')}{\hbar(\mathbf{k} \cdot \hat{e}_1)(\mathbf{k}' \cdot \hat{e}_1)} \int_0^L ds \int_0^L ds' \int_{-\infty}^{\infty} dt$$
$$\times e^{-i(\mathbf{k} \cdot \hat{e}_3)s - (\mathbf{k} \cdot \hat{e}_1)^2 \Delta(s)/2}$$
$$\times e^{+i\omega t} [e^{(\mathbf{k} \cdot \hat{e}_1)(\mathbf{k}' \cdot \hat{e}_1)\Delta(s, s', t)} - 1]$$
$$\times e^{i(\mathbf{k}' \cdot \hat{e}_3)s' - (\mathbf{k}' \cdot \hat{e}_1)^2 \Delta(s')/2}, \tag{86}$$

$$\Delta(s) \equiv \Delta(s, s, 0). \tag{87}$$

We point out to the interested reader the existence of general formulas in quantum field theory [34] that allow us to infer this result by looking at the analytic structure of the interaction Hamiltonian. The reason why this occurs is that the stress tensor σ_{ij} appearing in the Lagrangian density may be formally written as

$$\sigma_{ij}(s\hat{\tau} + r\bar{X}) = \exp[r\bar{X} \cdot \nabla_{\mathbf{x}}]\sigma_{ij}(s\hat{\tau} + \mathbf{x})|_{\mathbf{x}=0}$$
$$= \left[\exp(r\bar{X} \cdot \nabla_{\mathbf{x}})c_{ijkl}\frac{\partial u_k}{\partial x_l}(\mathbf{x})\right]_{\mathbf{x}=s\hat{\tau}} (88)$$

and then in momentum space the gradient takes the form of a wave number, thus showing that the exponentials contained in (86) are accounting for precisely this structure. These exponentials are preserved along the result because performing the contractions of Eq. (85) is equivalent to computing an expectation value over a Gaussian probability distribution, and thus the outcome naturally involves exponentials of the propagators.

It is important to stress that Eq. (86) contains the full extent of the quantum corrections to the phonon-phonon scattering amplitude implied by the action integral (84), to the lowest order in the amplitude of the interaction, as the propagators in the exponential are proportional to \hbar . Indeed, one may treat (86) as a power series on \hbar , where the zeroth-order term gives the contribution of the quadratic theory and the subsequent terms reveal quantum-mechanical effects. It is interesting to note that at this point a new characteristic length emerges: the product of quantities that give the string propagator its dimensions. Simple inspection gives that

$$d_q \equiv \sqrt{\frac{\hbar}{\rho b^2 c_T}} \sim \sqrt{\frac{\hbar}{mL\omega_1}} \tag{89}$$

PHYSICAL REVIEW B 99, 214102 (2019)

plays a similar role to L regarding how large the corrections are with respect to the first-order computation. If we plug in typical numerical values for ρ , b, and c_T , for instance, those of silicon, then we find $d_q \sim 10^{-9}$ cm.

In the spirit of alleviating the discussion while trying to keep track of the quantum effects that emerge in the presence of nonlinear interactions with dislocations, we will now study the quantum corrections explicitly in the case $n_D = 1$, and to first order in \hbar for the general case.

B. $n_D = 1$ case: An analytic exploration

Following the approach we have taken thus far, studying a $n_D = 1$ dislocation segment is equivalent to studying a string with a single oscillation mode, which may represent a very short dislocation in units of the interatomic distance of the crystal. Conversely, imposing it should always give a reasonable description of the physics at frequencies below c_T/L , but since we are currently exploring quantum corrections, we find the former to be the most conservative attitude towards this setting.

Nonetheless, it is the tractability of the computations at hand that turns our attention towards this particular case. For instance, the string propagators take simpler forms:

$$\Delta(s) = \frac{\hbar}{mL\omega_1} \sin^2\left(\frac{\pi s}{L}\right),\tag{90}$$

$$\Delta(s, s', t) = \frac{\hbar}{mL} \frac{e^{-i\omega_1|t|}}{\omega_1} \sin\left(\frac{\pi s}{L}\right) \sin\left(\frac{\pi s'}{L}\right), \quad (91)$$

and out of convenience we shall define

$$\Delta(s, s') \equiv \frac{\hbar}{mL\omega_1} \sin\left(\frac{\pi s}{L}\right) \sin\left(\frac{\pi s'}{L}\right).$$
(92)

Using these expressions, the temporal integral in (86) may be carried out explicitly in terms of incomplete Gamma functions. The relevant result to this is

$$\int_{-\infty}^{\infty} dt \, e^{i\omega t} e^{k_1 k_1' \Delta(s, s', t)} = \frac{-i}{4\pi \omega} \bigg[[-k_1 k_1' \Delta(s, s')]^{-\omega^2/\omega_1^2} \gamma \bigg(1 + \frac{\omega^2}{\omega_1^2}, -k_1 k_1' \Delta(s, s') \bigg) \\ - [-k_1 k_1' \Delta(s, s')]^{\omega^2/\omega_1^2} \gamma \bigg(1 - \frac{\omega^2}{\omega_1^2}, -k_1 k_1' \Delta(s, s') \bigg) \bigg],$$
(93)

where $\gamma(a, x)$ is the lower incomplete Gamma function, which admits an analytic expansion

$$\gamma(a,x) = x^a \Gamma(a) e^{-x} \sum_{n=0}^{\infty} \frac{x^n}{\Gamma(a+n+1)}.$$
 (94)

Then, what remains is an integral over a bounded domain of an analytic function, which may be solved numerically for the values of interest without issue. However, we will not proceed to do so since for values of practical interest ($d_q \sim 10^{-11}$ m) we can carry out a perturbative computation without losing much accuracy.

Before concluding this discussion, there is one feature of interest that is worth pointing out: by examining (93), we see that the result has poles in the frequency variable ω for

each positive multiple of ω_1 (i.e., $\omega = n\omega_1$, with *n* a positive integer). Therefore, we expect that the scattering cross section will have resonances at every frequency that is a multiple of ω_1 , although their amplitude will be suppressed by factors of $(kd_q)^2$ for every phononic excitation.

In the following subsection we give a concrete estimate of these corrections, for the general n_D case.

C. General $\mathcal{O}(\hbar)$ corrections

For practical purposes, since most of the time we will have $kd_q \ll 1$, in order to estimate the corrections to the scattering amplitude due to quantum effects it is sufficient to keep the first correction to the result of the quadratic theory, which is proportional to \hbar . As the difficulty of the computation is

significantly reduced with respect to that of the exact quantity, we can afford to leave n_D as arbitrary.

PHYSICAL REVIEW B 99, 214102 (2019)

Performing a Taylor expansion on \hbar , we can approximate (86) with

$$\mathcal{T} = -\frac{E^{*}(\mathbf{k};\iota)E(\mathbf{k}';\iota')}{\hbar k_{1}k_{1}'} \int_{0}^{L} ds \int_{0}^{L} ds' \int_{-\infty}^{\infty} dt e^{-ik_{3}s} \left[1 - \frac{k_{1}^{2}}{2}\Delta(s)\right] e^{ik_{3}'s'} \left[1 - \frac{k_{1}'^{2}}{2}\Delta(s')\right] e^{+i\omega t} \left[k_{1}k_{1}'\Delta(s,s',t) + \frac{k_{1}^{2}k_{1}'^{2}}{2}\Delta(s,s',t)^{2}\right] \\ = \frac{2iLE^{*}(\mathbf{k};\iota)E(\mathbf{k}';\iota')}{m} \left[\sum_{n=1}^{n_{D}} \frac{f_{n}^{(0)}(-k_{3})f_{n}^{(0)}(k_{3}')}{\omega_{n}^{2} - \omega^{2}} + \frac{\hbar k_{1}k_{1}'}{2mL\omega_{1}} \sum_{n,n'=1}^{n_{D}} \frac{n+n'}{nn'} \frac{f_{n,n'}^{(1)}(-k_{3})f_{n,n'}^{(1)}(k_{3}')}{(\omega_{n} + \omega_{n'})^{2} - \omega^{2}} - \frac{\hbar k_{1}^{2}}{2mL\omega_{1}} \sum_{n,n'=1}^{n_{D}} \frac{1}{n'} \frac{f_{n}^{(0)}(-k_{3})f_{n,n'}^{(0)}(k_{3}')}{\omega_{n}^{2} - \omega^{2}} - \frac{\hbar k_{1}'^{2}}{2mL\omega_{1}} \sum_{n,n'=1}^{n_{D}} \frac{1}{n'} \frac{f_{n}^{(0)}(-k_{3})f_{n,n'}^{(2)}(k_{3}')}{\omega_{n}^{2} - \omega^{2}} \right],$$

$$(95)$$

where the functions $f_{j(k)}^{(i)}(k_3)$ are defined in Appendix D. This constitutes the lowest-order correction in \hbar to the scattering amplitude defined by the quadratic theory (at its respective lowest order in perturbation theory).

For our present purposes, their most important property is that they peak when k_3L is a specific integer multiple of π . Furthermore, at those points they take values of order $\mathcal{O}(1)$. For instance, $f_n^{(0)}$ peaks in amplitude at $k_3L \sim n\pi$, while $f_{n,n'}^{(1)}$ has peaks at $k_3L \sim (n + n')\pi$.

This makes it possible to estimate, approximately, the precise order of magnitude of the quantum correction to the scattering amplitude: we need only compare the factors accompanying each term of the form $(\omega_n^2 - \omega^2)$, without worrying about divergences at $\omega = \omega_n$ as the exact computation will sum them into a finite expression. By rearranging the sum inside the square brackets in (95) with prefactor $\frac{\hbar k_1 k'_1}{2mL\omega_1}$ into a sum over n + n' and n', we may take $f_{n,n'}^{(1)}$ as weakly dependent on n' because its peak value close to $kL \sim (n + n')\pi$ will remain nearly constant (i.e., roughly independent of n' as long as n + n' remains fixed), preserving the dominant behavior as a function of k. Thus, we are left with harmonic sums that we can approximate by the means of $\sum_{n'=1}^{n^*} \frac{1}{n'} \approx \gamma_e + \ln(n^*)$, with γ_e the Euler-Mascheroni constant.

Therefore, we find that the peak of the scattering amplitude at the resonance frequency ω_{n^*} should be subject to corrections of magnitude

$$\sim \frac{\hbar k_1 k_1'}{2mL\omega_1} [\gamma_e + \ln(n^* - 1)]$$
 (96)

as a consequence of the term with $f_{n,n'}^{(1)}$ factors, while the ones with $f_{n,n'}^{(2)}$ induce a correction of size

$$\sim \frac{\hbar (k_1^2 + k_1'^2)}{4mL\omega_1} [\gamma_e + \ln(n_D)]$$
(97)

to each resonance peak. Consequently, as the dependence on n^* and n_D is logarithmic, a short-wavelength phonon with $k \sim 2\pi \times 10^9 \text{ m}^{-1}$ will have its scattering amplitude corrected by a factor of roughly

$$1 - \pi^2 \times 10^{-4} \times [\gamma_e + \ln(n_D)], \tag{98}$$

where we have taken $\gamma = c_L/c_T \sim 2$ and $\ln(\delta/\delta_0) \sim 3$.

In terms of measurability, we would like n_D to be as large as possible. Recent experiments [12] show that it may

be possible to probe samples with dislocation lengths up to $L \sim 1 \ \mu$ m, which sets $\ln(n_D)$ to be at most ~ 10 .

Thus, we deduce that in an optimistic scenario for the detectability of quantum corrections, those effects will be of relative size 1% to the classical predictions. While this may seem far-fetched given that one would have to make a controlled experiment with phonons of wavelength comparable to the lattice constant in a carefully devised material with dislocations of mesoscopic length while assuming the continuum model for the string still holds, the result doesn't vary much with n_D : should L be of order ~10 nm, the correction would only get reduced by a factor of 1/2. Therefore, the greatest challenge to test these predictions is to measure the scattering amplitude for phonons with high wave number.

VII. CONCLUSION

In this paper we have studied a theory of phonons in an elastic continuum interacting with quantum-dislocations segments. The results contained herein establish a theory incorporating the Peach-Koehler force, which had been unaddressed until now. In addition to that, for the quadratic action we established the finiteness of the theory at all wavelengths, avoiding the need to engage in renormalization procedures previously used in classical settings [23].

A number of tools have been developed, allowing for the computation of a number of quantities of interest. Chief among them is the phonon-dislocation cross section. The result differs substantially from the classic result that considers an infinitely long, static, dislocation line. The next subsection discusses this topic. A subsequent subsection discusses how the tools that have been developed can be put to use to solve a number of current problems of interest.

A. Comparison with the classic model

As discussed in the Introduction, current understanding on the scattering of phonons by dislocations relies on classic work by Klemens [1] and Carruthers [2]. Although in that approach the phonon-dislocation scattering cross section depends linearly on phonon frequency, Ohashi [35] has discussed how various estimates of the parameters on which these models depend can lead to estimates for the phonondislocation scattering cross section that differ by orders of magnitude. The result of our calculation for the phonon-

TABLE I. Classic and current modeling for the phonondislocation interaction compared and contrasted.

	Classic	This work
Dislocation length	infinite	finite length L
Dislocation response	static	dynamic
Frequency dependence of scattering cross section	linear	rich (see Fig. 3)

dislocation cross section is given by Eqs. (43) and (46) and is plotted in Fig. 3. The first striking difference with the classic results is the dependence on frequency, much richer than simply linear. A second important difference that is less apparent is that Eqs. (43) and (46) depend only on dislocation segment length L, Burgers vector b, and the properties of the elastic medium: mass density and elastic constants. While a continuum approach does limit this model to wavelengths larger than, say, five interatomic spacings, it is of great generality and can be applied to any material without adjustable parameters. The more salient differences between the two approaches are summarized in Table I.

B. Discussion and outlook

The findings laid out in this paper can be used and generalized in a variety of ways. First would be the replacement of a continuum solid by a crystal lattice. The free phonon aspects of the theory would be straightforward. On the other hand, the free dislocation term in the action would have to be considered with some care, taking into account the actual lattice that is considered, particularly its slip systems. Moreover, the interaction term would have to be worked out in a consistent fashion. Consideration of screw, rather than edge, dislocations, should be a straightforward matter.

The theory of this paper has been developed in three dimensions. It should not be difficult to specialize the action (1) to two dimensions, in which dislocations are points rather than strings so the whole formalism should be easier to manage. Indeed, this could be a good place to start working out the consequences of having a crystal lattice rather than a continuum solid. It could also have significant consequences for a number of materials of current interest [36,37].

Another direction of research is to study this model in the $L \rightarrow \infty$ limit, along with $n_D \rightarrow \infty$. While some qualitative features of this limit have been explored throughout this paper, it would be interesting to start with a translationally invariant

action along the equilibrium axis of the dislocation. The features observed in this limit should be sharper, as momentum conservation would be enforced through the aforementioned symmetry. Moreover, the length scale L would disappear from the results, leaving a scale invariant theory where in all likelihood the scattering amplitudes will only depend on geometric features of the problem (angle of incidence, polarization vectors).

We have considered in some detail the scattering of phonons by quantum dislocations. It should be possible to use these results, in conjunction with, say, kinetic theory arguments, to compute the contribution of quantum-dislocations segments to thermal conductivity. Results such as Eq. (35) for the \mathcal{T} matrix indicate that high-frequency phonons can have a significant contribution, contrary to the classical intuition that only phonons of wavelength comparable to the dislocation length L, hence low frequency, would contribute. Indeed, typical dislocation segments are 10-100 nm long. That is, say, 20-200 interatomic distances. A continuum approximation should give a reasonable indication of material behavior up to, say, five interatomic distances. So a 50-nm dislocation segment would have ten harmonics in play within a reasonable continuum approximation. Of course, in an experiment such as that of Sun et al. [12] the dislocations have been tailored to a micron length. In this case a continuum approximation will be good for 200 harmonics.

Finally, we took into account the intrinsically quantummechanical effects that would single out the interaction Hamiltonian among others that could generate the Peach-Koehler force at leading order. These corrections are small even for phonons of wavelengths comparable to the lattice constant, but at each order in perturbation theory include distinct form factors that might render the signal identifiable if detected.

On a longer term perspective, it should be possible to study the interaction of quantum-dislocation segments with electrons. Even at the level of a quadratic theory, the nontrivial interaction studied in this work should give rise to distinct correlations between electrons and phonons if the electrondislon coupling is included.

ACKNOWLEDGMENTS

B.S.H. was supported by CONICYT Grant No. CONICYT-PFCHA/MagísterNacional/2018-22181513. F.L. gratefully acknowledges the support of Fondecyt Grants No. 1160823 and No. 1191179. B.S.H. wishes to thank L. E. F. Foà Torres for helpful discussions.

APPENDIX A: AVERAGES OVER INTERNAL DEGREES OF FREEDOM IN THE QUADRATIC THEORY

If we have a solid filled with randomly oriented dislocations, then it is expectable that in the presence of weak scattering the amplitudes and cross sections are well described by averaging over internal degrees of freedom. Namely, to start with a definite object, we would like to average Eq. (33), which we now write in full in terms of the basic quantities of the problem:

$$\mathcal{T} = \frac{i\mu^{2}b^{2}e^{i\mathbf{x}_{0}\cdot(\mathbf{k}'-\mathbf{k})}k_{l}\mathbf{M}_{kl}\varepsilon_{l}(\mathbf{k})_{k}k_{l'}'\mathbf{M}_{k'l'}\varepsilon_{l'}(\mathbf{k}')_{k'}}{mL\rho\sqrt{\omega_{t}(\mathbf{k})\omega_{t'}(\mathbf{k}')}} \times \sum_{n=1}^{n_{D}}\sum_{n'=1}^{n_{D}}\frac{n\pi/L}{\sqrt{\omega_{n}^{2}-\omega^{2}}}\frac{e^{-iL(\mathbf{k}\cdot\hat{e}_{3})+in\pi}-1}{(\mathbf{k}\cdot\hat{e}_{3})^{2}-(n\pi/L)^{2}}\bigg[\frac{1}{1-\mathbf{T}(\omega)}\bigg]_{nn'}\frac{e^{iL(\mathbf{k}'\cdot\hat{e}_{3})-in'\pi}-1}{(\mathbf{k}'\cdot\hat{e}_{3})^{2}-(n'\pi/L)^{2}}\frac{n'\pi/L}{\sqrt{\omega_{n'}^{2}-\omega^{2}}},$$
(A1)

where summation over repeated indices k, k', l, l' is implied. The first, and easiest, task to carry out is to perform a spatial average on the distribution of dislocations. This translates into integrating the previous equation over \mathbf{x}_0 and multiplying by n_d (the dislocation number density):

$$\bar{\mathcal{T}}^{\text{spatial}} = n_d \int_{\mathbf{x}_0} \mathcal{T}|_{\mathbf{x}_0} = n_d (2\pi)^3 \delta^{(3)}(\mathbf{k} - \mathbf{k}') \times \mathcal{T}(\mathbf{k} = \mathbf{k}').$$
(A2)

Then, all that remains is to compute an angular average, i.e., over the possible orientations of the triad $\hat{e}_1, \hat{e}_2, \hat{e}_3$.

At this point we note that \hat{k} is the only physically relevant spatial direction remaining after the average is performed. Thus, for the purposes of computing an angular average, we may define integration angles around this axis. Let \hat{i} , \hat{j} , \hat{k} be the basis of reference, with \hat{i} , \hat{j} fixed unit vectors orthogonal to \hat{k} . Explicitly, if we let (θ, φ) be the spherical coordinate angles with respect to $\{\hat{i}, \hat{j}, \hat{k}\}$ and denote by $\{\hat{r}, \hat{\theta}, \hat{\varphi}\}$ the corresponding unit vectors,

$$\hat{e}_1 = \cos\phi\,\hat{\theta} + \sin\phi\,\hat{\varphi},\tag{A3}$$

$$\hat{e}_2 = \cos\phi\,\hat{\varphi} - \sin\phi\,\hat{\theta},\tag{A4}$$

$$\hat{e}_3 = \hat{r}.\tag{A5}$$

These conventions allow us to represent the direction in which the string is laid out through the angles (θ, φ) and the relative orientation of the Burgers vector through the angle ϕ . Therefore, an angular average of a function f of the angles (θ, φ, ϕ) is given by

$$\bar{f} = \frac{1}{8\pi^2} \int_0^{2\pi} d\phi \int_0^{2\pi} d\varphi \int_0^{\pi} d\theta \sin\theta f(\theta, \varphi, \phi).$$
(A6)

Now we proceed to compute the averaged scattering amplitude \mathcal{T} . The object of interest will be

$$\frac{1}{8\pi^2} \int_0^{2\pi} d\phi \int_0^{2\pi} d\phi \int_0^{\pi} d\theta \sin \theta k_l k_{l'} \mathbf{M}_{kl} \mathbf{M}_{k'l'} \frac{e^{-iL(\mathbf{k}\cdot\hat{e}_3)+in\pi}-1}{(\mathbf{k}\cdot\hat{e}_3)^2-(n\pi/L)^2} \frac{e^{iL(\mathbf{k}\cdot\hat{e}_3)-in'\pi}-1}{(\mathbf{k}\cdot\hat{e}_3)^2-(n'\pi/L)^2},$$
(A7)

leaving the polarization vectors out of the discussion so as to obtain a rank-2 tensor as a result and thus be able to choose the polarization modes later. In terms of the angles we defined earlier, Eq. (A7) is written as

$$\frac{k^2}{8\pi^2} \int_0^{2\pi} d\phi \int_0^{2\pi} d\phi \int_0^{\pi} d\theta \sin\theta [(\cos\phi\,\hat{\theta}_k + \sin\phi\,\hat{\varphi}_k)(\cos\phi\,\hat{\theta}_{k'} + \sin\phi\,\hat{\varphi}_{k'})\sin^2\theta\,\sin^2\phi \\ - (\cos\phi\,\hat{\theta}_k + \sin\phi\,\hat{\varphi}_k)(\cos\phi\,\hat{\varphi}_{k'} - \sin\phi\,\hat{\theta}_{k'})\sin^2\theta\,\sin\phi\,\cos\phi - (\cos\phi\,\hat{\varphi}_k - \sin\phi\,\hat{\theta}_k)(\cos\phi\,\hat{\theta}_{k'} + \sin\phi\,\hat{\varphi}_{k'})\sin^2\theta\,\sin\phi\,\cos\phi \\ + (\cos\phi\,\hat{\varphi}_k - \sin\phi\,\hat{\theta}_k)(\cos\phi\,\hat{\varphi}_{k'} - \sin\phi\,\hat{\theta}_{k'})\sin^2\theta\,\cos^2\phi] \frac{e^{-ikL\cos\theta}(-1)^n - 1}{(k\cos\theta)^2 - (n\pi/L)^2} \frac{e^{ikL\cos\theta}(-1)^{n'} - 1}{(k\cos\theta)^2 - (n'\pi/L)^2},$$
(A8)

and now the trigonometric integrals over (φ, ϕ) are straightforward. Performing them gives

$$\frac{k^2}{8} \int_0^{\pi} d\theta \sin^3\theta [2\sin^2\theta \,\hat{k}_k \hat{k}_{k'} + (1+\cos^2\theta)(\delta_{kk'} - \hat{k}_k \hat{k}_{k'})] \frac{e^{-ikL\cos\theta}(-1)^n - 1}{(k\cos\theta)^2 - (n\pi/L)^2} \frac{e^{ikL\cos\theta}(-1)^{n'} - 1}{(k\cos\theta)^2 - (n'\pi/L)^2}, \tag{A9}$$

and changing variables to $u = \cos \theta$ we get

$$\frac{k^2}{8} \int_{-1}^{1} du [2(1-u^2)^2 \hat{k}_k \hat{k}_{k'} + (1-u^4)(\delta_{kk'} - \hat{k}_k \hat{k}_{k'})] \frac{e^{-ikLu}(-1)^n - 1}{(ku)^2 - (n\pi/L)^2} \frac{e^{ikLu}(-1)^{n'} - 1}{(ku)^2 - (n'\pi/L)^2},$$
(A10)

which upon substitution in $\overline{\mathcal{T}}$ yields the coefficients $\mathbf{F}_T(k, \omega)$, $\mathbf{F}_L(k, \omega)$.

APPENDIX B: PHONON SCATTERING BY DISLOCATION TO ALL ORDERS IN THE QUADRATIC COUPLING

Let us note that given a quadratic interaction Hamiltonian, the computation of expectation values acquires a simple form: by expanding (25) in a power series of H_I , one needs to evaluate

$$\langle 0|a_{t'}(\mathbf{k}')H_I(t_1)\dots H_I(t_n)a_t^{\dagger}(\mathbf{k})|0\rangle, \qquad (B1)$$

which can be solved through repeated use of the commutation relations for a, a^{\dagger} and $a |0\rangle = 0$. Since every H_I is quadratic, and more precisely bilinear on **u** and *X*, each interaction Hamiltonian can be commuted exactly one time with $a_t(\mathbf{k})/a_t^{\dagger}(\mathbf{k})$ and exactly one time with a_n/a_n^{\dagger} . This means that one can build sequences, which are often written in terms of *Feynman diagrams* in the standard approach to QFT, to represent each contribution to the scattering amplitude. Even though closed sequences (loops) can appear, they arise in every scattering amplitude (even in the vacuum-vacuum amplitude) as a multiplicative factor, and thus they can be treated as overall normalization to the observables.

Therefore, we can restrict ourselves to studying the fully connected contributions only (i.e., those that cannot be separated into products of scattering amplitudes of simpler processes), and evaluate only the sequences in (B1) that start with $a_{t'}(\mathbf{k}')$ and end with $a_{t}^{\dagger}(\mathbf{k})$. Furthermore, using time-ordered quantities reveals that every sequence is equivalent, and they may all be summed together to obtain a compact result. Namely, if we define

$$\Delta_{kl}(\mathbf{k},s,t) \equiv \langle 0|a_{\lambda}(\mathbf{k})\frac{\partial u_{k}^{l}}{\partial x_{l}}((x_{0},y_{0},z_{0}+s),t)|0\rangle = \sqrt{\frac{\hbar}{\rho}}\varepsilon_{\lambda}(\mathbf{k})_{k}(-ik_{l})e^{-ik_{3}s}\frac{e^{i\omega_{\lambda}(\mathbf{k})t}}{\sqrt{2\omega_{\lambda}(\mathbf{k})}}e^{-i\mathbf{x}_{0}\cdot\mathbf{k}},\tag{B2}$$

$$\Delta_{klk'l'}(s-s',t-t') \equiv \Delta_{klk'l'}((x_0,y_0,z_0+s) - (x_0,y_0,z_0+s'),t-t'),$$
(B3)

then we may write

$$\langle f|i\rangle |_{\mathcal{O}(b^{2n})} = \left(-\frac{b^2}{\hbar^2}\right)^n \int_{-\infty}^{\infty} dt_1 \int_0^L ds_1 \dots \int_{-\infty}^{\infty} dt_{2n} \int_0^L ds_{2n} \Delta_{k_1 l_1}(\mathbf{k}^f, s_1, t_1) c_{12k_1 l_1} \Delta(s_1, s_2, t_1 - t_2) c_{12k_2 l_2} \\ \times \Delta_{k_2 l_2 k_3 l_3}(s_2 - s_3, t_2 - t_3) c_{12k_3 l_3} \dots c_{12k_{2n-2} l_{2n-2}} \Delta_{k_{2n-2} l_{2n-2} k_{2n-1} l_{2n-1}}(s_{2n-2} - s_{2n-1}, t_{2n-2} - t_{2n-1}) c_{12k_{2n-1} l_{2n-1}} \\ \times \Delta(s_{2n-1}, s_{2n}, t_{2n-1} - t_{2n}) c_{12k_{2n} l_{2n}} \Delta^*_{k_{2n} l_{2n}}(\mathbf{k}^i, s_{2n}, t_{2n}).$$
(B4)

Now we use the known formula

$$\frac{e^{-i\omega|t-t'|}}{2\omega} = \frac{1}{2\pi i} \int_{-\infty}^{\infty} d\omega' \frac{e^{-i\omega'(t-t')}}{-\omega'^2 + \omega^2 - i0^+},$$
(B5)

where 0^+ is the distributional positive infinitesimal that defines the prescription to be used when evaluating the integral, usually denoted by ϵ . With this expression we can perform explicitly the time integrals and get an overall energy conservation factor. It turns out that the integrals over the string coordinate *s* are also easy to do (this is because for each term in the string propagator, the *s* and *s'* contributions are separable within each sum): if we define

$$F(n,n') \equiv \frac{\mu^2 b^2 \mathbf{M}_{kl} \mathbf{M}_{k'l'}}{\rho} \int_0^L ds \int_0^L ds' \sin\left(\frac{n\pi s}{L}\right) \sin\left(\frac{n'\pi s'}{L}\right) \int \frac{d^3k}{(2\pi)^3} e^{i(\mathbf{k}\cdot\hat{e}_3)(s-s')} \\ \times k_l k_{l'} \left[\left(\delta_{kk'} - \frac{k_k k_{k'}}{k^2}\right) \frac{1}{\omega_T(\mathbf{k})^2 - \omega^2 - i0^+} + \frac{k_k k_{k'}}{k^2} \frac{1}{\omega_L(\mathbf{k})^2 - \omega^2 - i0^+} \right],$$
(B6)

then we find that

$$\mathcal{T}|_{\mathcal{O}(b^{2N})} = iE^{*}(\mathbf{k};\iota) \sum_{n_{1}=1}^{n_{D}} \frac{e^{-iL(\mathbf{k}\cdot\hat{e}_{3})+in_{1}\pi} - 1}{(\mathbf{k}\cdot\hat{e}_{3})^{2} - (n_{1}\pi/L)^{2}} \frac{2n_{1}\pi/L}{mL(\omega_{n_{1}}^{2} - \omega^{2})} \sum_{n_{2}=1}^{n_{D}} F(n_{1}, n_{2}) \frac{2}{mL(\omega_{n_{2}}^{2} - \omega^{2})} \\ \times \sum_{n_{3}=1}^{n_{D}} F(n_{2}, n_{3}) \frac{2}{mL(\omega_{n_{3}}^{2} - \omega^{2})} \dots \sum_{n_{N}=1}^{n_{D}} F(n_{N-1}, n_{N}) \frac{2n_{N}\pi/L}{mL(\omega_{n_{N}}^{2} - \omega^{2})} \frac{e^{iL(\mathbf{k}'\cdot\hat{e}_{3})-in_{N}\pi} - 1}{(\mathbf{k}'\cdot\hat{e}_{3})^{2} - (n_{N}\pi/L)^{2}} E(\mathbf{k}'; \iota').$$
(B7)

This can be written in a more succinct manner: if we define the following linear operator $T(\omega)$ through its matrix elements

$$[\mathbf{T}]_{n,n'}(\omega) \equiv \frac{2}{mL} \frac{F(n,n')}{\sqrt{\omega_n^2 - \omega^2} \sqrt{\omega_{n'}^2 - \omega^2}}$$
(B8)

and the n_D -dimensional vectors

$$[v(\mathbf{k})]_{n} \equiv \sqrt{\frac{2(n\pi/L)^{2}}{mL(\omega_{n}^{2} - \omega^{2})}} \frac{e^{iL(\mathbf{k}\cdot\hat{e}_{3}) - in\pi} - 1}{(\mathbf{k}\cdot\hat{e}_{3})^{2} - (n\pi/L)^{2}},$$
(B9)

then the scattering amplitude reads

$$\mathcal{T}|_{\mathcal{O}(b^{2N})} = iE^*(\mathbf{k};\iota)E(\mathbf{k}';\iota')\mathbf{v}^{\dagger}(\mathbf{k})\cdot\mathbf{T}^{N-1}(\omega)\cdot\mathbf{v}(\mathbf{k}'), \tag{B10}$$

and the resulting geometric series may be summed from N = 1 to ∞ to get

$$\mathcal{T} = \mathbf{v}^{\dagger}(\mathbf{k}) \cdot \frac{iE^{*}(\mathbf{k};\iota)E(\mathbf{k}';\iota')}{1 - \mathbf{T}(\omega)} \cdot \mathbf{v}(\mathbf{k}'), \tag{B11}$$

where $\frac{1}{1-\mathbf{T}(\omega)}$ denotes the inverse operator of $[1 - \mathbf{T}(\omega)]$.

APPENDIX C: KINEMATICAL FACTORS IN THE THREE-PHONON SCATTERING

Energy-momentum conservation dictates that in a scattering process of two massless particles, such as the phonons we have at hand, only a reduced number of processes are possible. Namely, given two incident phonons (with polarizations t_1 and t_2) and one outgoing phonon (with polarization t), it is necessary that $c_t > c_{t_1}$ or $c_t > c_{t_2}$ if noncollinear scattering is to happen.

Thus, we have three possible situations that will yield different kinematical restrictions between **k** and **k**₁, and factors $K(\mathbf{k}, \mathbf{k}_1; \{c_{t_i}\}) \equiv \left|\frac{\partial(\omega_i - \omega_{t_1} - \omega_{t_2})}{\partial |\mathbf{k}|}\right|^{-1}$ as a consequence of performing the integral over possible outgoing momenta against the energy-conservation Dirac delta $\delta[\omega_t(\mathbf{k}) - \omega_{t_1}(\mathbf{k}_1) - \omega_{t_2}(\mathbf{k} + \mathbf{k}_1)]$. For all of these situations, let $\cos \theta \equiv \frac{\mathbf{k}_1 \cdot \mathbf{k}}{|\mathbf{k}_1||\mathbf{k}|}$.

(1) $c_l = c_L$ and $c_{l_1} = c_{l_2} = c_T$. Here we have

$$|\mathbf{k}| = \frac{2c_T(c_L - c_T \cos \theta)}{c_L^2 - c_T^2} |\mathbf{k}_1|, \tag{C1}$$

and

$$K(\mathbf{k}, \mathbf{k}_{1}; \{c_{\iota_{i}}\}) = \left|c_{L} - c_{T}^{2} \frac{|\mathbf{k}| - |\mathbf{k}_{1}| \cos \theta}{c_{L} |\mathbf{k}| - c_{T} |\mathbf{k}_{1}|}\right|^{-1}.$$
(C2)

(2) $c_{\iota_1} = c_{\iota} = c_L$ and $c_{\iota_2} = c_T$. Here we have

$$|\mathbf{k}|^{2} - 2|\mathbf{k}||\mathbf{k}_{1}|\frac{c_{L}^{2} - c_{T}^{2}\cos\theta}{c_{L}^{2} - c_{T}^{2}} + |\mathbf{k}_{1}|^{2} = 0,$$
(C3)

and

$$K(\mathbf{k}, \mathbf{k}_{1}; \{c_{\iota_{l}}\}) = \left|c_{L} - c_{T}^{2} \frac{|\mathbf{k}| - |\mathbf{k}_{1}| \cos \theta}{c_{L}(|\mathbf{k}| - |\mathbf{k}_{1}|)}\right|^{-1}.$$
(C4)

(3) $c_{i_2} = c_i = c_L$ and $c_{i_1} = c_T$. Here we have

$$|\mathbf{k}| = \frac{c_L^2 - c_T^2}{2c_L(c_L\cos\theta - c_T)} |\mathbf{k}_1|,$$
(C5)

and

$$K(\mathbf{k}, \mathbf{k}_1; \{c_{\iota_i}\}) = \left| c_L - c_L^2 \frac{|\mathbf{k}| - |\mathbf{k}_1| \cos \theta}{c_L |\mathbf{k}| - c_T |\mathbf{k}_1|} \right|^{-1}.$$
(C6)

APPENDIX D: FORM FACTORS OF THE QUANTUM CORRECTIONS TO THE SCATTERING AMPLITUDE

In Sec. VI, we have defined and used three functions that characterize the form factors of the scattering amplitudes. The leading term includes the same factors as the quadratic theory:

$$f_n^{(0)}(k) \equiv n\pi \frac{e^{ikL}(-1)^n - 1}{(kL)^2 - (n\pi)^2},$$
(D1)

while the subleading terms (proportional to \hbar) also involve

$$f_{n,n'}^{(1)}(k) \equiv \frac{2i(n\pi)(n'\pi)(e^{ikL}(-1)^{n+n'}-1)}{(kL)^4 + (n\pi)^4 + (n'\pi)^4 - 2(kL)^2(n\pi)^2 - 2(kL)^2(n'\pi)^2 - 2(n\pi)^2(n'\pi)^2}$$
(D2)

$$f_{n,n'}^{(2)}(k) \equiv \frac{n\pi (e^{ikL}(-1)^n - 1)}{4} \left[\frac{1}{(kL + 2\pi n')^2 - (n\pi)^2} + \frac{2}{(kL)^2 - (n\pi)^2} + \frac{1}{(kL - 2\pi n')^2 - (n\pi)^2} \right].$$
 (D3)

By inspecting these functions, it is fairly straightforward to verify that they have peaks at $kL \sim (n + n')\pi$ and at $kL \sim n\pi$ respectively. $f_{n,n'}^{(2)}(k)$ also has peaks at $kL \sim \pi(n \pm 2n')$, but they can be shown to be of smaller amplitude by evaluating the function at those points. Moreover, their peak values are of order $\mathcal{O}(1)$:

$$f_n^{(0)}(n\pi/L) = i/2,$$
 (D4)

$$f_{n,n'}^{(1)}((n+n')\pi/L) = -1/4,$$
(D5)

$$f_{n,n'}^{(2)}(n\pi/L) = i/4.$$
 (D6)

Let us stress that these functions peak *close* to those points in amplitude (which is why we have used the similar " \sim " symbol), and increasingly so as *n*, *n'* take greater values.

Nonetheless, even though these are approximate features, the $\ln(n_D)$ scaling of the correction proportional to \hbar will always be present as there is a term in $f_{n,n'}^{(2)}(k)$ that is exactly independent of n', and has greater amplitude relative to the other terms.

- P. G. Klemens, The scattering of low-frequency lattice waves by static imperfections, Proc. Phys. Soc. London, Sect. A 68, 1113 (1955).
- [2] P. Carruthers, Scattering of phonons by elastic strain fields and the thermal resistance of dislocations, Phys. Rev. 114, 995 (1959).
- [3] A. Chernatynskiy and S. R. Phillpot, Phonon-mediated thermal transport: Confronting theory and microscopic simulation with experiment, Curr. Opin. Solid State Mater. Sci. 17, 1 (2013).
- [4] D. G. Cahill, P. V. Braun, G. Chen, D. R. Clarke, S. Fan, K. E. Goodson, P. Keblinski, W. P. King, G. D. Mahan, A. Majumdar, H. J. Maris, S. R. Phillpot, E. Pop, and L. Shi, Nanoscale thermal transport. II. 2003-2012, Appl. Phys. Rev. 1, 011305 (2014).
- [5] T. Feng and X. Ruan, Prediction of spectral phonon mean free path and thermal conductivity with applications to thermoelectrics and thermal management: A review, J. Nanomater. 2014, 206370 (2014).
- [6] S. I. Kim, K. H. Lee, H. A. Mun, H. S. Kim, S. W. Hwang, J. W. Roh, D. J. Yang, W. H. Shin, X. S. Li, Y. H. Lee, G. J. Snyder, and S. W. Kim, Dense dislocation arrays embedded in grain boundaries for high-performance bulk thermoelectrics, Science 348, 109 (2015).
- [7] H.-S. Kim, S. I. Kim, K. H. Lee, S. W. Kim, and G. J. Snyder, Phonon scattering by dislocations at grain boundaries in polycrystalline Bi_{0.5}Sb_{1.5}Te₃, Phys. Status Solidi B 254, 1600103 (2017).
- [8] J. Xie, Y. Ohishi, S. Ichikawa, H. Muta, K. Kurosaki, and S. Yamanaka, Naturally decorated dislocations capable of enhancing multiple-phonon scattering in Si-based thermoelectric composites, J. Appl. Phys. **123**, 115114 (2018).
- [9] Z. Chen, B. Ge, W. Li, S. Lin, J. Shen, Y. Chang, R. Hanus, G. J. Snyder, and Y. Pei, Vacancy-induced dislocations within grains for high-performance PbSe thermoelectrics, Nat. Commun. 8, 13828 (2017).
- [10] C. Zhou, Y. K. Lee, J. Cha, B. Yoo, S.-P. Cho, T. Hyeon, and I. Chung, Defect engineering for high-performance n-type PbSe thermoelectrics, J. Am. Chem. Soc. 140, 9282 (2018).
- [11] T. Wang, J. Carrete, N. Mingo, and G. K. H. Madsen, Phonon scattering by dislocations in GaN, ACS Appl. Mater. Interfaces 11, 8175 (2019).
- [12] B. Sun, G. Haunschild, C. Polanco, J. Ju, L. Lindsay, G. Koblmüller, and Y. Kan Koh, Dislocation-induced thermal transport anisotropy in single-crystal group-III nitride films, Nat. Mater. 18, 136 (2019).
- [13] T. Ninomiya, Dislocation vibration and phonon scattering, J. Phys. Soc. Jpn. 25, 830 (1968).
- [14] T. Ninomiya, Eigenfrequencies in a dislocated crystal, in Journal Of Research Of The National Bureau Of Standards Section A-Physics And Chemistry (US Government Printing Office Superintendent Documents, Washington, DC 20402, 1969), Vol. 5, p. 544.

- [15] M. Li, W. Cui, M. S. Dresselhaus, and G. Chen, Electron energy can oscillate near a crystal dislocation, New J. Phys. **19**, 013033 (2017).
- [16] M. Li, Z. Ding, Q. Meng, J. Zhou, Y. Zhu, H. Liu, M. S. Dresselhaus, and G. Chen, Nonperturbative quantum nature of the dislocation-phonon interaction, Nano Lett. 17, 1587 (2017).
- [17] M. Li, Y. Tsurimaki, Q. Meng, N. Andrejevic, Y. Zhu, G. D. Mahan, and G. Chen, Theory of electron-phonon-dislon interacting system-toward a quantized theory of dislocations, New J. Phys. 20, 023010 (2018).
- [18] A. Granato and K. Lücke, Theory of mechanical damping due to dislocations, J. Appl. Phys. 27, 583 (1956).
- [19] A. Granato and K. Lücke, Application of dislocation theory to internal friction phenomena at high frequencies, J. Appl. Phys. 27, 789 (1956).
- [20] A. Maurel, V. Pagneux, F. Barra, and F. Lund, Interaction between an elastic wave and a single pinned dislocation, Phys. Rev. B 72, 174110 (2005).
- [21] N. Rodríguez, A. Maurel, V. Pagneux, F. Barra, and F. Lund, Interaction between elastic waves and prismatic dislocation loops, J. Appl. Phys. **106**, 054910 (2009).
- [22] A. Maurel, V. Pagneux, F. Barra, and F. Lund, Wave propagation through a random array of pinned dislocations: Velocity change and attenuation in a generalized Granato and Lücke theory, Phys. Rev. B 72, 174111 (2005).
- [23] D. Churochkin, F. Barra, F. Lund, A. Maurel, and V. Pagneux, Multiple scattering of elastic waves by pinned dislocation segments in a continuum, Wave Motion 60, 220 (2016).
- [24] N. Mujica, M. T. Cerda, R. Espinoza, J. Lisoni, and F. Lund, Ultrasound as a probe of dislocation density in aluminum, Acta Mater. 60, 5828 (2012).
- [25] V. Salinas, C. Aguilar, R. Espinoza-González, F. Lund, and N. Mujica, In situ monitoring of dislocation proliferation during plastic deformation using ultrasound, Int. J. Plast. 97, 178 (2017).
- [26] C. Espinoza, D. Feliú, C. Aguilar, R. Espinoza-González, F. Lund, V. Salinas, and N. Mujica, Linear versus nonlinear acoustic probing of plasticity in metals: A quantitative assessment, Materials 11, 2217 (2018).
- [27] T. Wang, J. Carrete, A. van Roekeghem, N. Mingo, and G. K. H. Madsen, *Ab initio* phonon scattering by dislocations, *Phys.* Rev. B **95**, 245304 (2017).
- [28] M. Peach and J. S. Koehler, The forces exerted on dislocations and the stress fields produced by them, Phys. Rev. 80, 436 (1950).
- [29] F. Lund, Response of a stringlike dislocation loop to an external stress, J. Mater. Res. 3, 280 (1988).
- [30] M. Srednicki, *Quantum Field Theory* (Cambridge University Press, Cambridge, UK, 2007).
- [31] M. C. W. van Rossum and T. M. Nieuwenhuizen, Multiple scattering of classical waves: Microscopy, mesoscopy, and diffusion, Rev. Mod. Phys. 71, 313 (1999).
- [32] J. D. Jackson, *Classical Electrodynamics* (Wiley, New York, 1998).

- [33] L. D. Landau and E. M. Lifshitz, *Theory of Elasticity*, 2nd ed. (Pergamon, New York, 1989).
- [34] B. Scheihing Hitschfeld, Probability density functionals in perturbation theory within the QFT in-in formalism, arXiv:1901.09734 [hep-th].
- [35] K. Ohashi, Scattering of lattice waves by dislocations, J. Phys. Soc. Jpn. 24, 437 (1968).
- [36] C. Tan, X. Cao, X.-J. Wu, Q. He, J. Yang, X. Zhang, J. Chen, W. Zhao, S. Han, G.-H. Nam, M. Sindoro, and H. Zhang, Recent advances in ultrathin two-dimensional nanomaterials, Chem. Rev. 117, 6225 (2017).
- [37] X. Gu, Y. Wei, X. Yin, B. Li, and R. Yang, Colloquium: Phononic thermal properties of two-dimensional materials, Rev. Mod. Phys. 90, 041002 (2018).