Giant Electrocaloric Effect Around T_c

Maimon C. Rose^{*} and R. E. Cohen[†]

Geophysical Laboratory, Carnegie Institution of Washington, 5251 Broad Branch Road, NW, Washington, DC 20015, USA (Received 6 July 2012; published 2 November 2012; corrected 6 November 2012)

We use molecular dynamics with a first-principles-based shell model potential to study the electrocaloric effect (ECE) in lithium niobate, LiNbO₃, and find a giant electrocaloric effect along a line passing through the ferroelectric transition. With an applied electric field, a line of maximum ECE passes through the zero field ferroelectric transition, continuing along a Widom line at high temperatures with increasing fields, and along the instability that leads to homogeneous ferroelectric switching below T_c with an applied field antiparallel to the spontaneous polarization. This line is defined as the minimum in the inverse capacitance under an applied electric field. We investigate the effects of pressure, temperature and an applied electric field on the ECE. The behavior we observe in LiNbO₃ should generally apply to ferroelectrics; we therefore suggest that the operating temperature for refrigeration and energy scavenging applications should be above the ferroelectric transition region to obtain a large electrocaloric response. The relationship between T_c , the Widom line, and homogeneous switching should be universal among ferroelectrics, relaxors, multiferroics, and the same behavior should be found under applied magnetic fields in ferromagnets.

DOI: 10.1103/PhysRevLett.109.187604

PACS numbers: 77.70.+a, 34.20.Cf, 71.15.Pd, 77.80.-e

The electrocaloric effect (ECE), the reversible temperature change of a polarizable material under the application and/or removal of an electric field, has the potential for efficient solid-state refrigeration [1], but fundamental questions about the nature of the ECE have plagued the field for at least 50 years [2,3]. We show how the ECE can be large well above T_c , in spite of the apparent thermodynamic argument that it vanishes above T_c . The ECE is the change in entropy with electric field, and thus can be used to pump heat or scavenge energy. Experiments show temperature changes of up to 12 K on application of reasonable electric fields of 480 kV/cm in PZT [4,5]. Simulations with an effective Hamiltonian of the ECE show good agreement with experiments, [6,7]. We study the behavior of LiNbO₃ as a simple, uniaxial ferroelectric [8,9] for which we have a well-tested first-principles based interatomic potential [10-13], with which we previously studied the converse effect, pyroelectricity, under zero applied field [13]. Recently the ECE in $Ba_{0.5}Sr_{0.5}TiO_3$ was simulated using an effective Hamiltonian at constant volume [14]. Here we use an interatomic potential which includes all degrees of freedom to perform simulations at constant pressure and temperature, and develop a different picture of the ECE from Ref. [14]. We carefully study the ECE around T_c , and find that ferroelectric switching below T_c is closely related to the polarization response above T_c under applied fields.

We performed molecular dynamics (MD) simulations on supercells of $8 \times 8 \times 8$ unit cells, with a total of 5210 atoms using the DLPOLY package [15] with a Nosé-Hoover thermostat and barostat in the *N* σ *T* ensemble. The shell model potential was fit to first-principles density functional theory (LDA) energies, forces, stress, effective charges, dielectric constants, phonons frequencies and eigenvectors and has proven predictive and robust. At lower temperatures, long runs were needed to reach equilibrium; e.g., at 800 K, 22.5 ns was required to equilibrate the shell and atomic positions. Once equilibrium was reached, the stable configuration was used as a starting point for runs at similar temperatures. For all simulations with the electric field applied in the direction opposite to the polarization, the simulations were either 44 or 110 ps long with a time step of 0.2 and 0.5 fs, respectively. At 4 or 10 ps intervals the electric field was increased by 5 MV/m. For simulations with the field applied parallel to the spontaneous polarization, we ran a simulation at a fixed applied field and temperature for 100-200 ps with a time step of 0.5 fs. All averages were taken after the equilibration period, which was typically 25–50 ps. Simulations with applied pressure ran for 100 ps with a time step of 0.5 fs. We employ the convention defining fields applied in the same direction as the spontaneous polarization as *positive* or *parallel* and the fields applied in the direction opposite that of the spontaneous polarization as *negative* or *antiparallel*. The results of polarization versus temperature and applied field are shown in Fig. 1. We find the zero-field ferroelectric to paraelectric transition to be 1506 K, which slightly overestimates the literature value of 1480 K [8].

To investigate the electrocaloric effect we used the Maxwell relation

$$\left(\frac{\partial S}{\partial E}\right)_T = \left(\frac{\partial P}{\partial T}\right)_E \tag{1}$$

or



FIG. 1 (color online). (a) Average polarization of LiNbO₃ with applied field along the same direction as the spontaneous polarization and (b) derivative of polarization with respect to temperature. The Widom line T^* above T_c is traced out by the inflections in *P* or minima in dP/dT.

$$\left(\frac{\partial T}{\partial E}\right)_{S} = \frac{TV}{C_{p,E}} \left(\frac{\partial P}{\partial T}\right)_{E},\tag{2}$$

where P is the macroscopic polarization, E is the macroscopic electric field, C is the heat capacity, V is the volume, T is the absolute temperature, and p is the pressure, which when integrated gives

$$\Delta T = -\int_{0}^{E} \frac{TV}{C_{p,E}} \left(\frac{\partial P}{\partial T}\right)_{E} dE.$$
 (3)

To calculate the change in the temperature, equation (2) can be solved numerically using MATHEMATICA. For our case, approximating the solution using Eq. (3) by fixing T on the right-hand side gives an error of less than 1% in ΔT , which is less than errors from the model potential, LDA, etc. The maximum ΔT is found at progressively higher temperatures as the strength of the field is increased



FIG. 2 (color online). Calculated change in temperature as a function of temperature for various applied electric fields.

(Fig. 2). We also performed constant energy NVE simulations with applied fields, and found agreement within error to the results in Fig. 2, obtained from Eq. (3), considering the differences between constant V and constant p simulations.

For small negative or antiparallel fields below the ferroelectric transition we expect to find the same values of the ECE as for small positive fields since $\left(\frac{\partial P}{\partial T}\right)|_E$ is continuous around E = 0. When we apply a negative field larger than the coercive field E_c at a given temperature $T_{\rm hs}$, the polarization switches homogeneously, and the direction of the polarization of the crystal becomes parallel with the direction of the applied field (see Ref. [16], p. 79, for a discussion of this instability). We call this temperature for a given electric field the homogenous switching temperature, $T_{\rm hs}$. Normally switching occurs through growth of preexisting domains with a more preferred polarization direction, or nucleation and growth of new domains. Homogeneous switching, with no preexisting domains, is the limit of metastability of the energetically unfavored polarization direction in an applied field. We recently studied homogeneous switching in detail in PbTiO₃ [17]. This switching occurs, depending on the strength of the applied negative field, on the time scale of our simulations between 4 and 10 ps.

We performed constant energy (*NVE*) simulations to study the temperature change during polarization switching. As expected, the temperature goes up sharply with switching: since the potential energy drops, the kinetic energy, and thus *T*, increases. By varying the applied field frequency, however, it should be possible to get the polarization switching to go 180° out of phase and make a refrigeration cycle based on polarization switching. Such behavior may be an explanation of the dependence of ECE on applied field frequency seen in experiments [1].

We find a line of maximum ECE as a function of temperature and applied field (Fig. 3). In order to understand the line of maximum ECE, we consider the thermodynamics of ferroelectrics in an applied electric field. At zero field the ferroelectric transition, T_1 , is first order, and with applied field, T_1 increases as $\frac{dT_1}{dE} = -\frac{\Delta P}{\Delta S}$ [18]. With increasing applied field, a tricritical point, $T_{\rm tri}$, is reached where the transition becomes second-order, T_s . In BaTiO₃ this first-order region between T_1 and T_{tri} is 18 K [3]. With a further increase in field a critical point T_c is reached, and there is no phase transition above that temperature and applied field, E_{crit} . We were not able to resolve the region between T_1 and T_c in our MD simulations at zero pressure. Although there is no phase transition above T_c for higher fields, there is still an inflection point in P versus T and a line is traced out with increasing E that can be considered the Widom line for this problem [19-22]. We label the Widom line T^* . At temperatures below T_1 , negative fields greater in magnitude than the coercive field switch the polarization, tracing the line of homogeneous



FIG. 3 (color online). Effects of pressure and electric field on the transitions in LiNbO₃. T_1 , T_c , T^* along the Widom line, and $T_{\rm hs}$, the homogeneous switching temperature fall along a smooth curve. The right hand figure shows the line of minimum inverse capacitance, and the inset shows the relationship between the various temperatures along these minima schematically, as discussed in the text. We could not constrain the location of $T_{\rm tri}$ and T_c in our simulations at zero pressure due to the small temperature region between them and T_1 . $T_{\rm hs}$ is presented by the dashed red segment, the first-order transition region between T_1 and $T_{\rm tri}$ is the solid black segment, T_s is the dashed blue segment between $T_{\rm tri}$ and T_c , and T^* is the dotted violet high T segment.

switching, $T_{\rm hs}$. This instability is found clearly in firstprinciples computations at constant electric field and zero temperature in PbTiO₃ [see Fig. 6(c) in Ref. [23]]. The importance of the inverse capacitance $C^{-1} \propto \epsilon^{-1}$, which is the second derivative of the internal energy with electric displacement field D, where ϵ is the dielectric constant is discussed in Ref. [24]. We propose a line of minima in the inverse capacitance C^{-1} that joins $T_{\rm hs}$, T_1 , $T_{\rm tri}$, T_c , and T^* . Below T_c , $C^{-1} = 0$ along this line, whereas it is a minimum above T_c defining T^* . These temperatures are sketched in the inset to Fig. 3.

As J.F. Scott discusses, there has been an argument spanning many decades over whether the ECE is expected above or below T_1 [3]. The confusion stems from misconstruing the Maxwell relation [Eq. (1)]. Above T_1 , P = 0 at zero field, implying zero ECE, but at fields $P \neq 0$ so that there is an ECE in any material, not just a ferroelectric. Furthermore there is no requirement of an underlying ferroelectric phase transition. The fact that the dielectric constant $\epsilon \propto C$ is high above T_1 in a ferroelectric, however, makes the application of ferroelectrics above T_1 optimal, rather than far below T_1 as seems to be standard practice now. The susceptibility is maximal along the Widom line, so that is where we expect to see the greatest ECE, as we find. The maximum in ΔT occurs along the line defined by min C^{-1} , and our results clarify the issue of ECE above T_1 . The order parameter Q for polarization correlations $Q = \lim_{r \to \infty} \langle P(r)P(0) \rangle|_{E}$, and the maxima in the ECE should be where $\frac{d^2Q}{dEdT}$ is maximal.

Ponomareva and Lisenkov state that " ΔT peaks near the transition temperatures which is the consequence of the larger configurational disorder associated with these points" [14]. To the contrary, we find that ΔT continues to increase as the electric field increases, well above the zero field T_1 . So we find that operation above T_1 would be advantageous in ECE applications. The issue of disorder will be discussed further below.

We have also simulated LiNbO₃ as a function of applied pressure (Figs. 3 and 4). As pressure increases, T_1 strongly decreases, so that it is 750 K at 40 GPa. As pressure increases and T_1 decreases, we find consistency with the picture above, with the ECE maximal along the Widom line. Unexpectedly, we found that pressure increases the phase transition region between T_1 and T_{tri} under applied field, so that it is more easily discernible (Fig. 4). We also find a structural phase transition between 60 and 70 GPa, consistent with the transition seen experimentally at about 40 GPa [25,26].

Our results agree well with recent experiments: Bai *et al.* found that in BaTiO₃ films the maximum ECE occurs above T_c and increases with applied field [27,28]. Relaxors and relaxor ferroelectrics are expected to show similar behavior to what we see in LiNbO₃ (e.g., Fig. 3 in Ref. [22]).

One might find it surprising at first that an apparently kinetic phenomenon, ferroelectric switching, is related to the thermodynamics at T_1 , and moreover, to the behavior high above the zero field T_c where there is no phase transition at all. We can understand this behavior from an atomistic perspective by considering a simple classical double well representing the underlying potential surface (Fig. 5). The key is that the same double well potential surface underlies ferroelectric switching, T_1 , and the maximum in $\epsilon \propto C$: In zero applied field, T_1 is given by coupled



FIG. 4 (color online). Effect of pressure and electric field on polarization in $LiNbO_3$. Note the strong decrease in the transition temperatures with pressure, and the increase in the phase transition region which appears to be first order up to at least 25 MV/m and about 100 K at 20 GPa. At zero pressure the phase transition disappears at relatively small fields.



FIG. 5 (color online). The connection between the transition temperatures and switching below T_1 with an antiparallel applied field is shown in a simple schematic. These do not show the Landau free energy, but rather the potential energy versus local polarization. In all cases an activation barrier exists for changing the local polarization.

local double well potentials. In the displacive limit T_1 is the temperature where there is enough kinetic energy to traverse the hump in the underlying effective double wells. In an applied field the underlying potentials are asymmetric, and it takes a higher T to go over the hump. There is no phase transition above the critical field, but the underlying potential surface is still asymmetric due to the field, and the susceptibility, which diverges at a true phase transition, instead peaks at the temperature where local modes start to hop over the hump. This is the Widom line. Below T_1 the effective potentials are asymmetric due to the coupling between local modes; the coupling can be thought of as a local Weiss field from the rest of the crystal. When a field greater than the coercive field is applied, the polarization switches. In terms of the double well picture in Fig. 5, the field makes a population inversion, where the high energy state is occupied. At low temperatures or below the coercive field for a given temperature the atoms will be stuck in the high energy state; as temperature is raised there will be a point at which the local modes all cross the hump and go into the lower energy state. So we see the origin of the connection between switching, T_1 , and the Widom line. In the order-disorder limit, with a huge hump that cannot be broached, the dynamics are governed by nucleation and growth, but we still expect to see a relationship between switching, T_1 , and the Widom line since the field dependence is still governed by the $E \cdot P$ term in the free energy.

This behavior for applied fields carries over as well to magnetism, and surprisingly does not seem to have been remarked upon in the literature. In experiments for magnetization of pure iron under applied magnetic fields, the Widom line is clearly seen about T_c , and the Widom line comes in with a finite slope at T_c [29]. This suggests that

magnetic switching should also follow this line below T_c , otherwise the Widom line would come in with zero slope. So homogeneous switching, T_c , and the Widom line in ferromagnets is related in the same way to applied magnetic fields, as ferroelectrics behave in applied electric fields.

Some have attributed the ECE to polarization disordering giving a resulting change in entropy [14], but this simple view can be misleading. For example, an isolated supercooled liquid will crystallize with a concomitant increase in entropy, as required by the second law of thermodynamics, even though a crystal is more ordered than a liquid. Pressure decreases T_c , and thus increases the ECE, not because it directly causes greater disorder (an entropic effect), but simply because the paraelectric phase is denser than the ferroelectric phase, and thus favored by pressure. The Maxwell relation, Eq. (1), says everything necessary about the relationship of the ECE to the pyroelectric effect. Furthermore, this is an exact expression, and thus the "direct" and "indirect" approaches to the ECE must agree within the error of experiments or simulations, in contrast to Ref. [14]. It is also important to realize that the entropy change for the ferroelectric to paraelectric firstorder phase transition, ΔS_{tr} , is not the pertinent quantity for the ECE, but rather $(\partial S/\partial E)|_T$. Large ΔS_{tr} can give rise to a large ECE near T_1 , but only in the first-order transition region. We find larger ECE at higher fields and temperatures beyond $T_{\rm tri}$.

Our MD simulations with first-principles potentials on LiNbO₃ give some universal conclusions about the electrocaloric effect. We expect the ECE to be maximal above T_1 , suggesting materials with T_1 below room temperature (or the operating temperature) would be optimal. We find a relationship between T_1 , the Widom line, and homogeneous switching, and suggest this may be universal among ferroelectrics, relaxors, multiferroics, and ferromagnets. The ECE should be large in any insulator with a large, temperature dependent, dielectric susceptibility, not just ferroelectrics. We have shown the importance of the Widom line and the nature of the ECE above T_1 , the relationship between homogeneous switching and behavior above T_1 in an applied electric field, the continuity of the Widom line with the switching behavior below T_1 , the realization that ECE does not require a ferroelectric, the relationship of switching and the Widom line in ferromagnets as well as ferroelectrics, clarification of conditions to maximize the ECE in materials, the behavior of the ECE under pressure, and, finally, the application of an accurate first-principles based shell-model to behavior in an applied electric field.

This work was supported as part of the EFree, an Energy Frontier Research Center funded by the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences under Award No. DE-SC0001057, and the Carnegie Institution of Washington. We thank P. Ganesh, I. Naumov, J. F. Scott, Q. Peng, and M. Ahart for useful discussions. *mrose@gl.ciw.edu

cohen@gl.ciw.edu

- [1] Y. Bai, G.-P. Zheng, and S.-Q. Shi, J. Appl. Phys. **108**, 104102 (2010).
- [2] F. Jona and G. Shirane, *Ferroelectric Crystals* (Dover, New York, 1962), p. 402.
- [3] J. F. Scott, Annu. Rev. Mater. Sci. 41, 229 (2011).
- [4] A. S. Mischenko, Q. Zhang, J. F. Scott, R. W. Whatmore, and N. D. Mathur, Science 311, 1270 (2006).
- [5] A. S. Mischenko, Q. Zhang, R. W. Whatmore, J. F. Scott, and N. D. Mathur, Appl. Phys. Lett. 89, 242912 (2006).
- [6] S. Prosandeev, I. Ponomareva, and L. Bellaiche, Phys. Rev. B 78, 052103 (2008).
- [7] S. Lisenkov and I. Ponomareva, Phys. Rev. B 80, 140102 (2009).
- [8] A. M. Glass and M. E. Lines, Phys. Rev. B 13, 180 (1976).
- [9] M. E. Lines and A. M. Glass, Phys. Rev. Lett. 39, 1362 (1977).
- [10] M. Sepliarsky and R. E. Cohen, in *Fundamental Physics of Ferroelectrics 2002*, edited by R. Cohen, AIP Conf. Proc. Vol. 626 (AIP, Melville, NY, 2002), p. 36, http://scitation.aip.org/proceedings/confproceed/626.jsp.
- [11] M. Sepliarsky, Z. Wu, A. Asthagiri, and R.E. Cohen, Ferroelectrics 301, 55 (2004).
- [12] M. Sepliarsky and R. E. Cohen, J. Phys. Condens. Matter 23, 435902 (2011).
- [13] Q. Peng and R. E. Cohen, Phys. Rev. B 83, 220103 (2011).
- [14] I. Ponomareva and S. Lisenkov, Phys. Rev. Lett. 108, 167604 (2012).
- [15] W. Smith, C. W. Yong, and P. M. Rodger, Mol. Simul. 28, 385 (2002).

- [16] L. Landau, E. Lifshitz, and L. Pitaevskii, *Electrodynamics of Continuous Media* (Pergamon Press, Oxford, 1984), 2nd ed., p. 460.
- [17] X. Zeng and R.E. Cohen, Appl. Phys. Lett. 99, 142902 (2011).
- [18] G. Akcay, S.P. Alpay, J.V. Mantese, and G.A. Rossetti, Appl. Phys. Lett. **90**, 252909 (2007).
- [19] L. Xu, P. Kumar, S. V. Buldyrev, S.-H. Chen, P. H. Poole, F. Sciortino, and H. E. Stanley, Proc. Natl. Acad. Sci. U.S.A. **102**, 16558 (2005).
- [20] G. Simeoni, T. Bryk, F. Gorelli, M. Krisch, G. Ruocco, M. Santoro, and T. Scopigno, Nat. Phys. 6, 503 (2010).
- [21] Z. Kutnjak, J. Petzelt, and R. Blinc, Nature (London) **441**, 956 (2006).
- [22] Z. Kutnjak, R. Blinc, and Y. Ishibashi, Phys. Rev. B 76, 104102 (2007).
- [23] J. Hong and D. Vanderbilt, Phys. Rev. B 84, 115107 (2011).
- [24] M. Stengel, N. A. Spaldin, and D. Vanderbilt, Nat. Phys. 5, 304 (2009).
- [25] A. Jayaraman and A. A. Ballman, J. Appl. Phys. 60, 1208 (1986).
- [26] A. Suchocki, W. Paszkowicz, A. Kaminska, A. Durygin, S. K. Saxena, L. Arizmendi, and V. Bermudez, Appl. Phys. Lett. 89, 261908 (2006).
- [27] Y. Bai, G.-P. Zheng, K. Ding, L. Qiao, S.-Q. Shi, and D. Guo, J. Appl. Phys. **110**, 094103 (2011).
- [28] Y. Bai, K. Ding, G.-P. Zheng, S.-Q. Shi, and L. Qiao, Phys. Status Solidi A 209, 941 (2012).
- [29] X.J. Liu, Y.M. Fang, C.P. Wang, Y.Q. Ma, and D.L. Peng, J. Alloys Compd. 459, 169 (2008).