

and

$$H_{cz}(t) \propto [1 - t^2][1 + 0.391(1 - t)], \quad t \lesssim 1. \quad (9)$$

This equation also does not predict a positive curvature.

Eilenberger¹⁰ has calculated $\kappa_1(t)$, starting from Gorkov's equations, for a series of ratios of coherence length to mean free path, valid for all temperatures and including anisotropic impurity scattering. These results show that the temperature dependence of $\kappa_1(t)$ [and thus $H_{cz}(t)$, via Eq. (7)] is strongly dependent on scattering anisotropy at all temperatures. (This includes higher temperatures where positive curvature is found, and where no other anomalous critical-field effects due to anisotropies have previously been found.) Strong anisotropy of both the electron-phonon interaction and the Fermi surface are probable in layer compounds, and it is likely that the origins of positive curvature are in these anisotropies.

*Jet Propulsion Laboratory part of this research

sponsored by the National Aeronautics and Space Administration under contract No. NAS7-100.

†Winter term student at the National Aeronautics and Space Administration Lewis Research Center during January 1974.

¹J. A. Woollam, D. J. Flood, D. E. Wagoner, R. B. Somoano, and A. Rembaum, NASA Report No. TMX-68206, 1973 (unpublished).

²J. A. Woollam, D. J. Flood, D. E. Wagoner, R. Somoano, and A. Rembaum, *Bull. Amer. Phys. Soc.* **18**, 385 (1973).

³F. R. Gamble, F. J. DiSalvo, R. A. Klemm, and T. H. Geballe, *Science* **168**, 568 (1970).

⁴Y. Muto, N. Yoyota, K. Noto, and A. Hoshi, *Phys. Lett.* **45A**, 99 (1973). These authors noticed positive curvature in their data but did not discuss the result.

⁵R. C. Morris and R. V. Coleman, *Phys. Rev. B* **7**, 991 (1973).

⁶R. B. Somoano and A. Rembaum, *Phys. Rev. Lett.* **27**, 402 (1971).

⁷R. B. Somoano, V. Hadek, and A. Rembaum, *J. Chem. Phys.* **58**, 697 (1973).

⁸E. A. Lynton, *Superconductivity* (Methuen and Company, Ltd., London, 1962), or other standard text on superconductivity.

⁹K. Maki, *Physics* (Long Is. City, N.Y.) **1**, 21 (1964).

¹⁰G. Eilenberger, *Phys. Rev.* **153**, 584 (1967).

Conductivity of One-Dimensional Interacting Fermions*

Daniel C. Mattis

Belfer Graduate School of Science, Yeshiva University, New York, New York 10033

(Received 6 February 1974)

Using an exactly soluble model, the decay rate of a current-carrying state of one-dimensional fermions is calculated in the presence of random scatterers at finite temperature and the dc conductivity thereby inferred. For interacting fermions it is modified by a factor $(T/T + \theta)^g$, where g is a positive (negative) coupling constant for repulsive (attractive) two-body forces. While the conductivity could be greatly enhanced for $g < 0$ and $T \ll \theta$, one-dimensional superconductivity appears ruled out at any finite temperature.

The conductivity $\sigma(T)$ of a gas of interacting one-dimensional (1D) fermions at finite temperature has been obtained in the presence of random scatterers. The main results can be summarized in the formula

$$\sigma(T) = [T/(T + \theta)]^g \sigma_0 \quad (1)$$

in which σ_0 is the dc conductivity of a noninteracting Fermi gas ($g=0$), a quantity which is inversely proportional to the density of scattering centers and to the scattering strength of each, and which is finite at $T=0$ and slowly varying with temperature. The exponent g characterizes the strength of the two-body interactions, and is pos-

itive for repulsive forces and negative for attractive forces. θ is a constant related to the range of the forces, expressed in degrees kelvin.

Equation (1), which is asymptotically exact in the weak-coupling limit $|g| \ll 1$, indicates that even for weakly repulsive two-body forces the electrical conductivity vanishes at $T=0$, and that, conversely, for even weakly attractive two-body forces the conductivity increases without limit as $T \rightarrow 0$. These results agree at $T=0$ with my earlier analysis of the ground-state conductivity¹ and are also compatible with an independent study of Green functions and correlation functions at finite temperature² in which impurities were not

explicitly considered. Interest in the topic has recently intensified as a result of interesting experimental studies of pseudo-1D structures, such as tetrathiofulvalinium tetracyanoquinodimethane (TTF-TCNQ), by Heeger and co-workers,³ generating some controversy,⁴ but also rekindling the hope of discovering high-temperature superconductivity, perhaps in 1D manifolds. The formula Eq. (1) precludes 1D superconductivity on purely theoretical grounds but allows for substantial enhancement of the conductivity over that for noninteracting particles, as seems to be the case experimentally.³

The basis of the present work is an extension of Fermi's "Golden Rule" to finite temperature,

$$H = \hbar v_0 \sum k(n_{1k} - n_{2k}) + (\lambda/L) \sum U(p) [|\rho_1(p) + \rho_2(p)|]^2 \quad (5)$$

and the current operator is

$$j_{op} = v_0 \sum (n_{1k} - n_{2k}). \quad (6)$$

The fermion Hamiltonian (5) was originally proposed by Luttinger,⁵ solved by Lieb and the present author,⁶ and is discussed in our book on one-dimension,⁷ to which the reader is referred for background information and algebraic details. In addition, a very useful representation of the wave operators $\psi(x)$ as exponentials of the density-fluctuation operators $\rho(p)$ was recently discovered, simultaneously and independently, by Luther and Peschel² and by the present author.¹ This representation permits the explicit and exact evaluation of operators such as (4) and thermal averages such as (2), which could not otherwise be performed for interacting particles.

I briefly summarize the steps leading to Eq. (1), and conclude this work by comparing it to calculations⁸ in which the BCS theory⁹ is applied to the study of the possible superconductivity of

viz.,

$$dj/dt = (2v_0/\hbar^2) \int_{-\infty}^{+\infty} dt \langle [H^+(0), H^-(t)] \rangle. \quad (2)$$

In this formula, the angular brackets signify thermal and configurational averages. H^\pm represent the forward/backward scattering matrix elements, chosen to be

$$H^+ = \int dx W^*(x) \psi_1^\dagger(x) \psi_2(x) \equiv \int dx W^*(x) H^+(x), \quad (3)$$

$$H^- = \int dx W(x) \psi_2^\dagger(x) \psi_1(x) \equiv \int dx W(x) H^-(x),$$

with $W(x)$ a random traceless scattering potential. The time dependence of operators is given by

$$H^\pm(x, t) = e^{iHt/\hbar} H^\pm(x) e^{-iHt/\hbar}, \quad (4)$$

where the fermion Hamiltonian is given as

1D electrons.

First, it is most convenient to evaluate traces such as occur in Eq. (2) in the representation where H is diagonal. The appropriate unitary transformation, $O \rightarrow \exp(+iS)O \exp(-iS)$, is given by

$$S = (2\pi i/L) \sum_{\text{all } p} p^{-1} \varphi(p) \rho_1(p) \rho_2(-p). \quad (7)$$

We recall the commutation relations among the $\rho^{\pm 1}$:^{6,7}

$$[\rho_i(p), \rho_j(-p)] = (-1)^i \delta_{ij} p L / 2\pi \quad (8)$$

with $i, j = 1$ for the right-going, and 2 for the left-going particles. The correct value of $\varphi(p)$ is¹

$$\varphi(p) = -\frac{1}{4} \ln[1 + 2\lambda U(p)/\pi \hbar v_0]. \quad (9)$$

Using an earlier calculation¹⁰ of $H^-(x, 0)$ we obtain $H^+(x, 0)$ by Hermitean conjugation and $H^-(x, t)$ by Eq. (4). Thus we have the essential operator part of Eq. (2):

$$[H^+(x, 0), H^-(x', t)] = C(x' - x, t) [B^{-1\dagger}(x, 0) B(x, 0) A^\dagger(x, 0) A^{-1}(x, 0), B^\dagger(x', t) B^{-1}(x', t) A^{-1\dagger}(x', t) A(x', t)], \quad (10)$$

where

$$C(x' - x, t) = L^{-2} \exp\{i[(k_{1F} - k_{2F})(x' - x) - v_0(k_{1F} + k_{2F})t]\} \exp(-2\alpha) \quad (11)$$

and¹

$$\alpha = (2\pi/L) \sum_{p>0} p^{-1} (e^{2\varphi(p)} - 1) = (2\pi/L) \sum_{p>0} [E^{-1}(p) - p^{-1}],$$

with

$$E(p) \equiv p[1 + 2\lambda U(p)/\pi \hbar v_0]^{1/2}. \quad (12)$$

The operators in (10) are

$$A(x, t) = \exp\left\{(2\pi/L) \sum_{p>0} p^{-1} \rho_1(-p) e^{ipx} e^{i\phi(p)} \exp[-iE(p)v_0 t]\right\},$$

$$B(x, t) = \exp\left\{(2\pi/L) \sum_{p>0} p^{-1} \rho_2(p) e^{-ipx} e^{i\phi(p)} \exp[-iE(p)v_0 t]\right\}, \quad (13)$$

with Hermitean conjugates obtainable using the identity $\rho_i^\dagger(p) = \rho_i(-p)$. Averaging the exponentiated Bose-Einstein operators, one obtains for Eq. (2)

$$dj/dt = (2v_0/\hbar^2) L^{-2} \int dx \int dR \langle W^*(x)W(x+R) \rangle \exp[i(k_{1F} - k_{2F})R] \\ \times \int_{-\infty}^{\infty} dt (-2i) \sin[v_0(k_{1F} + k_{2F})t] \Sigma(v_0 t + R) \Sigma(v_0 t - R) \exp(Q_1 - Q_2). \quad (14)$$

The calculations are greatly simplified if the scattering potential is spatially uncorrelated, i.e., $\langle W^*(x)W(x+R) \rangle = M\delta(R)$, where M is a constant. The remaining quantities are

$$\Sigma(y) \equiv \exp\left[(2\pi/L) \sum_{p>0} p^{-1} e^{ipy}\right] = \sum_{p>0} e^{ipy} \quad (15)$$

as previously defined,¹ and the convergent integrals

$$Q_1(R, t) = (4\pi/L) \sum_{p>0} \left\{ p^{-1} [1 - \exp(iv_0 p t) \cos pR] - E^{-1}(p) [1 - \exp[iE(p)v_0 t] \cos pR] \right\}, \quad (16)$$

$$Q_2(R, t) = (8\pi/L) \sum_{p>0} E^{-1}(p) f[E(p)] \left\{ \sin^2 \frac{1}{2} [pR + v_0 E(p)t] \sin^2 \frac{1}{2} [pR - v_0 E(p)t] \right\}, \quad (17)$$

with the Bose-Einstein distribution function being

$$f(E) = [\exp(v_0 E/kT) - 1]^{-1}. \quad (18)$$

To evaluate Q_1 and Q_2 , essentially "Debye-Waller" factors, analytically we go to the weak-coupling limit and assume $U(p)$ is slowly varying up to a cutoff at $p = p_0$, so that $U(p) \approx U(0)$ for $p < p_0$ and vanishes for $p > p_0$. We then define the dimensionless coupling constant

$$g = 2\lambda U(0)/\pi \hbar v_0 \quad (19)$$

which is now assumed to be small, $|g| \ll 1$, and evaluate dj/dt to leading order in g . By our assumptions on the scattering mechanism, we can set $R = 0$ in the integrals, which then assume the following asymptotic forms for large t :

$$\exp[Q_1(0, t)] = (1 + p_0 v_0 |t|/\hbar)^g, \quad (20)$$

$$\exp[-Q_2(0, t)] = \exp[-(\gamma kT |t|/\hbar)], \quad (21)$$

where γ is a number $O(1)$. Study of the integral in (14) shows that the dominant contributions are from regions where the complex phases vanish and for a range of t of the order of \hbar/kT . For small g , we take the slowly varying factor as given in (20) out of the integral, Eq. (14), replacing it by an order-of-magnitude estimate, $\exp[Q_1(0, \hbar/kT)]$. We can set $g = 0$ in the remaining integrals, to leading order. Recognizing the remainder with $g = 0$ as the decay rate of a current of noninteracting fermions, $(dj/dt)_0$, one easily proves that this quantity is proportional to the current itself, with a constant of propor-

tionality $-\tau_0^{-1}$, where τ_0 is the scattering decay time for free particles. [The simplest method of proof involves an independent evaluation of Eq. (2) using the free-fermion operators suitable for the case $g = \lambda = 0$.] Thus, we establish that the current decays exponentially,

$$\frac{dj}{dt} = \left(1 + \frac{p_0 v_0 \hbar}{kT}\right)^g \left(\frac{dj}{dt}\right)_0 = -\left(1 + \frac{p_0 v_0 \hbar}{kT}\right)^g \tau_0^{-1} j \quad (22)$$

and obtain the new decay time by inspection. Identification of $p_0 v_0 \hbar$ with $k\theta$ and of the ratio of decay times to the ratio of conductivities completes the derivation of Eq. (1), constituting the principal result.

It is evident that if a BCS superconducting, coherent ground state is assumed for 1D electrons with attractive interactions, the fluctuations would be so large at finite temperature as to destroy the self-consistency of the assumed long-range order, and restore finite conductivity. As an example, a free-electron sea interacting with phonons has been shown to behave as a Peierls insulator for 1D at low temperature,⁸ rather than as a superconductor as would be the case⁹ in 3D. To examine this behavior within the context of our exactly soluble model, I have calculated the Cooper-pair amplitude, $\langle \psi_1(x) \psi_2(x') \rangle$, with the angular brackets indicating the matrix element between eigenstates of H differing by two particles in occupation number and thermally averaged. This quantity can also be obtained as the square

root of the pair-pair correlation function obtained by Luther and Peschel,² evaluated at infinite separation. Calculating it directly, using the wave-operator representation of Ref. 1, one finds that the key to the behavior of this amplitude is dominated by two divergent integrals, denoted Q_3 and Q_4 :

$$\langle \psi_1(x)\psi_2(x') \rangle \propto \exp(Q_3) \exp(-Q_4), \quad (23)$$

where

$$\begin{aligned} \exp(Q_3) &= \exp\left[(2\pi/L) \sum_{p>0} p^{-1}(1 - e^{-2\phi(p)})\right] \\ &\approx (1 + Lp_0)^{-g/2} \end{aligned} \quad (24)$$

Thus $\exp(Q_3) = 0$ for repulsive two-body forces, $= 1$ for $g = 0$, and diverges weakly for attractive forces. Q_4 contains the temperature dependence. We have

$$\begin{aligned} \exp(-Q_4) &= \exp\left\{- (4\pi/L) \sum_{p>0} p^{-1} f[E(p)] e^{-2\phi(p)}\right\} \\ &\approx \exp(-2LkT/\hbar v_0); \end{aligned} \quad (25)$$

and thus, at any finite temperature, and regardless of the sign of magnitude of the two-body forces, $\exp(-Q_4) \neq 0$. The vanishing of the Cooper-pair amplitude at any finite temperature is compatible only with a lack of long-range superconducting order, and confirms the finite conductivity obtained in Eq. (1). In conclusion, while attractive forces lead to many-body effects which can enhance the conductivity of 1D fermions, they cannot make them superconduct at finite temperature.

*Work sponsored by the U. S. Air Force Office of Scientific Research, Air Force Systems Command, under Grant No. AFOSR-72-2153C.

¹D. C. Mattis, "New-Wave Operator Identity Applied to the Study of Persistent Currents in 1D" (to be published).

²A. Luther and I. Peschel, Phys. Rev. B (to be published).

³L. B. Coleman, J. J. Cohen, D. J. Sandman, F. G. Yamagashi, A. F. Garito, and A. J. Heeger, Solid State Commun. **12**, 1125 (1973); S. K. Khanna, E. Ehrenfreund, A. F. Garito, and A. J. Heeger, "Microwave Properties of High Purity TTF-TCNQ" (to be published).

⁴E.g., D. E. Schafer, F. Wadl, G. Q. Thomas, J. Ferraris, and D. O. Cowan, "Apparent Giant Conductivity Peaks in an Anisotropic Medium: TTF-TCNQ" (to be published).

⁵J. M. Luttinger, J. Math. Phys. (N.Y.) **4**, 1154 (1963).

It should be noted that the lack of electron spin in Luttinger's model is easily remedied. Because this does not affect any important results, I adhere to the model of spinless fermions for simplicity, although I modify the model somewhat, by taking interaction operators $|\rho_1(p) + \rho_2(p)|^2$ which are positive definite, rather than Luttinger's $\rho_1(p)\rho_2(-p)$, which have an indefinite sign. This is so as to establish an unambiguous dependence on the sign of the coupling constants $\lambda U(p)$.

⁶D. C. Mattis and E. H. Lieb, J. Math. Phys. (N.Y.) **6**, 304 (1965).

⁷E. H. Lieb and D. C. Mattis, *Mathematical Physics in One Dimension* (Academic, New York, 1966).

⁸B. R. Patton and L. J. Sham, Phys. Rev. Lett. **31**, 631 (1973).

⁹J. Bardeen, L. N. Cooper, and J. R. Schrieffer, Phys. Rev. **108**, 1175 (1957).

¹⁰Equation (19) of Ref. 1.

Resonance Absorption of Acoustic Waves by Acceptor Holes in Ge under Strong Magnetic Field

H. Tokumoto, T. Ishiguro, R. Inaba,* K. Kajimura, K. Suzuki,† and N. Mikoshiba
Electrotechnical Laboratory, Mukodai, Tanashi, Tokyo 188, Japan

(Received 31 December 1973)

The peak structures observed in the magnetoacoustic attenuation in *p*-Ge are ascribed to the resonance absorption by acceptor holes, which is caused by the sublevel crossings due to the second-order Zeeman effect. The anisotropy with respect to the direction of a magnetic field is explained. The behavior of the magnetothermal conductivity, regarded as evidence for the Jahn-Teller effect, can also be explained by our model.

The interaction between phonons and acceptor holes has been investigated by means of thermal conductivity,^{1,2} heat-pulse propagation,^{3,4} and acoustic attenuation.^{5,6} In *p*-Si, the results of these measurements are explained in terms of the quartet model proposed by Suzuki and Miko-

shiba.⁷ In *p*-Ge, the heat-pulse propagation can be explained by this model,⁴ but the observed magnetothermal conductivity was found to be different, even in a qualitative sense, from what was expected.⁸ Challis and Halbo proposed that the discrepancy may be attributed to the neglect