Field-induced charge symmetry revealed by nuclear magnetic resonance in the topological insulator Bi₂Te₃

R. Guehne¹,^{1,*} J. Haase,¹ C. Shekhar,² and C. Felser²

¹Felix Bloch Institute for Solid State Physics, Leipzig University, Linnéstraße 5, 04103 Leipzig, Germany ²Max Planck Institute for Chemical Physics of Solids, Nöthnitzer Straße 40, 01187 Dresden, Germany

(Received 31 August 2020; accepted 6 January 2021; published 19 February 2021)

Nuclear magnetic resonance (NMR) was recently shown to measure the bulk band inversion of Bi_2Se_3 through changes in the ²⁰⁹Bi nuclear quadrupole interaction, and the corresponding tensor of the local electric field gradient was found to follow, surprisingly, the direction of the external magnetic field if the sample is rotated. This manifests a hidden property of the charge carriers in the bulk of this topological insulator, which is explored here with another material, Bi_2Te_3 . It is found that two electric field gradients appear to be present at ²⁰⁹Bi, one rests with the lattice, as usual, while a second follows the external field if it is rotated with respect to the crystal axes. These electronic degrees of freedom and their lifetime is believed to be responsible for an alternate quadrupolar relaxation that should lead to other special properties including the electronic specific heat.

DOI: 10.1103/PhysRevResearch.3.L012018

Gapless surface states of Bi₂Se₃-type three-dimensional topological insulators are of great interest from fundamental as well as applied physics' perspective [1], and they have been studied extensively with surface sensitive methods [2–4]. A spin-orbit coupling (SOC) induced energy band inversion at the Γ point in the Brillouin zone of these materials was anticipated to lead to these topologically protected states [5]. However, related bulk properties of these materials have hardly been investigated.

Nuclear magnetic resonance (NMR) as a local, bulk probe was used, in a few applications, to study magnetic properties, in particular with aim at the surface states by using nanopowders, to increase the surface area [6,7]. However, definite conclusions are difficult as the NMR of spin-orbit coupled systems is not well understood [8], and bulk properties are expected to be altered by very small grains, as well [9]. For example, a special Bloembergen-Rowland type electronic susceptibility was found to be present in these narrow gap materials as it leads to large, field independent NMR linewidths [10].

Very recently, some of us have shown that NMR can indeed detect the band inversion of itinerant carriers via its effect on the local charge symmetry that influences the nuclear levels through the electric quadrupole interaction [11], leading to the well known splitting of NMR lines for spin I > 1/2 nuclei [12]. This quadrupole splitting is known to be very sensitive to the local charge symmetry represented by the electric field gradient (EFG) at the nuclear site; it even detects lattice

strain arising from impurities. It is thus not surprising that quadrupole splittings also reflect changes of the electronic wave function due to SOC. Furthermore, the experiments can be reliably compared to first-principles calculations.

Very unusual, however, and unfortunately not easily tractable with first-principles calculations, is the orientation dependence of the quadrupole splitting in Bi_2Se_3 [11], i.e., if one changes the orientation of the crystal with respect the external magnetic field (B_0). In NMR it is always assumed that the EFG, a second-rank tensor, rests with the crystal axes system. For example, this leads to typical powder spectra when the grains are oriented randomly, or, in case of single crystals, to special orientation dependences of the NMR spectra, which are a fingerprint of the local crystal symmetry. Surprisingly, for Bi_2Se_3 , this tensor appears to follow the external field to a large extent, as shown in Fig. 1.

In leading order of the nuclear Zeeman interaction, the electric quadrupole splitting is usually expressed in terms of an orientation dependent quadrupole frequency (v_Q) given by the orientation dependent influence of the second rank tensor of the local electric field gradient (V_{XX}, V_{YY}, V_{ZZ}) . The local symmetry at the Bi nucleus requires that $V_{XX} = V_{YY}$ and only one tensor component enters the well-known expression $v_Q = 3eQV_{ZZ}/(4I(2I-1)h) \cdot (3\cos^2\beta - 1)$, where *I* is the nuclear spin and eQ the nuclear electric quadrupole moment. The azimuthal angle β spans between V_{ZZ} and the external magnetic field B_0 .

For ²⁰⁹Bi in Bi₂Se₃ (I = 9/2), V_{ZZ} is strongly influenced by the band inversion and depends on the carrier concentration [11]. However, there is hardly any orientational dependence, i.e., V_{ZZ} remains nearly aligned with B_0 , cf. Fig. 1(c). Interestingly, this phenomenon is most prominent for higher carrier concentrations, $n \ge 10^{19} \text{ cm}^{-3}$ [11], so that one has to associate it with the doped electrons. It was argued that the system's massive SOC ($g_{\text{eff}} \approx 30$ [14]) allows the external magnetic field to deform partially filled Bi orbitals.

^{*}r.guehne@physik.uni-leipzig.de

Published by the American Physical Society under the terms of the Creative Commons Attribution 4.0 International license. Further distribution of this work must maintain attribution to the author(s) and the published article's title, journal citation, and DOI.



FIG. 1. ²⁰⁹Bi NMR of single crystalline Bi₂Se₃ at 11.74 T and 300 K: (a) expected quadrupole splitting, v_Q , in the high magnetic field (B_0) case. The tensor of the electric field gradient (EFG) at the Bi nucleus and its orientation with respect to the external field determine v_Q . (b) the crystal symmetry at the Bi site *and* the band structure (band topology following [13]) affect v_Q through local changes in the wave function or carrier concentration [11]. (c) comparison with measurements (green spectra) are in quantitative agreement with DFT calculations [11], however, the expected orientation dependence of $(3 \cos^2 \beta - 1)$ from this second rank tensor (orange spectra) is lacking, on the contrary, an orientation *in*dependent splitting (green spectra and lines) suggests that the EFG rotates with B_0 , rather than being tied to the crystal, as depicted in panel (d).

The resulting EFG is then set by B_0 , in stark contrast to an ordinary EFG that is pinned to the crystal axes. In other words, the effect involves rotational degrees of freedom of strongly spin-orbit coupled conduction electrons, with their orbital angular momenta being partially unquenched due to B_0 [15]. Earlier ²⁰⁹Bi NMR studies of Bi₂Se₃ [16–19] are in agreement with the above-mentioned special results, but the short nuclear spin relaxation times for Bi apparently hindered a clear identification of this effect, before Ref. [18].

A magnetic field affecting the EFG is not uncommon. Field induced charge density waves in superconducting cuprates are an example [20,21]. In certain paramagnetic systems with a cubic local environment, exotic magnetic correlation patterns can also give rise to an EFG [22]. The ordinary first-order quadrupole interaction can show a magnetic field dependence, as well, if electronic wave functions are deformed and thus an EFG is induced even in closed shell systems such as noble gases [23]. Field induced charge rotation based on spin-orbit interaction has also been reported for impurity nuclei in ferromagnetic materials [24,25]. The effect as observed in Bi₂Se₃ is special, though, because it is related to rotational degrees of freedom of nonlocalized conduction electrons.

In order to shed more light on this unusual behavior, we decided to investigate Bi₂Te₃, the closest relative of Bi₂Se₃, with ²⁰⁹Bi NMR. We find the quadrupole splitting to be an order of magnitude larger compared to that in Bi₂Se₃, and the orientation dependent splitting appears closer to what is expected from *ordinary* behavior. However, near the magic angle $(\cos^2 \beta = 1/3)$, where the usual quadrupole splitting disappears, it becomes apparent that a quadrupolar split spectrum



FIG. 2. (a) quadrupole spectrum of ²⁰⁹Bi in Bi₂Te₃ (black) obtained for $c \parallel B_0$ at 11.74 T (selective spin echoes with $\pi/2$ -pulse width of 3 μ s), including a fit (red line, see text for details). Also shown is a typical ²⁰⁹Bi spectrum of single crystalline Bi₂Se₃ (S3 in [11]). (b) saturation recovery of the Bi central transitions in Bi₂Te₃ (squares) and Bi₂Se₃ (circles), respectively, next to the satellite recoveries in Bi₂Te₃ (triangles). (c) spin-echo decay times, T_2 , for each of the 2I = 9 Bi transitions in Bi₂Te₃ and Bi₂Se₃.

remains, similar to what was observed in Bi_2Se_3 , manifesting a clear discrepancy with the expected behavior. In fact, a closer look at the total angular dependence shows this phenomenon also at other angles. Again, it appears that the electronic degrees of freedom change with the orientation of the external field, yielding a nonvanishing splitting even at the magic angle. In contrast to Bi_2Se_3 , however, the quadrupole interaction in Bi_2Te_3 appears to have two EFGs, a large lattice component that rotates together with the sample, and a second component that follows the field. Hence, the ²⁰⁹Bi quadrupole interaction in Bi_2Te_3 provides another perspective on a very unusual effect related to so far unknown electronic properties of conduction electrons in topological insulators.

Bi₂Te₃ used for the investigations here was grown by the self-flux method. A stoichiometry ratio of Bi (purity: 99.999%) and Te (purity: 99.999%) are sealed in a dry quartz ampoule with vacuum of 10^{-5} mbar. Except for the cooling rate of 2K/h from 800 – 500° for the crystal growth, the other heating profile is the same as in Ref. [26]. A *c*-axis-oriented plateletlike crystal of several mm in dimension was mechanically separated from the ingot.

All experiments were carried out at room temperature with commercial NMR consoles using a home-built probe that fits standard 2.35 T, 7.05 T, 11.74 T, and 17.6 T magnets. We employed spin echoes $(\pi/2 - \tau - \pi)$ to measure individual transitions, their decay (T_2) , as well as their recovery after saturation (T_1) , besides, solid echoes $(\pi/2 - \tau - \pi/2)$ to excite the whole set of transitions simultaneously where possible.

We start with ²⁰⁹Bi NMR spectra of the Bi₂Te₃ single crystal with the magnetic field B_0 along the crystal *c* axis (*c* || B_0), where $\beta = 0$, cf. Fig. 2(a).

We find the expected 2I = 9 resonances, and a simple fit of Gaussian lines to the total spectrum is in very good agreement with the expected pattern for a magnetic (the same for all transitions) and quadrupolar (contribution changes with transitions and is absent for the central line)

broadening; we find $v_Q = 1.171(2)$ MHz, а central transition linewidth of 80(2) kHz, and a relative quadrupole broadening of 7%, i.e., about 80 kHz for the first pair of satellites. For comparison, we show the spectrum for Bi_2Se_3 , as well (sample S3 in Ref. [11]). The quadrupole splitting frequency is 0.14 MHz with a central transition width of 77(4) kHz and a relative quadrupolar broadening of up to 9%, i.e., \sim 13 kHz for the first satellites [11]. Thus, while the quadrupole coupling and its distribution are nearly a factor of 10 larger in Bi2Te3, the magnetic (central) widths are similar. This NMR line broadening agrees with theoretical linewidths of an enhanced nuclear dipole coupling arising from the Bleombergen-Rowland electronic spin susceptibility [10,27].

Comparison of the relaxation in Bi₂Te₃ and Bi₂Se₃ reveals similarities, as well. Selective recoveries of the central transitions are shown in Fig. 2(b), with apparent recovery times of 303(5) μ s for Bi₂Te₃ and 750(50) μ s for Bi₂Se₃. Since individual transitions are well separated in the case of Bi₂Te₃, we measured their recovery, as well (brown symbols). The recovery slows down with increasing satellite order, from 311(5) μ s (1st satellite) over 337(5) μ s and 382(5) μ s (2nd and 3rd, respectively) to 672(10) μ s (4th). Comparison with a purely magnetic relaxation [17,28] based on the recovery of the central transition reveals discrepancies, especially for the outer satellites, indicating contributions from quadrupolar relaxation [29,30].

Selective spin-spin relaxation experiments, Fig. 2(c), yield the same T_2 values within error for both samples, with a characteristic increase in T_2 with growing satellite order. The central transition T_2 values are further in good correlation with their width in frequency domain, and thus with the aforementioned model calculations based on the special Bloembergen-Rowland type of indirect nuclear dipole coupling.

We now turn to orientation dependent spectra shown in Fig. 3(b). The gray solid lines represent the expected resonance frequencies as a function of β , as obtained from exact diagonalization of the total Hamiltonian with $v_0 =$ 1.171 MHz for an axially symmetric field gradient, at a resonance frequency of 80.4 MHz ($B_0 = 11.74$ T). While the central transition follows the predicted frequency dependence on angle [Fig. 4(a)], the satellite resonances do not. In particular, near the magic angle the total satellite spectral weight is distributed over a very large spectral range, while some asymmetry of the spectrum is expected from higher order effects. The broad spectral range and its asymmetry follow from broadband solid echo spectra as well as from frequency stepped, selective excitation. A more detailed orientation dependence near the magic angle is shown in panel b, with the expected (yellow area) and the measured (gray areas) spectral intensity (green line is the expectation for the central transition). With the magnetic field perpendicular to the c axis the spectrum approaches what is expected from $c \parallel B_0$. The question arises how one can understand the disagreement, in particular near the magic angle.

Frequency stepped spin-echo spectra near the magic angle show, cf. Fig. 4(b), that the spectrum is independent of the field, at least for $B_0 \ge 2$ T. Hence, it cannot stem from a distribution of shifts ($\propto B_0$), or from an ordinary variation

PHYSICAL REVIEW RESEARCH 3, L012018 (2021)



FIG. 3. Orientation dependent ²⁰⁹Bi NMR spectra of Bi₂Te₃ (black spectra represent individually measured transitions, black circles frequency swept spectra, and the blue spectrum was obtained from a solid echo experiment). Main panel (a) the top trace for $c \parallel B_0$ ($\beta = 0^\circ$) is connected with what is expected from the quadrupole interaction by gray lines with the bottom trace $c \perp B_0$ ($\beta = 90^\circ$). (b) shows a magnified window of solid echo experiments between $\beta = 50^\circ$ and 60° . The two pink lines give the traces of the two outermost satellites, i.e., spectral density is only expected in the yellow area. In contrast, the measured spectra cover a much larger range of about ± 1 MHz (gray filling).



FIG. 4. (a) the resonance frequency of the central transition as a function of β reflects an axial symmetric Knight shift anisotropy plus higher order quadrupole interaction (solid line). (b) frequency swept spin echoes spectra at $B_0 = 2.35$ T (diamonds), 7.05 T (squares), and 17.6 T (triangles) for the magic angle. The spectra are shifted with respect to the center of gravity of their expected second-order quadrupole patterns, represented by the colored bars. (c) selective spin-echo nutation for the magic angle +240 kHz off center (triangles) in agreement with the central transition nutation for $c \parallel B_0$ (solid squares, line) confirms a quadrupolar origin of the broad magic angle spectrum. Consequently, broad band solid echo nutation (open squares) behaves differently, with a much slower nutation frequency. (d) magic angle broad band solid echo spectra for $\tau = 32 \,\mu s$ of Bi₂Te₃ ($\alpha = 0^{\circ}$ and 90°) and Bi₂Se₃.

of the quadrupole interaction ($\propto B_0^{-1}$ for the second-order splitting at the magic angle). Selective nutation [Fig. 4(c)] reveals that the signal intensity belongs to single transitions, so it must be given by quadrupolar satellites that extend over a range of about 1 MHz. Note that the total spectral intensity remains constant as a function of β , thus, the observed effects concern the bulk signal. This means, the spectral intensity near the magic angle cannot be accounted for by sample inhomogeneity.

Obviously, the description above points immediately to a second quadrupolar broadening mechanism (of about 500 kHz) as it produces the desired broadening, i.e., the splitting up of the satellite transitions without affecting the central transition and keeping the asymmetry set by the center of gravity of the second-order satellite spectrum [colored bars in Fig. 4(b)]. However, this additional broadening must be rather independent from the main broadening mechanism and, given the lack of a special line shape, is likely to carry an additional inhomogeneity. Since the orientation dependence of the spectra is not very good at other angles, it is likely that the second term is already present far away from the magic angle, with a possible orientation dependent magnitude. For example, we find a much increased quadrupolar broadening even for $c \perp B_0$. In contrast, the rather narrow lines obtained for $c \parallel B_0$ may indicate that this orientation is exceptional because of the symmetry given by the similar coordination of the six Se neighbors with respect to B_0 .

Note that symmetry in the plane is conserved as a rotation about the crystal *c* axis ($\alpha = 0^{\circ}$, 90°) inside the NMR coil does not change the spectrum, cf. Fig. 4(d), as expected.

Given the similarity of a nonvanishing magic angle quadrupole splitting in both materials, Bi₂Te₃ and Bi₂Se₃, cf. Fig. 4(d), and their close electronic relationship, i.e., very large effective *g* factors of conduction electrons [14,31], we argue that quadrupole coupling that follows the field arises from the effect of the magnetic field on special electronic states, while the much stronger (normal) Bi quadrupole interaction in Bi₂Te₃ is related to a large EFG component from the ionic lattice. Note that for Bi₂Se₃ the effect of a nontrivial, orientation independent quadrupole splitting dominates the observation, with a negligible lattice EFG ($v_{latt}^{latt} \leq 10$ kHz). In Bi₂Te₃, the opposite situation holds, with a dominating lattice EFG yielding a first-order orientation dependence (with small

second-order corrections), which gives way to a nontrivial EFG component from special electronic states (precessing about B_0) dominating the NMR near the magic angle.

In the last part of the discussion, we reconsider spin-lattice relaxation in the context of a special EFG arising from these electrons final lifetime of precession, as it must result in fluctuations of the EFG and thus nuclear relaxation. Results on the recovery of individually saturated Bi transitions in Bi₂Te₃ for $c \parallel B_0$ indicate a quadrupolar spin-lattice relaxation. The estimated recovery times of the central transitions in Bi₂Te₃ and Bi₂Se₃, however, are in clear disagreement with the measured quadrupole splittings for $c \parallel B_0$, because quadrupolar relaxation is expected to be proportional to v_0^2 . One may thus invoke contributions from magnetic relaxation. Though, when comparing the magic angle spectra for Bi₂Te₃ and Bi_2Se_3 in Fig. 4(d), both patterns are rather similar, the one obtained from Bi₂Te₃ is only slightly larger than the one from Bi₂Se₃. Hence, an alternative scenario to account for Bi spin-lattice relaxation in Bi2Te3 and Bi2Se3 could be related to the nontrivial EFG component that may be related to a special electronic thermal reservoir.

In summary, ²⁰⁹Bi NMR of Bi_2Te_3 reveals a nontrivial quadrupole interaction in the sense that the local charge distribution is altered by an external magnetic field. This bears strong similarities to what was observed in Bi_2Se_3 , an electronically similar material. This behavior points to low energy electronic degrees of freedom in Bi_2Te_3 and Bi_2Se_3 . Not only is this behavior crucial for the understanding and analysis of NMR data in such materials, it also raises the question of the role of these excitations for other material properties, for example, their so far unconsidered potential to contribute to the excellent thermoelectric performance [32].

R.G. and J.H. thank O. Sushkov, I. Garate, G. Williams, S. Chong, A. Pöppl, N. Georgieva, J. Nachtigal, A. Isaeva, and O. Oeckler, as well as the AMR group from the Felix Bloch Institute, Leipzig. We acknowledge the financial support by the Deutsche Forschungsgemeinschaft, Project No. 442459148, and by Leipzig University. The samples were provided for this study under the ERC Advanced Grant No. 742068 TOPMAT. We acknowledge support from Leipzig University for Open Access Publishing.

- Y. Ando, Topological insulator materials, J. Phys. Soc. Jpn. 82, 102001 (2013).
- [2] Y. Xia, D. Qian, D. Hsieh, L. Wray, A. Pal, H. Lin, A. Bansil, D. Grauer, Y. S. Hor, R. J. Cava, and M. Z. Hasan, Observation of a large-gap topological-insulator class with a single Dirac cone on the surface, Nat. Phys. 5, 398 (2009).
- [3] T. Zhang, P. Cheng, X. Chen, J. F. Jia, X. Ma, Ke He, L. Wang, H. Zhang, Xi Dai, Z. Fang, X. Xie, and Q. K. Xue, Experimental Demonstration of Topological Surface States Protected by Time-Reversal Symmetry, Phys. Rev. Lett. **103**, 266803 (2009).
- [4] F. Zhang, C. L. Kane, and E. J. Mele, Surface states of topological insulators, Phys. Rev. B 86, 081303(R) (2012).
- [5] H. Zhang, C.-X. Liu, X.-L. Qi, Xi Dai, Z. Fang, and S.-C. Zhang, Topological insulators in Bi₂Se₃, Bi₂Te₃ and Sb₂Te₃ with a single Dirac cone on the surface, Nat. Phys. 5, 438 (2009).
- [6] D. Koumoulis, T. C. Chasapis, R. E. Taylor, M. P. Lake, D. King, N. N. Jarenwattananon, G. A. Fiete, M. G. Kanatzidis, and Louis-S. Bouchard, NMR Probe of Metallic States in Nanoscale Topological Insulators, Phys. Rev. Lett. **110**, 026602 (2013).

- [7] W. Papawassiliou, A. Jaworski, A. J. Pell, J. H. Jang, Y. Kim, S.-C. Lee, H. J. Kim, Y. Alwahedi, S. Alhassan, A. Subrati, M. Fardis, M. Karagianni, N. Panopoulos, J. Dolinšek, and G. Papavassiliou, Resolving Dirac electrons with broadband highresolution NMR, Nat. Commun. 11, 1 (2020).
- [8] S. Boutin, J. Ramírez-Ruiz, and I. Garate, Tight-binding theory of NMR shifts in topological insulators Bi₂Se₃ and Bi₂Te₃, Phys. Rev. B 94, 115204 (2016).
- [9] L. Gioia, M. G. Christie, U. Zülicke, M. Governale, and A. J. Sneyd, Spherical topological insulator nanoparticles: Quantum size effects and optical transitions, Phys. Rev. B 100, 205417 (2019).
- [10] N. M. Georgieva, D. Rybicki, R. Guehne, G. V. M. Williams, S. V. Chong, K. Kadowaki, I. Garate, and J. Haase, ⁷⁷Se nuclear magnetic resonance of topological insulator Bi₂Se₃, Phys. Rev. B 93, 195120 (2016).
- [11] R. Guehne, V. Chlan, G. V. M. Williams, S. V. Chong, K. Kadowaki, A. Pöppl, and J. Haase, Unusual ²⁰⁹Bi NMR quadrupole effects in topological insulator Bi₂Se₃, J. Magn. Reson. **302**, 34 (2019).
- [12] Charles P. Slichter, *Principles of Magnetic Resonance*, third enlarged ed. (Springer, Berlin, 1990).
- [13] C.-X. Liu, X.-L. Qi, H. J. Zhang, Xi Dai, Z. Fang, and S.-C. Zhang, Model hamiltonian for topological insulators, Phys. Rev. B 82, 045122 (2010).
- [14] H. Köhler and E. Wöchner, The g-factor of the conduction electrons in Bi₂Se₃, Phys. Status Solidi B 67, 665 (1975).
- [15] O. Sushkov (private communication).
- [16] B.-L. Young, Z.-Yo Lai, Z. Xu, A. Yang, G. D. Gu, Z.-H. Pan, T. Valla, G. J. Shu, R. Sankar, and F. C. Chou, Probing the bulk electronic states of Bi₂Se₃ using nuclear magnetic resonance, Phys. Rev. B 86, 075137 (2012).
- [17] D. M. Nisson, A. P. Dioguardi, P. Klavins, C. H. Lin, K. Shirer, A. C. Shockley, J. Crocker, and N. J. Curro, Nuclear magnetic resonance as a probe of electronic states of Bi₂Se₃, Phys. Rev. B 87, 195202 (2013).
- [18] D. M. Nisson, A. P. Dioguardi, X. Peng, D. Yu, and N. J. Curro, Anomalous nuclear magnetic resonance spectra in Bi₂Se₃ nanowires, Phys. Rev. B **90**, 125121 (2014).
- [19] S. Mukhopadhyay, S. Krämer, H. Mayaffre, H. F. Legg, M. Orlita, C. Berthier, M. Horvatić, G. Martinez, M. Potemski, B. A. Piot *et al.*, Hyperfine coupling and spin polarization in the bulk of the topological insulator Bi₂Se₃, Phys. Rev. B **91**, 081105(R) (2015).

- [20] T. Wu, H. Mayaffre, S. Krämer, M. Horvatić, C. Berthier, W. N. Hardy, R. Liang, D. A. Bonn, and M.-H. Julien, Magnetic-field-induced charge-stripe order in the hightemperature superconductor YBa₂Cu₃O_y, Nature 477, 191 (2011).
- [21] S. Reichardt, M. Jurkutat, R. Guehne, J. Kohlrautz, A. Erb, and J. Haase, Bulk charge ordering in the CuO₂ plane of the cuprate superconductor YBa₂Cu₃O_{6.9} by high-pressure NMR, Condens. Matter **3**, 23 (2018).
- [22] Y. Tokunaga, D. Aoki, Y. Homma, S. Kambe, H. Sakai, S. Ikeda, T. Fujimoto, R. E. Walstedt, H. Yasuoka, E. Yamamoto, A. Nakamura, and Y. Shiokawa, NMR Evidence for Higher-Order Multipole Order Parameters in NpO₂, Phys. Rev. Lett. **97**, 257601 (2006).
- [23] J. Vaara and P. Pyykkö, Magnetic-field-induced quadrupole splitting in gaseous and liquid ¹³¹Xe NMR: Quadratic and Quartic Field Dependence, Phys. Rev. Lett. 86, 3268 (2001).
- [24] M. Aiga and J. Itoh, Nuclear electric quadrupole interaction of Ir nuclei in ferromagnetic dilute alloys of iron and nickel, J. Phys. Soc. Jpn. 37, 967 (1974).
- [25] G. Seewald, E. Zech, and H. Haas, Spin-orbit induced noncubic charge distribution in cubic ferromagnets. II. Tight-binding analysis, Phys. Rev. B 66, 174402 (2002).
- [26] C. E. ViolBarbosa, C. Shekhar, B. Yan, S. Ouardi, Eiji Ikenaga, G. H. Fecher, and C. Felser, Direct observation of band bending in the topological insulator Bi₂Se₃, Phys. Rev. B 88, 195128 (2013).
- [27] J. Ramírez-Ruiz, C. Gauvin-Ndyae, and I. Garate (private communication).
- [28] M. Takigawa, J. L. Smith, and W. L. Hults, Temperaturedependent anisotropy of Cu(2) nuclear-relaxation rate in YBa₂Cu₃O₇ below T_c , Phys. Rev. B 44, 7764 (1991).
- [29] J. Van Kranendonk, Theory of quadrupolar nuclear spin-lattice relaxation, Physica **20**, 781 (1954).
- [30] A. Suter, M. Mali, J. Roos, and D. Brinkmann, Mixed magnetic and quadrupolar relaxation in the presence of a dominant static Zeeman Hamiltonian, J. Phys.: Condens. Matter. 10, 5977 (1998).
- [31] H. Köhler, Anisotropic g-factor of the conduction electrons in Bi₂Te₃, Phys. Status Solidi B **75**, 127 (1976).
- [32] C. Fu, Y. Sun, and C. Felser, Topological thermoelectrics, APL Mater. 8, 040913 (2020).